THE PRINCIPAL REQUIREMENTS OF THE PORTLAND CEMENT SPECIFICATIONS OF VARIOUS COUNTRIES

Collection of specifications was begun in 1915, was interrupted by the war, and resumed in 1920. For countries indicated by * there are available no recent reports, but only the replies to first inquiry. Such data is included, although some may now be obsolete.

COUNTRIES	CHEMICAL REQUIREMENTS: MAXIMUM PERCENTAGE — INSOLUBLE RESIDUE	IGNITION LOSS	SO_3	MgO	Al_2O_3	ADD AFTER BURNING	MISCELLANEOUS	SPECIFIC GRAVITY	FINENESS OF GRINDING: MINIMUM % PASSING SIEVE	DESCRIPTION OF SIEVE USED — MESH PER UNIT	NEAREST SIEVE IN U.S. STD. SCREEN SCALE	SETTING TIME (VICAT): INITIAL — MINIMUM TIME (MINUTES)	FINAL — MIN.-MAX. (HOURS)	SOUNDNESS: AIR	WATER	ACCELERATED	LE CHATELIER — MM.
ARGENTINE	a	a	2.0	4		3a	(a) Not over 3% foreign useful material. $\frac{CaO}{SiO_2+Al_2O_3+Fe_2O_3}$ = Not less than 1.7	3.05	95	30 cm	80		3-10	Pm	P	P Boiling	10
AUSTRALIA New South Wales - Public Works	2		2.0-b				(b) Total SO_3	3.00	87	120 in	120 R			P	P	P Deval	
									75	180	170 A	60	3-12			Pan Exp'l %	
Victoria State — Public Works								3.10	90	50 in	50 A	20	2-7	P	P	P s	
Melbourne & Metropolitan Bd. of Wks.			2.0	3	5-10		Combined SiO_2 = 20 to 27%. Max. Fe_2O_3 = 6.0. Lime = 58-64; not over 61% unless rotary kln.	3.00	95	50 in	50 A					P sa°	
									80	17,000 sq/in	120-140 A					S or b.	
Melbourne City Council uses British Stds.																	
*AUSTRIA			2.5	5		3	$\frac{CaO}{SiO_2+Al_2O_3+Fe_2O_3}$ = 1.7 minimum	3.10	95	30 cm	60-70	30			P	P	
									70	70	170				d		
BELGIUM	1.5	3	2.5	3		0	(a) Plaster only. CaO = 61% minimum after calcination.	3.07	95	30 cm	80	45	4-12			P b	6
BRAZIL This is not a standard, but is a railway spec. which is sometimes used.	1.5	3	1.5	3			Alkali not over 3%	3.10	97	30 cm	80 A	?	?			B b	
CANADA Spec. used by Dept. of Pub. Wks.			1.75	4				3.10	92	100 in	100			P	P	P s.	
									75	200	200	30	¼-10			Warm Water 44°	
*CHINA A Railway Specification. The Dept. of Public Works at Shanghai, and also at Hong Kong use British Stds.	1.5	2 a	2.75-b	3-b		a	(a) Not over 2% water. (b) Total SO_3. Hydraulic Modulus = 2 to 2.85	3.15	97	76 in	70 A	Rapid 02	½-2				10
								3.10 at 4 wks	82	180	170 A	Slow 20	2-7	After 7-day aeration — 5			
*CUBA			2.0	4		3		3.05	90	100 in	100	6 Gillmore	10			P	P b.
DENMARK German specs. also used.						3			97	30 cm	70 A	30-90					
									?	5000 sq cm	170 A	60	2-15			P	10
ENGLAND	1.5	3	2.75-c	3		b	(a) Total S calc. as SO_3. (b) Water or gypsum only. No slag permitted. After deducting CaO required for SO_3, and calc. by chem. equivalents, $\frac{\text{Al}_2\text{O}_3}{\text{Fe}_2\text{O}_3}$ = 2 to 2.85.		99	76 in	70	20	10					10
									86	180	170	Rapid 02	½	After 7-day aeration — 5			
FRANCE			3.0-a	5	10	b	(a) No appreciable sulphides. (b) No foreign materials. (c) Ratio $SiO_2:Al_2O_3$ to CaO+MgO = 0.47 minimum, variation 0.02 for each 1% less Al_2O_3.		90	30 cm	80	20	2-12					10
Special requirements for sea water work →			1.5-a	2-c	8-c	b			90	30	80	20	3-12			P. sea water	
																For Sea Water Work — 5	
GERMANY			2.5	5		3	$\frac{CaO}{SiO_2 \text{ (soluble)}+Al_2O_3+Fe_2O_3}$ = 1.7 minimum.		95	30 cm	70	60				P	
*HUNGARY				3		2		3.10?	90	30 cm	60-70	Rapid 10		P	P	B b.	
									55	70	170	Slow 30					
*ITALY		5 a	1.2	3		a	(a) A Govt. R.R. spec. of 1915, which prohibited any inert or injurious materials.	3.05	98	30 cm	70						
									80	70	170	60	5-12		P	B b.	?
JAMAICA		2-a	2.0			b	(a) Not over 2% water. (b) Only water of gypsum; (other) only 2% calc. as SO_3	3.15	97	76 in	70						10
								3.10 at 4 wks	82	180	170			After 7-day aeration — 5			
JAPAN		5 (Sea Water Work — 1.5)	2.5	3		3a	(a) No addition to cement except gypsum, which is not to exceed 3% by weight.	3.05	90	30 cm	60-70	60	10		P	P b	
MADAGASCAR General details essentially as for France, except as shown here																	
MALTA						None			90	50 in	50 A						
MARTINIQUE			3-a	5	10		(a) No appreciable sulphides.		90	30 cm	80 A						
									70	70	170 A	20	2-12				
MEXICO	a		1.75	4		3-a	(a) Not over 2% sand of inert material. The following ratio must be complied with: $\frac{2.8 \times \%SiO_2 + 1.1 \times \%Al_2O_3 + 0.7 \times \%Fe_2O_3}{\%CaO + 1.4 \times \%MgO} = 1$ to 1.2	3.05	96	100 in	100							
									80	200	200	20	2-7	P	P	P b.	
MOROCCO Used for Govt. work in the French zone. No standard specification is used by the Moorish Govt.									90	30 cm	80	30	3-12			P	
									70	70	170	60	½-½				5
												Rapid for Sea Water					
*NETHERLANDS Army Engineers Reinforced Concrete (Engrs.) Dept. of Water-Ways	1.5	3-a 2.2	2.5			a a	(a) No slag.	3.10	95	30 cm	60-70	135	10	P	P	P b.	
								3.10	70	70	170	120	3		P		
									90	30	60-70				P		10
NORWAY	1.5	4	2.5	4		a	(a) Water or gypsum only. $\frac{CaO}{SO_3+Al_2O_3+Fe_2O_3}$ = 1.7 min.	3.05	96	30 cm	60-70						
									70	5,000 sq cm	170	60	10		P	B b	5
PORTUGAL			2.5-a	3			(a) No appreciable sulphides. Hydraulic Index = 0.42 to 0.50.	3.00	90	30 cm	70 A							5
									70	5,000 sq. cm.	170 A	30	3 12				
*RUSSIA			1.75	3		2	$\frac{CaO}{SiO_2+Fe_2O_3+Al_2O_3}$ = 1.7 to 2.2.	3.05	90	30 cm	60-70						
									50	70	170	20	1 12		P	P d.	
SPAIN	1.5	4 6	2.5-a c	3-a		3	(c) Total S not over 1%. (b) Not over 2% water. (a) SO_3+MgO not over 5%. $\frac{CaO}{SiO_2+Al_2O_3}$ = 1.8 to 2.3. $\frac{SiO_2}{Al_2O_3}$ = 2.5 min.	3.05	97	30 cm	80 A						
									75	70	170 A	30	4 14	Pm.	P	P	
SWEDEN			2.5	5		3	$\frac{CaO}{SiO_2+Al_2O_3+Fe_2O_3}$ = 1.7 minimum.		95	30 cm	70	60			P		12
SWITZERLAND						4	$\frac{CaO}{SiO_2+Al_2O_3+Fe_2O_3}$ = 1.7 minimum.		98	30 cm	60-70						
									?	70	170	60			B P	B b. Dry location. For damp location	
SYRIA			1.0														5
TUNISIA For sulphate lands			2.0-a 0.8-a	3 2	15 1.5		(a) No appreciable sulphides. For sulphate lands: comb. SiO_2 = 25% min. Ferrous oxide = 1% max.		90	30 cm	80						
									70	70	170	20	2-12				10
UNITED STATES	0.85	4	2.0	5		a	(a) Only gypsum or water.	3.10	78	290 in	200	45 Vicat	10				5
												60 Gillmore	10			Ps.	
URUGUAY	a	a	2.0	4		3a	$\frac{\text{Al}_2\text{O}_3}{\text{Fe}_2\text{O}_3}$ (1.7 minimum. (a) For gypsum only. (b) For gypsum & inert material, not over 3%)	3.10	98	30 cm	80 A						
									85	70	170 A	35	3-10	Pm.	P		10

COUNTRIES	MINIMUM STRENGTH (lbs/sq. in.): TENSILE NEAT — DAYS-7	TENSILE NEAT — 28	TENSILE 1:3 MORTAR — 7	TENSILE 1:3 MORTAR — 28	COMPRESSIVE NEAT — 7	COMPRESSIVE NEAT — 28	COMPRESSIVE 1:3 MORTAR — 7	COMPRESSIVE 1:3 MORTAR — 28	MISCELLANEOUS. M: Machine Moulding. C.S.: Combined Storage — 1-day moist air, 6 days water, 21 days air.	STANDARD SAND — SIZES IN NEAREST SIEVE WOVEN CLOSSTED S.S.	PACKING: MARKING, WEIGHTS, GENERAL NOTES
ARGENTINE	427	498 a	171	228 b					(a) Gain 42.7 unless 7-d = 568, when 28-d should show no decrease. (b) Gain = 14.2 lbs. M.	14 - 18	Grass wt; Name, where made, trade mark. Waterproof paper-lined bbls. for Imports.
AUSTRALIA New South Wales - Public Works	585 715 - Deval		165 250 - Deval	250				2250 3570 c.s.	M.	20 - 30	Brand on bbls. Dept. seal on bags. Bags = 125-lb net, bbl = 375-lb. net.
Victoria State — Public Works	400	a	150	250 b					2-d. neat = 160; 4-d. = 250. (a, b) Gains over 7-d strength from 5 to 25%, per sliding scale.		Brand, maker, Bbl. = 375-lb net. Bags = aliquot parts of bbl.
Melbourne & Metropolitan Bd. of Wks.	450	c							(c) To exceed 7-d		Bbl. = 375-lb. net, and is unit of purchase. Bags also used.
Melbourne City Council uses British Stds.											
*AUSTRIA			171	285 356 c.s.			1708	2846 3558 c.s.	28-d. is decisive; 7-d for control. M.	20 - 30	bbl. = 200 kg. gross; bag = 50 kg. 100 kg. is unit of purchase. Mark: Gross wt, name, where made, year.
BELGIUM			185 157 a	285 228 a			1850 1565 a	2846 2277 a	M. (a) Acceptable under special conditions. Comp. test not always required.	20 - 30	Bbl. = 170 Kg. net. Specs. cover packing details.
BRAZIL This is not a standard, but is a railway spec. which is sometimes used.											Bbls. = 140 or 170 kg. net, 150 or 180 gross.
CANADA Spec. used by Dept. of Pub. Wks.	500	600	200	275	3500	6000	1000	2500	1-day neat = 200 lbs. tens; 1500 comp. A.S.T.M. moulding methods. Comp. test optional.	20 - 30	Brand and maker. Bag = 87½ lb. net.
*CHINA A Railway Specification. The Dept. of Public Works at Shanghai, and also at Hong Kong use British Stds.	400	a	150	250 a					(a) 28-d. to gain 5% over 7-d. strength	20 - 30	
*CUBA	450	550	140	200 a					A standard hand hammer is used. (a) To gain 10% over 7-d.	20 - 30	Maker, brand, Dept. of Pub. Wks. trade stamp. Bbl. = 170 kg. net; bags 49.5 to 50 kg net. Specs. cover details.
DENMARK German specs. also used.			171 a	228			1708 a	2846	Machine moulding usually; sometimes hand. (a) 7-d. for control only.	14 - (20-25)	Gr. wt, brand or maker, factory, Portland Cement. Bbls. = 90 or 180 kg, 95.23 or 170 net; bags approx. 85 net.
ENGLAND	450	a	200	b					(a) = 7-d. + $\frac{40,000}{7\text{-d.}}$ (b) = 7-d. + $\frac{10,000}{7\text{-d.}}$ where 7-d. = 7-day strength. A standard spatula is used in moulding mortars.	20 - 30	Maker.
FRANCE	356	498 a	114	213 b					(a) Gain 42.7 lbs. (b) Gain 28.4 lbs over 7-d.	10, 14, 18, 35 Three sizes equal vols of each size	Maker, net wt. on bbls; maker on bags. Bags = 25 or 50 kg net.
Special requirements for sea water work →											
GERMANY			171				1708	2846 3558 c.s.	M. 28-d is decisive test.	14 - (20-25)	"Portland Cement" gr. wt, firm or trademark.
*HUNGARY			a	228 a				2277	M. or trowel moulding, former preferable. (a) 7-d. and tens. tests for control only.	20 - 30	Portland Cement, Gr. Wt, factory, address, lead seal on bag with foregoing data. Bbl. = 180 kg; bag = 60.
*ITALY	498	a	228	285 b			2561	3131 b	(a) 28-d. is decisive test. Values of 228 and 285 allowed respectively as tens. and comp. strength under certain conditions for small lots. M.	14 - 18	Name and mark of maker.
JAMAICA	400	500 b	150	250 a					(a) Gain 20% over 7-d. (b) Gain to be in accordance with sliding scale, 5 to 25%.	20 - 30	Maker.
JAPAN	427 b		142	256 a				1991	Mach. moulding sparingly permitted. (a) Gain over 7-d. (b) If mortar test too low.	20, 30, 35 Equal pts, 2 sizes	
MADAGASCAR General details essentially as for France, except as shown here	427	498 a	171	256 b					(a) Gain 42.7 lbs. (b) Gain 28.4 lbs over 7-d.	As for France	Net wt, maker, Bbl. = 200 kg. gross. Specifications cover construction of bbls.
MALTA	444										Bbls used. Their construction is described in specifications.
MARTINIQUE	356	498 a	114	213 b					(a) Gain 42.7 lbs. (b) Gain 28.4 lbs.		Bbl.
MEXICO	541	640	157	228					1-d. Neat = 199 lbs. Moulding methods approximately the same as in U.S.	20 - 30	Bbl. = 167 kg. net; bag = 50 kg. net. Factory, where made.
MOROCCO Used for Govt. work in the French zone. No standard specification is used by the Moorish Govt.	285 356 442	338 a 498 a 228 a	100 114 85	185 b ← For Bldgs. 213 c ← Marine, Slow 171 c ← Marine, Rapid					(a) Gain 42.7 lbs over 7-d. (b) Gain 42.7 lbs. (c) Gain 28.4 lbs.	As for France	Bbl. or bag.
*NETHERLANDS Army Engineers Reinforced Concrete (Engrs.) Dept. of Water-Ways	356	498	199 171	285 285 b			1708	2846 b	M. (a) Gain: — tensile 10%; compressive 25%.	German Sand ?	Maker, place, sealed. Certificate of origin with shipment. Bbl. or bag.
			142	228			1423				
NORWAY			199	285			1992	2846	M. 28-d. is decisive test.	As for Germany	Portland Cement, factory or trade mark, gross wt. Bbl. = 170 kg. net; bag = 56.7 kg. net.
PORTUGAL	356	498 a	114	213 b		4981		2277	Gains of 28-d. over 7-d. (a) 57; (b) 42.7 lbs.		
*RUSSIA	285	356	85	142				1423	Specs. require certain ratios of comp. to tens. strengths. M. for comp; hammer for tens.	As for Japan	"Portland Cement," factory, supply number, year made. Bbl. = 370-lb. net; approx. 397 gross.
SPAIN			228	285			1992	2561	M. for comp; hammer for tens.	14 - 18	
SWEDEN			199				1992	3558 c.s. 2846	Tens. and 7-d. comp. tests not decisive. M.	German Sand	"Portland Cement," factory or trademark, gross wt. Bbl. or bag used.
SWITZERLAND				313				3700	28-d. compressive is decisive test. M.	20 - 30	Brand and maker, gross wt on bags, other than bags. Bags = 50 kg. gross.
SYRIA			171								
TUNISIA For sulphate lands										As for France	
UNITED STATES	427	498 a	171	300 a					(a) To exceed 7-d. strength.	20 - 30	Maker and brand. Bbl. = 376, bag = 94 lb. net.
URUGUAY	427	498 a	171	228 b					(a) 42.7 lbs. above 7-d. unless 7-d. = 568, when 28-d. must show addl. increase. (b) 142 lb above 7-d.	14 - 18	Imports in waterproof paper lined bbls, with gross wt, place of origin, maker's mark.

FOLLOWING COUNTRIES USE SPECIFICATIONS DESCRIBED.

*ARABIA - Aden Govt. uses British Specs.
AZORES - Probably Portuguese Specs.
BALLEARIC Is. - A Spanish Spec.
BOLIVIA - Sometimes Argentine
BURMA - Govt. uses British Specs.
CEYLON - British Specs.
CHOSEN - Tests made; details unknown.
EGYPT - Cairo Dept. of Pub. Wks uses British
FINLAND - No Std. - German specs. used.
FORMOSA - Japanese Specs.
GREECE - No Std; usually German.
GUIANA (BRITISH) - No Std. - Some Depts use British
*HAITI - No Std; sometimes A.S.T.M.
INDIA - Dept. of Pub. Wks uses British
INDO-CHINA - French Specs.
IRELAND - British
KENYA COLONY (AFRICA) - British
PALESTINE - British
PARAGUAY - No Std; sometimes Argentine
ROUMANIA - Tests per I.A.T.M.
SANTO DOMINGO, D.R. Pub. Wks. Dept. uses U.S.
SIAM - A Govt. Dept - British Specs.
SOCIETY Is. - A French Spec.
SOUTH AFRICA - Union Govt. Pub. Wks. - British
TRINIDAD, B.W.I. - British Specs.

NO STD. SPECS.

ALGERIA
BAHAMA
BULGARIA
*CHILE
*COLOMBIA
COSTA RICA
EQUADOR
GUADALOUPE
GUATEMALA
HONDURAS
LIBERIA
NICARAGUA
PANAMA
*PERSIA
PERU
TURKEY
VENEZUELA

Some of these countries use specs. of country from which cement is bought; consider reputation of brand, and sometimes tests are made by them, or for them by another country.

SPECIAL REQUIREMENTS.

APPARENT DENSITY — France requires 1100 grams min. wt. per liter for medium and slow cements and 850 for quick. Portugal, Tunisia, for w/per liter require 1000 g. In Australia, Melbourne & Metropolitan Bd. of Wks requires 116-lb per struck bushel; Victoria Public Wks. Dept. requires 114-lb. Some countries prescribe the method of filling the measures.

MISCELLANEOUS — Some countries have requirements for such properties as color, reputation, packing details, variation and loss in weight, residence of the manufacturer's representative, certificates, and country where made.

GENERAL NOTES.

Any close comparison of the specifications of various countries requires consideration of their respective methods of testing. There will be found much variation in such important details as the following:

SPECIFIC GRAVITY — Treatment before test.
FINENESS — Measurements of sieve wires and openings, size of sample, method of sieving, point of terminating test.
SETTING TIME — Apparatus used, storage of test piece, condition considered as the "set", percentage of water.
SOUNDNESS — Test pieces, storage prior to test, rate of raising temperature of accelerated tests, degree and duration of the temperature; interpretation of results; if more than one test, which is decisive.
STRENGTH — Moulding and storage of test pieces, their dimensions and shapes, rate of applying load, number of specimens broken at one period, method of computing average strength, increases of strength required in certain intervals.
MIXING — Percentage and kind of water, manner and time of mixing, apparatus, size of batch.

STORAGE WATER — Kind of water, temperature, renewal periods.
STANDARD SANDS — Kind, size or sizes, how prepared; if more than one size, what proportions of each.
CHEMICAL REQUIREMENTS — Limits of composition for special classes of cements; methods of computing; special ratios to be complied with; such details of analytical methods as are included in some specifications.

U.S. DEPARTMENT OF COMMERCE
BUREAU OF STANDARDS
S.W. STRATTON, DIRECTOR
AUG. 17, 1921.
JRO