

CLASSIFICATION OF ACOUSTIC MATERIALS.

The following compilation of acoustic materials has been prepared to assist in the determination of the acceptability of materials which may be proposed to be furnished under Federal Specifications SS-A-118 and SS-A-111. These may be obtained from the Government Printing Office, Washington, D. C. for 5 cents each. The inclusion of a material in this list should not be construed as a general approval of this material. The compilation is based upon the sound absorption coefficients given in Letter Circular LC-632, dated February 12, 1941. It includes some materials which are not covered by the Federal Specifications, and others which do not meet all of their requirements.

Mounting:

1. Cemented to gypsum wall board. This is considered equivalent to cementing to plaster or masonry.
2. Nailed on 13/16" x 2" furring 12" o.c. unless otherwise indicated.
3. Metal supports attached to 13/16" x 2" wood furring.
4. Laid directly on laboratory floor.
5. Nailed on 2 x 4's 12" o.c. unless otherwise indicated.
6. Cemented to the floor of the reverberation chamber.
7. Back of sample covered with concrete.
8. Attached to metal suspension system. 4" air space back of tile.
9. Acoustic tile nailed to 13/16" x 2" furring 18" o.c. Space between furring filled with Rockwool
10. Laid on 2 x 8's, 12" o.c.
11. Laid on 24 gauge sheet iron, nailed to 13/16" x 2" furring 24" o.c.

Fire Resistance:

- c. Combustible, as defined in Federal Specification SS-A-118.
- s. Slow burning, as defined in Federal Specification SS-A-118.
- r. Fire retardant, as defined in Federal Specification SS-A-118.
- i. Incombustible, as defined in Federal Specification SS-A-118.



INDEX

<u>MATERIAL</u>	<u>PAGE</u>
Absorbatone . . . . .	2,8
Absorbex . . . . .	1,2,4,5,6,7,8,9,11,12,13
Acoustex . . . . .	2,3,4,5,6,7,9,10,11,13
Acoustic Plaster . . . . .	16,18
Accusti-Celotex . . . . .	1,3,4,5,6,7,9,10,11,12,13
Acoustilite . . . . .	2,3,9,11
Acousti-Metal . . . . .	2,8
Acoustone . . . . .	1,2,3,4,5,6,9,10,11,12
Air-Acoustic Sheets . . . . .	4,6,10,12
Akoustolith Tile . . . . .	1,2,3,4,5,6,7,8,9,10,11,12,13
Akoustolith Plaster . . . . .	15,18,19
Basalt Rock . . . . .	3,9
Berry-Cel . . . . .	1,8,9
Calacoustic Plaster . . . . .	15,18
Calicel . . . . .	1,2,3,4,5,8,9,10,12
Calistone . . . . .	2,4,5,9,12
Cork Acoustical . . . . .	6,7,13
Cork B Acoustical . . . . .	7,13
Corkoustic . . . . .	3,4,5,6,12,13
Dodson Acoustic Plaster . . . . .	15,19
Econacoustic . . . . .	3,5,10,12
Fiberlite . . . . .	4,6,11,12
Fibretext . . . . .	4,5,6,7,10,11,13
Hawaiian Cane Tile . . . . .	5,7,11,12
Hushkote Acoustic Plaster . . . . .	15,18
Kalite Cast . . . . .	4,5,6,7,11,12,13
Kalite Acoustic Plaster . . . . .	15,18
Kencoustex . . . . .	11
Kencoustic . . . . .	5,13
KenKoustone . . . . .	7,13
Koustex . . . . .	4,10
Limpet (Sprayed Asbestos) . . . . .	14,15,17,18
Macoustic Plaster . . . . .	14,15,16,18,19
Maizewood Tile . . . . .	5,11
Muffletone . . . . .	2,3,4,5,10,11,12
Nuwood Bevel Lap Tile . . . . .	7,13
Old Newark Acoustic Plaster . . . . .	15,16,17,18
Permacoustic . . . . .	2,5,10
Perfatone . . . . .	2,8
Pyrocoustic . . . . .	3,10,11
Quietone . . . . .	3,6,11,12
Reverbolite Plaster . . . . .	15,16,18
Rockwall Acoustic Plaster . . . . .	16,18,19



INDEX

<u>Material</u>	<u>Page</u>
Sabinite Plaster . . . . .	15,16,17,18,19
Sanacoustic . . . . .	1,3,8,9
Sphinxstone . . . . .	3,11
Spongeacoustic . . . . .	4,11
Spray Acoustic, Type X . . . . .	14,17
Stackoustic . . . . .	2,3
Stucoustic . . . . .	14,15,17,18
Studio Element . . . . .	4,10
Super-Acoustic Plaster . . . . .	15,18
Temcoustic . . . . .	5,12
Temlok DeLuxe . . . . .	7,13
Transite Acoustic Units . . . . .	3,11
Travacoustic . . . . .	2,10
Trutone . . . . .	6,12



FRE-FABRICATED ACOUSTIC UNITS

FEDERAL SPECIFICATION SS-A-118	Material	Manufacturer	Thickness	Mounting	Weight (lb) sq ft	Fire Resistance
CLASS A (.90 and over) (Sound Absorption Coefficients at 512 cycles per second)						
VII	Absorbex Type A	The Celotex Corporation	1"	9	2.6	r
VII	Absorbex Type F (3 gauge)	" "	2"	7	4.7	r
V	Acousti-Celotex Type C4**	" "	1 1/4"	1	1.58	c
V	Acousti-Celotex Type C4**	" "	1 1/4"	8	1.44	c
V	Acousti-Celotex Type C4, slow burning**	" "	1 1/4"	1	1.80	s
V	Acousti-Celotex Type C6**	" "	1 1/4"	4	1.44	c
V	Acousti-Celotex Type M3	" "	1 1/4"	1	2.58	i
VI	Acoustone Type F, mill painted	U. S. Gypsum Co.	15/16"	1	1.54	i
I	Alkoustolith Tile Grade C	R. Gaastavino Company	4"	4	19.5	i
I	Alkoustolith Tile Grade C	" "	5"	4	24.4	i
I	Alkoustolith Tile Grade C	" "	5"	5	24.4	i
I	Alkoustolith Tile Grade C	" "	5"	10	24.4	i
I	Alkoustolith Tile Grade D	" "	4"	4	18.8	i
II	Berry-Cel	F. E. Berry, Jr. & Co. Inc.	1"	8	2.57	i
II	Berry-Cel (plus rockwool back of tile)	" "	1" (tile)	8	2.99	i
II	Calicel Acoustic Tile	The Celotex Corporation	1 1/4"	1	3.42	i
IV	Sanacoustic Pad 1 1/4", plus metal facing, pad supports and furring 2 1/2"	Johns-Manville Sales Corp.	-	3	1.2 (pad)	i

\*\*Coefficient of sound absorption at 2048 cycles less than 3/4 of the coefficient at 512 cycles.





PRE-FABRICATED ACOUSTIC UNITS

FEDERAL SPECIFICATION SS-A-118	Material	Manufacturer	Thickness	Mounting	Weight (lb) sq ft	Fire Resistance
CLASS B (.85 to .89)						
TYPE	(Sound Absorption Coefficients at 512 cycles per second)					
IV	Acousti-Metal, Rockwool pad, plus metal facing & pad supports 1 5/8", plus furring 4"	National Gypsum Company	-	3	0.98 (pad)	i
VI	Acoustone Type D	U. S. Gypsum Co.	15/16"	1	1.48	i
VI	Acoustone Type F, mill painted	" " "	13/16"	1	1.33	i
I	Acoustolith Tile Grade B-2	R. Guastavino Company	2"	4	8.5	i
II	Calicel Acoustic Tile	The Celotex Corporation	1"	5	2.66	i
I	Calistone	" " "	2"	4	9.3	i
-	Stackoustic	Johns-Manville Sales Corp.	3"	4	1.3 plus wt. of covering.	
CLASS C (.80 to .84)						
TYPE	(Sound Absorption Coefficients at 512 cycles per second)					
VII	Absorbatone	Luse Stevenson Company	1"	10	2.2	r
VII	Absorbex Type A on 1" Absorbex Type F (10 gauge)	The Celotex Corporation	2"	4	-	r
VII	Acoustex Type 7OR	National Gypsum Company	1 1/8"	2	2.5	r
VIII	Acoustilite	The Insulite Company	3/4"	2	0.57	c
VI	Acoustone Type F	U. S. Gypsum Co.	13/16"	1	1.24	i
VI	Acoustone Type F	" " "	15/16"	1	1.46	i
I	Acoustolith Tile Sample No. 104	R. Guastavino Co.	4"	4	21.2	i
I	Calistone, Long edges splayed on opposite sides. 5 holes 3" in diam. through body of tile.	The Celotex Corporation	4"	4	17.6	i
I	Calistone	" " "	5"	4	22.4	i
I	Calistone Type Y	" " "	5"	4	25.7	i
II	Muffletone, Standard Finish	" " "	1"	1	1.83	i
IV	Perfatone, Rockwool pad, plus metal facing and pad supports 1 5/8", plus furring 8"	U. S. Gypsum Company	-	8	.93 (pad)	i
VI	Permacoustic	Johns-Manville Sales Corp.	1"	1	2.33	i
II	Travaoustic	National Gypsum Co.	1"	1	2.04	i



PRE-FABRICATED ACOUSTIC UNITS

FEDERAL SPECIFICATION	Material	Manufacturer	Thickness	Mounting	Weight (lb)	Fire Resistance
SS-A-118			in	ing	(lb)	Resistance
			sq ft			
CLASS D (.75 to .79)						
(Sound Absorption Coefficients at 512 cycles per second)						
VII	Acoustex Type 6OR	National Gypsum Company	1"	2	2.07	r
V	Acousti-Celotex Type C3	The Celotex Corporation	13/16"	1	0.94	c
V	Acousti-Celotex Type C4	"	1 1/2"	8	1.93	s
V	Acousti-Celotex Type C5*	"	13/16"	2	.86	c
V	Acousti-Celotex C6	"	1 1/4"	8	1.65	s
VIII	Acoustilite	The Insulite Company	3/4"	1	.59	c
VI	Acoustone Type D	U. S. Gypsum Company	13/16"	1	1.40	i
VI	Acoustone Type F, mill painted	"	11/16"	1	1.13	i
I	Alkoustolith Tile Grade B-1	R. Guestavino Company	1 1/2"	5	5.8	i
I	Alkoustolith Tile Grade C	"	4"	10	19.5	i
I	Basalt Rock Type A	Basalt Rock Company	5"	4	25.2	i
II	Calicel Acoustic Tile	The Celotex Corporation	1 1/2"	5	3.42	i
VI	Corkoustic Type B5* **	Armstrong Cork Company	1 1/2"	2	.75	s
VI	Corkoustic Type B6* **	"	1 1/2"	1	.85	s
VIII	Econacoustic	National Gypsum Company	1"	1	0.71	c
VIII	Fiberlite	The Insulite Company	1/2"	2	.44	c
VII	Fibretex Type 6OR (1)	Johns-Manville Sales Corp.	1"	2	2.07	r
VII	Kencoustex	David E. Kennedy, Inc.	1"	1	2.24	r
II	Muffletone, Standard Finish	The Celotex Corporation	1"	1	1.84	i
VI	Pyrocoustic	Minfelt Insulation Company	13/16"	1	1.1	i
VIII	Quietone*	U. S. Gypsum Company	1"	4	0.81	c
I	Sphinxstone	The Sphinx Acoustical Co.	2"	4	-	i
IV	Sanacoustic, Rockwool pad, plus metal facing and pad supports, plus furring 5 1/4"	Johns-Manville Sales Corp.	-	8	1.2	i
IV	Transite Acoustical Units	Johns-Manville Sales Corp.	1 1/8"	4	(Pad) 2.0	i

\*Coefficient of sound absorption at 128 cycles less than 1/8 of the coefficient at 512 cycles.

\*\*Coefficient of sound absorption at 2048 cycles less than 3/4 of the coefficient at 512 cycles.

(1) These figures are based on tests of Acoustex manufactured by the National Gypsum Company.



## PRE-FABRICATED ACOUSTIC UNITS

FEDERAL SPECIFICATION	Material	Manufacturer	Thick- ness	Mouit- ing	Weight (lb)	Fire Resistance
SS-A-118					sq ft	
CLASS E (.70 to .74)						
(Sound Absorption Coefficients at 512 cycles per second)						
VIII	Air-Acoustic Sheets	Johns-Manville Sales Corp.	1"	11	1.51	r
VII	Acoustex Type 50R	National Gypsum Company	7/8"	2	1.79	r
VII	Acoustex Type 70R	" "	1 1/8"	1	2.5	r
V	Acousti-Celotex Type C2	The Celotex Corporation	5/8"	1	.88	c
VI	Acoustone Type F, mill painted	U. S. Gypsum Company	13/16"	8	1.31	i
I	Arkustolith Tile Grade D	R. Guastavino Co.	4"	10	18.8	i
II	Calicel Acoustic Tile	The Celotex Corporation	1"	1	2.66	i
I	Calistone	" "	2"	5	9.3	i
VI	Corkoustic Type B5*	Armstrong Cork Co.	1 1/2"	1	.82	s
VIII	Fiberlite	The Insullite Co.	1/2"	2	.44	c
VII	Fibretex Type 50R	Johns-Manville Sales Corp.	7/8"	2	1.79	r
II	Kalite, cast on 1/4" backing of moulding plaster Grade A (Coarse)	Certain-teed Products Corp.	2"	4	--	i
VII	Koustex	David E. Kennedy, Inc.	1 1/2"	1	2.2	r
II	Muffleton, Travertine Finish	The Celotex Corporation	1"	1	1.96	i
III	Spongeacoustic	Johns-Manville Sales Corp.	3/4"	1	1.58	i
VIII	Studio Element	" "	1"	4	1.47	
CLASS F (.65 To .69)						
(Sound Absorption Coefficients at 512 cycles per second)						
VII	Absorbex Type C (14 gauge)	The Celotex Corporation	5/8"	2	--	r
V	Acousti-Celotex Type C2	" "	5/8"	1	.89	s
V	Acousti-Celotex Type C3	" "	13/16"	8	1.09	c
V	Acousti-Celotex Type C3	" "	15/16"	1	1.35	s
V	Acousti-Celotex Type C3	" "	13/16"	8	1.06	s
V	Acousti-Celotex Type C8	" "	1"	2	1.44	c
V	Acousti-Celotex Type M1	" "	9/16"	1	1.23	i
V	Acousti-Celotex Type M2	" "	1"	8	2.32	i
VI	Acoustone Type D*	United States Gypsum Co.	11/16"	1	1.30	i

\*Coefficient of sound absorption at 128 cycles less than 1/8 of the coefficient at 512 cycles.



PRE-FABRICATED ACCUSTIC UNITS

FEDERAL SPECIFICATION	Material	Material	Thickness	Mounting	Weight (lb)	Fire Resistance
SS-A-118					sq ft	
CLASS F (.65 to .69) Continued						
(Sound Absorption Coefficients at 512 cycles per second)						
TYPE						
VI	Acoustone Type F	United States Gypsum Co.	1 1/16"	1	1.15	i
VI	Acoustone Type F, mill painted*	" "	9/16"	1	.97	i
I	Acoustolith Grade B-1	R. Guastavino Company	2"	5	9.4	i
I	Acoustolith Grade B-2	" "	1 1/2"	4	6.1	i
VI	Corkoustic Type B5*	Armstrong Cork Company	1 1/2"	1	.75	s
VIII	Econacoustic	National Gypsum Company	1/2"	1 or 2	0.48	c
VIII	Hawaiian Cane Products	Hawaiian Cane Products, Ltd.	1"	1	0.75	c
VI	Kencoustic (cork)	David E. Kennedy, Inc.	1 1/2"	1	.88	s
II	Muffletone, Standard Finish	The Celotex Corporation	3/4"	1	1.62	i
VI	Permacoustic	Johns-Manville Sales Corp.	1"	5	2.33	i
VIII	Temcoustic F2	Armstrong Cork Company	7/8"	1	1.02	c

CLASS G (.60 to .64)						
(Sound Absorption Coefficients at 512 cycles per second)						
TYPE						
VII	Absorbex Type A	The Celotex Corporation	1"	1	2.4	r
VII	Acoustex Type 4OR	National Gypsum Company	3/4"	2	1.54	r
V	Acousti-Celotex Type C2	The Celotex Corporation	5/8"	2	.88	c
V	Acousti-Celotex Type C2	" "	5/8"	2	1.07	s
V	Acousti-Celotex Type C5	" "	13/16"	1	-	c
V	Acousti-Celotex Type C5	" "	13/16"	8	1.12	s
V	Acousti-Celotex Type MU-1	" "	1/2"	1	1.39	i
VI	Acoustone Type D	U. S. Gypsum Co.	9/16"	1	1.09	i
VI	Acoustone Type F, mill painted	" "	9/16"	1	.97	i
II	Calicel Acoustic Tile*	The Celotex Corporation	3/4"	1	-	i
I	Calistone	" "	4"	4	17.8	i
VII	Fibretext Type 4OR	Johns-Manville Sales Corp.	3/4"	2	1.54	r
II	Kalite cast on 1/4" backing of moulding plaster Grade A(Coarse)	Certain-teed Products Corp.	1 1/2"	4	-	i
VI	Kencoustic (cork) Type CB-1.5* **	David E. Kennedy, Inc.	1 1/2"	1	-	s
VIII	Maizewood Tile	Maizewood Products Corporation	1 1/2"	4	2.1	c

\*Coefficient of sound absorption at 128 cycles less than 1/8 of the coefficient at 512 cycles.  
 \*\*Coefficient of sound absorption at 2048 cycles less than 3/4 of the coefficient at 512 cycles.





PRE-FABRICATED ACOUSTIC UNITS

FEDERAL SPECIFICATION	Material	Manufacturer	Thickness	Mounting	Weight (lb)	Fire Resistance
SS-A-118					sq ft	
CLASS H (.55 to .59)						
(Sound Absorption Coefficients at 512 cycles per second)						
VII	Acoustex Type 30R	National Gypsum Company	5/8"	2	1.34	r
VII	Acoustex Type 60R	" "	1"	1	--	r
I	Acoustolith Tile Grade D	R. Guastavino Company	2"	4	--	i
VI	Cork* **	Armor Insulating Company	1 1/2"	1	0.96	s
VI	Corkoustic Type B4	Armstrong Cork Company	1 1/4"	1	.63	s
VI	Acoustone Type F	U. S. Gypsum Co.	5/16"	1	.38	i
VII	Fibretex Type 30R	Johns-Manville Sales Corp.	5/8"	2	1.34	r
VII	Fibretex Type 60R	" "	1"	1	--	r
II	Kalite, cast on 1/4" backing of moulding plaster, Grade D (fine)	Certain-teed Products Corp.	1 1/2"	4	--	i
II	Kalite, cast on 1/4" backing moulding plaster, Grade D (fine)	" "	2"	4	--	i
VIII	Quietone	U. S. Gypsum Company	1/2"	1	0.47	c
CLASS I (.50 to .54)						
(Sound Absorption Coefficients at 512 cycles per second)						
VII	Acoustex Type 60R	National Gypsum Company	1"	1	2.31	r
VIII	Air-Acoustic Sheets	Johns-Manville Sales Corp.	1/2"	11	.80	r
I	Acoustolith Tile Grade C	R. Guastavino Company	2"	4	10.1	i
VIII	Fiberlite	The Insulite Company	1/2"	1	.41	c
CLASS J (.45 to .49)						
(Sound Absorption Coefficients at 512 cycles per second)						
VII	Absorbex Type F (10 gauge)	The Celotex Corporation	1"	2	--	r
V	Acousti-Celotex Type C1	" "	1/2"	1	.78	c
I	Acoustolith Tile Grade B-2	R. Guastavino Company	1"	4	4.6	i
II	Kalite, cast on 1/4" backing of moulding plaster, Grade D (Fine)	Certain-teed Products Corp.	1"	4	--	i
II	Trutone, cast on 1/4" gypsum wall-board	Acoustone Company, Ltd.	7/8"	4	--	i

\*Coefficient of sound absorption at 128 cycles less than 1/8 of the coefficient at 512 cycles.

\*\*Coefficient of sound absorption at 2048 cycles less than 3/4 of the coefficient at 512 cycles.



PRE-FABRICATED ACOUSTIC UNITS

FEDERAL SPECIFICATION	Material	Manufacturer	Thickness	Mounting	Weight (lb)	Fire Resistance
SS-A-118					sq ft	
CLASS K (.40 to .44)						
TYPE V	Acousti-Celotex Type C1	The Celotex Corporation	1/2"	1	.88	s
I	Akoustolith Tile Grade C	R. Guastavino Company	1 1/2"	4	7.5	i
VIII	Hawaiian Cane Tile	Hawaiian Cane Products, Ltd.	1"	2	.81	c
II	Kalite, cast on 1/4" backing of moulding plaster, Grade A (Coarse)	Certain-teed Products Corp.	1"	4	-	i
CLASS L (.35 to .39)						
TYPE VII	Acoustex Type 4OR	National Gypsum Company	3/4"	1	1.75	r
VI	Acoustical Cork "B"	United Cork Companies	1 1/2"	2	.94	s
VII	Fibretex Type 4OR	Johns-Manville Sales Corp.	3/4"	1	1.75	r
VIII	Nuwood Bevel Lap Tile	Wood Conversion Co.	1"	6	1.41	c
VIII	Temlok Deluxe	Armstrong Cork Company	1/2"	4	1.18	c
VIII	Temlok Deluxe	" "	7/8"	4	1.19	c
VIII	Temlok Deluxe	" "	1 3/8"	4	1.65	c
CLASS M (.30 to .34)						
TYPE VII	Absorbex Type C	The Celotex Corporation	1"	4	-	r
VI	Cork*	Armor Insulating Company	1"	1	0.67	s
VIII	Nuwood Bevel Lap Tile	Wood Conversion Company	1/2"	6	0.69	c
II	KenKoustone	David E. Kennedy, Inc.	1"	1	2.74	-
CLASS N (.25 to .29)						
TYPE I	Akoustolith Tile Grade D	R. Guastavino Company	1"	4	-	i

\*Coefficient of sound absorption at 128 cycles less than 1/8 of the coefficient at 512 cycles.



PRE-FABRICATED ACOUSTIC UNITS

FEDERAL SPECIFICATION SS-A-113	Material	Manufacturer	Thickness	Mounting	Weight (lb)	Fire Resistance
TYPE					sq. ft.	

CLASS AA (.90 or over)

Noise Coefficients						
I	Alkoustolith Tile Grade C	R. Guastavino Company	5"	4	24.4	i
I	Alkoustolith Tile Grade C	"	5"	10	24.4	i
II	Berry-Cel, plus Rockwool at back of tile.	F. E. Berry, Jr. & Co., Inc.	1"	8	2.99	i
-	Stackoustic	Johns-Manville Sales Corp.	3" (tile)	4	1.3 plus wt. of covering	

CLASS BE (.85)

Noise Coefficients						
VII	Absorbatone	Luse Stevenson Company	1"	10	2.2	r
IV	Acousti-Metal, Rockwool pad, plus metal facing and pad supports, 1 5/8" plus furrings 5 1/4".	National Gypsum Company	-	8	0.98	i
I	Alkoustolith Tile Grade C	R. Guastavino Company	5"	5	24.4	i
II	Calicel Acoustic Tile	The Celotex Corporation	1"	5	2.66	i
II	Calicel Acoustic Tile	"	1 1/2"	5	3.42	i
IV	Perfatone, Rockwool pad plus metal facing & pad supports, plus furrings 8"	U. S. Gypsum Company	-	8	.93 (pad)	i
IV	Sanacoustic, Rockwool pad plus metal facing & pad supports, plus furrings 5 1/4"	Johns-Manville Sales Corp.	-	8	1.2 (pad)	i

CLASS CC (.80)

Noise Coefficients						
VII	Absorber Type A	The Celotex Corporation	1"	9	2.6	r
I	Alkoustolith Tile Grade B-1	R. Guastavino Company	1 1/2"	5	5.8	i
I	Alkoustolith Tile Grade C	"	4"	10	19.5	i
I	Alkoustolith Tile Grade C	"		Not nailed		
I	Alkoustolith Tile Grade C	"	4"	4	19.5	i
I	Alkoustolith Tile Grade D	"	4"	10	18.8	i
I	Alkoustolith Tile Grade D	"	4"	4	18.8	i
I	Alkoustolith Tile, Sample No. 104	"	4"	4	21.2	i



PRE-FABRICATED ACUSTIC UNITS

FEDERAL SPECIFICATION	Material	Manufacturer	Thickness	Mounting	Weight (lb) sq ft	Fire Resistance
SS-A-116						
CLASS CC (.80) Continued						
Noise Coefficients						
VI	Acoustone Type F, mill painted	U. S. Gypsum Co.	15/16"	1	1.54	i
II	Berry-Cel	F. E. Berry, Jr. & Co. Inc.	1"	8	2.57	i
I	Calistone	The Celotex Corporation	2"	5	9.3	i
I	Calistone	" "	5"	4	22.4	i
I	Calistone Type Y	" "	5"	4	25.7	i
IV	Sanacoustic, Rockwool pad, plus metal facing, pad supports and furring 2 1/2"	Johns-Manville Sales Corp.	--	3	1.2 (Pad)	i

FEDERAL SPECIFICATION	Material	Manufacturer	Thickness	Mounting	Weight (lb) sq ft	Fire Resistance
CLASS IC (.75)						
Noise Coefficients						
VII	Absorbex Type A on 1"	The Celotex Corporation	2"	4	--	r
VII	Absorbex Type F (10 gauge)	" "	2"	7	4.7	r
VIII	Absorbex Type F (6 gauge)	The Insulite Company	3/4"	2	0.57	c
VII	Acoustilite	National Gypsum Co.	1 1/8"	2	2.5	r
V	Acoustex Type 70R	The Celotex Corporation	1 1/2"	3	1.44	c
V	Acousti-Celotex Type C4	" "	13/16"	2	.86	c
V	Acousti-Celotex Type C5	" "	1 1/2"	8	1.65	s
V	Acousti-Celotex Type C6	" "	1 1/4"	1	2.58	i
V	Acousti-Celotex Type M3	" "	2"	5	9.4	i
I	Alkoustolith Tile Grade B-1	R. Guastavino Co.	15/16"	1	1.48	i
VI	Acoustone Type D	U. S. Gypsum Co.	15/16"	1	1.46	i
VI	Acoustone Type F	" "	13/16"	8	1.31	i
VI	Acoustone Type F, mill painted	" "	2"	5	9.4	i
I	Alkoustolith Tile Grade B-1	R. Guastavino Co.	5"	4	25.2	i
I	Basalt Rock Type A	Basalt Rock Company	1 1/4"	1	3.42	i
II	Calicel Acoustic Tile	The Celotex Corporation	2"	4	9.3	i
I	Calistone	" "	4"	4	17.6	i
I	Calistone, long edges splayed on opposite sides, 5 holes 3" in diam. through body of tile.	" "				





PRE-FABRICATED ACOUSTIC UNITS

FEDERAL SPECIFICATION	Material	Manufacturer	Thickness	Mounting	Weight (lb)	Fire Resistance
SS-A-113					sq. ft.	
CLASS DD (.75) Continued						
Noise Coefficients						
TYPE						
II	Mufflestone, Standard Finish	The Celotex Corporation	1"	1	1.83	i
VI	Permacoustic	Johns-Manville Sales Corp.	1"	5	2.33	i
VI	Permacoustic	" "	1"	1	2.33	i

CLASS EE (.70)						
Noise Coefficients						
TYPE						
VII	Acoustex Type 50R	National Gypsum Company	7/8"	2	1.79	r
VII	Acoustex Type 50R	" "	1"	2	2.07	r
VII	Acoustex Type 70R	" "	1 1/8"	1	2.5	r
V	Acousti-Celotex Type C3	The Celotex Corporation	13/16"	8	1.09	c
V	Acousti-Celotex Type C3	" "	13/16"	8	1.06	s
V	Acousti-Celotex Type C4	" "	1 1/4"	1	1.80	s
V	Acousti-Celotex Type C4	" "	1 1/4"	8	1.93	s
V	Acousti-Celotex Type C5	" "	13/16"	8	1.12	s
V	Acousti-Celotex Type C6	" "	1 1/4"	4	1.44	c
V	Acousti-Celotex Type C8	" "	1"	2	1.44	c
V	Acousti-Celotex Type M2	" "	1"	8	2.32	i
VI	Acoustone Type D	U. S. Gypsum Company	13/16"	1	1.40	i
VI	Acoustone Type F	" "	13/16"	1	1.24	i
VI	Acoustone Type F, mill painted	" "	1 1/16"	1	1.13	i
VI	Acoustone Type F, mill painted	" "	13/16"	1	1.33	i
VIII	Air-Acoustic Sheets	Johns-Manville Sales Corp.	1"	11	1.51	r
I	Alkacolith Tile Grade B-2	R. Guastavino Company	2"	4	8.5	i
II	Calicel Acoustic Tile	The Celotex Corporation	1"	1	2.66	i
VIII	Econacoustic	National Gypsum Company	1"	1	0.71	c
VII	Fibretext Type 50R	Johns-Manville Sales Corp.	7/8"	2	1.79	r
VII	Fibretext Type 60R	" "	1"	2	2.07	r
VII	Koustex	David E. Kennedy, Inc.	1 1/4"	1	2.2	r
II	Mufflestone, Standard Finish	The Celotex Corporation	1"	1	1.84	i
VI	Pyrocoustic	Minfelt Insulation Co.	13/16"	1	1.1	i
VIII	Studio Element	Johns-Manville Sales Corp.	1"	4	1.47	-
II	Travacoustic	National Gypsum Co.	1"	1	2.04	i



PRE-FABRICATED ACOUSTIC UNITS

FEDERAL SPECIFICATION	Material	Manufacturer	Thickness	Mounting	Weight (lb)	Fire Resistance
SS-A-118					sq. ft.	
CLASS FF (.65)						
Noise Coefficients						
VII	Acoustex Type 3OR	National Gypsum Company	5/8"	2	1.34	r
VII	Acoustex Type 4OR	" "	3/4"	2	1.54	r
VII	Acoustex Type 6OR	" "	1"	1	-	r
V	Acousti-Celotex Type C2	The Celotex Corporation	5/8"	2	.88	c
V	Acousti-Celotex Type C3	" "	13/16"	1	0.94	c
V	Acousti-Celotex Type C4	" "	1 1/2"	1	1.58	c
V	Acousti-Celotex Type M1	" "	9/16"	1	1.23	i
VIII	Acoustilite	The Insulite Company	3/4"	1	.59	c
VI	Acoustone Type D	U. S. Gypsum Company	11/16"	1	1.30	i
VI	Acoustone Type F	" "	11/16"	1	1.15	i
I	Alcoustolith Tile Grade B-2	R. Gustavino Company	1 1/2"	4	6.1	i
VIII	Fiberlite, painted by mfr.	The Insulite Company	1/2"	2	.44	c
VII	Fibretext Type 3OR	Johns-Manville Sales Corp.	5/8"	2	1.34	r
VII	Fibretext Type 4OR	" "	3/4"	2	1.54	r
VIII	Hawaiian Cane Tile	Hawaiian Cane Products Co.	1"	1	0.75	c
II	Kalite, Grade A (Coarse)	Certain-teed Products Corp.	2"	4	-	i
VII	Kencoustex	David E. Kennedy, Inc.	1"	1	2.24	r
VIII	Maizewood Tile	Maizewood Products Corp.	1 1/2"	4	2.1	c
II	Mufflstone, Travertine Finish	The Celotex Corporation	1"	1	1.96	i
VI	Pyrocoustic	Minfelt Insulation Company	13/16"	1	1.1	i
VIII	Quietone	U. S. Gypsum Company	1"	4	0.81	c
I	Sphinxstone	The Sphinx Acoustical Co.	2"	4	-	i
III	Spongecoustic	Johns-Manville Sales Corp.	3/4"	1	1.58	i
IV	Transite Acoustical Unit	" "	1 1/8"	4	3.0	i

CLASS GG (.60)						
Noise Coefficients						
VII	Absorbex Type A	The Celotex Corporation	1"	1	2.4	r
VII	Acoustex Type 6OR	National Gypsum Company	1"	1	2.31	r
V	Acousti-Celotex Type C2	The Celotex Corporation	5/8"	1	.88	c
V	Acousti-Celotex Type C2	" "	5/8"	1	.89	s



PRE-FABRICATED ACOUSTIC UNITS

FEDERAL SPECIFICATION SS-A-113	MATERIAL	MANUFACTURER	THICKNESS	MOUNTING	WEIGHT (lb) sq ft	FIRE RESISTANCE
CLASS GG (.50) Continued						
Noise Coefficients						
V	Acousti-Celotex Type C2	The Celotex Corporation	5/8"	2	1.07	s
V	Acousti-Celotex Type C3	" "	13/16"	1	1.35	s
VI	Acoustone Type D	U. S. Gypsum Co.	9/16"	1	1.09	i
VI	Acoustone Type F	" "	9/16"	1	.88	i
VI	Acoustone Type F, mill painted	" "	9/16"	1	.97	i
VIII	Air-Acoustic Sheets	Joins-Manville Sales Corp.	1/2"	11	.80	r
II	Calicel Acoustic Tile	The Celotex Corporation	3/4"	1	-	i
I	Calistone	" "	4"	4	17.8	i
VIII	Econacoustic	National Gypsum Co.	1/2"	1 or 2	0.48	c
II	Kalite, Grade A (Coarse)	Certain-teed Products Corp.	1 1/2"	4	-	i
II	Muffleton, Standard Finish	The Celotex Corporation	3/4"	1	1.62	i
VI	Temcoustic F-2	Armstrong Cork Company	7/8"	1	1.02	c
CLASS HH (.55)						
Noise Coefficients						
VII	Absorbex Type C (14 gauge)	The Celotex Corporation	1"	2	-	r
V	Acousti-Celotex Type C5	" "	13/16"	1	-	c
V	Acousti-Celotex Type MU-1	" "	1/2"	1	1.39	i
I	Akoustolith Tile Grade B-2	R. Guastavino Company	1"	4	4.0	i
I	Akoustolith Tile Grade C	" "	2"	4	10.1	i
I	Akoustolith Tile Grade D	" "	2"	4	-	i
VI	Corkoustic Type B5	Armstrong Cork Company	1 1/2"	1	.75	s
VI	Corkoustic Type B5	" "	1 1/2"	2	.75	s
VI	Corkoustic Type B5	" "	1 1/2"	1	.82	s
VI	Corkoustic Type B6	" "	1 1/2"	1	.85	s
VIII	Hawaiian Cane Tile	Hawaiian Cane Products, Ltd.	1"	2	.81	c
VIII	Fiberlite, painted by mfr.	The Insulite Company	1/2"	1	.41	c
II	Kalite, Grade D (Fine)	Certain-teed Products Corp.	1 1/2"	4	-	i
II	Kalite, Grade F (Fine)	" "	2"	4	-	i
VIII	Quietone	U. S. Gypsum Company	1/2"	1	0.47	c
II	Trutone Tile, cast on 1/4" gypsum wallboard	Acoustone Company, Ltd.	7/8"	4	-	i



PRE-FABRICATED ACOUSTIC UNITS

FEDERAL SPECIFICATION	Material	Manufacturer	Thickness	Mounting	Weight (lb) sq ft	Fire Resistance
CLASS II (.50)						
Noise Coefficients						
VII	Acoustex Type 4CR	National Gypsum Company	3/4"	1	1.75	r
I	Acoustolith Tile Grade C	R. Guastavino Company	1 1/8"	4	7.5	i
VI	Corboustic Type B4	Armstrong Cork Company	1 1/8"	1	.03	s
VII	Fibretex Type 4CR	Johns-Manville Sales Corp.	3/4"	1	1.75	r
II	Kalite, Grade A (Coarse)	Certain-teed Products Corp.	1"	4	-	i
VI	Zencoustic (cork)	David E. Kennedy, Inc.	1 1/8"	1	.88	s
CLASS JJ (.45)						
Noise Coefficients						
VII	Absorbex Type C	The Celotex Corporation	1"	4	-	r
VII	Absorbex Type F (10 gauge)	" "	1"	2	-	r
V	Acousti-Celotex Type C1	" "	1/2"	1	.78	c
II	Kalite, Grade D (Fine)	Certain-teed Products Corp.	1"	4	-	i
VI	Zencoustic (cork) Type CE-1.5	David E. Kennedy, Inc.	1 1/8"	1	-	s
CLASS KK (.40)						
Noise Coefficients						
V	Acousti-Celotex Type C1	The Celotex Corporation	1/2"	1	.88	s
I	Acoustolith Tile Grade D	R. Guastavino Company	1"	4	-	i
VI	Acoustical Cork "E"	United Cork Companies	1 1/8"	2	.94	s
VIII	Temlok DeLuxe	Armstrong Cork Company	7/8"	4	1.19	c
VIII	Temlok DeLuxe	" "	1 3/8"	4	1.5	c
CLASS LL (.35)						
Noise Coefficients						
VI	Cork	Armor Insulating Company	1"	1	.67	s
VI	Cork	" "	1 1/8"	1	.96	s
VIII	Muwood Bevel Lap Tile	Wood Conversion Company	1"	6	1.41	c
CLASS MM (.30)						
Noise Coefficients						
VIII	Muwood Bevel Lap Tile	Wood Conversion Company	1/2"	6	0.09	c
VIII	Temlok DeLuxe	Armstrong Cork Company	1/2"	4	1.18	c
CLASS OO (.20)						
Noise Coefficients						
II	KenKoustone	David E. Kennedy, Inc.	1"	1	2.34	-





## ACOUSTIC MATERIALS FOR PLASTIC APPLICATION

FEDERAL SPECIFICATION	Material	Manufacturer	Thickness
SS-A-111			
		CLASS A (.90 or over)	
TYPE	Sound Absorption Coefficients (at 512 cycles per second)		
III	Limpet (Sprayed Asbestos), applied with air gun on metal lath, finished with roller. Not painted.	Keasbey & Mattison Company	3/4"
III	Limpet (Sprayed Asbestos), applied with air gun on metal lath, finished with roller. Not painted.	Keasbey & Mattison Company	1/2"
III	Limpet (Sprayed Asbestos), applied with air gun on gypsum wall board, finished with roller. Not painted.	Keasbey & Mattison Company	1 1/2"
III	Spray-Acoustic Type X, applied with air gun on gypsum wall board, finished with roller.	Sprayo-Flake Co.	1 1/8"
		CLASS B (.85 to .89)	
III	Spray-Acoustic Type X, applied with air gun on metal lath, finished with roller.	Sprayo-Flake Co.	5/8"
		CLASS E (.70 to .74)	
III	Limpet (Sprayed Asbestos), applied with air gun on gypsum wall board. Not painted.	Keasbey & Mattison Co.	3/4"
		CLASS F (.65 to .69)	
I	Macoustic Plaster, trowel finish	National Gypsum Company	3/4"
I	Stucoustic Plaster Type A.D.	California Stucco Products of New England, Inc.	3/4"



ACOUSTIC MATERIALS FOR PLASTIC APPLICATION

FEDERAL SPECIFICATION	Material	Manufacturer	Thickness
CLASS G (.60 to .64)			
TYPE	Sound Absorption Coefficients (at 512 cycles per second)		
I	Kalite Plaster H, coarse aggregate	Certain-teed Products Corp.	3/4"
I	Old Newark Acoustic Plaster	Newark Plaster Company	3/4"
CLASS H (.55 to .59)			
I	Sabinito Plaster A	U. S. Gypsum Company	3/4"
CLASS I (.50 to .54)			
Sound Absorption Coefficients (at 512 cycles per second)			
I	Hushkote Acoustic Plaster	Cleveland Gypsum Supply Co.	5/8"
III	Limpet (Sprayed Asbestos), applied with air gun on hard asbestos board.	Keasboy & Mattison Company	1/2"
I	Macoustic Plaster, trowel finish	National Gypsum Company	1/2"
I	Reverbolite Plaster (Regular)	The Celotex Corporation	1/2"
I	Stucoustic Plaster, Type A.D.	California Stucco Products of New England, Inc.	1/2"
CLASS J (.45 to .49)			
Sound Absorption Coefficients (at 512 cycles per second)			
I	Hushkote Acoustic Plaster	Cleveland Gypsum Supply Co.	1/2"
I	Hushkote Acoustic Plaster	" "	3/4"
I	Kalite Plaster H, Coarse Aggregate	Certain-teed Products Corp.	1/2"
I	Super-Acoustic Plaster	Gypsum Insulation & Mfg. Co.	1/2"



ACOUSTIC MATERIALS FOR PLASTIC APPLICATION

FEDERAL SPECIFICATION	Material	Manufacturer	Thickness
SS-a-111			
		CLASS K (.40 to .44)	
		Sound Absorption Coefficients (at 512 cycles per second)	
I	Acoustic Plaster	Hollywood Stucco Products, Inc.	1/2"
I	Calacoustic Plaster	Pacific Portland Cement Co.	1/2"
I	Macoustic Plaster, trowel finish	National Gypsum Company	1/2"
I	Old Newark Acoustic Plaster	Newark Plaster Company	1/2"
I	Reverbolite Plaster (Furice Aggregate)	The Celotex Corporation	1/2"
I	Sabinite Plaster F	U. S. Gypsum Company	1/2"
		CLASS L (.35 to .39)	
		Sound Absorption Coefficients (at 512 cycles per second)	
I	Akoustolith Plaster	R. Guastavino Company	3/4"
I	Rockwall Acoustic Plaster	National Gypsum Company	1/2"
I	Sabinite Plaster A	U. S. Gypsum Company	1/2"
		CLASS M (.30 to .34)	
		Sound Absorption Coefficients (at 512 cycles per second)	
I	Dodson Acoustic Plaster	The Dodson Manufacturing Co.	3/4"
		CLASS N (.25 to .29)	
		Sound Absorption Coefficients (at 512 cycles per second)	
I	Sabinite Plaster Hydraulic	U. S. Gypsum Company	1/2"
		CLASS P (less than .20)	
		Sound Absorption Coefficients (at 512 cycles per second)	
I	Akoustolith Plaster	R. Guastavino Company	1/4"



ACOUSTIC MATERIALS FOR PLASTIC APPLICATION

FEDERAL SPECIFICATION SS-A-111	FEDERAL SPECIFICATION Material	Manufacturer	Thickness
CLASS AA (.90) Noise Coefficients			
III	Limpet (Sprayed Asbestos), applied with air gun on metal lath.	Keasbey & Mattison Co.	3/4"
III	Limpet (Sprayed Asbestos), applied with air gun on gypsum wall board.	" " "	1 1/2"
III	Spray-Acoustic Type X, applied with air gun on metal lath.	Sprayo-Flake Co.	5/8"
CLASS BB (.85) Noise Coefficients			
III	Limpet (Sprayed Asbestos), applied with air gun on metal lath.	Keasbey & Mattison Co.	1/2"
III	Spray-Acoustic Type X, applied with air gun on gypsum wall board.	Sprayo-Flake Co.	1 1/8"
CLASS EE (.70) Noise Coefficients			
III	Limpet (Sprayed Asbestos), applied with air gun on gypsum wall board.	Keasbey & Mattison Co.	3/4"
CLASS GG (.60) Noise Coefficients			
I	Old Newark Acoustic Plaster	Newark Plaster Co.	3/4"
I	Sabinite Plaster A	U. S. Gypsum Co.	3/4"
I	Stucoustic Plaster	California Stucco Products of New England, Inc.	1/2"





## ACOUSTIC MATERIALS FOR PLASTIC APPLICATION

FEDERAL SPECIFICATION SS-A-111	Material	Manufacturer	Thickness
	CLASS HH (.55) Noise Coefficients		
TYPE			
I	Acoustic Plaster	Hollywood Stucco Products, Inc.	1/2"
I	Kalite Plaster H, Coarse Aggregate	Certain-teed Products Corp.	3/4"
I	Kalite Plaster H, Coarse Aggregate	" " "	1/2"
I	Macoustic Plaster, trowel finish	" " "	1/2"
I	Macoustic Plaster, trowel finish	National Gypsum Company	3/4"
I	Reverbolite Plaster (Regular)	" " "	1/2"
I	Sabinite Plaster A	The Celotex Corporation	1/2"
I	Sabinite Plaster F	U. S. Gypsum Company	1/2"
I	Stuacoustic Plaster Type A.D.	" " "	1/2"
		California Stucco Products of New England, Inc.	3/4"
	CLASS II (.50) Noise Coefficients		
I	Calacoustic Plaster	Pacific Portland Cement Co.	1/2"
I	Hushkote Acoustic Plaster	Cleveland Gypsum Co.	1/2"
I	Old Newark Acoustic Plaster	Newark Plaster Co.	1/2"
I	Rockwall Acoustic Plaster, trowel finish	National Gypsum Co.	1/2"
I	Super-Acoustic Plaster	Gypsum Insulation & Mfg. Co.	1/2"
	CLASS JJ (.45) Noise Coefficients		
I	Akoustolith Plaster	R. Guastavinc Company	3/4"
I	Hushkote Acoustic Plaster	Cleveland Gypsum Company	5/8"
I	Hushkote Acoustic Plaster	" " "	3/4"
I	Reverbolite Plaster (Pumice Aggregate)	The Celotex Corporation	1/2"



ACOUSTIC MATERIALS FOR PLASTIC APPLICATION

FEDERAL SPECIFICATION	Material	Manufacturer	Thickness
SS-A-111			
		CLASS KX (.40) Noise Coefficients	
I	Dodson Acoustic Plaster	The Dodson Manufacturing Co.	3/4"
I	Macoustic Plaster, trowel finish	National Gypsum Company	1/2"
I	Rockwall Acoustic Plaster, cork float finish	" " "	1/2"
		CLASS LL (.35) Noise Coefficients	
I	Sabirite Plaster (Hydraulic)	U. S. Gypsum Company	1/2"
		CLASS III (.25) Noise Coefficients	
I	Akoustolith Plaster	R. Guastavino Company	1/4"

