

NBS CIRCULAR 552

2d Edition

Standard Samples
A Catalog of Reference Materials
Issued by the
National Bureau of Standards

UNITED STATES DEPARTMENT OF COMMERCE

NATIONAL BUREAU OF STANDARDS

U. S. DEPARTMENT OF COMMERCE

Sinclair Weeks, Secretary

NATIONAL BUREAU OF STANDARDS

A. V. Astin, Director



The National Bureau of Standards

Functions and Activities

The functions of the National Bureau of Standards are set forth in the Act of Congress, March 3, 1901, as amended by Congress in Public Law 619, 1950. These include the development and maintenance of the national standards of measurement and the provision of means and methods for making measurements consistent with these standards; the determination of physical constants and properties of materials; the development of methods and instruments for testing materials, devices, and structures; advisory services to Government Agencies on scientific and technical problems; invention and development of devices to serve special needs of the Government; and the development of standard practices, codes, and specifications. The work includes basic and applied research, development, engineering, instrumentation, testing, evaluation, calibration services, and various consultation and information services. A major portion of the Bureau's work is performed for other Government Agencies, particularly the Department of Defense and the Atomic Energy Commission. The scope of activities is suggested by the listing of divisions and sections on the inside of the back cover.

Publications

The results of the Bureau's work take the form of either actual equipment and devices or published papers, these papers appear either in the Bureau's own series of publications or in the journals of professional and scientific societies. The Bureau itself publishes three monthly periodicals, available from the Government Printing Office: The Journal of Research, which presents complete papers reporting technical investigations; the Technical News Bulletin, which presents summary and preliminary reports on work in progress; and Basic Radio Propagation Predictions, which provides data for determining the best frequencies to use for radio communications throughout the world. There are also five series of nonperiodical publications: The Applied Mathematics Series, Circulars, Handbooks, Building Materials and Structures Reports, and Miscellaneous Publications.

Information on the Bureau's publications can be found in NBS Circular 460, Publications of the National Bureau of Standards (\$1.25) and its Supplement (\$0.75), available from the Superintendent of Documents, Government Printing Office, Washington 25, D. C.

UNITED STATES DEPARTMENT OF COMMERCE • Sinclair Weeks, *Secretary*

NATIONAL BUREAU OF STANDARDS • A. V. Astin, *Director*

Standard Samples

A Catalog of Reference Materials

Issued by the National Bureau of Standards



National Bureau of Standards Circular 552 (Second Edition)

Issued April 15, 1957

Supersedes Circular 552, August 31, 1954

CONTENTS

	Page
1. General information.....	1
1.1. Introductory.....	1
1.2. Standards out of stock.....	1
1.3. New standards.....	1
2. Purchase procedure.....	2
2.1. Identification of samples.....	2
2.2. Ordering.....	2
2.3. Terms and shipping.....	2
2.3.1. Domestic shipments.....	2
2.3.2. Foreign shipments.....	2
2.3.3. Payment for foreign orders.....	2
3. Descriptive list of reference materials, with weights and fees.....	3
3.1. Standard samples of certified chemical composition.....	3
3.1.1. Chemical standards.....	3
Steels.....	3
Irons.....	3
Steel-making alloys.....	4
Nonferrous alloys.....	4
Titanium-base alloys.....	4
Ores.....	4
Ceramic materials.....	4
3.1.2. Spectrographic standards.....	5
Low-alloy steels.....	5
Stainless steels.....	5
Tool steels.....	5
Aluminum alloys.....	5
Nickel oxides.....	5
Tin metal.....	6
Zinc-base die-casting alloys.....	6
3.2. Standard samples of certified properties or purity.....	6
3.2.1. Microchemical standards.....	6
3.2.2. Chemicals.....	6
3.2.3. pH standards.....	6
3.2.4. Hydrocarbons and organic sulfur compounds.....	7
Paraffins.....	7
Alkyl cyclopentanes.....	8
Alkyl cyclohexanes.....	8
Monoolefins.....	9
Diolefins.....	9
Cyclomonoolefins.....	10
Acetylenes.....	10
Alkyl benzenes.....	10
Naphthalenes.....	11
Polycyclic aromatic hydrocarbons.....	11
Organic sulfur compounds.....	11
3.2.5. Melting-point standards.....	12
3.2.6. Viscometer calibrating liquids.....	12
3.2.7. Radioactivity standards.....	13
Alpha, beta, gamma standards.....	13
Radium standards (for radon analysis).....	13
Radium gamma-ray standards.....	14
Rock standards.....	14
3.3. Standard rubbers and rubber compounding materials.....	14
3.3.1. Rubbers.....	14
3. Descriptive list of reference materials—Continued	1
3.3 Standard rubbers, etc.—Continued	1
3.3.2. Rubber compounding materials.....	14
3.4. Miscellaneous standard materials.....	15
3.4.1. Turbidimetric and fineness standard.....	15
3.4.2. Paint pigments for color and tinting strength only.....	15
3.4.3. Light sensitive papers.....	15
3.4.4. Standard colors for kitchen and bathroom accessories.....	15
3.4.5. Limestone slabs for calking compound tests.....	15
4. Summary of analyses.....	16
4.1. Averaged analyses.....	16
Aluminum-base alloys (chemical standards).....	16
Cobalt-base alloys.....	16
Copper-base alloys.....	16
Lead- and tin-base alloys.....	16
Magnesium-base alloy.....	16
Nickel-base alloys (chemical standards).....	17
Titanium-base alloys.....	17
Zinc-base die-casting alloy (chemical standard).....	17
Steel-making alloys.....	17
Iron ores.....	17
Irons (chemical standards).....	18
Steels (chemical standards).....	18
Low alloy steels (spectrographic standards).....	20
Stainless steels (spectrographic standards).....	20
Tool steels (spectrographic standards).....	21
Aluminum alloys (spectrographic standards).....	21
Nickel oxides (spectrographic standards).....	21
Tin metal (spectrographic standards).....	21
Zinc-base die-casting alloys (spectrographic standards).....	21
Manganese ore.....	22
Tin ores.....	22
Zinc ore.....	22
Phosphate rock.....	22
Alumina refractories, bauxite, cement, and clays.....	22
Feldspar.....	22
Glass sands.....	23
Glasses.....	23
Limestone, dolomite, silica brick, burned magnesite, and titanium dioxide.....	23
Silicon carbide.....	23
4.2. Chemicals.....	24
Acid potassium phthalate.....	24
Benzoinic acid.....	24
Sodium oxalate.....	24
Arsenic trioxide.....	24
Potassium dichromate.....	24
Sugars.....	24

Standard Samples

A Catalog of Reference Materials Issued by the National Bureau of Standards

A descriptive listing of the various Standard Samples issued by the National Bureau of Standards is given. A schedule of weights and fees, as well as directions for ordering, is included. Summarized tables of analyses are presented, to indicate the type of standards of composition presently available. Announcements of new standards will be made in scientific and trade journals, and the current status of the various standards will be indicated by an insert sheet issued with the Circular.

1. General Information

1.1. Introductory

This Circular lists the reference materials issued by the National Bureau of Standards and provides information on their procurement. Each of these materials bears a distinguishing name and number, by which it is permanently identified, and each sample bearing a given designation is of identical composition or properties (within the limits required by the use for which the material is intended) with every other sample bearing the same designation.

The first reference materials issued by this Bureau were a small group of metals certified with respect to their chemical composition. Because of their use as standards in chemical analysis, the term "Standard Samples" was applied to them. This term was extended first to similar composition standards, and later to cover materials certified with respect to chemical purity or to some physical or chemical property. By usage the term has been extended also to certain reference materials that are issued without certification of composition or properties. In this Circular the materials are classified into groups according to the purposes for which they are intended and the kind of certification, if any, that applies to them.

More than 500 different Standard Samples of metals, ores, ceramics, chemicals, and hydrocarbons are now available for distribution. About 225 of these are certified for chemical composition. Some 90 of the composition standards have been prepared specifically for use in spectrographic analysis. Other standard samples include those certified for such properties as acidity (*pH*), viscosity, melting-point, density, index of refraction, and heat of combustion. Recent additions include a number of radioactive materials for use in nuclear physics, biochemical research, and allied fields.

Some of the principal uses of NBS standard samples are: Checking methods of analysis and analytical techniques; standardizing solutions for volumetric analysis; developing new or improved methods of analysis; evaluating the accuracy of analytical methods; and calibrating and stand-

ardizing spectrometers, spectrographs, colorimeters, *pH* meters, Geiger counters, scintillators, ionization chambers, pyrometers, polarimeters, refractometers, viscometers, and other laboratory and plant instruments.

Standard hydrocarbons, certified for degree of purity, serve to calibrate instruments used in controlling the production of plastics, synthetic rubber, and motor fuels.

Also listed in the Circular are a number of reference materials for which it is not feasible to supply numerical values of composition or properties or for which such certification would not be useful. These materials nevertheless provide assurance of identity among all samples bearing a given designation and thus permit standardization of test procedures and referral of physical or chemical data on unknown materials to a common basis.

Information on certain physical standards, individually certified and intended primarily for the calibration of instruments, that was formerly included in the Circular, does not appear in this edition. For information on these calibration standards consult "Test Fee Schedules of the National Bureau of Standards." Copies are available free on request.

1.2. Standards Out of Stock

The preparation of "renewal" samples is intended to be completed at the time each kind of sample becomes exhausted, but owing to delays encountered in obtaining a proper grade of material and for other reasons, this is not always possible. If orders are received for samples that are out of stock, notice will be mailed to that effect. The composition of a "renewal" of an analyzed sample will not usually be identical with that of its predecessor, but it will be quite similar, especially with regard to the characteristic constituent or constituents.

1.3. New Standards

When new samples or renewals of old ones are issued, announcement will be made in scientific and trade journals and in the Federal Register.

2. Purchase Procedure

2.1. Identification of Samples

The samples are listed by groups; the sample numbers represent the order of issuance of the first representative of each kind. Renewals of an analyzed sample are indicated by the original number, with an added letter to denote its intended relation. Thus, 10a is the first, 10b the second, and 10c the third renewal of No. 10 Bessemer 0.4 C steel. In this way a given number will always represent a material of fixed or approximately fixed composition. Numbers missing from the series in the following table represent samples of which the supply has become exhausted and which it is not the present intention to replace.

2.2. Ordering

Orders should give both the *number and name* of the sample wanted. Example: No. 10g, steel, Bessemer, 0.4 C. The list of standard samples, their numbers, prices, and analyses are to be found in the succeeding pages. No samples of smaller size than those listed are distributed.

For oils and hydrocarbons, see special order procedure indicated on page 12.

2.3. Terms and Shipping

2.3.1. Domestic Shipments

Shipments of material (other than hydrocarbons, organic sulfur compounds and radioactive standards) intended for the United States, its posses-

sions, Mexico, Canada, and Cuba are normally shipped prepaid parcel post unless the purchaser requests a different mode of shipment, in which case the shipment will be sent collect. Hydrocarbons, organic sulfur compounds, rubber compounding materials, viscometer calibrating oils, and radioactive standards are shipped express collect. (See page 12.) No discounts are given on NBS Standard samples.

2.3.2. Foreign Shipments

Small shipments will be forwarded as a United States Government shipment via International Parcel Post (providing that the parcel does not exceed the weight limits as prescribed by Postal Laws and Regulations to foreign countries). Shipments exceeding the parcel post weight limit must be handled through an agent (shipping or brokerage firm) located in the United States as designated by the purchaser. Parcels will be packed for overseas shipment and forwarded via express collect to the United States firm designated as agent.

2.3.3. Payment for Foreign Orders

Remittances in payment of foreign orders must be made payable to the National Bureau of Standards, and are required in advance. These remittances must be drawn on a bank in the United States and payable at the standard rate of United States currency.

3. Descriptive List of Reference Materials With Weights and Fees

3.1. Standard Samples of Certified Chemical Composition

[For detailed information on compositions and properties certified, see p. 16 to 24, as indicated in the table of contents, p. ii.
 (See mimeographed insert for standards out of stock, renewals, and new standards.)]

3.1.1. Chemical Standards

Sample No.	Name	Approximate weight of sample in grams	Price per sample	Sample No.	Name	Approximate weight of sample in grams	Price per sample
STEELS							
8h	Bessemer, 0.1 C-----	150	\$4.50	72f	Cr-Mo (SAE X4130)-----	150	\$4.50
10g	Bessemer, 0.3 C-----	150	4.50	111b	Ni-Mo (SAE 4620)-----	150	4.50
170	B. O. H., 0.03 C, 0.2 Ti-----	150	4.50	36a	Cr2-Mo1-----	150	4.50
15f	B. O. H., 0.1 C-----	150	4.50	106a	Cr-Mo-Al (Nitr alloy G)-----	150	4.50
11g	B. O. H., 0.2 C-----	150	4.50	139	Cr-Ni-Mo (NE 8637)-----	150	4.50
12f	B. O. H., 0.4 C-----	150	4.50	156	Cr-Ni-Mo (NE 9450)-----	150	4.50
152	B. O. H., 0.5 C, 0.04 Sn-----	150	4.50	159	Cr1-Mo0.4-Ag0.1-----	150	4.50
13e	B. O. H., 0.6 C-----	150	4.50				
14d	B. O. H., 0.8 C-----	150	4.50	50c	W18-Cr4-V1-----	150	4.75
16d	B. O. H., 1.0 C-----	150	4.50	132a	Mo5-W6-Cr4-V1.5-----	150	5.00
					Mo8-W2-Cr4-V1-----	150	4.75
19f	A. O. H., 0.2 C-----	150	4.50	153	Mo8-W1.5-Cr4-V2-Co8-----	150	4.75
20f	A. O. H., 0.4 C-----	150	4.50	155	Cr0.5-W0.5-----	150	4.75
					Co43-Mo4-Nb3-W4 (S-816)-----	150	5.75
51b	Electric furnace, 1.2 C-----	150	4.50	168	Co41-Mo4-Nb3-Ta1-W4 (S-816)-----	150	5.75
65d	Basic electric, 0.3 C-----	150	4.50	73b	Stainless (Cr12)-----	150	5.00
100a	Manganese (SAE T1345)-----	150	4.50	133a	Stainless (Cr13-Mo0.3-S0.3)-----	150	4.75
105	High-sulfur, 0.2 C (carbon only)-----	150	2.00	101d	Cr18-Ni9 (SAE 30905)-----	150	4.75
125a	High-silicon, 3 Si-----	150	4.50				
129a	High-sulfur (SAE X1112)-----	150	4.50	121b	Cr18-Ni11 (Ti-bearing)-----	150	4.75
130a	Lead-bearing, 0.2 Pb-----	150	5.00	123b	Cr-Ni-Nb 0.7-Ta 0.2-----	150	5.00
151	Boron-bearing, 0.003 B-----	150	3.00	160a	Cr19-Ni9-Mo3-----	150	5.00
					Cr19-Ni9 (carbon only)-----	150	4.50
30e	Cr-V (SAE 6150)-----	150	4.50	166a			
32e	Cr-Ni (SAE 3140)-----	150	4.50	126b	High-nickel (Ni36)-----	150	5.00
33d	Ni-Mo (SAE 4820)-----	150	4.50	161	Casting alloy (Ni64-Cr17-Fe15)-----	150	4.75
IRONS							
3	White iron-----	125	\$4.25	82a	Nickel-chromium cast iron-----	150	\$4.75
4i	Cast iron-----	150	4.75	107a	Nickel-chromium-molybdenum cast iron-----	150	4.75
5k	Cast iron-----	150	4.75				
6f	Cast iron-----	150	4.75				
7f	Cast iron-----	150	4.75	122d	Cast iron (car wheel)-----	150	4.75
55d	Ingot iron-----	150	4.75				

3. Descriptive List of Reference Materials With Weights and Fees—Continued

3.1. Standard Samples of Certified Chemical Composition—Continued

3.1.1. Chemical Standards—Continued

Sample No.	Name	Approximate weight of sample in grams	Price per sample	Sample No.	Name	Approximate weight of sample in grams	Price per sample
STEEL-MAKING ALLOYS							
57	Refined silicon	60	\$4.00	66a	Spiegeleisen	100	\$4.00
58	Ferrosilicon (Si 75%)	75	4.00	68b	Ferromanganese	100	4.00
61a	Ferrovanadium (high carbon)	100	4.00	71	Calcium molybdate	60	4.00
64b	Ferrochromium (high carbon)	100	4.00	90	Ferrophosphorus	75	4.00
				116b	Ferrotitanium (low carbon)	100	4.00
NONFERROUS ALLOYS							
85b	Aluminum alloy, wrought	75	\$4.50	124c	Bronze (Cu85-Pb5-Sn5-Zn5)	150	\$5.75
86c	Aluminum-base casting alloy	75	4.50	158	Bronze, silicon	150	5.75
87a	Aluminum-silicon alloy	75	4.50	167	Co43-Mo4-Nb3-W4	150	5.75
53d	Bearing metal, lead-base	170	5.75	168	Co41-Mo4-Nb3-Ta1-W4	150	5.75
54d	Bearing metal, tin-base	170	5.75	157a	Nickel silver (Cu58-Ni12-Zn29)	135	5.75
37d	Brass, sheet	150	5.75	161	Nickel-base casting alloy	150	4.75
52c	Bronze, cast	150	5.75	169	Ni77-Cr20 alloy	150	5.75
184	Bronze, leaded-tin	150	5.75	171	Magnesium-base alloy	100	4.00
62c	Bronze, manganese	150	5.75	127a	Solder (Pb70-Sn30)	170	5.75
164	Bronze, manganese-aluminum	150	5.75	94b	Zinc-base die-casting alloy	150	4.50
63c	Bronze, phosphorus	150	5.75				
TITANIUM-BASE ALLOYS							
173	Al6-V4	100	\$7.00	174	Al4-Mn4	100	\$7.00
ORES							
69a	Bauxite	60	\$4.00	56b	Phosphate rock (Tennessee)	45	\$4.00
27c	Iron ore, Mesabi	125	4.00	137	Tin ore (Bolivian concentrate)	50	4.00
28a	Iron ore, Norrie	50	2.00	138	Tin ore (N. E. I. concentrate)	50	4.00
25c	Manganese ore	100	4.00	113	Zinc ore (Tri-State concentrate)	50	4.00
CERAMIC MATERIALS							
76	Burned refractory (40% Al ₂ O ₃)	60	\$4.00	93	Glass, high boron	45	\$4.00
77	Burned refractory (60% Al ₂ O ₃)	60	4.00	81	Glass sand	60	4.00
78	Burned refractory (70% Al ₂ O ₃)	60	4.00	165	Glass sand (low iron)	60	4.00
177	Cement, portland	15	4.25	1a	Limestone, argillaceous	50	4.00
97	Clay, flint	60	4.00	88	Limestone, dolomitic	50	4.00
98	Clay, plastic	60	4.00	102	Silica brick	60	4.00
99	Feldspar, soda	40	4.00	104	Burned magnesite	60	4.00
89	Glass, lead-barium	45	4.00	112	Silicon carbide	85	4.00
91	Glass, opal	45	4.00	154a	Titanium dioxide	40	3.75
92	Glass, low boron	45	4.00				

3. Descriptive List of Reference Materials With Weights and Fees—Continued

3.1. Standard Samples of Certified Chemical Composition—Continued

3.1.2. Spectrographic Standards

Sample Nos. ¹	Name	Price per sample ²	Sample Nos. ¹	Name	Price per sample ¹
LOW-ALLOY STEELS					
401	(3) B. O. H., 0.4C	\$5.00	414	(3) Cr-Mo (SAE 4140)	\$5.00
402	802 B. O. H., 0.8C	5.00	415a	Bessemer, 0.5C	5.00
403a	803a A. O. H., 0.6C	5.00	416a	(3) Nitr alloy G	5.00
404a	804a Basic electric	5.00			
405a	805a Medium manganese	5.00	417	(3) A. O. H., 0.4C	5.00
			417a	B. O. H., 0.4C	5.00
407a	807a Chromium-vanadium	5.00	418	(3) Cr-Mo (SAE X4130)	5.00
408a	808a Chromium-nickel	5.00	418a	Cr-Mo (SAE X4130)	5.00
409b	809b Nickel	5.00	419	(3) Ni-Mo (SAE 4620)	5.00
410a	810a Cr2-Mo1	5.00	420a	820a Ingot iron	5.00
			421	821 Cr-W, 0.9C	5.00
411a	811a Cr-Mo (SAE X4130)	5.00	425	825 Mn-Ni-Cr (NE 9450) (boron only)	5.00
412a	812a Cr-Ni-Mo (NE 8637)	5.00	427	827 Cr-Mo (SAE 4150) (boron only)	5.00
413	(3) A. O. H., 0.4C	5.00	428	(3) Mn-Cr (boron only)	5.00
			830	Ni-Cr-B (boron only)	5.00

STAINLESS STEELS

		Minor and trace elements			Major and minor elements	
442	(3)	Stainless (Cr16-Ni10)	\$8.00	445	845 Cr13-Mo0.9 (Modified AISI 410)	\$6.00
443	(3)	Stainless (Cr18-Ni9)	8.00	446	846 Cr18-Ni9 (Modified AISI 321)	6.00
444	(3)	Stainless (Cr21-Ni10)	8.00	447	847 Cr24-Ni13 (Modified AISI 309)	6.00
				448	848 Cr9-Mo0.3 (Modified AISI 403)	6.00
				449	849 Cr5.5-Ni6.5	6.00
				450	850 Cr3-Ni25	6.00

TOOL STEELS

436	836	Special (Cr6-Mo3-W10)	\$8.00	439	839 Mo High Speed (AISI-SAE M36)	\$8.00
437	837	Special (Cr8-Mo2-W3-Co3)	8.00	440	840 Special W High Speed (Cr2-W13-Co12)	8.00
438	838	Mo High Speed (AISI-SAE M30)	8.00	441	841 W High Speed (AISI-SAE T1)	8.00

¹ Sizes: 400 series, rods $\frac{7}{32}$ in. in diameter, 4 in. long (20 g); 800 series, rods $\frac{1}{2}$ in. in diameter, 2 in. long (50 g).

² For each sample in the 400 and 800 series.

³ This standard is available in only one size.

Sample No.	Name	Approximate weight of sample in grams	Price per sample	Sample No.	Name	Approximate weight of sample in grams	Price per sample
------------	------	---------------------------------------	------------------	------------	------	---------------------------------------	------------------

ALUMINUM ALLOYS

602 ¹	Aluminum alloy, wrought (2024)	160	\$8.00	604	Aluminum-base casting alloy (142)	160	\$8.00
------------------	--------------------------------	-----	--------	-----	-----------------------------------	-----	--------

¹ Size: Disks $\frac{21}{2}$ in. in diameter, $\frac{3}{4}$ in. thick.

NICKEL OXIDES¹

671 ²	Nickel oxide 1	25	\$4.00	672	Nickel oxide 2	25	\$4.00
------------------	----------------	----	--------	-----	----------------	----	--------

¹ Although intended primarily as spectrographic standards, these samples are equally suitable for chemical standards.

² Each sample consists of 25 g of powder.

3. Descriptive List of Reference Materials With Weights and Fees—Continued

3.1. Standard Samples of Certified Chemical Composition—Continued

3.1.2. Spectrographic Standards—Continued

Sample No.	Name	Approximate weight of sample in grams	Price per sample	Sample No.	Name	Approximate weight of sample in grams	Price per sample
TIN METAL							
431 ¹	Tin A	25	\$8.00	831 ¹	Tin A	45	\$14.00
432	Tin B	25	8.00	832	Tin B	45	14.00
433	Tin C	25	8.00	833	Tin C	45	14.00
434	Tin D	25	8.00	834	Tin D	45	14.00
435	Tin E	25	8.00	835	Tin E	45	14.00

¹ Sizes: 400 series, rods $\frac{3}{8}$ in. in diameter, 4 in. long; 800 series, rods, $\frac{1}{2}$ in. in diameter, 2 in. long.

ZINC-BASE, DIE-CASTING ALLOYS

625 ¹	Zinc-base A ²	250	\$8.00	628	Zinc-base D	250	\$8.00
626	Zinc-base B	250	8.00	629	Zinc-base E	250	8.00
627	Zinc-base C	250	8.00	630	Zinc-base F	250	8.00

¹ Size: Bar segments, $1\frac{3}{4}$ in. square and $\frac{3}{4}$ in. thick.

² NBS Nos. 625, 626, and 627 correspond to ASTM Alloy AG40A; NBS Nos. 628, 629, and 630 correspond to ASTM Alloy AC41A.

3.2. Standard Samples of Certified Properties or Purity

3.2.1. Microchemical Standards

Sample No.	Name	Constituents determined or intended use	Approximate weight of sample in grams	Price per sample
140	Benzoic acid	C, H	2	\$3.50
141	Acetanilide	N, C, H	2	3.50
142	Anisic acid	Methoxyl	2	3.50
145	2-iodobenzoic acid	I	2	3.50

3.2.2. Chemicals

84e	Acid potassium phthalate	Acidimetric value	60	\$3.75
39g	Benzoic acid	Calorimetric value	30	3.75
350	Benzoic acid	Acidimetric value	30	3.75
40f	Sodium oxalate	Oxidimetric value	60	3.75
83b	Arsenic trioxide	Oxidimetric value	75	3.75
136a	Potassium dichromate	Oxidimetric value	75	3.75
17	Sucrose (cane-sugar)	Saccharimetric value	60	3.75
41	Dextrose (glucose)	Reducing value	70	3.75

3.2.3. pH Standards

185b	Acid potassium phthalate	pH (approx.) 4.0	60	\$2.50
186lb	Potassium dihydrogen phosphate	pH (approx.) 6.8 ¹	² 60	5.00
186IIb	Disodium hydrogen phosphate	pH (approx.) 9.2	30	2.50
187a	Borax	pH (approx.) 3.6	60	2.50
188	Potassium hydrogen tartrate	pH (approx.) 1.7	65	2.50
189	Potassium tetroxalate			

¹ 2 phosphates are to be used together in equal molar proportions.

² 30 g of each phosphate are furnished.

3. Descriptive List of Reference Materials With Weights and Fees—Continued

3.2. Standard Samples of Certified Properties or Purity—Continued

3.2.4. Hydrocarbons and Organic Sulfur Compounds

Sample No. ¹	Formula	Compound	Amount of impurity ²	Volume per sample ³	Price per sample
		Name			
PARAFFINS					
201a-5	C ₅ H ₁₂	<i>n</i> -Pentane	0.15±0.07	5	\$10
201a-8S	C ₅ H ₁₂	<i>n</i> -Pentane	.15±0.07	8	18
201a-25	C ₅ H ₁₂	<i>n</i> -Pentane	.15±0.07	25	35
202a-8S	C ₅ H ₁₂	2-Methylbutane (isopentane)	.09±0.06	8	18
299-5S	C ₅ H ₁₂	2,2-Dimethylpropane (neopentane)	.04±0.02	5	25
203b-5	C ₆ H ₁₄	<i>n</i> -Hexane	.020±0.010	5	10
203a-8S	C ₆ H ₁₄	<i>n</i> -Hexane	.10±0.05	8	18
203b-25	C ₆ H ₁₄	<i>n</i> -Hexane	.020±0.010	25	35
204a-8S	C ₆ H ₁₄	2-Methylpentane	.16±0.08	8	18
205a-8S	C ₆ H ₁₄	3-Methylpentane	.20±0.15	8	18
206a-8S	C ₆ H ₁₄	2,2-Dimethylbutane	.10±0.04	8	18
207a-8S	C ₆ H ₁₄	2,3-Dimethylbutane	.11±0.06	8	18
216a-5	C ₇ H ₁₆	<i>n</i> -Heptane	0.01±0.01	5	10
216a-8S	C ₇ H ₁₆	<i>n</i> -Heptane	.01±0.01	8	18
216a-25	C ₇ H ₁₆	<i>n</i> -Heptane	.01±0.01	25	35
223-5S	C ₇ H ₁₆	2-Methylhexane	.23±0.07	5	18
224-5S	C ₇ H ₁₆	3-Methylhexane	.25±0.15	5	18
225-5S	C ₇ H ₁₆	3-Ethylpentane	.13±0.03	5	18
226-5S	C ₇ H ₁₆	2,2-Dimethylpentane	.21±0.06	5	18
227-5S	C ₇ H ₁₆	2,3-Dimethylpentane	.25±0.15	5	18
228-5S	C ₇ H ₁₆	2,4-Dimethylpentane	.17±0.05	5	18
229-5S	C ₇ H ₁₆	3,3-Dimethylpentane	.20±0.15	5	18
222-5S	C ₇ H ₁₆	2,2,3-Trimethylbutane	.06±0.03	5	18
230-5S	C ₈ H ₁₈	<i>n</i> -Octane	.06±0.04	5	25
231-5S	C ₈ H ₁₈	2-Methylheptane	.41±0.18	5	25
232-5S	C ₈ H ₁₈	3-Methylheptane	.50±0.23	5	25
233-5S	C ₈ H ₁₈	4-Methylheptane	.12±0.07	5	25
234-5S	C ₈ H ₁₈	3-Ethylhexane	.30±0.20	5	25
235-5S	C ₈ H ₁₈	2,2-Dimethylhexane	.29±0.11	5	25
236-5S	C ₈ H ₁₈	2,3-Dimethylhexane	.30±0.20	5	25
237-5S	C ₈ H ₁₈	2,4-Dimethylhexane	.30±0.20	5	25
238-5S	C ₈ H ₁₈	2,5-Dimethylhexane	.30±0.09	5	25
239-5S	C ₈ H ₁₈	3,3-Dimethylhexane	.30±0.20	5	25
240-5S	C ₈ H ₁₈	3,4-Dimethylhexane	.30±0.20	5	25
241-5S	C ₈ H ₁₈	2-Methyl-3-ethylpentane	.23±0.11	5	25
242-5S	C ₈ H ₁₈	3-Methyl-3-ethylpentane	.08±0.04	5	25
243-5S	C ₈ H ₁₈	2,2,3-Trimethylpentane	.42±0.20	5	25
217-8S	C ₈ H ₁₈	2,2,4-Trimethylpentane ^{5,6}	.12±0.05	8	18
217a-25	C ₈ H ₁₈	2,2,4-Trimethylpentane ^{5,6}	.04±0.03	25	35
244-5S	C ₈ H ₁₈	2,3,3-Trimethylpentane	.40±0.08	5	25
245-5S	C ₈ H ₁₈	2,3,4-Trimethylpentane	.19±0.06	5	25
252-5S	C ₉ H ₂₀	<i>n</i> -Nonane	.08±0.06	5	35
541-5S	C ₉ H ₂₀	2,2,3-Trimethylhexane	.30±0.20	5	35
253-5S	C ₉ H ₂₀	2,2,4-Trimethylhexane	.30±0.20	5	35
254-5S	C ₉ H ₂₀	2,2,5-Trimethylhexane	.20±0.04	5	35
542-5S	C ₉ H ₂₀	2,3,3-Trimethylhexane	.13±0.06	5	35
255-5S	C ₉ H ₂₀	2,3,5-Trimethylhexane	.30±0.20	5	35
256-5S	C ₉ H ₂₀	2,4,4-Trimethylhexane	.29±0.11	5	35
544-5S	C ₉ H ₂₀	3,3,4-Trimethylhexane	.23±0.10	5	35
289-5S	C ₉ H ₂₀	3,3-Diethylpentane	.018±0.011	5	35
296-5S	C ₉ H ₂₀	2,2,3,3-Tetramethylpentane	.064±0.020	5	35
297-5S	C ₉ H ₂₀	2,2,3,4-Tetramethylpentane	.035±0.014	5	35
257-5S	C ₉ H ₂₀	2,2,4,4-Tetramethylpentane	.16±0.08	5	35
298-5S	C ₉ H ₂₀	2,3,3,4-Tetramethylpentane	.051±0.037	5	35
505-5S	C ₁₀ H ₂₂	<i>n</i> -Decane	.04±0.02	5	35
562-5S	C ₁₁ H ₂₄	<i>n</i> -Undecane	.04±0.03	5	35
559-5S	C ₁₂ H ₂₆	<i>n</i> -Dodecane	.031±0.025	5	35
554-5S	C ₁₂ H ₂₆	2,2,4,6,6-Pentamethylheptane	.06±0.04	5	35
573-5S	C ₁₃ H ₂₈	<i>n</i> -Tridecane	.09±0.06	5	35
580-5S	C ₁₄ H ₃₀	<i>n</i> -Tetradecane	.07±0.06	5	35
581-5S	C ₁₅ H ₃₂	<i>n</i> -Pentadecane	.07±0.05	5	35
568-5S	C ₁₆ H ₃₄	<i>n</i> -Hexadecane	.06±0.04	5	35

See footnotes at end of tables.

3. Descriptive List of Reference Materials With Weights and Fees—Continued

3.2. Standard Samples of Certified Properties or Purity—Continued

3.2.4. Hydrocarbons and Organic Sulfur Compounds—Continued

Sample No. ¹	Compound		Amount of impurity ²	Volume per sample ³	Price per sample
	Formula	Name			
ALKYL CYCLOPENTANES					
219-5S	C ₅ H ₁₀	Cyclopentane-----	0.05±0.02	ml 5	\$18
208a-5	C ₆ H ₁₂	Methylcyclopentane-----	.11±0.06	5	10
208a-8S	C ₆ H ₁₂	Methylcyclopentane-----	.11±0.06	8	18
208a-25	C ₆ H ₁₂	Methylcyclopentane-----	.11±0.06	25	35
266-5S	C ₇ H ₁₄	Ethylcyclopentane-----	.06±0.03	5	25
267-5S	C ₇ H ₁₄	1,1-Dimethylcyclopentane-----	.03±0.02	5	35
268-5S	C ₇ H ₁₄	1, <i>cis</i> -2-Dimethylcyclopentane-----	.031±0.016	5	35
269-5S	C ₇ H ₁₄	1, <i>trans</i> -2-Dimethylcyclopentane-----	.19±0.10	5	35
270-5S	C ₇ H ₁₄	1, <i>cis</i> -3-Dimethylcyclopentane-----	.65±0.23	5	35
271-5S	C ₇ H ₁₄	1, <i>trans</i> -3-Dimethylcyclopentane-----	.39±0.09	5	35
272-5S	C ₈ H ₁₆	<i>n</i> -Propylcyclopentane-----	.20±0.10	5	25
273-5S	C ₈ H ₁₆	Isopropylcyclopentane-----	.20±0.07	5	25
274-5S	C ₈ H ₁₆	1-Methyl-1-ethylcyclopentane-----	.13±0.08	5	50
275-5S	C ₈ H ₁₆	1-Methyl- <i>cis</i> -2-ethylcyclopentane-----	.48±0.24	5	50
279-5S	C ₈ H ₁₆	1,1,2-Trimethylcyclopentane-----	.015±0.009	5	50
280-5S	C ₈ H ₁₆	1,1,3-Trimethylcyclopentane-----	.48±0.32	5	50
290-5S	C ₈ H ₁₆	1, <i>cis</i> -2, <i>cis</i> -3-Trimethylcyclopentane-----	.10±0.06	5	50
292a-5S	C ₈ H ₁₆	1, <i>trans</i> -2, <i>cis</i> -3-Trimethylcyclopentane-----	.14±0.04	5	50
294-5S	C ₈ H ₁₆	1, <i>cis</i> -2, <i>trans</i> -4-Trimethylcyclopentane-----	.42±0.23	5	50
295-5S	C ₈ H ₁₆	1, <i>trans</i> -2, <i>cis</i> -4-Trimethylcyclopentane-----	.24±0.10	5	50
517-5S	C ₉ H ₁₆	<i>n</i> -Butylcyclopentane-----	.034±0.025	5	35
518-5S	C ₉ H ₁₆	Isobutylcyclopentane-----	.16±0.08	5	35
583-5S	C ₁₀ H ₁₆	Cyclopentylcyclopentane-----	.05±0.03	5	35
588-5S	C ₁₅ H ₃₀	<i>n</i> -Decylcyclopentane-----	.20±0.18	5	35
ALKYL CYCLOHEXANES					
209a-5	C ₆ H ₁₂	Cyclohexane-----	0.010±0.006	5	\$10
209a-8S	C ₆ H ₁₂	Cyclohexane-----	.010±0.006	8	18
209a-25	C ₆ H ₁₂	Cyclohexane-----	.010±0.006	25	35
218a-5	C ₇ H ₁₄	Methylecyclohexane ⁵ -----	.03±0.02	5	10
218a-8S	C ₇ H ₁₄	Methylecyclohexane ⁵ -----	.03±0.02	8	18
218a-25	C ₇ H ₁₄	Methylecyclohexane ⁵ -----	.03±0.02	25	35
258-5S	C ₈ H ₁₆	Ethylcyclohexane-----	.13±0.08	5	25
259-5S	C ₈ H ₁₆	1,1-Dimethylcyclohexane-----	.19±0.03	5	35
260-5S	C ₈ H ₁₆	1- <i>cis</i> -2-Dimethylcyclohexane-----	.024±0.015	5	35
261-5S	C ₈ H ₁₆	1, <i>trans</i> -2-Dimethylcyclohexane-----	.08±0.07	5	35
263-5S	C ₈ H ₁₆	1, <i>cis</i> -3-Dimethylcyclohexane ⁷ -----	.09±0.05	5	35
262-5S	C ₈ H ₁₆	1, <i>trans</i> -3-Dimethylcyclohexane ⁸ -----	.16±0.07	5	35
264-5S	C ₈ H ₁₆	1, <i>cis</i> -4-Dimethylcyclohexane-----	.06±0.04	5	35
265-5S	C ₈ H ₁₆	1, <i>trans</i> -4-Dimethylcyclohexane-----	.14±0.08	5	35
506-5S	C ₉ H ₁₈	<i>n</i> -Propylcyclohexane-----	.08±0.05	5	25
507-5S	C ₉ H ₁₈	Isopropylcyclohexane-----	.16±0.07	5	25
516-5S	C ₉ H ₁₈	1,1,3-Trimethylcyclohexane-----	.21±0.05	5	50
508-5S	C ₁₀ H ₂₀	<i>n</i> -Butylcyclohexane-----	.08±0.04	5	35
509-5S	C ₁₀ H ₂₀	Isobutylcyclohexane-----	.17±0.09	5	35
510-5S	C ₁₀ H ₂₀	<i>sec</i> -Butylcyclohexane-----	.430±0.20	5	35
511-5S	C ₁₀ H ₂₀	<i>tert</i> -Butylcyclohexane-----	.05±0.03	5	35
591-5S	C ₁₆ H ₃₂	<i>n</i> -Decylcyclohexane-----	.14±0.11	5	35

See footnotes at end of tables.

3. Descriptive List of Reference Materials With Weights and Fees—Continued

3.2. Standard Samples of Certified Properties or Purity—Continued

3.2.4. Hydrocarbons and Organic Sulfur Compounds—Continued

Sample No. ¹	Formula	Compound Name	Amount of impurity ²	Volume per sample ³	Price per sample
MONOOLEFINS					
281-5S	C ₅ H ₁₀	1-Pentene	0.66 ± 0.40	5 ml	\$25
282c-5S	C ₅ H ₁₀	cis-2-Pentene		5	25
283-5S	C ₅ H ₁₀	trans-2-Pentene	.09 ± 0.05	5	25
284-5S	C ₅ H ₁₀	2-Methyl-1-butene	.14 ± 0.08	5	25
285-5S	C ₅ H ₁₀	3-Methyl-1-butene	.24 ± 0.12	5	25
286-5S	C ₅ H ₁₀	2-Methyl-2-butene	.06 ± 0.04	5	25
519-5S	C ₆ H ₁₂	1-Hexene	.14 ± 0.08	5	35
526-5S	C ₆ H ₁₂	cis-2-Hexene	.30 ± 0.10	5	35
527-5S	C ₆ H ₁₂	trans-2-Hexene	.17 ± 0.11	5	35
528-5S	C ₆ H ₁₂	cis-3-Hexene	.13 ± 0.08	5	35
529-5S	C ₆ H ₁₂	trans-3-Hexene	.06 ± 0.03	5	35
530-5S	C ₆ H ₁₂	2-Methyl-1-pentene	.19 ± 0.09	5	35
531-5S	C ₆ H ₁₂	3-Methyl-1-pentene	.30 ± 0.20	5	35
532-5S	C ₆ H ₁₂	4-Methyl-1-pentene	.18 ± 0.12	5	35
533-5S	C ₆ H ₁₂	2-Methyl-2-pentene	.09 ± 0.05	5	35
534-5S	C ₆ H ₁₂	3-Methyl-cis-2-pentene	.15 ± 0.08	5	35
535-5S	C ₆ H ₁₂	3-Methyl-trans-2-pentene	.14 ± 0.09	5	35
537-5S	C ₆ H ₁₂	4-Methyl-cis-2-pentene	.08 ± 0.07	5	35
536-5S	C ₆ H ₁₂	4-Methyl-trans-2-pentene	.25 ± 0.07	5	35
538-5S	C ₆ H ₁₂	2-Ethyl-1-butene	.10 ± 0.04	5	35
539-5S	C ₆ H ₁₂	2,3-Dimethyl-1-butene	.14 ± 0.13	5	35
287-5S	C ₆ H ₁₂	3,3-Dimethyl-1-butene	.09 ± 0.06	5	35
540-5S	C ₆ H ₁₂	2,3-Dimethyl-2-butene	.10 ± 0.05	5	35
520-5S	C ₇ H ₁₄	1-Heptene	.20 ± 0.10	5	35
589-5S	C ₇ H ₁₄	4-Methyl-1-hexene	.22 ± 0.16	5	35
547-5S	C ₇ H ₁₄	4,4-Dimethyl-1-pentene	.15 ± 0.08	5	35
582-5S	C ₇ H ₁₄	4,4-Dimethyl-cis-2-pentene	.21 ± 0.11	5	35
574-5S	C ₇ H ₁₄	4,4-Dimethyl-trans-2-pentene	.09 ± 0.03	5	35
550-5S	C ₇ H ₁₄	2,3,3-Trimethyl-1-butene	.06 ± 0.04	5	35
521-5S	C ₈ H ₁₆	1-Octene	.24 ± 0.13	5	35
548-5S	C ₈ H ₁₆	trans-4-Octene	.16 ± 0.11	5	35
545-5S	C ₈ H ₁₆	2,4,4-Trimethyl-1-pentene	.09 ± 0.03	5	35
546-5S	C ₈ H ₁₆	2,4,4-Trimethyl-2-pentene	.08 ± 0.05	5	35
551-5S	C ₉ H ₁₈	1-Nonene	.24 ± 0.18	5	35
552-5S	C ₁₀ H ₂₀	1-Decene	.11 ± 0.07	5	35
555-5S	C ₁₁ H ₂₂	1-Undecene	.09 ± 0.08	5	35
584-5S	C ₁₂ H ₂₄	1-Dodecene	.13 ± 0.07	5	35
590-5S	C ₁₆ H ₃₂	1-Hexadecene	.16 ± 0.07	5	35
DIOLEFINS					
512-5S	C ₄ H ₆	1,2-Butadiene	0.08 ± 0.05	5	\$25
513-5S	C ₄ H ₆	1,3-Butadiene	.08 ± 0.04	5	25
569-5S	C ₅ H ₈	1,2-Pentadiene	.34 ± 0.15	5	35
563-5S	C ₅ H ₈	1-cis-3-Pentadiene	.08 ± 0.04	5	35
564-5S	C ₅ H ₈	1-trans-3-Pentadiene	.08 ± 0.04	5	35
565-5S	C ₅ H ₈	1,4-Pentadiene	.07 ± 0.05	5	35
558-5S	C ₅ H ₈	2,3-Pentadiene	.15 ± 0.07	5	35
549-5S	C ₅ H ₈	2-Methyl-1, 3-butadiene (isoprene)	.04 ± 0.03	5	35
553-5S	C ₆ H ₁₀	1,5-Hexadiene	.11 ± 0.08	5	35

See footnotes at end of tables.

3. Descriptive List of Reference Materials With Weights and Fees—Continued

3.2. Standard Samples of Certified Properties or Purity—Continued

3.2.4. Hydrocarbons and Organic Sulfur Compounds—Continued

Sample No. ¹	Compound		Amount of impurity ²	Volume per sample ³	Price per sample
	Formula	Name			
CYCLOMONOOLEFINS					
288-5S	C ₅ H ₈	Cyclopentene-----	.034±0.021	5	\$25
522-5S	C ₆ H ₁₀	Cyclohexene-----	.028±0.020	5	35
557-5S	C ₈ H ₁₂	4-Ethenyl-1-cyclohexene (4-vinyl-1-cyclohexene)-----	.10±0.07	5	35
ACETYLENES					
514-5S	C ₄ H ₆	1-Butyne-----	.13±0.07	5	\$25
515-5S	C ₄ H ₆	2-Butyne-----	.069±0.038	5	25
ALKYL BENZENES					
210b-5	C ₆ H ₆	Benzene-----	.023±0.015	5	\$10
210a-8S	C ₆ H ₆	Benzene-----	.03±0.02	8	18
210a-25	C ₆ H ₆	Benzene-----	.03±0.02	25	35
211b-5	C ₇ H ₈	Methylbenzene (toluene) ₅ -----	.03±0.02	5	10
211a-8S	C ₇ H ₈	Methylbenzene (toluene) ₅ -----	.04±0.02	8	18
212a-5	C ₈ H ₁₀	Ethylbenzene-----	.04±0.02	5	10
212a-8S	C ₈ H ₁₀	Ethylbenzene-----	.04±0.02	8	18
212a-25	C ₈ H ₁₀	Ethylbenzene-----	.04±0.02	25	35
213b-5	C ₈ H ₁₀	1,2-Dimethylbenzene (<i>o</i> -xylene)-----	.005±0.004	5	10
213a-8S	C ₈ H ₁₀	1,2-Dimethylbenzene (<i>o</i> -xylene)-----	.010±0.007	8	18
213a-25	C ₈ H ₁₀	1,2-Dimethylbenzene (<i>o</i> -xylene)-----	.010±0.007	25	35
214c-5S	C ₈ H ₁₀	1,3-Dimethylbenzene (<i>m</i> -xylene)-----	.05±0.03	5	10
215c-5	C ₈ H ₁₀	1,4-Dimethylbenzene (<i>p</i> -xylene)-----	.06±0.03	8	18
215b-8S	C ₈ H ₁₀	1,4-Dimethylbenzene (<i>p</i> -xylene)-----	.06±0.03	25	35
215b-25	C ₈ H ₁₀	1,4-Dimethylbenzene (<i>p</i> -xylene)-----	.06±0.03	25	35
221-5S	C ₉ H ₁₂	<i>n</i> -Propylbenzene-----	.25±0.08	5	25
220-5	C ₉ H ₁₂	Isopropylbenzene-----	.07±0.03	5	10
220a-8S	C ₉ H ₁₂	Isopropylbenzene-----	.05±0.03	8	18
220-25	C ₉ H ₁₂	Isopropylbenzene-----	.07±0.03	25	35
246-5S	C ₉ H ₁₂	1-Methyl-2-ethylbenzene-----	.27±0.07	5	35
247-5S	C ₉ H ₁₂	1-Methyl-3-ethylbenzene-----	.43±0.15	5	35
248-5S	C ₉ H ₁₂	1-Methyl-4-ethylbenzene-----	.13±0.03	5	35
249-5S	C ₉ H ₁₂	1,2,3-Trimethylbenzene-----	.018±0.012	5	35
250-5S	C ₉ H ₁₂	1,2,4-Trimethylbenzene-----	.33±0.20	5	35
251-5S	C ₉ H ₁₂	1,3,5-Trimethylbenzene-----	.05±0.02	5	35
501-5S	C ₁₀ H ₁₄	<i>n</i> -Butylbenzene-----	.12±0.08	5	35
502-5S	C ₁₀ H ₁₄	Isobutylbenzene-----	.13±0.09	5	35
503-5S	C ₁₀ H ₁₄	<i>sec</i> -Butylbenzene-----	.12±0.06	5	35
504-5S	C ₁₀ H ₁₄	<i>tert</i> -Butylbenzene-----	.06±0.03	5	35
560-5S	C ₁₀ H ₁₄	1-Methyl-3-isopropylbenzene-----	.064±0.038	5	35
571-5S	C ₁₀ H ₁₄	1-Methyl-4-isopropylbenzene-----	.05±0.03	5	35
523-5S	C ₁₀ H ₁₄	1,2-Diethylbenzene-----	.05±0.03	5	35
524-5S	C ₁₀ H ₁₄	1,3-Diethylbenzene-----	.07±0.04	5	35
525-5S	C ₁₀ H ₁₄	1,4-Diethylbenzene-----	.07±0.02	5	35
566-5S	C ₁₀ H ₁₄	1,3-Dimethyl-5-ethylbenzene-----	.11±0.06	5	35
575-5S	C ₁₀ H ₁₄	1,2,3,5-Tetramethylbenzene-----	.08±0.02	5	35
585-5S	C ₁₀ H ₁₄	1,2,4,5-Tetramethylbenzene-----	.14±0.04	5	35
572-5S	C ₁₁ H ₁₆	1-Methyl-3- <i>tert</i> -butylbenzene-----	.08±0.05	5	35
576-5S	C ₁₁ H ₁₆	1-Methyl-4- <i>tert</i> -butylbenzene-----	.05±0.03	5	35
586-5S	C ₁₆ H ₂₆	<i>n</i> -Decylbenzene-----	.20±0.16	5	35

See footnotes at end of tables.

3. Descriptive List of Reference Materials With Weights and Fees—Continued

3.2. Standard Samples of Certified Properties or Purity—Continued

3.2.4. Hydrocarbons and Organic Sulfur Compounds—Continued

Sample No. ¹	Compound		Amount of impurity ²	Volume per sample ³	Price per sample ³
	Formula	Name			
NAPHTHALENES					
577-5S	C ₁₀ H ₈	Naphthalene	0.04±0.03	5 ml	\$35
587-5S	C ₁₀ H ₁₂	1,2,3,4-Tetrahydronaphthalene	.14±0.06	5 ml	35
578-5S	C ₁₁ H ₁₄	1-Methylnaphthalene	.08±0.03	5 ml	35
579-5S	C ₁₁ H ₁₄	2-Methylnaphthalene	.09±0.06	5 ml	35
POLYCYCLIC AROMATIC HYDROCARBONS					
556-5S	C ₉ H ₁₀	2,3-Dihydroindene (Indan)	0.06±0.02	5 ml	\$35
567-5S	C ₁₀ H ₁₈	cis-Decahydronaphthalene (cis-Bicyclo [4.4.0] decane)	.11±0.05	5 ml	35
561-5S	C ₁₀ H ₁₈	trans-Decahydronaphthalene (trans-Bicyclo [4.4.0] decane)	.04±0.03	5 ml	35
ORGANIC SULFUR COMPOUNDS ¹⁰					
904-5S	C ₂ H ₆ S	Ethanethiol (ethyl mercaptan)	0.05±0.04	5 ml	\$35
907-5S	C ₂ H ₆ S ₂	Methylidithiomethane (dimethyl disulfide) ¹¹	.03±0.02	5 ml	35
902-5S	C ₂ H ₈ S	Methylthioethane (methyl ethyl sulfide) ¹¹	.04±0.04	5 ml	35
901-5S	C ₄ H ₄ S	Thiophene	.013±0.011	5 ml	35
903-5S	C ₄ H ₁₀ S	Ethylthioethane (diethyl sulfide) ¹¹	.06±0.04	5 ml	35
905-5S	C ₄ H ₁₀ S	2-Methyl-2-propanethiol (<i>tert</i> -butyl mercaptan)	.08±0.04	5 ml	35
908-5S	C ₄ H ₁₀ S ₂	Ethyldithiodisulfide (diethyl disulfide) ¹¹	.10±0.08	5 ml	35
906-5S	C ₅ H ₁₀ S	1-Pentanethiol (<i>n</i> -pentyl mercaptan)	.08±0.05	5 ml	35

¹ The designations following the sample numbers indicate the following: “-5S” or “-8S”, a sample of 5 ml or 8 ml sealed “in vacuum” in a special Pyrex-glass ampoule with internal “break-off” tip; “-5”, “-25”, or “-50”, a sample of 5, 25, or 50 ml sealed “in vacuum” in a plain-glass ampoule. Although, with a few exceptions, each of the samples originally distributed by the NBS and the API was from a single preparation, this will not continue to be true when the original preparations are exhausted and replacements are made. Such new preparations will be indicated by differences in the sample number. For example, in this list isopropylbenzene 220-5 and 220-25 are from one preparation and 220a-8S is from another.

² Unless otherwise indicated, the purity has been evaluated from measurements of freezing points. See J. Research NBS **35**, 355 (1945) RP1676.

³ Tolerances approximately ±10 percent. All volumes have been estimated in the liquid state, including those of compounds normally solid.

⁴ Estimated by analogy with isomers subjected to similar purification.

⁵ Certified with regard to density and refractive index.

⁶ Certified with regard to calorimetric heat of combustion.

⁷ This isomer, formerly known as “*trans*”, see Science **105**, 647 (1947), has the following properties: Boiling point at one atmosphere, 120.09° C; refractive index, *nd* at 25° C, 1.4206; density at 25° C, 0.7626 g/ml. See NBS Circular 461, p. 45 (1947).

⁸ This isomer, formerly known as “*cis*”, see Science **105**, 647 (1947), has the following properties: Boiling point at one atmosphere, 124.45° C; refractive index, *nd* at 25° C, 1.4284; density at 25° C, 0.7806 g/ml. See NBS Circular 461, p. 45 (1947).

⁹ When sealed. Polymer formed may be removed as residue by simple vaporization of the sample “in vacuum” at an appropriate temperature.

¹⁰ In the determination of the purity of these compounds, an apparatus providing no connection with the atmosphere was employed. See Anal. Chem., **22**, 1521 (1950).

¹¹ These compounds are here named in accordance with the recommendations of the International Union of Pure and Applied Chemistry. The samples themselves bear labels in accordance with recommendations made for the naming of sulfur compounds in petroleum. See Chem. and Eng. News **24**, 2765 (1946). The samples are labeled as follows: 907-5S, 2,3-dithiobutane; 902-5S, 2-thiabutane; 903-5S, 3-thiapentane; and 908-5S, 3,4-dithiobutane.

SAMPLES CERTIFIED FOR DENSITY AND REFRACTIVE INDEX

The following three compounds of the original NBS list are certified with respect to values of density, for air-

saturated material at 1 atm, at 20°, 25°, and 30° C, to ±0.00002 g/ml, and also with respect to values of refractive index, for each of seven wavelengths (helium 668 and 502, hydrogen 656 (C) and 486 (F), mercury 546 (e) and 436 (g), and sodium 589 (D₁, D₂) at 20°, 25°, and 30° C to ±0.00002:

No. 217a-----2,2,4-Trimethylpentane.

No. 218a-----Methylcyclohexane.

No. 211a, 211b---Toluene.

These standards may be used to calibrate refractometers, piconometers, and density balances, as well as spectrometers. A certificate is supplied with each of these samples.

SAMPLES CERTIFIED FOR CALORIMETRIC HEAT OF COMBUSTION

Standard Sample 217a, 2,2,4-Trimethylpentane, is also certified with regard to the value for calorimetric heat of combustion, primarily for calibrating apparatus for determining the heating value of gasoline and other liquid fuels.

INSTRUCTIONS AND CONNECTING TUBES

A set of instructions for transferring standard samples of hydrocarbons “in vacuum” may be obtained on request.

The unsaturated hydrocarbons are usually sealed in ampoules of Pyrex Red glass. In order to facilitate the handling of these ampoules, each laboratory obtaining one or more samples in such ampoules will be supplied gratis one special graded glass connecting tube of appropriate diameter, consisting of Pyrex Red to Pyrex Uranium to Pyrex Clear glass.

3. Descriptive List of Reference Materials With Weights and Fees—Continued

3.2.4. Hydrocarbons and Organic Sulfur Compounds—Continued

ORDERS

The standard samples of hydrocarbons listed herein were prepared through a cooperative undertaking between the American Petroleum Institute and the National Bureau of Standards. The preparation of the organic sulfur compounds involved, in addition, the cooperation of the U. S. Bureau of Mines at Laramie, Wyo. By agreement with the American Petroleum Institute, distribution of these two groups of standard samples by the National Bureau of Standards is limited to laboratories not directly associated with the petroleum industry.

Orders from such laboratories should be sent to the National Bureau of Standards, Washington 25, D. C. Orders from laboratories that are associated with the petroleum industry should be sent, in duplicate, with payment in advance, to the American Petroleum Institute, Carnegie Institute of Technology, Pittsburgh, Pa.

In all cases, compounds should be specified by both name and sample number.

SHIPMENTS

All orders for hydrocarbons or organic sulfur compounds are shipped express collect.

3.2.5. Melting-Point Standards

44d	Aluminum	659.7° C	200	\$4.00
45c	Copper	1083.3° C	450	4.00
49d	Lead	327.40° C	600	4.00
42e	Tin	231.91° C	350	4.00
43f	Zinc	419.50° C	350	4.00

3.2.6. Viscometer Calibrating Liquids

These oils are not intended for use as permanent viscosity standards. They are not suitable for stockroom items and should be ordered only for immediate use. They are available only in containers of nominal 1-pint capacity. This quantity is sufficient for the calibration of most viscometers. In cases where a larger quantity (e. g., duplicate samples) is required, a satisfactory explanation of the need for the larger quantity must be given in the order or accompanying letter. All available liquids are hydrocarbon oils and are listed in the tables below.

(A) Oils for use with viscometers calibrated in units of absolute or kinematic viscosity. Price covers the sample and a report containing accurate values at the time of shipment, for absolute viscosity, kinematic viscosity, and density at the following temperatures:

Oils D through N	20° C, 25° C, 100° F, and 210° F
Oil OB	20° C, 25° C, and 40° C
Oil P	30° C, 40° C, and 50° C

Viscosity values at other temperatures in the range 20° to 100° C (30° to 100° C for oil P) are supplied as a special service. For oils D through N, the charge for this special service is \$15.00 per sample per temperature. For oils OB and P, the charge is \$32.00 per sample per temperature. These special service charges are in addition to the charge for the sample and usual report.

The approximate viscosities and the prices of the calibrating oils are as follows:

Oil	Absolute viscosity, in poises, at—				Kinematic viscosity, in stokes, at—				Price ¹ per sample F. O. B. Washington, D. C.	
	20° C	25° C	100° F	210° F	20° C	25° C	100° F	210° F		
D	0.020	0.018	0.014	0.006	0.026	0.023	0.019	0.008	\$15.00	
H	.074	.063	.044	.013	.091	.078	.055	.017	15.00	
I	.12	.10	.066	.017	.14	.12	.081	.022	15.00	
J	.21	.17	.11	.023	.25	.21	.13	.028	15.00	
K	.41	.32	.18	.032	.48	.38	.22	.040	15.00	
L	1.0	.74	.37	.049	1.1	.84	.43	.060	15.00	
M	3.0	2.1	1.0	.099	3.4	2.4	1.1	.12	15.00	
N	14	9.6	4.0	.25	16	11	4.6	.30	15.00	
	20° C	25° C	30° C	40° C	50° C	20° C	25° C	30° C	40° C	50° C
OB	330	210		62		380	240		70	
P			480	200	95			540	230	110

(B) Oils for use with Saybolt viscometers. Price covers the sample and a report containing an accurate value at the time of shipment, for viscosity at the indicated temperature. Viscosity values at other temperatures or in other units are not supplied. Saybolt viscosity values are based on determined values for kinematic viscosity and the standard conversion tables published by the American Society for Testing Materials.

The approximate viscosities and the prices of the Saybolt calibrating oils are as follows:

Oil	Temper- ature ° F	Viscosity	Price ¹ per sample F. O. B. Washington, D. C.
SB	100	300 seconds, Saybolt Universal	\$6.50
SC	130	300 seconds, Saybolt Universal	6.50
SF	122	110 seconds, Saybolt Furol	6.50

¹ On account of the nature of the material, samples of oils for use as viscometer calibrating liquids will be shipped via railway express, express charges collect.

3. Descriptive List of Reference Materials With Weights and Fees—Continued

3.2. Standard Samples of Certified Properties or Purity—Continued

3.2.7. Radioactivity Standards*

ALPHA, BETA, GAMMA STANDARDS

Sample No.	Radiation	Nuclide	Nominal activity ^a	Volume	Price per sample
4900	α	Polonium-210 ^b	200 dps	(c)	\$20.00
4901	α	Polonium-210 ^b	500 dps	(c)	20.00
4902	α	Polonium-210 ^b	1000 dps	(c)	20.00
4903	α	$U_3O_8^d$	15 dps	(c)	20.00
4910	β (α)	RaD+E ^e	200 dps	(c)	20.00
4911	β (α)	RaD+E ^e	500 dps	(c)	20.00
4912	β (α)	RaD+E ^e	1000 dps	(c)	20.00
4913	β (γ)	Cobalt-60	10^4 dps/ml ^f	(h)	20.00
4914	γ (β)	Cobalt-60	10^5 dps ^f	5.0 ml	20.00
4915	γ (β)	Cobalt-60	10^6 dps ^e	5.0 ml	20.00
4916	β	Phosphorous-32 ⁱ	10^5 dps/ml ^f	(h)	20.00
4917	β (γ)	Iodine-131 ⁱ	10^5 dps/ml ^f	(h)	20.00
4918	β (γ)	Gold-198 ⁱ	10^5 dps/ml ^f	(h)	20.00
4919	β	{Stontium-90 Yttrium-90}	{ 10^4 dps/ml ^f	(h)	20.00
4920	β	Thallium-204	10^4 dps/ml ^f	(h)	20.00
4921	β (γ)	Sodium-22	10^4 dps/ml ^f	(h)	20.00
4922	γ (β)	Sodium-22	10^6 dps ^g	5.0 ml	20.00
4923	β (γ)	Sodium-24 ⁱ	10^5 dps/ml ^f	(h)	20.00
4924	β	Carbon-14	10^8 dps/ml ^f	25.0 ml	20.00
4925	β	Carbon-14	10^4 dps/ml ^f	(j)	20.00
4926	β	Hydrogen-3	10^4 dps/ml ^f	25.0 ml	20.00
4927	β	Hydrogen-3	10^6 dps/ml ^f	(h)	20.00
4928	β	Sulphur-35	10^4 dps/ml ^f	(h)	20.00
4929	K	Iron-55	10^5 dps/ml ^f	(h)	k 20.00
4930	K (γ)	Zinc-65	10^5 dps/ml ^f	(h)	20.00
4931	γ (β)	Cesium-137	10^6 dps ^e	5.0 ml	k 20.00
4932	γ (β)	Mercury-203	10^6 dps ^g	5.0 ml	k 20.00
4933	β (γ)	Potassium-42 ⁱ	10^5 dps/ml ^f	(h)	20.00
4934	β (γ)	Tantalum-182	10^5 dps/ml ^f	(h)	20.00

*Radioactivity standards are shipped express collect. Only one of each of the longer-lived standards is normally issued to any laboratory as they are intended for the calibration of reference standards for general use. Short-lived standards, which are distributed at approximately six monthly intervals for the same purpose, may, however, be ordered as the need arises.

^a The disintegration rate as of the reference date is given on a certificate accompanying the standards.

^b Samples consist of a practically weightless deposit of polonium-210, deposited on a silver disk 1 in. in diameter, $\frac{1}{16}$ in. thick and faced with 0.002 in. of palladium. Please note that standard samples Nos. 4900, 4901, and 4902 are now polonium-210. This change makes possible the preparation of small diameter weightless sources with little self-absorption and no beta emission. Corrections for decay may be made accurately. If uncalibrated, strong alpha sources with a longer half-life are desired and the above characteristics are not required, the beta sources Nos. 4910, 4911, and 4912 may be used. Two years after plating, the alpha emission rate in the forward direction is approximately one-half the given disintegration rate and decays with approximately the half-life of radium D.

^c Deposited source.

^d Samples consist of U_3O_8 deposited on a 0.1-mm platinum foil and mounted on an aluminum disk, $\frac{1}{4}$ in. in diameter and $\frac{1}{32}$ in. thick. The alpha-ray disintegration rate as of the date of calibration is indicated on the certificate accompanying the standard.

^e Standards consist of a deposit of Pb-210-Bi-210 in equilibrium, deposited on a silver disk 1 in. in diameter, $\frac{1}{16}$ in. thick, and faced with 0.002 in. of palladium.

^f Total activity of these standards is such that they may be ordered singly under the general licensing provisions of the Atomic Energy Act of 1954 (please refer to Federal Register, vol. 21, p. 213, January 11, 1956).

^g These standards can be issued only under the special licensing provisions of the Atomic Energy Act of 1954, and it is therefore required that a copy of the purchaser's AEC By-Product Material License be on file at the National Bureau of Standards.

^h Approximately 3 ml of low-solids carrier solution containing the active nuclide in a flame-sealed glass ampoule.

ⁱ Distributed periodically at announced intervals.

^j Benzoic acid (7C-14) in about 3 ml of toluene in a screw-cap glass vial.

^k In preparation.

RADIUM STANDARDS (FOR RADON ANALYSIS)

Sample No.	Radium content (in grams)	Volume (ml) ^a	Price per sample
4950	10^{-9}	100	\$20.00
4951	10^{-11}	100	20.00
4952	Blank solution	100	2.00

^a Samples are sealed in glass containers.

3. Descriptive List of Reference Materials With Weights and Fees—Continued

RADIUM GAMMA-RAY STANDARDS

Sample No.		Radium content (in micrograms)	Volume (ml) ^a	Price per sample
4955	0.1		5	\$20.00
4956	0.2		5	20.00
4957	0.5		5	20.00
4958	1.0		5	20.00
4959	2.0		5	20.00
4960	5.0		5	20.00
4961	10		5	20.00
4962	20		5	20.00
4963	50		5	20.00
4964	100		5	20.00

^aSamples are contained in flame-sealed glass ampoules.

ROCK STANDARDS

Sample No.	Radium rock samples ^a		Price per sample
	Rock	Average radium content (micromicrogram of radium per gram of rock)	
4975	Dunite	0.009 ± 0.004	\$3.00
4976	Carthage limestone	.15 ± 0.03	3.00
4977	Berea sandstone	.24 ± 0.02	3.00
4978	Columbia River basalt	.33 ± 0.03	3.00
4979	Chelmsford granite	2.96 ± 0.08	3.00
4980	Quartzite	0.06 ± 0.01	3.00
4981	Graniteville granite	3.3 ± 0.2	3.00
4982	Gabbro-diorite	0.18 ± 0.02	3.00
4983	Milford granite	.23 ± 0.02	3.00
4984	Triassic diabase	.18 ± 0.03	3.00
4985	Deccan trap	.21 ± 0.04	3.00
4986	Kimberlite	.59 ± 0.04	3.00

^aEach sample consists of 100 g of pulverized rock taken from bulk material analyzed for radium content. Petrographic data and approximate chemical analysis of a representative sample of each rock is also given in a certificate accompanying each sample.

3.3. Standard Rubbers and Rubber Compounding Materials

3.3.1. Rubbers¹

Sample No.	Name	Approximate weight of sample in grams	Price per sample	Sample No.	Name	Approximate weight of sample in grams	Price per sample
386	Styrene-butadiene, type 1500	34,000	\$27.00	² 387	Styrene-butadiene, type 1000	34,000	\$23.00

¹Normally, samples are shipped railway express, express charges collect.

²This standard sample is the remainder of X-768 GR-S established by the Federal Facilities Corp., Office of Synthetic Rubber.

3.3.2. Rubber Compounding Materials¹

370a	Zinc oxide	2,000	\$2.15	377	Phenyl-beta-naphthylamine	600	\$4.00
371b	Sulfur	1,400	1.75	378	Oil furnace black	7,000	3.50
372b	Stearic acid	600	1.90	379	Conducting black	5,500	3.50
373b	Benzothiazyl-disulfide	500	1.75	380	Calcium carbonate	6,000	2.50
374a	Tetramethylthiuram-disulfide	500	3.50	381	Calcium silicate	4,000	2.50
375c	Channel black	7,500	3.50	382	Gas furnace black	7,500	3.50
376a	Light magnesia	450	2.40				

¹Normally, samples are shipped railway express, express charges collect.

3. Descriptive List of Reference Materials With Weights and Fees—Continued

3.4. Miscellaneous Standard Materials

3.4.1. Turbidimetric and Fineness Standard

Sample No.	Name	Constituents determined or intended use	Approximate weight of sample in grams	Price per sample
114i	Cement	No. 325 sieve residue, 8.1%----- Surface area, 1,870 cm ² /g----- Air permeability, 3,100 cm ² /g-----	20	\$2.50

3.4.2. Paint-Pigment Standards for Color and Tinting Strength Only

Sample No.	Name	Approximate weight of sample in grams	Price per sample	Sample No.	Name	Approximate weight of sample in grams	Price per sample
300	Toluidine red toner	40	\$3.00	314	Yellow iron oxide, light lemon	20	\$3.00
301	Yellow ocher	45	3.00	315	Yellow iron oxide, lemon	20	3.00
302	Raw sienna	45	3.00	316	Yellow iron oxide, orange	25	3.00
303	Burnt sienna	50	3.00	317	Yellow iron oxide, dark orange	40	3.00
304	Raw umber	45	3.00	318	Lampblack	15	3.00
305	Burnt umber	50	3.00	319	Primrose chrome yellow	65	3.00
306	Venetian red	60	3.00	320	Lemon chrome yellow	60	3.00
				321	Medium chrome yellow	65	3.00
307	Metallic brown	60	3.00				
308	Indian red	50	3.00	322	Light chrome orange	100	3.00
309	Mineral red	65	3.00	323	Dark chrome orange	100	3.00
310	Bright red oxide	50	3.00	324	Ultramarine blue	37	3.00
311	Carbon black (high color)	10	3.00	325	Iron blue	25	3.00
312	Carbon black (all-purpose)	20	3.00	326	Light chrome green	60	3.00
313	Black iron oxide	42	3.00	327	Medium chrome green	50	3.00
				328	Dark chrome green	45	3.00

3.4.3. Light-Sensitive Papers

Sample No.	Item	Unit of issue	Price per set
1015	Light-sensitive paper for calibration of carbon-arc fading lamps for color-fastness tests of textiles. See current NBS Letter Circular 1024 on this subject for directions for use.	Package of 100 pieces	\$3.00
1016	Booklet of standard faded strips of light-sensitive paper for use with above sample. See NBS Letter Circular 1024 for directions for using the booklet.	Booklet	26.00

3.4.4. Standard Colors for Kitchen and Bathroom Accessories¹

Sample No.	Item	Unit of issue	Price per set
1000	Enameled iron plaques, 3 by 5 inches, in accordance with Commercial Standards CS62-38 and CS63-38.	Set of 10	\$10.00

¹ Calibration of these standards for use with three-filter reflectometers may be obtained by applying to the Bureau.

3.4.5. Limestone Slabs for Calking Compound Test

Sample No.	Description	Unit of issue	Price per set
1005	Limestone slabs, as required by Federal Specification TT-C-598, "Compound, Calking; Plastic".	Set of 12 slabs	\$9.00

4. Summary of Analyses

The values given in the following sections are listed primarily as a guide to purchasers. In some cases provisional values are given which may differ

slightly from those given on the certificates. For this reason *the certificates issued with the standards should always be consulted to obtain the proper values.*

4.1. Averaged Analyses

ALUMINUM-BASE ALLOYS (CHEMICAL STANDARDS)

Sample No.	Cu	Mn	Si	Mg	Fe	Ti	Zn	Pb	Sn	Ga	Ni	Cr
85b	3.99	0.61	0.17	1.49	0.22	0.023	0.030	0.022	-----	-----	0.085	0.21
86c	7.92	.041	.68	0.002	.90	.035	1.50	.031	-----	-----	.030	.029
87a	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----

COBALT-BASE ALLOYS

Sample No.	Kind		Co	Ni	Cr	Mo	W	Nb	Ta	Fe	Mn	C	P	S	Si	Cu	V	Ti
167	Heat-resisting alloy (S816)-----	-----	42.90	20.65	20.00	3.90	4.50	3.15	0.08	2.13	1.64	0.38	0.010	0.007	0.44	0.03	0.01	-----
168	Heat-resisting alloy (S816)-----	-----	41.20	20.25	20.33	3.95	3.95	2.95	.95	3.43	1.50	.37	.008	.005	.80	.035	.03	0.06

COPPER-BASE ALLOYS

Sample No.	Kind		Cu	Zn	Sn	Pb	Ni	Fe	Al	Mn
37d	Sheet brass-----	-----	70.78	26.65	0.97	0.94	0.58	0.076	-----	-----
164	Manganese aluminum bronze-----	-----	63.76	21.89	.63	.22	.046	2.52	6.21	4.68
52e	Cast bronze-----	-----	89.25	2.12	7.85	.011	.76	0.004	-----	-----
62e	Manganese bronze-----	-----	59.16	37.24	0.39	.24	.28	.74	1.22	0.66
63e	Phosphor-bronze-----	-----	80.48	0.093	9.03	9.35	.32	.0013	-----	-----
158	Silicon bronze-----	-----	90.86	2.07	0.97	0.004	.006	1.48	0.54	1.31
157a	Nickel silver-----	-----	-----	-----	-----	-----	-----	-----	-----	-----
124c	Ounce metal-----	-----	84.22	4.93	5.13	4.74	0.60	0.107	-----	-----
184	Leaded-tin bronze-----	-----	88.96	2.69	6.38	1.44	.50	.005	-----	-----
			Sb	As	Ag	Si	S	P	Co	
164	Manganese aluminum bronze-----	-----	-----	-----	-----	0.038	-----	-----	-----	
52e	Cast bronze-----	-----	-----	-----	-----	.068	0.002	0.001	-----	
62e	Manganese bronze-----	-----	0.52	0.023	-----	-----	.060	.145	-----	
63e	Phosphor-bronze-----	-----	-----	-----	-----	2.72	-----	-----	-----	
158	Silicon bronze-----	-----	-----	-----	-----	-----	-----	-----	-----	
157a	Nickel silver-----	-----	-----	.20	-----	-----	0.002	.048	.024	-----
124c	Ounce metal-----	-----	-----	-----	-----	-----	-----	-----	.009	-----
184	Leaded-tin bronze-----	-----	-----	-----	-----	-----	-----	-----	-----	-----

LEAD- AND TIN-BASE ALLOYS

Sample No.	Kind		Pb	Sn	Sb	Bi	Cu	Fe	As	Ag	Ni	Al
53d	Lead-base-----	-----	4.94	9.92	0.13	0.27	-----	0.045	-----	0.002	-----	-----
127a	Solder-----	-----	30.03	0.79	.036	.004	-----	.129	0.004	.002	-----	-----
54d	Tin-base-----	-----	0.62	88.6	7.05	.04	3.57	0.03	.09	.003	.003	-----

MAGNESIUM-BASE ALLOY

Sample No.	Al	Zn	Mn	Si	Cu	Pb	Fe	Ni
171	2.98	1.05	0.45	0.012	0.011	0.0033	0.0018	0.0009

4.1. Averaged Analyses—Continued

NICKEL-BASE ALLOYS (CHEMICAL STANDARDS)

Sample No.	Kind	Ni	Cu	Mn	Si	Co	Fe	Cr	Al	Ti	C	S	P	Zr	V	Ca	N
161	Ni-base casting	64.29	0.045	1.28	1.56	0.47	15.01	16.88	-----	0.34	0.006	0.012	-----	0.029	-----	0.027	
169	Ni-Cr	77.26	.015	0.073	1.42	.19	0.54	20.26	0.095	0.006	.043	.002	-----	0.042	.018	0.015	.031

TITANIUM-BASE ALLOYS

Sample No.	Kind	Al	V	Mn	Fe	Cr	Si	Mo	C	N						
173	Al6-V4	5.42	4.09	-----	0.16	-----	-----	-----	-----	0.018	-----	-----	-----	-----	-----	
174	Al4-Mn4	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	

ZINC-BASE DIE-CASTING ALLOY (CHEMICAL STANDARDS)

Sample No.	Al	Cu	Mg	Fe	Mn	Pb	Ni	Sn	Cd
94b	4.07	1.01	0.042	0.018	0.014	0.006	0.006	0.006	0.002

STEEL-MAKING ALLOYS

Sample No.	Kind	C	Mn	P	S	Si	V	Ti	Al	Ca	Fe	Cr
57	Refined silicon	0.087	0.034	0.008	0.005	96.8	-----	0.10	0.67	0.73	0.65	0.025
58	Ferrosilicon (75% Si)	.033	.165	.016	.01	75.6	0.004	.085	.77	.45	22.5	.07
116b	Ferrotitanium	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----
		C	Mn	P	S	Si	Ni	Cr	V	Al	Fe	
61a	Ferrovanadium	1.06	1.78	0.119	0.005	5.12	-----	0.68	50.19	0.02	-----	-----
64b	Ferrochromium	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----
66a	Spiegeleisen	4.39	19.77	.049	.021	2.26	-----	-----	-----	-----	-----	-----
68b	Ferromanganese	6.77	79.97	.293	.006	0.44	-----	-----	-----	-----	-----	-----
90	Ferrophosphorus	-----	-----	26.2	-----	-----	-----	-----	-----	-----	-----	-----
71	Calcium molybdate	-----	-----	Mo=35.3; Fe=1.92; Ti=0.06.	-----	-----	-----	-----	-----	-----	-----	-----

IRON ORES

Sample No.	Name	SiO ₂	P	Fe	Mn
27c	Mesabi	2.08	0.028	65.0	-----
28a	Norrie	-----	-----	0.435	-----

4.1. Averaged Analyses—Continued

IRONS (CHEMICAL STANDARDS)

Sample No.	Kind	C		Mn	P	S		Si	Cu	Ni
		Total	Graphitic			By oxidation	Evolved as H ₂ S			
3	White	2.26	<0.01	0.35	0.120	0.090	-----	0.99	0.128	0.018
4i	Cast	3.27	2.65	.79	.130	.055	0.055	1.46	.25	.064
5k	Cast	2.71	1.99	.536	.263	.100	.096	2.08	1.50	.051
6f	Cast	2.91	2.19	.499	.530	.106	.103	1.85	0.252	.060
7f	Cast	2.80	2.50	.447	.881	.078	.078	1.89	.021	.011
55d	Ingot	0.011	-----	.030	.005	.014	.015	<0.001	.056	.010
82a	Ni-Cr	2.24	1.71	.649	.053	.102	.094	2.07	.076	1.07
107a	Ni-Cr-Mo	2.72	1.84	.582	.278	.095	-----	1.35	.103	0.968
122d	Cast (car-wheel)	-----	-----	-----	-----	-----	-----	-----	-----	-----

STEELS (CHEMICAL STANDARDS)

8h	Bessemer	0.117	-----	0.454	0.094	0.050	0.050	0.027	0.054	0.019
10g	Bessemer	-----	-----	-----	-----	-----	-----	-----	-----	-----
170	B. O. H. (Ti-bearing)	.035	-----	.226	.012	.032	-----	.060	.102	.041
15f	B. O. H.	.084	-----	.39	.005	.032	.033	.042	.085	.029
11g	B. O. H.	.191	-----	.513	.008	.026	.026	.203	.046	.020
12f	B. O. H.	.452	-----	.838	.015	.037	.037	.244	.121	.062
152	B. O. H. (tin-bearing)	.466	-----	.782	.019	.027	.027	.244	.127	.062
13e	B. O. H.	.636	-----	.890	.021	.016	.015	.239	.103	.110
14d	B. O. H.	.841	-----	.399	.014	.027	.027	.126	.084	.041
16d	B. O. H.	1.01	-----	.439	.014	.033	.034	.188	.052	.022
19f	A. O. H.	0.193	-----	.497	.029	.043	.041	.204	.151	.317
20f	A. O. H.	.380	-----	.754	.028	.034	.032	.299	.238	.243
51b	Electric	1.21	-----	.57	.012	.014	.013	.25	.072	.055
65d	Basic electric	.26	-----	.73	.015	.009	.010	.37	.050	.060
100a	Manganese (SAE T1345)	.447	-----	1.66	.020	.027	.027	.243	.050	.032
105	High-sulfur	.193	-----	-----	-----	-----	-----	-----	-----	-----
125a	High-silicon	.032	-----	0.052	.006	.013	-----	3.32	.084	.053
129a	High-sulfur (SAE X1112)	.097	-----	.806	.094	.272	-----	0.021	.021	.027
130a	Lead-bearing	-----	-----	-----	-----	-----	-----	-----	-----	-----
151	Boron	-----	-----	-----	-----	-----	-----	-----	-----	-----
30e	Cr-V steel (SAE 6150)	.505	-----	.786	.026	.035	.036	.269	.094	.027
32e	Cr-Ni steel (SAE 3140)	-----	-----	-----	-----	-----	-----	-----	-----	-----
33d	Ni-Mo steel (SAE 4820)	.173	-----	.537	.006	.010	.010	.253	.123	3.58
72f	Cr-Mo steel (SAE X4130)	.30	-----	.55	.013	.023	-----	.25	.062	0.057
111b	Ni-Mo steel (SAE 4620)	.193	-----	.706	.012	.015	.013	.302	.028	1.81
36a	Cr2-Mo1	.120	-----	.432	.014	.016	-----	.356	.114	0.243
106a	Cr-Mo-Al	.355	-----	.546	.016	.018	.017	.254	.156	.277
139	Cr-Ni-Mo (NE 8637)	.394	-----	.867	.019	.024	.024	.292	.089	.563
156	Cr-Ni-Mo (NE 9450)	.515	-----	1.40	.032	.017	.017	.226	.053	.475
159	Cr1-Mo0.4-Ag0.1	.521	-----	0.807	.036	.027	.026	.258	.181	.137
50e	W18-Cr4-V1	.71	-----	.34	.022	.009	-----	.32	.077	.069
132a	W6-Mo5	.825	-----	.268	.029	.006	-----	.190	.120	.137
134a	W2-Mo8-Cr4-V1	.81	-----	.219	.019	.006	-----	.32	.100	.088
153	W1.5-Mo8-Cr4-V2-Co8	.864	-----	.219	.025	.008	-----	.187	.099	.107
155	W0.5-Cr0.5	.905	-----	1.24	.015	.010	-----	.322	.083	.100
73b	Cr12	.36	-----	0.36	.018	.006	-----	.44	.126	.197
133a	Cr13-Mo0.3-S0.3	.120	-----	1.03	.026	.326	-----	.412	.118	.241
101d	Cr18-Ni9 (SAE 30905)	.056	-----	0.739	.020	.017	-----	.471	.184	9.05
121b	Cr18-Ni-11-Ti0.4	.072	-----	1.50	.026	.007	-----	.596	.125	11.16
123b	Cr-Ni-Nb-Ta	-----	-----	-----	.024	-----	-----	.52	-----	-----
160a	Cr-Ni-Mo	-----	-----	-----	-----	-----	-----	-----	-----	-----
166a	Cr-Ni	.027	-----	0.38	-----	-----	-----	.20	.082	35.98
126b	Ni36	.090	-----	-----	-----	-----	-----	-----	-----	-----

4.1. Averaged Analyses—Continued

IRONS (CHEMICAL STANDARDS)—Continued

Ni	Sample No.	Cr	V	Mo	W	Co	Ti	As	Sn	Al (total)	Al ₂ O ₃	N	Nb	Ta	B
0.018	3	0.051	0.007	0.005	-----	-----	0.010	-----	-----	-----	-----	-----	-----	-----	0.0007
.064	4i	.103	.013	.003	-----	-----	.026	0.018	-----	-----	0.007	-----	-----	-----	-----
.051	5k	.109	.014	.007	-----	-----	.028	.027	-----	-----	.009	-----	-----	-----	-----
.060	6f	.442	.032	.009	-----	-----	.063	.032	-----	-----	.005	-----	-----	-----	-----
.011	7f	.015	.048	.003	-----	-----	.062	.088	-----	-----	.004	-----	-----	-----	-----
.010	55d	.005	<0.001	.001	-----	0.007	-----	.009	0.005	0.002	-----	.004	-----	-----	-----
1.07	82a	.323	.019	.008	-----	-----	.065	-----	-----	-----	-----	-----	-----	-----	-----
.968	107a	.479	.028	.771	-----	-----	.035	-----	-----	-----	-----	-----	-----	-----	-----
	122d	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----

STEELS (CHEMICAL STANDARDS)—Continued

0.019	8h	0.022	0.015	0.004	-----	-----	-----	0.003	-----	-----	0.017	-----	-----	-----	-----
.041	10g	-----	.038	.003	.006	-----	-----	0.231	-----	.018	0.027	-----	-----	-----	-----
.029	170	-----	.009	.001	.007	-----	-----	-----	-----	-----	-----	.005	-----	-----	-----
.020	15f	-----	.015	.001	.005	-----	-----	-----	-----	.004	-----	.006	-----	-----	-----
.062	11g	-----	.075	.003	.010	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----
.062	12f	-----	.050	.001	.013	-----	-----	-----	-----	.036	-----	.004	-----	-----	-----
.110	152	-----	.128	.003	.032	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----
.041	13e	-----	.065	.002	.007	-----	-----	-----	-----	-----	-----	.004	-----	-----	-----
.022	14d	-----	.042	.002	.006	-----	-----	-----	-----	-----	-----	.003	-----	-----	-----
.317	16d	-----	.053	.007	.058	-----	-----	-----	-----	.022	-----	.004	-----	-----	-----
.243	19f	-----	.097	.007	.058	-----	-----	-----	-----	.021	-----	.005	-----	-----	-----
.055	20f	-----	.46	.002	.015	-----	-----	-----	-----	-----	.060	.011	-----	-----	-----
.060	51b	-----	.050	.024	-----	-----	-----	-----	-----	-----	.040	.013	-----	-----	-----
.032	65d	-----	.051	.003	.008	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----
.053	100a	-----	.023	.001	.007	-----	-----	<0.01	-----	.007	<0.01	-----	.002	-----	<0.001
.027	105	-----	.021	.004	.007	-----	-----	0.007	-----	-----	-----	-----	-----	-----	-----
	125a	-----	-----	-----	-----	{ Lead }	-----	-----	-----	-----	-----	-----	-----	-----	-----
	129a	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----
	130a	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----
0.027	151	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	0.0027	-----	-----
	30e	-----	.934	.149	.007	-----	-----	-----	-----	-----	-----	.007	-----	-----	-----
	32e	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----
.057	33d	-----	.143	.002	.246	-----	-----	-----	-----	-----	-----	.011	-----	-----	-----
.057	72f	-----	.89	.005	.18	-----	-----	-----	-----	-----	-----	.010	-----	-----	-----
.051	111b	-----	.070	.003	.255	-----	-----	-----	-----	.043	-----	-----	-----	-----	-----
.243	36a	2.41	.006	.920	-----	-----	-----	-----	.011	-----	1.08	0.011	-----	-----	-----
.277	106a	1.15	.002	.203	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----
.563	139	0.549	.002	.178	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----
.475	156	.429	.002	.138	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----
.137	159	1.00	.054	.414	-----	-----	-----	-----	-----	-----	{ Silver }	{ 0.090 }	-----	-----	-----
.069	50c	4.11	1.16	.080	18.46	-----	-----	-----	.021	.019	-----	-----	-----	-----	-----
.137	132a	4.21	1.94	4.51	6.20	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----
.088	134a	3.68	1.25	8.32	2.01	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----
.107	153	4.14	2.04	8.38	1.58	8.45	-----	-----	-----	-----	-----	-----	-----	-----	-----
.100	155	0.485	0.014	0.039	0.517	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----
.197	73b	12.82	.031	.014	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----
.241	133a	12.89	.026	.294	-----	-----	-----	-----	-----	-----	.032	-----	-----	-----	-----
.05	101d	18.68	.049	.110	-----	0.058	-----	-----	.009	-----	-----	.024	-----	-----	-----
.6	121b	17.69	.041	.073	-----	-----	.414	-----	-----	-----	-----	.012	-----	-----	-----
	123b	-----	.05	.17	.18	-----	.006	-----	-----	-----	-----	0.75	0.20	-----	-----
	160a	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----
	166a	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----
	126b	0.064	.001	-----	-----	.03	-----	-----	-----	-----	-----	-----	-----	-----	-----

4.1. Averaged Analyses—Continued

LOW ALLOY STEELS (SPECTROGRAPHIC STANDARDS)

Sample Nos. ¹	Kind	Mn	Si	Cu	Ni	Cr	V	Mo	Al (total)	Sn	Co
401	(³) B. O. H., 0.4 C ²	0.34	0.015	0.015	0.005	0.015					
402	802 B. O. H., 0.8 C	.46	.060	.025	.010	.025					
403a	803a A. O. H., 0.6 C	1.04	.34	.096	.190	.101	0.005	0.033			
404a	804a Basic electric	0.88	.44	.050	.040	.025	.002	.007			
405a	805a Medium manganese	1.90	.27	.032	.065	.037		.005	0.056		
407a	807a Chromium-vanadium	0.76	.29	.132	.169	.92	.146				
408a	808a Chromium-nickel	.76	.28	.10	.20	.655	.002	.065			
409b	809b Nickel	.46	.27	.104	3.29	.072	.002	.009		0.012	0.025
410a	810a Cr 2-Mo ₁		.36	.11	.024	2.39			.91		
411a	811a Cr-Mo (SAE X4130)		.29	.105	.24	0.93	.002	.22			
412a	812a Cr-Ni-Mo (NE 8637)	.87	.30	.090	.56	.55			.18		
413	(³) A. O. H., 0.4 C	.67	.22	.25	.18	.055	.007	.006			
414	(³) Cr-Mo (SAE 4140)	.67	.26	.11	.080	.99	.003	.32	.020	.014	
415a	815a Bessemer, 0.5 C		.10	.012	.006	.008	.006		.11		
416a	(³) Nitr alloy G	.54	.25	.15	.28	1.14		.20	1.08	.011	
417	(³) A. O. H., 0.4 C	.64	.18		.105	0.028	.004		0.013	.020	
417a	817a B. O. H., 0.4 C	.78		.13	.062	.050		.013		.036	
418	(³) Cr-Mo (SAE X4130)	.52	.28		.11	.96		.22			
418a	818a Cr-Mo (SAE X4130)	.52	.27	.040	.125	1.02		.21			
419	(³) Ni-Mo (SAE 4620)	.72	.27	.080	1.71	.24		.22		.009	
420a	820a Ingot iron	.017		.027	0.0092	.0032		.0013	.003	.0017	.006
421	821 Cr-W, 0.9 C	1.24		.080	.10	.49	.012	.040	Tungsten 0.52		Boron
425	825 Mn-Ni-Cr-(NE 9450)										0.006
427	827 Cr-Mo (SAE 4150)										.0027
428	(³) Mn-Cr										.0059
(³)	830 Ni-Cr-B										.019

¹ Sizes: 400 series, rods $\frac{7}{32}$ in. in diameter, 4 in. long; 800 series, rods $\frac{1}{2}$ in. in diameter, 2 in. long.

² The carbon contents of the steel standards are between 0.1 and 0.9 percent.

³ This standard is available in only one size.

STAINLESS STEELS (SPECTROGRAPHIC STANDARDS)

(Minor and Trace Elements)

Sample No. ¹	Kind	Al	B	Co	Cu	Mo	Nb	Pb	Sn	Ti	V	W	Zn	Zr
442	Cr16-Ni 10 ²	0.0003	0.0005	0.13	0.11	0.12	0.03	0.002	0.003	0.002	0.032	0.08	0.003	---
443	Cr18-Ni 9	.0006	.0012	.12	.14	.12	.06	.003	.006	.003	.064	.09	.005	---
444	Cr21-Ni 1	.0025	.0033	.22	.24	.22	.21	.004	.013	.019	.12	.18	.004	---

¹ Size: Rods $\frac{7}{32}$ in. in diameter, 4 in. long.

² By difference, the iron contents of these standards are: 442, 70.4%; 443, 67.9%; and 444, 62.7%.

STAINLESS STEELS (SPECTROGRAPHIC STANDARDS)

(Major and Minor Elements)

Sample Nos. ¹	Kind	Mn	Si	Cu	Ni	Cr	Mo
445	845 Cr13-Mo0.9 (Modified AISI 410) ²	0.77	0.53	0.065	0.28	13.30	0.92
446	846 Cr18-Ni9 (Modified AISI 321)	.53	1.20	.19	9.10	18.37	.43
447	847 Cr24-Ni13 (Modified AISI 309)	.23	0.37	.19	13.26	23.73	.059
448	848 Cr9-Mo0.3 (Modified AISI 403)	2.10	1.25	.16	0.52	9.10	.33
449	849 Cr5.5-Ni16.5	1.62	0.68	.21	6.62	5.48	.15
450	850 Cr3-Ni25		.12	.36	24.8	2.99	

¹ Sizes: 400 series, rods $\frac{7}{32}$ in. in diameter, 4 in. long; 800 series, rods $\frac{1}{2}$ in. in diameter, 2 in. long.

² The carbon content of the standards is between 0.06 and 0.1 percent. By difference, the iron contents of the standards are: 445 and 845, 83.1%; 446 and 846, 68.9%; 447 and 847, 61.7%; 448 and 848, 85.3%; 449 and 849, 84.3%; 450 and 850, 70.7%.

4.1. Averaged Analyses—Continued

TOOL STEELS (SPECTROGRAPHIC STANDARDS)

Sample Nos. ¹	Kind				Mn	Si	Cu	Cr	V	Mo	W	Co
436 836	Special (Cr6-Mo3-W10) ²				0.21	0.32	0.075	6.02	0.63	2.80	9.7	-----
437 837	Special (Cr8-Mo2-W3-Co3)				.48	.53	-----	7.82	3.04	1.50	2.8	2.9
438 838	Mo High Speed (AISI-SAE M30)				.20	.17	.17	4.66	1.17	8.26	1.7	4.9
439 839	Mo High Speed (AISI-SAE M36)				.18	.21	.12	2.72	1.50	4.61	5.7	7.8
440 840	Special W High Speed (Cr2-W13-Co12)				.15	.14	.059	2.12	2.11	0.070	13.0	11.8
441 841	W High Speed (AISI-SAE T1)				.27	.16	.072	4.20	1.13	.84	18.5	-----

¹ Sizes: 400 series, rods $\frac{7}{32}$ in. in diameter, 4 in. long; 800 series, rods $\frac{1}{2}$ in. in diameter, 2 in. long.

² The carbon content of the standards is between 0.7 and 0.8 percent. By difference, the iron contents of the standards are: 436 and 836, 79.2%; 437 and 837, 79.7%; 438 and 838, 77.6%; 439 and 839, 76.0%; 440 and 840, 69.1%; 441 and 841, 73.6%.

ALUMINUM ALLOYS (SPECTROGRAPHIC STANDARDS)

Sample No. ¹	Kind				Cu	Mg	Si	Mn	Fe	Ni	Cr	Ti	Zn
602	Aluminum alloy, wrought (2024)				4.44	1.49	0.130	0.63	0.28	-----	0.007	0.012	-----
604	Aluminum-base casting alloy (142)				3.98	1.56	.27	-----	.45	2.00	-----	.100	0.029

¹ Size: Disks $2\frac{1}{2}$ in. in diameter, $\frac{3}{4}$ in. thick.

NICKEL OXIDES (SPECTROGRAPHIC STANDARDS)¹

Sample No. ²	Kind				Co	Cu	Fe	Mg	Mn	Si	Ti	Al	Cr
671	Nickel oxide 1				0.31	0.20	0.39	0.030	0.13	0.047	0.024	0.009	0.025
672	Nickel oxide 2				.55	.018	.079	.020	.095	.11	.009	.004	.003

¹ Although intended primarily as spectrographic standards, these samples are equally suitable for chemical standards.

² Each sample consists of 25g of powder.

TIN METAL (SPECTROGRAPHIC STANDARDS)

Sample Nos. ¹	Cu	Pb	As	Sb	Ni	Zn	Ag	Bi	Cd	Co
431 831	0.19	0.19	0.16	0.19	0.038	0.041	0.015	0.020	0.020	0.021
432 832	.097	.094	.075	.095	.020	.020	.0095	.0098	.0095	.011
433 833	.055	.055	.047	.050	.0095	.0095	.0055	.0052	.0053	.0045
434 834	.019	.022	.019	.019	.0044	.0046	.0018	.0020	.0020	.0020
435 835	.0077	.015	.0090	.010	.0024	.0020	.0010	.0011	.0011	.0011

¹ Sizes: 400 series, rods $\frac{1}{4}$ in. in diameter, 4 in. long; 800 series, rods $\frac{1}{2}$ in. in diameter, 2 in. long.

ZINC-BASE, DIE-CASTING ALLOYS (SPECTROGRAPHIC STANDARDS)

Sample No. ¹	Kind ²	Cu	Al	Mg	Fe	Pb	Cd	Sn	Cr	Mn	Ni	Si
625	Zinc-base A	0.035	3.06	0.070	0.035	0.0014	0.0006	0.0005	0.013	0.031	0.019	0.018
626	Zinc-base B	.055	3.57	.020	.105	.0021	.0014	.0011	.039	.048	.048	.042
627	Zinc-base C	.135	3.89	.030	.023	.0082	.0049	.0042	.004	.014	.003	.024
628	Zinc-base D	.61	4.61	.009	.066	.0044	.0041	.0017	.009	.009	.030	.009
629	Zinc-base E	1.50	5.16	.094	.016	.013	.015	.012	.0008	.002	.008	.078
630	Zinc-base F	0.98	4.30	.030	.022	.0083	.0048	.0040	.003	.011	.003	.023

¹ Size: Bar segments, $1\frac{3}{4}$ in. square and $\frac{3}{4}$ in. thick.

² NBS Nos. 625, 626, and 627 correspond to ASTM Alloy AG40A; NBS Nos. 628, 629, and 630 correspond to ASTM Alloy AC41A.

4.1. Averaged Analyses—Continued

MANGANESE ORE

Sample No.		Total manganese	Available oxygen	SiO ₂	P ₂ O ₅	
25c	-----	55.8	16.7	2.36	0.22	-----

TIN ORES

Sample No.		Sn
137	Bolivian concentrate-----	56.6
138	N. E. I. concentrate-----	74.8

ZINC ORE

Sample No.		Zn
113	Tri-State concentrate-----	61.1

PHOSPHATE ROCK

Sample No.	Kind	P ₂ O ₅	Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	F	SiO ₂
56b	Tennessee brown-----	31.55	-----	-----	44.06	-----	3.4	10.1

ALUMINA REFRACTORIES, BAUXITE, CEMENT, AND CLAYS

Sample No.	Kind	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	TiO ₂	ZrO ₂	MnO	Mn ₂ O ₃	P ₂ O ₅	V ₂ O ₅	Cr ₂ O ₃
76	Alumina refractory-----	54.7	37.7	2.4	2.2	0.07	-----	-----	0.07	0.02	-----
77	Alumina refractory-----	32.4	59.4	0.90	2.9	.09	-----	-----	.45	.03	-----
78	Alumina refractory-----	20.7	70.0	.79	3.4	.12	-----	-----	.62	.05	-----
69a	Bauxite-----	6.0	55.0	5.8	2.8	.18	<0.01	-----	.08	.03	0.05
177	Portland cement-----	21.9	5.3	2.4	0.27	-----	-----	0.05	.05	-----	-----
97	Flint clay-----	42.9	38.8	0.98	2.4	.25	.002	-----	.08	.04	.08
98	Plastic clay-----	59.1	25.5	2.05	1.4	.04	.005	-----	.08	.025	.02

Sample No.	Kind	CaO	SrO	BaO	MgO	Li ₂ O	Na ₂ O	K ₂ O	SO ₃	Loss on ignition	CuO
76	Alumina refractory-----	0.27	-----	-----	0.58	0.11	0.15	1.54	-----	0.22	-----
77	Alumina refractory-----	.26	-----	-----	.50	.35	.06	2.11	-----	.21	-----
78	Alumina refractory-----	.38	-----	-----	.51	.20	.06	2.83	-----	.26	-----
69a	Bauxite-----	.29	0.01	-----	.02	-----	<.01	<.01	0.04	29.55	-----
177	Portland cement-----	64.25	0.05	-----	2.42	<.005	.14	.56	1.59	1.14	-----
97	Flint clay-----	0.10	-----	.015	0.26	.23	.07	.54	.04	13.35	0.003
98	Plastic clay-----	.21	-----	.06	.72	.03	.26	3.17	.07	7.28	.009

FELDSPAR

Sample No.	Kind	K ₂ O	Na ₂ O	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	CaO	MgO	TiO ₂	Loss on ignition
99	Soda-----	0.41	10.73	68.66	19.06	0.067	0.36	0.053	0.017	0.52

4.1. Averaged Analyses—Continued

GLASS SANDS

Sample No.		Fe ₂ O ₃	Al ₂ O ₃	TiO ₂	ZrO ₂	CaO	MgO
81		0.073	0.265	0.095	0.031	0.029	0.016
165		.019					

GLASSES

Sample No.	Kind	SiO ₂	PbO	Al ₂ O ₃	Fe ₂ O ₃	ZnO	MnO	TiO ₂	ZrO ₂	CaO	BaO
89	Lead-barium	65.35	17.50	0.18	0.049		0.088	0.01	0.005	0.21	1.40
91	Opal	67.53	0.097	6.01	.081	0.08	.008	.019	.01	10.48	
92	Low-boron										
93	High-boron	80.60		1.94	.076			.027	.013	(1)	
		MgO	K ₂ O	Na ₂ O	B ₂ O ₃	P ₂ O ₅	As ₂ O ₅	As ₂ O ₃	SO ₃	Cl	F
89	Lead-barium	0.03	8.40	5.70		0.23	0.36	0.03	0.03	0.05	
91	Opal	.008	3.25	8.48		.022	.102	.091		.014	5.72
92	Low-boron				0.70						
93	High-boron	.026	0.16	4.16	12.76	(1)	.14	.085	.009	.036	
											Loss on ignition

¹ Not detected.

LIMESTONE, DOLOMITE, SILICA BRICK, BURNED MAGNESITE, AND TITANIUM DIOXIDE

Sample No.	Kind	SiO ₂	Fe ₂ O ₃	Al ₂ O ₃	TiO ₂	MnO	CaO	SrO	MgO	Na ₂ O
1a	Limestone	14.11	1.63	4.16	0.16	0.038	41.32	0.23	2.19	0.39
88	Dolomite	0.31	0.084	0.067	.005	.006	30.49	<.01	21.48	.08
102	Silica brick ¹	93.94	.66	1.96	.16	.005	2.29		.21	.015
104	Burned magnesite	2.54	7.07	0.84	.03	.43	3.35		85.67	.015
154a	Titanium dioxide				99.6					
		K ₂ O	SO ₃	S	P ₂ O ₅	CO ₂	C	H ₂		Loss on ignition
1a	Limestone	0.71	0.04	0.25	0.15	33.53	0.61			34.55
88	Dolomite	.03	.035	.013	.003	47.25	.08	0.008		47.52
102	Silica brick	.32			.025		.			0.38
104	Burned magnesite	.015			.057					

¹ Density 2.33 g/cm³ at 25° C.

SILICON CARBIDE

Sample		Total Si	Total C	Free C	SiC	Fe	Al	Ti	Zr	Ca	Mg
112		69.11	29.10	0.09	96.85	0.45	0.23	0.025	0.027	0.03	0.02

4.2. Chemicals


Sample No.	Name	Purity on basis of titration	Heat of combustion
84e	Acid potassium phthalate-----	100.02	
39g	Benzoic acid-----	99.99	
40f	Sodium oxalate-----	99.96	
83b	Arsenic trioxide-----	100.00	
136a	Potassium dichromate-----	99.99	

SUGARS

Sample No.	Kind	Moisture	Reducing sub- stances	Ash
17	Sucrose-----	<0.003	<0.002	<0.003
41	Dextrose-----	$<.01$	-----	$<.003$

MASS

003
003



THE NATIONAL BUREAU OF STANDARDS

The scope of activities of the National Bureau of Standards at its headquarters in Washington, D. C., and its major field laboratories in Boulder, Colorado, is suggested in the following listing of the divisions and sections engaged in technical work. In general, each section carries out specialized research, development, and engineering in the field indicated by its title. A brief description of the activities, and of the resultant publications, appears on the inside front cover.

WASHINGTON, D. C.

Electricity and Electronics. Resistance and Reactance. Electron Tubes. Electrical Instruments. Magnetic Measurements. Dielectrics. Engineering Electronics. Electronic Instrumentation. Electrochemistry.

Optics and Metrology. Photometry and Colorimetry. Optical Instruments. Photographic Technology. Length. Engineering Metrology.

Heat and Power. Temperature Physics. Thermodynamics. Cryogenic Physics. Rheology and Lubrication. Engine Fuels.

Atomic and Radiation Physics. Spectroscopy. Radiometry. Mass Spectrometry. Solid State Physics. Electron Physics. Atomic Physics. Nuclear Physics. Radioactivity. X-rays. Betatron. Nucleonic Instrumentation. Radiological Equipment. AEC Radiation Instruments.

Chemistry. Organic Coatings. Surface Chemistry. Organic Chemistry. Analytical Chemistry. Inorganic Chemistry. Electrodeposition. Gas Chemistry. Physical Chemistry. Thermochemistry. Spectrochemistry. Pure Substances.

Mechanics. Sound. Mechanical Instruments. Fluid Mechanics. Engineering Mechanics. Mass and Scale. Capacity, Density, and Fluid Meters. Combustion Controls.

Organic and Fibrous Materials. Rubber. Textiles. Paper. Leather. Testing and Specifications. Polymer Structure. Organic Plastics. Dental Research.

Metallurgy. Thermal Metallurgy. Chemical Metallurgy. Mechanical Metallurgy. Corrosion. Metals Physics.

Mineral Products. Engineering Ceramics. Glass. Refractories. Enamelled Metals. Concreting Materials. Constitution and Microstructure.

Building Technology. Structural Engineering. Fire Protection. Heating and Air Conditioning. Floor, Roof, and Wall Coverings. Codes and Specifications.

Applied Mathematics. Numerical Analysis. Computation. Statistical Engineering. Mathematical Physics.

Data Processing Systems. SEAC Engineering Group. Components and Techniques. Digital Circuitry. Digital Systems. Analog Systems. Application Engineering.

● Office of Basic Instrumentation

● Office of Weights and Measures

BOULDER, COLORADO

Cryogenic Engineering. Cryogenic Equipment. Cryogenic Processes. Properties of Materials. Gas Liquefaction.

Radio Propagation Physics. Upper Atmosphere Research. Ionospheric Research. Regular Propagation Services. Sun-Earth Relationships.

Radio Propagation Engineering. Data Reduction Instrumentation. Modulation Systems. Navigation Systems. Radio Noise. Tropospheric Measurements. Tropospheric Analysis. Radio Systems Application Engineering.

Radio Standards. Radio Frequencies. Microwave Frequencies. High Frequency Electrical Standards. Radio Broadcast Service. High Frequency Impedance Standards. Calibration Center. Microwave Physics. Microwave Circuit Standards.

