

The program of research on building materials and structures carried on by the National Bureau of Standards was undertaken with the assistance of the Central Housing Committee, an informal organization of governmental agencies concerned with housing construction and finance, which is cooperating in the investigations through a committee of principal technicians.

CENTRAL HOUSING COMMITTEE ON RESEARCH, DESIGN, AND CONSTRUCTION

A. C. SHIRE, *Chairman*. United States Housing Authority. HOWARD P. VERMILYA, Vice Chairman. Federal Housing Administration.

STERLING R. MARCH, Secretary.

MARY F. TAYLOR, Assistant Secretary.

PIERRE BLOUKE, Federal Home Loan Bank Board.

HUGH L. DRYDEN, National Bureau of Standards.

LOUIS A. SIMON, Public Buildings Administration.

LUTHER M. LEISENRING, Construction Division (War).

EDWARD A. POYNTON, Office of Indian Affairs. JOHN S. DONOVAN, Farm Security Administration.

GEORGE W. TRAYER, Forest Service (F. P. Laboratory).

ROLLO H. BRITTEN, Public Health Service.

GEORGE E. KNOX, Yards and Docks (Navy).

WILLIAM R. TALBOTT, Veterans' Administration.

WALLACE ASHBY, Bureau of Agricultural Chemistry and Engineering

NATIONAL BUREAU OF STANDARDS STAFF COMMITTEE ON ADMINISTRATION AND COORDINATION

HUGH L. DRYDEN, Chairman. Mechanics and Sound

PHAON H. BATES, Clay and Silicate Products.

HOBART C. DICKINSON, Heat and Power. GUSTAV E. F. LUNDELL, Chemistry.

ADDAMS S. MCALLISTER, Codes and Specifications.

WARREN E. EMLEY, Organic and Fibrous Materials. HENRY S. RAWDON, Metallurgy.

The Forest Products Laboratory of the Forest Service is cooperating with both committees on investigations of wood constructions.

[For list of BMS publications and directions for purchasing, see cover page III.]

UNITED STATES DEPARTMENT OF COMMERCE · Jesse H. Jones, Secretary NATIONAL BUREAU OF STANDARDS · Lyman J. Briggs, Director

BUILDING MATERIALS and STRUCTURES

REPORT BMS67

Structural Properties of "Mu-Steel" Prefabricated Sheet-Steel Constructions for Walls, Partitions, Floors, and Roofs Sponsored by Herman A. Mugler

by HERBERT L. WHITTEMORE, AMBROSE H. STANG, and VINCENT B. PHELAN



ISSUED APRIL 12, 1941

The National Bureau of Standards is a fact-finding organization; it does not "approve" any particular material or method of construction. The technical findings in this series of reports are to be construed accordingly.

UNITED STATES GOVERNMENT PRINTING OFFICE • WASHINGTON • 1941 FOR SALE BY THE SUPERINTENDENT OF DOCUMENTS, WASHINGTON, D. C. • PRICE 15 CENTS

Foreword

This report is one of a series issued by the National Bureau of Standards on the structural properties of constructions intended for low-cost houses and apartments. These constructions were sponsored by organizations within the building industry advocating and promoting their use. The sponsor built and submitted the specimens described in this report for participation in the program outlined in BMS2, Methods of Determining the Structural Properties of Low-Cost House Constructions. The sponsor, therefore, is responsible for the design of the constructions and for the description of the materials and methods of fabrication. The Bureau is responsible for the testing of the specimens and the preparation of the report.

This report covers only the load-deformation relations and strength of the structural element submitted when subjected to compressive, transverse, impact, concentrated, and racking loads by standardized methods simulating the loads to which the element would be subjected in actual service.

The National Bureau of Standards does not "approve" a construction, nor does it express an opinion as to its merits for reasons given in reports BMS1 and BMS2. The technical facts presented in this series provide the basic data from which architects and engineers can determine whether a construction meets desired performance requirements.

LYMAN J. BRIGGS, Director.

Structural Properties of "Mu-Steel" Prefabricated Sheet-Steel Constructions for Walls, Partitions, Floors, and Roofs Sponsored by Herman A. Mugler

by HERBERT L. WHITTEMORE, AMBROSE H. STANG, and vincent B. PHELAN

CONTENTS

	Page
vord	11
Introduction	1
Sponsor and product	2
Specimens and tests	2
Materials	4
1. Steel	4
2. Bolts	4
3. Paint	4
4. Insulating board	4
5. Sheathing paper	5
6. Wood	5
7. Nails	5
8. Roof covering	6
Wall CU	6
1. Sponsor's statement	6
(a) Four-foot wall specimens	6
(b) Eight-foot wall specimens	9
(c) Comments	9
2 Compressive load	9
3 Transverse load	11
4 Impact load	11
5 Concentrated load	12
6 Backing load	13
o, manning load	10
	$Vord_{-}$ Introduction

ABSTRACT

For the program on the determination of the structural properties of low-cost house constructions, Herman A. Mugler submitted 33 specimens representing his "Mu-Steel" prefabricated sheet-steel wall, partition, floor, and roof constructions.

The wall specimens were subjected to compressive, transverse, impact, concentrated, and racking loads; the partition specimens to impact and concentrated loads; the floor specimens to transverse, impact, and concentrated loads; and the roof specimens to transverse and concentrated loads. The transverse, impact, and concentrated loads were applied to both faces of the wall specimens. The impact and concentrated loads were applied to both faces of the partition speci-

		Page
VI.	Partition CV	13
	1. Sponsor's statement	13
	(a) Description	14
	(b) Comments	15
	2. Impact load	15
	3. Concentrated load	-16
VII.	Floor CW	17
	1. Sponsor's statement	17
	(a) Description	17
	(b) Comments	19
	2. Transverse load	20
	3. Impact load	20
	4. Concentrated load	21
VIII.	Roof CX	21
	1. Sponsor's statement	21
	(a) Description	21
	(b) Comments	23
	2. Transverse load	23
	3. Concentrated load	24
IX.	Additional comments by sponsor	24

mens. The loads simulated the loads to which the elements are subjected in actual service.

The deformations under load and the sets after the load was removed were measured for uniform increments of load. The results of the measurements are presented in graphs and tables.

I. INTRODUCTION

To provide technical facts on the performance of constructions for low-cost houses, to discover promising new constructions, and ultimately to determine the properties necessary for acceptable performance in actual service, the National Bureau of Standards has invited the cooperation of the building industry in a program of research on building materials and structures suitable for low-cost houses and apartments. The objectives of this program are described in BMS1, Research on Building Materials and Structures for Use in Low-Cost Housing.

To determine the strength of house constructions in the laboratory, standardized methods were developed for applying loads to portions of a completed house. Included in this study were masonry and wood constructions of types which have been extensively used in this country for houses and whose behavior under widely different service conditions is well known to builders and the public. The reports on these constructions are BMS5, Structural Properties of Six Masonry Wall Constructions, and BMS25, Structural Properties of Conventional Wood-Frame Constructions for Walls, Partitions, Floors, and Roofs. The masonry specimens were built by the Masonry Construction Section of this Bureau, and the woodframe specimens were built and tested by the Forest Products Laboratory at Madison, Wis.

The present report describes the structural properties of four elements of a house sponsored by one of the manufacturers in the building industry. The wall specimens were subjected to compressive, transverse, impact, concentrated, and racking loads, simulating the loads to which the walls of a house are subjected. In actual service compressive loads on a wall are produced by the weight of the roof, second floor and second-story walls, if any, by furniture and occupants, and by snow and wind loads on the roof. Transverse loads on a wall are produced by wind, concentrated and impact loads by accidental contact with heavy objects, and racking loads by the action of the wind on the adjoining walls. For non-loadbearing partitions, impact loads may be applied accidentally by furniture or persons falling against the partition, and concentrated loads by furniture, a ladder, or other object leaning against the partition. Transverse loads are applied to floors by furniture and occupants; concentrated loads by furniture, for example the legs of a piano; and impact loads by objects falling on the floor or by persons jumping on the floor. Transverse loads are applied to roofs by wind and snow; concentrated loads by persons walking on the roof, and by tools and equipment when the roof is constructed and repaired.

The deflection and set under each increment of load were measured because the suitability of a construction depends not only on its resistance to deformation when loads are applied, but also on its ability to return to its original size and shape when the loads are removed.

II. SPONSOR AND PRODUCT

The specimens were submitted by Herman A. Mugler, Lynbrook, N. Y., and represented prefabricated wall, partition, floor, and roof constructions marketed under the trade name "Mu-Steel." These constructions consisted of channel-shaped panels of sheet steel fastened together by bolts.

III. SPECIMENS AND TESTS

The specimens represented four elements of a house and were assigned the following symbols: wall, CU; partition, CV; floor, CW; roof, CX. The individual specimens were assigned the designations given in table 1.

 TABLE 1.—Specimen designations, wall CU, partition

 CV, floor CW, and roof CX

Element	Specimen desig- nation	Load	Load applied	
Wall	$C_{1}, C_{2}, C_{3}, C_{3}, C_{1}, T_{2}, T_{3}, T_{2}, T_{3}, T_{4}, T_{5}, T_{6}$	Compressive	Upper end.	
Do		Transverse	Inside face.	
D0 D0 D0	I_{4}, I_{5}, I_{5} I_{1}, I_{2}, I_{3} I_{4}, I_{5}, I_{6}	Impact ado	Inside face. Outside face.	
Do Do Do	$\begin{array}{cccccccccccccccccccccccccccccccccccc$	Concentrateddo Backing	Inside face. Outside face. Near upper end	
Partition	I_1, I_2, I_3	Impact a	"Inside" face. ^b	
Do	I_4, I_5, I_6		"Outside" face.	
Do	$\begin{array}{cccccccccccccccccccccccccccccccccccc$	Concentrated	"Inside" face,	
Do		do	"Outside" face,	
Floor		Transverse	Upper face,	
Do	11, I2, I3	Impact a	Do.	
Do	P1, P2, P3	Concentrated	Do.	
Do	P1, P2, P3	Concentrated	Do. Do.	

 a The impact and the concentrated loads were applied to the same specimens, the impact loads first. b The quoted "inside" and "outside" faces refer to partition specimens

only, \sim The transverse and the concentrated loads were applied to the same specimens, the transverse loads first.

Except as mentioned below, the specimens were tested in accordance with BMS2, which report also gives the requirements for the specimens and describes the presentation of the results of the tests, particularly the load-deformation graphs.

Because, under compressive load, there may be considerable shortening at the bolted connections between the panels and the sill and the cap, the shortening of the entire specimen may not be proportional to the value obtained from the compressometers attached to the specimen over only a portion of its entire height. Therefore, the shortenings and the sets were measured with compressometers attached to the steel plates through which the load was applied, not attached to the speeimen as described in BMS2.

The lateral deflections under compressive loads were measured with a deflectometer of fixed gage length, which consisted of a light (duralumin) tubular frame having a leg at one

end and a hinged plate at the other. The deflectometer was attached in a vertical position by clamping the hinged plate to one of the faces of the specimen near the top. The gage length (distance between the points of support) was 7 ft. 6 in. A dial micrometer was mounted on the frame at midlength, with the spindle in contact with the wall specimen. The dial was graduated to 0.001 in. and the readings were recorded to the nearest division. There were two deflectometers on the specimen, one near each outer stud (i. e., the two flanges of adjacent channels). This method of measurement was used instead of the taut-wire mirrorscale method described in BMS2.

The indentation under concentrated load and the set after the load was removed were measured, not the set only as described in BMS2. The apparatus is shown in figure 1.

The load was applied to the steel disk, A, to which the crossbar, B, was rigidly attached. The load was measured by means of the ring dynamometer, C. Two stands, D, rested on the face of the specimen, each supporting a



FIGURE 1.—Concentrated load on partition specimen CV-P5.
A, disk; B, crossbar; C, ring dynamometer; D, stand; E, dial micrometer.

dial micrometer, E, the spindle of which was in contact with the crossbar 8 in. from the eenter of the disk. The micrometers were graduated to 0.001 in. and readings were recorded to the nearest division. The initial reading (average of the micrometer readings) was observed under the initial load, which included the weight of the disk and dynamometer. A load was applied to the disk, and the average of these micrometer readings minus the initial reading was taken as the depth of the indentation under load.

The deformations under racking load were measured with a right-angle deformeter, consisting of a steel channel and a steel angle braced to form a rigid connection. The channel of the deformeter was fastened along the top of the specimen by self-tapping screws with the steel angle extending downward in the plane of the specimen. To the stop, which prevented motion of the specimen horizontally, a dial micrometer was attached with the spindle in contact with the steel angle of the deformeter. The gage length (distance from the top of the specimen to the middle of the stop) was 8 ft. 2½ in. The micrometer was graduated to 0.001 in. and readings were recorded to the nearest division. The deformeter was used instead of the taut-wire mirror-scale deflectometer described in BMS2.

Because the partition specimens were unsymmetrical about a plane midway between the faces, six specimens were tested, not three as stated in BMS2.

The speed of the movable head of the testing machine was adjusted to 0.072 in./min for the compressive load on walls, 0.126 in./min for the transverse load on walls, 0.160 in./min for the transverse load on floors, and 0.211 in./min for the transverse load on roofs.

The tests were begun December 19, 1939 and completed January 29, 1940. The sponsor's representative witnessed the tests.

IV. MATERIALS

The information on the materials was obtained from the sponsor and from inspection of the specimens. The Forest Products Laboratory identified the species of the wood in the siding, subflooring, flooring, and spacer blocks. The Paper Section of this Bureau determined the physical properties of the insulating board. The Engineering Mechanics Section determined the moisture content of the wood.

1. Steel

Sheet.—Open-hearth, hot-rolled, annealed, pickled, black. The specified chemical composition of the steel is given in table 2. Specified tensile strength, minimum 40,000, maximum 50,000 lb/in². Bethlehem Steel Co.

 TABLE 2.—Specified chemical composition of the sheet steel

Elucont	Content					
Flement	Minimum	Maximum				
	Percent	Percent				
Carbon	0.08	0. 11				
Manganese	. 30	. 50				
Phosphorus		. 04				
Silicon		. 02				
Common	10					

Structural.—Open-hearth, hot-rolled, annealed. Angles, 2- by 2- by ¼-in. Bethlehem Steel Co.

2. Bolts

Store bolts.—Mild steel, $\frac{1}{4}$ - in. diam, $\frac{1}{2}$ in. long, round head (slotted), National Coarse (N. C.) threads 20 per inch, threaded full length, unfinished, bright. Nuts: mild steel, square, regular, $\frac{1}{46}$ in. thick, $\frac{1}{46}$ in. across flats, unfinished, bright. Corbin Screw Co.

3. Paint

The paint was ready-mixed aluminum paint. The formula for the paint was not furnished by the dealer. Marketing and Merchandising Corporation, "Tru Test, No. TT554."

4. INSULATING BOARD

The insulating board, ½ in. thick, was made from wood fibers produced by a cold-grinding process. The fibers were chemically treated and intimately mixed with finely divided asphalt before felting into a board to provide greater resistance to water, rot, and termites. One surface of the boards had the appearance of a closely woven fabric designated "linen texture" and the other the appearance of a loosely woven fabric designated "burlap texture." Color, grayish brown. Insulite Co., "Graylite."

The physical properties of the insulating board are given in table 3. The samples of the board were taken from the specimens after they had been tested.

TABLE 3.—Physical properties of insulating board, $\frac{1}{2}$ in. thick

[The samples were taken from the specimens after they had been tested]

Property					
Tensile strength:					
Machine direction lb/in. ²	303				
Cross direction lb/in. ²	218				
Transverse strength: ^a					
Machine direction lb	18				
Cross direction lb	14				
Deflection at rupture:					
Machine direction in	. 60				
Cross direction in .	. 67				
Linear expansion for 45-percent change in relative humidity:					
Machine directionpercent	. 05				
Cross directionpercent	. 10				
Nail-holding strength:					
Machine directionlb	73				
Cross directionlb	71				
Densitylb/ft ²	17.0				
Moisture content, based on weight when drypercent	4				
Air permen bility	503				
ft ² (lb/in. ²)	393				
Water absorption, by volumepercent	4.9				

^a Span, 12 in.: width of specimens, 3 in.

The tensile strength, linear expansion, water absorption, and transverse strength and deflection at ultimate load were determined in accordance with Federal Specification LLL-F-321a, Fiber Board; Insulating. For these properties the insulating board complied with the requirements for class A.

The density, air permeability, and nailholding strength were determined by the methods described in BMS13, Properties of Some Fiber Building Boards of Current Manufacture.

The moisture content was determined by drying in an oven at 212° F until the weight was constant.

5. Sheathing Paper

"Black Diamond."—Paper, impregnated with asphalt, one-ply; weight, 69 lb/500 ft²; width of roll, 3 ft 0 in. The Barrett Co., No. 14.

"Fords."—Paper, impregnated with asphalt, one-ply; weight, 55 lb/500 ft²; width of roll, 3 ft 0 in. The Ford Roofing Products Co.

6. Wood

Bevel Siding.—Identified as a yellow pine, probably Pinus ponderosa, No. 2 common, $\frac{3}{4}$ in. thick tapered to $\frac{5}{16}$ in., $\frac{9}{2}$ in. wide, dressed.

Flooring, subflooring, and sheathing.—Identified as southern yellow pine, No. 2 common, ²‰ in. thick by 5¼ in. face width (nominal 1 by 6 in). S2S (surfaced two sides), tongued and grooved.

Spacer blocks.—Identified as cypress (*Taxo-dium distichum*), No. 1 common, S2S1E (surfaced two sides one edge), ³/₄- by 1[%]/₈-in.

Moisture content.—The moisture content of the wood members in each structural specimen was determined by the use of an electric moisture meter. Readings were taken on each piece of bevel siding and three spacer blocks for each wall specimen; on three spacer blocks for each partition specimen; on four pieces of flooring, four pieces of subflooring, and three spacer blocks for each floor specimen; and on four pieces of sheathing and three spacer blocks for each roof specimen. To calibrate the moisture meter, moisture determinations were made on 18 pieces of subflooring, and 15 pieces of spacer blocks by drying them to constant weight at 212° F. From these determinations the correction to be applied to the meter readings was found to be ± 0.3 for siding, ± 0.2 for subflooring, flooring, and sheathing, and ± 0.7 for spacer blocks. Values of the moisture content given in table 4, except as indicated by footnote "b", were obtained by applying these corrections to the average of the meter readings and rounding the results to the nearest whole percent.

TABLE 4. - Moisture content of wood

[Determined on day the structural specimen was tested]

	Con-	Moisture content •				
Wood	tion symbol	Mini- mum	Maxi- mum	A ver- age		
Bevel siding, yellow pine Subflooring, southern yellow pine Finish flooring, southern yellow pine. Sheathing, southern yellow pine Spacer blocks, cypress	$\begin{array}{c} CU\\ CW\\ CW\\ CW\\ CX\\ CX\\ CV\\ CV\\ CW\\ CX\end{array}$	Percent 7 7 7 7 8 8	Percent 11 18 21 11 8 13 	Percent § 11 11 9 8 11 ^b 6 ^b 5		

Based on the weight when dry.

 Determined by drying in an oven, hecause the values were below the range of the moisture meter.

7. NAILS

Screw nails.

Heavy duty, steel, No. 5 Screw Gage (0.125in. diam), 1½ in. long, quadruple thread, 7 threads per inch, flat head, diamond point, hardened, 250 nails per pound. Hillwood Manufacturing Co., "Helyx Drive Screw Nails."

Heavy duty, steel, No. 7 Screw Gage (0.151in. diam), 1³/₄ in. long, quadruple thread, 7 threads per inch, flat head, diamond point, hardened, 148 nails per pound. Hillwood Manufacturing Co., "Helyx Drive Screw Nails."

Heavy duty, steel, No. 7 Screw Gage (0.151in. diam), 2½ in. long, quadruple thread, 5 threads per inch, flat head, diamond point, hardened, 104 nails per pound. Hillwood Manufacturing Co., "Helyx Drive Screw Nails."

Finishing.—Steel wire, 8d, No. 12½ Stl. W. G. (0.0985-in. diam), 2½ in. long, bright, 189 nails per pound.

Roofing.—Steel wire, No. 10 Stl. W. G. (0.135-in. diam), 1 in. long, $\frac{7}{16}\text{-in. diam}$ flat head, bright, 215 nails per pound.

8. Roof Covering

Roll roofing.—Asphalt, smooth-surface; weight, 55 lb/108 ft²; width of roll, 36 in. Continental Roofing Mills, "Battle Axe."

Roofing felt.—Asphalt-saturated; weight, 12 lb/108 ft²; width of roll, 36 in. The Ford Roofing Products Co., "Fords."

Roof-coating.—Asphalt, containing finely ground asbestos fiber, diluted to a brushing consistency with a volatile solvent. Continental Roofing Mills, "Contico."



FIGURE 2.—Four-foot wall specimen CU.
 A, full-width wall panels; B, half-width wall panels; C, angle sill; D, angle cap; E insulating board; F, bevelsiding; C, spacer blocks.

V. WALL CU

1. Sponsor's Statement

Wall CU consisted of prefabricated sheetsteel ehannels fastened at the flanges; the webs were the inside face. The outside face was insulating board eovered with bevel siding.

The price of this construction in Washington, D. C., as of July 1937, was \$0.43/ft².

(a) Four-Foot Wall Specimens

Each 4-ft wall specimen, shown in figure 2, was 8 ft % in. high, 5 ft 0 in. wide, and 5% in. thick and consisted of two full-width channelshaped wall panels, A; two half-width panels, B; angle sill, C; angle cap, D; insulating board, E; bevel siding, F; and spacer blocks, G.

Wall panels.—The full-width wall panels, A, were sheet steel, No. 16 U. S. Std. Gage (0.0613 in. thick), 8 ft $\frac{1}{8}$ in. high, 1 ft 8 in. wide, and 4 in. deep. The edges of the flanges were turned in 2 in., as shown in figure 3, for attaching the outside face and to increase the strength of the panel. Adjacent panels were fastened through the flanges by stove bolts $\frac{1}{4}$ -in. diam, $\frac{1}{2}$ in. long. There were two rows of 9 bolts each spaced as shown in figure 4.

The half-width panels, B, were the same as a full-width panel cut along a longitudinal center line. There are no half-width panels in a house.

Sill.—The angle sill, C, sheet steel, No. 11 U. S. Std. Gage (0.1225 in. thick), was $4\frac{1}{8}$ by 2 in. by 5 ft $\frac{1}{4}$ in. long. The sill was fastened to the panels by 10 stove bolts, $\frac{1}{4}$ -in. diam, $\frac{1}{2}$ in. long, through the vertical (2-in.) leg and the webs of the panels. The spacing of the bolts is shown in figure 4.

Cap.—The angle cap, D, rolled structural steel, was 2 by 2 by $\frac{1}{4}$ in., 5 ft $\frac{1}{4}$ in. long. The eap was fastened to the panels in the same manner as the sill, by 10 stove bolts, $\frac{1}{4}$ -in. diam, $\frac{1}{2}$ in. long, through the vertical leg of the cap and the webs of the panels. The spacing of the bolts is shown in figure 4.

Fabrication.—Adjacent panels were clamped together and the bolt holes were laid off with a rule and marked with a center punch. The holes were drilled with a twist drill, ¼-in. diam, mounted in an electric hand drill.

The sill and the cap were then clamped to the wall panels and the bolt holes laid off. The difference between the nominal spacing and the actual spacing of the holes was as much as $\frac{1}{4}$ in. in some instances.

In a house all the panels are full width and there are no half-width panels. The middle bolt fastening the sill and the cap to the web of a panel is at midwidth of the panel. In the 4-ft wall specimens, therefore, there should have been a half-sized bolt (one-half









FIGURE 4.—Bolt spacing for wall and portition panels.

the cross-sectional area of the full-sized bolt) at the edge of the specimen, fastening the sill and cap to each half-width panel. For convenience the bolts were full-sized (¼-in. diam) and, to provide an effective fastening, 1¼ in. from the edge of the specimen. It is believed that these changes had very little effect upon the structural properties of the wall specimens.

Paint.—Each panel, sill, and cap was covered with two coats of aluminum paint applied with

[7]



sheathing paper 8 in. wide, 5 ft. 0 in. long. Both insulating board and sheathing paper were held in place by the bevel siding. *Bevel siding.*—The

bevel siding, F, was 12 pieces of vellow pine, ¾ in. thick, tapered to $\frac{5}{16}$ in., $9\frac{1}{2}$ in. wide, 5 ft. 0 in. long, exposed 8 in. to the weather, fastened to the flanges of the panels by 1³/₄-in.screw nails. There were two nails through each piece of siding at each stud. One nail was near the upper edge through the siding, the insulating board, and through the flange of the stud. The other nail was near the lower edge through the two pieces of siding, the insulating board, and through the flange. The nails in adjacent pieces of siding were staggered with respect to the joint between the panels and close to it.

There was no paint on the bevel siding. *Blocks.*—The spacer blocks, *G*, were cy-



A, full-width wall panels; C, angle sill; D, angle cap; E, insulating board; F, bevel siding; H, special wall panel; I blocks, G, were cyand J, structural-steel channels; K, sheet-steel strip. 34 by 1^{58} in., 4

a brush, one coat before assembling and one after.

Insulating board.—The insulating board, E, consisted of two pieces of "Graylite," 4 ft. 0 in. high, 5 ft. 0 in. wide, $\frac{1}{2}$ in. thick, applied with the "burlap-texture" surface outward. There was one transverse joint, at midheight of the specimen, which was covered with a strip of in. long, nine blocks along each edge of the specimen, spaced 1 ft. Each block was fastened to the half-width panel by one 1³/₄-in. screw nail through the steel and into the block, and to the outside face by one 8d finishing nail through the siding and insulating board and into the block. There are no spacer blocks in a house.



FIGURE 6.— Wall specimen CU-C1 under compressive load A, compressometer; B, deflectometer.

(b) Eight-Foot Wall Specimens

The 8-ft. wall specimens, shown in figure 5, were 8 ft. $\frac{3}{8}$ in. high, 8 ft. 8 in. wide, and $5\frac{5}{8}$ in. thick. They were similar to the 4-ft. specimens, except that there were five full-width panels. There were no half-width panels and no spacer blocks; but there was a special wall panel, H, having a face width of 2 in., at each edge of the specimen, to make the outer studs like the inner studs.

To apply the racking load uniformly along the width of the specimens, rolled structuralsteel channels, I and J, were fastened to each specimen. The channel, I, 6 in. wide, weighing 10.5 lb./ft., was 8 ft. 8% in. long and was fastened to the sill by six square-headed bolts, $\frac{1}{2}$ -in. diam., 1 in. long, spaced $1\frac{1}{2}$ in. from each stud.

A sheet-steel strip, K, No. 16 U. S. Std. Gage (0.0613 in. thick), 8 in. wide and 8 ft. 8 in.

long, was fastened to the angle cap by 17 stove bolts, ¼-in, diam., ½ in, long, one bolt adjacent to each bolt fastening the angle cap to the wall panels. The 6-in, channel, J, 10.5 lb./ft., was 8 ft. 8¾ in, long and was fastened to the sheetsteel strip, K, by six bolts, ½-in, diam, 1 in, long, spaced 1½ in, from each stud. There are no channels or sheet-steel strips in a house.

The insulating board consisted of two pieces, 4 ft. 0 in. high, 8 ft. 8 in. wide. The horizontal joint at midheight was covered with a strip of sheathing paper 8 in. wide and 8 ft. 8 in. long. The bevel siding was 8 ft. 8 in. long. The insulating board and the bevel siding were fastened to the wall panels in the same way as in the 4-ft. specimens.

(c) Comments

Standard wall panels, all 1 ft. 8 in. wide, are available, having depths of 4, 6, and 8 in. and lengths up to 20 ft. Panels having other dimensions are special. To expedite the erection of the building, the holes for the bolts in the panels may be punched before the panels are shipped to the site.

In a house the angle sill for the wall is supported by the steel floor panels and bolted to them. At a corner, the flange of one wall panel is bolted to the web of the adjacent panel. At the bottom and top of openings for doors and windows, channels of sheet steel, No. 16 U. S. Std. Gage (0.0613 in. thick), are placed horizontally over the ends of wall panels. Conventional doors and windows, either wood or metal, may be used.

If the roof is flat, wall panels may be bolted horizontally to the roof panels for a parapet.

The outside face of the walls may be shingles, siding, stucco, or brick veneer. The inside face may be either painted or papered.

2. Compressive Load

Wall specimen CU-C1 under compressive load is shown in figure 6. The results for wall specimens CU-C1, C2, and C3 are given in table 5 and in figures 7 and 8. The lateral deflections shown in figure 8 are plotted to the right of the vertical axis for deflections of the specimens toward the outside face and to the left for deflections toward the inside face.

TABLE 5.—Structural properties of wall CU

[Weight, based on the face area: 6.81 lb/ft²]

Compressive load ¢		Transverse load; span 7 ft 6 in.		Impact load; span 7 ft 6 in.		Concentrated load		Racking load	
Specimen	Maximum load	Specimen	Maximum load	Specimen	Maximum height of drop	Specimen	Maximum load	Specimen	Maximum load
C1 C2 C3	Kips/ft b 11. 26 12. 48 11. 51	T1 T2 T3	<i>lb/ft</i> ² 368 339 357	11 12 13	ft c 10.0 c 10.0 c 10.0 c 10.0	P1 P2 P3	/b c 1,000 c 1,000 c 1,000 c 1,000	R1 R2 R3	Kips/ft b 2, 18 2, 06 2, 17
A verage	11.75	Average	355	Average	• 10.0	Average	° 1,000	A verage	2.14
		T_{4} T_{5} T_{6}	288 270 291	14 15 16	¢ 10.0 ¢ 10.0 ¢ 10.0	$\begin{array}{c} P4 \\ P5 \\ P6 \end{array}$	889 793 820		
		A verage	283	Average	° 10, 0	A verage	834		

The compressive loads were applied one-third the thickness of the structural portion (1.33 in.) from the inside face.



FIGURE 7.—-Compressive load on wall CU.

Load-shortening (open circles) and load-set (solid circles) results for specimens CU-CI, C2, and C3. The load was applied 1.33 in. (one-third the thickness of structural portion of the wall) from the inside face. The loads are in kips per foot of actual width of specimen.

There were considerable differences in the shortening and in the set of the individual specimens, particularly under low loads. At the bottom and top the insulating board projected beyond the ends of the specimens and the web of some of the wall panels projected beyond the turned-in portion of the flanges as much as 1/32 in. Also, the sill was not in close contact with the end of the panels.

The load was eccentric toward the inside face, and the lateral deflection of specimens

CU-C1 and C2 was toward the outside face. However, the deflection of CU-C3 was toward the inside face for loads up to 5 kips/ft, when the bolts which fastened the sill to the panels sheared and allowed the ends of the panels to come into contact with the sill. Under greater loads the deflection was toward the outside face but was somewhat less than the deflection of specimens CU-C1 and C2.

The lateral set of each of the specimens under



FIGURE 8.—Compressive load on wall CU.

Load-lateral deflection (open circles) and load-lateral set (solid circles) results for specimens CU-CI, C2, and C3. The load was applied 1.33 in. (one-third the thickness of the structural portion of the wall) from the inside face. The loads are in kips per foot of actual width of specimen. The deflections and sets are for a gage length of 7 ft 6 in., the gage length of the data set. length of the deflectometer.

most loads was toward the inside face. No explanation of the negative lateral sets was found.

The web (inside face) of one full-width panel began to buckle locally about 2 ft from the top of specimen CU-C1 under a load of 4.5 kips/ft and under a load of 7.0 kips/ft on specimens C2and C3. Under a load of 7.5 kips/ft, the web of each panel buckled near the top in specimen C1; and under a load of 8.0 kips/ft, on specimen C2. One stud buckled near the bottom of specimen C3 under a load of 9.0 kips/ft. Under greater loads this buckling increased until the maximum load was reached.

3. TRANSVERSE LOAD

The results of the transverse loads are shown in table 5 and in figure 9 for wall specimens CU-T1, T2, and T3, loaded on the inside face,



FIGURE 9.— Transverse load on wall CU, load applied to inside face.

 $\begin{array}{c} \mbox{Load-deflection (open circles) and load-set (solid-circles) results for specimens $CU-T1$, $T2$, and $T3$ on the span 7 ft 6 in. } \end{array}$

and in figure 10 for wall specimens T_4 , T_5 , and T_6 , loaded on the outside face.

Under the maximum load applied to the inside face (web of panels), specimens CU-T1, T2, and T3 failed by buckling of two or more studs between the loading rollers.

Specimens $CU-T_4$, T5, and T6 were loaded on the outside face (siding). The flanges buckled where they were pierced by the nails fastening the insulating board and the siding. Under a load of 240 lb/ft² on specimens T_4 and T5, the buckling of the flanges increased under



Load-deflection (open circles) and load-set (solid circles) results for specimens CU-T4, T5, and T6 on the span 7 ft 6 in.

the loading rollers. Under the maximum load, each specimen failed by buckling of the studs under the loading rollers.

4. Impact Load

The results of the impact loads are shown in table 5 and in figure 11 for wall specimens CU-I1, I2, and I3, loaded on the inside face, and in figure 12 for specimens CU-I4, I5, and I6, loaded on the outside face.

The impact loads were applied to the center of the inside face of specimens I1, I2, and I3, the sandbag striking the steel sheet directly over the center stud. The center stud was buckled slightly after a drop of 7.0 ft on specimen CU-I1 and after a drop of 8.0 ft on specimens I2 and I3. There was no failure of either face of specimens I1 and I2. In specimen I3 after the 10-ft drop, there was a $\frac{1}{4}$ -in. opening between the inner panels on the face struck and one piece of siding on the opposite face was completely separated from the specimen.

After the 10-ft drop, the sets in specimens CU-I1, I2, and I3 were 0.51, 0.62, and 0.69 in., respectively.



FIGURE 11.—Impact load on wall CU, load applied to inside face.

Height of drop-deflection (open circles) and height of drop-set (solid circles) results for specimens CU-II, I2, and I3 on the span 7 ft 6 in.

	Specimen 14		$rac{\operatorname{Specimen}}{I^5}$		Specimen <i>I</i> 6	
Description of effects	Height of drop	Deflection	Height of drop	Deflection	Height of drop	Deflection
Faee loaded: Flange of center stud buck-						
led where the sandbag struck Nails through siding pulled from the study where the	ft 4.0	in. 1. 17	ft 4. 5	in. 0. 71	ft 4.0	in. 0. 73
sandbag struck	5.5	2.00	5.5	1.41	5.0	1.44
where the sandbag struck. Failure: Crack in siding	5. 0	1.72	6, 5	1.92	6.0	2.08
specimen	6.0	2.17	8.0	2.72	6.5	2.40
Face not loaded: Failure; wall panels separated where sand- bag struck	7.0	2.74	8. 0	2. 72	7.5	3.09

TABLE 6.—	Effects	of in	npact l	load	on	wall	specimen
CU-I4,	15, an	nd 16,	loaded	on i	the	outside	e face

The impact loads were applied to the center of the outside face of specimens I4, I5, and I6,

the sandbag striking the bevel siding directly over the center stud. The effects of the impact loads are given in table 6.

After the 10-ft drop the set in specimen CU-I4 was 1.16 in.; in I5, 1.60 in.; and in I6, 2.93 in.

5. Concentrated Load

The results of the concentrated loads are given in table 5 and in figure 13 for specimens CU-P1, P2, and P3, loaded on the inside face, and in figure 14 for specimens CU-P4, P5, and P6, loaded on the outside face.

The concentrated loads were applied to the inside face (web of panels) of specimens CU-P1, P2, and P3 on a full-width panel midway between studs and 2 ft from one end of the specimen. After a load of 1,000 lb had been applied, the sets in specimens P1, P2, and P3 were 0.33, 0.14, and 0.19 in., respectively. No other effects were observed.

The concentrated loads were applied to the outside face (siding) of specimens CU-P4, P5,



FIGURE 12.—Impact load on wall CU, load applied to outside face.

Height of drop-deflection (open circles) and height of drop-set (solid circles) results for specimens CU-I4, I5, and I6 on the span 7 ft 6 in.

and P6 midway between studs, 2 ft 7 in. from one end of the specimen. The siding cracked parallel to the grain under the loading disk at a load of 512 lb on specimen P4, 560 lb on P5, and 650 lb on P6. Under the maximum load on each specimen, the disk punched through the siding and into the insulating board.





Load-indentation (open circles) and load-set (solid circles) results for specimens CU-PI, P2, and P3.



FIGURE 14. Concentrated load on wall CU, load applied to outside face.

Load-indentation (open circles) and load-set (solid circles) results for specimens $CU\-P4,$ P5, and P6.

6. RACKING LOAD

Wall specimen $CU^{*}RI$ under racking load is shown in figure 15. The results for wall specimens $CU^{*}RI$, R2, and R3 are shown in table 5 and figure 16.

The racking loads were distributed along the top of the specimen by a structural-steel channel bolted to a steel plate which was in turn bolted to the angle cap. The sill angle was also



FIGURE 15.—Wall specimen CU-R1 under racking load. A, deformeter.

bolted to a structural-steel channel which was in contact with the stop.

At a load of 2.0 kips/ft the wall panels in specimens R2 and R3 began to buckle. The maximum load sheared the bolts fastening the sill in specimens R1 and R2 and the bolts fastening the angle cap in specimen R3.

VI. PARTITION CV

1. Sponsor's Statement

Partition CV consisted of prefabricated sheetsteel channels joined at the flanges and steel sheets. The face formed by the webs of the channels was designated the "inside" face, which corresponded to the inside face of wall CU. The face formed by the steel sheet fastened to the flanges of the panels was designated the "outside" face. The surface of the steel was covered with paint.

The price of this construction in Washington, D. C., as of July 1937, was \$0.35/ft².





(a) Description

The partition specimens, shown in figure 17, were 8 ft $\frac{3}{2}$ in. high, 5 ft 0 in. wide, and $4\frac{1}{16}$ in. thick. Each consisted of two full-width channel-shaped partition panels, A_i two half-width partition panels, B_i angle sill, C_i angle cap, D_i two steel sheets, E_i and spacer blocks, F.

Partition panels.—The full-width partition panels, A, were sheet steel, No. 16 U. S. Std. Gage (0.0613 in. thick), 8 ft $\frac{1}{8}$ in. long, 1 ft 8 in. wide, and 4 in. deep. The edges of the flanges were turned in 2 in., as shown in figure 3, for attaching the "outside" face and to increase the strength of the panel. Adjacent panels were fastened through the flanges by stove bolts, $\frac{1}{4}$ -in. diam, $\frac{1}{2}$ in. long. There were two rows of nine bolts each, spaced as shown in figure 4.

The half-width panels, *B*, were the same as a full-width panel cut along a longitudinal center line. In a house there are no half-width panels.

Sill.—The angle sill, C, sheet steel, No. 11 U. S. Std. Gage (0.1225 in. thick), was $4\frac{1}{8}$ by 2 in. by 5 ft $\frac{1}{4}$ in. long. The sill was fastened to the panels by 10 stove bolts, $\frac{1}{4}$ -in. diam, $\frac{1}{2}$ in. long, through the vertical (2-in.) leg of the angle and the webs of the panels. The spacing of the bolts is shown in figure 4.

Cap.—The angle cap, D, rolled structural steel, was 2 by 2 by $\frac{1}{4}$ in., 5 ft $\frac{1}{4}$ in. long. The





cap was fastened to the panels by 10 stove bolts, $\frac{1}{2}$ -in. diam, $\frac{1}{2}$ in. long, through the vertical leg of the cap and the webs of the panels. The spacing of the bolts is shown in figure 4.

Fabrication.—Adjacent panels were clamped together and the bolt holes laid off with a rule and marked with a center punch. The holes were drilled with a twist drill, ¼-in. diam, mounted in an electric hand drill.

The sills and the cap were then clamped to the wall panels and the bolt holes laid off. The difference between the nominal spacing and the actual spacing of the holes was as much as $\frac{1}{4}$ in. in some instances.

In a house all the panels are full width and no half-width panels are used. The middle bolt fastening the sill and the cap to the web of a panel is at midwidth of the panel. In the 4-ft partition specimens, therefore, there should have been a bolt of one-half the cross-sectional area at the edge of the specimen fastening the sill and cap to each half-width panel. For convenience the bolts were full-sized (¼-in. diam) and, to provide an effective fastening, 1¼ in. from the edge of the specimen. It is believed that these changes had very little effect upon the structural properties of the specimens.

Sheets.—The steel sheets, E, No. 16 U. S. Std. Gage (0.0613 in. thick), were 8 ft 0 in. long and 2 ft 6 in. wide. There was a vertical joint on the center stud. Each sheet was fastened to each stud by a row of 1½-in. screw nails spaced 1 ft. The nails were driven close to the joint between panels to minimize bending of the flanges. In some instances the flanges were bent inward $\frac{1}{16}$ in.

Paint.—After the panels, sill, and cap were assembled, the exposed surface was covered with one coat of aluminum paint applied with a brush. Both sides of the steel sheets were covered with one coat of aluminum paint before fastening to the wall panels.

Blocks.—The spacer blocks, F, were cypress, % by 1% in., 4 in. long, spaced 1 ft, nine blocks along each edge of the specimen. Each block was fastened to the half-width panel and to the steel sheet by one 1½-in. screw nail through the steel and into the block. In a house there are no spacer blocks.

(b) Comments

The panels, sill, and cap of the partition specimens were like those in wall CU.

In a house the edge flange of the partition is bolted to the web of the wall panels at the intersection of a partition and an outside wall.

2. IMPACT LOAD

The results of the impact tests are shown in table 7 and figure 18 for partition specimens CV-I1, I2, and I3, loaded on the "inside" face; in figure 19 for specimens CV-I4, I5, and I6, loaded on the "outside" face.



FIGURE 18.—Impact load on partition CV, load applied to "inside" face.

Height of drop-deflection (open circles) and height of drop-set (solid circles) results for specimens CV-II, I2, and I3 on the span 7 ft 6 in.

 TABLE 7.—Structural properties of partition CV

 (Weight bound of four energy 5.00 b (m))

[weight,	based	on	lace	area:	1.08	10/11*]	
							_

Impact load; s	pan 7 ft 6 in.	Concentrated load			
Specimen	Maximum height of d r op	Specimen	Maximum load		
11 12 13	$ \begin{array}{c} ft \\ a 10.0 \\ a 10.0 \\ a 10.0 \end{array} $	P1 P2 P3	$\begin{array}{c} lb \\ & b \\ \\ \\ b \\ 1,000 \\ b \\ 1,000 \end{array}$		
Average	a 10. 0	Average	^b 1,000		
I4 15 16	a 10. 0 a 10. 0 a 10. 0 a 10. 0	P4 P5 P6	a 1,000 a 1,000 a 1,000		
Average	a 10.0	Average	a 1,000		

^aTest discontinued; specimen damaged. ^bTest discontinued; specimen undamaged.

The impact loads were applied to the center of the "inside" face of specimens I1, I2, and I3, the sandbag striking the web of the panels directly over the center stud. The effects are given in table 8.

TABLE 8.—Effects of impact load on partition specimens CV-11, 12, and 13, loaded on the "inside" face

	$rac{\mathrm{Spec}}{l}$	imen 1	Specimen I2		Specimen I3	
Description of effects	Height of drop	Deflec- tion	Height of drop	Deflec- tion	Height of drop	Deflec- tion
Face loaded: Local buckling of steel where the sandbag struck. Flanges of panels began to separate along center stud	<i>ft</i> 6, 0 5, 0	<i>in.</i> 1. 01 0. 80	<i>ft</i> 4, 5 6, 0	<i>in.</i> 0.70 1.11	ft 6. 5	in. 1.10
Face not loaded: Steel sheet began to sepa- rate; the nails pulled from flanges of wall panels	3, 5 6, 5	. 62 1. 40	3. 5 5. 0	0. 54 . 87	5. 5 7. 0	0.95 1.22



FIGURE 19.—Impact load on partition CV, load applied to "outside" face.

Height of drop-deflection (open circles) and height of drop-set (solid circles) results for specimens $CV-I_4$, I_5 , and I_6 on the span 7 ft 6 in.

After the 10-ft drop the set in speeimen CV-I1 was 0.95 in.; in I2, 1.13 in.; and in I3, 0.94 in.; and the flanges had separated $\frac{1}{2}$ in. where the sandbag struck.

The impact loads were applied to the center of the "outside" face of specimens I_4 , I_5 , and I_6 , the sandbag striking the steel sheet directly over the center stud. The effects are given in table 9.

After the 10-ft drop the set in specimen CV-I4 was 2.21 in.; in I5, 2.24 in.; and in I6, 2.50 in.

 TABLE 9.—Effects of impact load on partition specimens

 CV-14, 15, and 16, loaded on the "outside" face

	Specimen I4		${{ m Specimen} \over I5}$		$rac{\mathrm{Specimen}}{I6}$	
Description of effects	Height of drop	Deflec- tion	Height of drop	Deflec- tion	Height of drop	Deflec- tion
Face loaded:						
Steel sheets buckled where sandbag struck Nails in one or more studs	ft 4.0	in. 0.94	<i>ft</i> 4.0	in. 0.89	ft 4.0	in. 0.91
of the panels	2.5	. 47	7.5	2.90	8.5	3.01
stud Steel sheets buckled adja- cent to center stud at top	4.0	. 94	4. 0	0. 89	5.0	1. 63
and bottom of specimen			6, 5	2.44	6.0	2.10
Flanges of panels buckled where sandhag struck Face not loaded: Flanges of pan-	10. 0	3. 75	10. 0	3.80	10.0	3. 52
sandbag struck	8.0	2, 91	6.5	2.44	6, 5	



FIGURE 20.—Concentrated load on partition CV, load applied to "inside" face.

Load-indentation (open circles) and load-set (solid circles) results for specimens CV-P1, P2, and P3.

3. Concentrated Load

Partition specimen CV-P5 under concentrated load is shown in figure 1. The results for partition specimens CV-P1, P2, and P3, loaded on the "inside" face, are shown in table 7 and figure 20. The results for partition specimens CV-P4, P5, and P6, loaded on the "outside" face, are shown in table 7 and figure 21.

The concentrated loads were applied to the "inside" face of specimens CV-P1, P2, and P3 on the web of a wall panel midway between the studs and 20 in. from the bottom of the specimen. After a load of 1,000 lb had been applied, the set in specimen CV-P1 was 0.125 in.; in P2, 0.128 in.; and in P3, 0.095 in. No other effects were observed.

The concentrated loads were applied to the "outside" of specimens CV-P4, P5, and P6 on the steel sheet midway between the studs and 20 in, from the bottom of the specimen. Under a load of 1,000 lb the steel sheet for each specimen deflected 3.5 in., to within 0.5 in. of the opposite face, and the flanges of the panels separated adjacent to the disk. After the 1,000-lb load had been removed, the set in specimen P4 was 0.87 in.; in P5, 1.21 in.; and P6, 1.01 in.

VII. FLOOR CW

1. Sponsor's Statement

Floor CW consisted of prefabricated sheetsteel channels joined at the flanges; the webs were the lower face. The upper face was a wood subfloor and a wood finish floor. The surface of the channels was covered with paint.

• The price of this construction in Washington, D. C., as of July 1937, was \$0.44/ft².

(a) Description

Each floor specimen, shown in figure 22, was 12 ft 6 in. long, 5 ft 0 in. wide, and 9_{16}^{\ast} in. deep and consisted of two full-width channel-shaped floor panels, A; two half-width floor panels, B; subflooring, C; spacer blocks, D; and finish flooring, E.

Floor panels.—The full-width floor panels, A, sheet-steel, No. 16 U. S. Std. Gage (0.0613 in. thick), were 12 ft 6 in. long, 1 ft 8 in. wide, and 8 in. deep. The edges of the flanges were turned in 2 in., as shown in figure 23, for attaching the subfloor and to increase the strength of the panel. Adjacent panels were fastened through the flanges by stove bolts, $\frac{1}{4}$ -in. diam, $\frac{1}{2}$ in. long. There were two rows of 14 bolts each, spaced as shown in figure 24.

The half-width floor panels, B, were the same

as a full-width panel cut along a longitudinal center line. In a house there are no half-width panels.

Fabrication.—Adjacent panels were clamped together, and the bolt holes were laid off with a rule and marked with a center punch. The holes were drilled with a twist drill, ¼-in. diam, mounted in an electric hand drill.

Paint.—Before assembling, the flange of each floor panel was covered with one coat of aluminum paint applied with a brush to the surface which would come into contact with the adjacent panel. After the panels were assembled, they were covered with two coats of aluminum paint applied with a brush.

Subfloor.—The subflooring, C, was southern yellow pine, ${}^{25/2}_{22}$ in. thick by 5¼ in. face width,



FIGURE 21.--Concentrated load on partition CV, load applied to "outside" face.

Load-indentation (open circles) and load-set (solid circles) results for specimens CV-P4, P5, and P6.

tongued and grooved, and was laid at right angles to the panels. Each piece was fastened to each joist by one 1³/₄-in. serew nail, driven through the wood and the flange. (A "joist" is the two flanges of adjacent channels.) The nails in adjacent boards were through alternate flanges of the center joist and in the outside flanges of the outer joists. The nails were close to the joint between panels to minimize bending



of the flanges. A few nails were between the flanges.

Blocks.—The spacer blocks, D, were cypress, $\frac{3}{4}$ by 1% by 8 in. long, 13 along each edge of the specimen, spaced 1 ft. Each block was fastened to the half-width panel by one 1%-in. screw nail through the steel and into the block and to the subfloor by one 1%-in. screw nail through the is customary) by screw nails, 2½ in. long, spaced 1 ft. 8 in. Most of the nails in the pieces of finish floor over the joists bent and passed between the flange of the joist and the subfloor.

(b) Comments

Standard floor panels, 1 ft. 8 in. wide and 8 in. deep, are available in lengths up to 20 ft. Te



FIGURE 24.—Bolt spacing for floor and roof panels.

subfloor and into the block. In a house there are no spacer blocks.

Finish floor.—The finish floor, E, like the subfloor, was southern yellow pine, 2 /₃₂ in. thick by 5¼ in. face width, tongued and grooved. It was laid parallel to the panels. Each piece was blind-fastened to the subfloor through the grooved edge (not through the tongued edge as

expedite the erection of the building, the holes for the bolts in the panels may be punched before the panels are shipped to the site.

In a building the first-story floor panels are supported on a masonry wall and a center girder. The top of the masonry wall is covered with asphalt mastic; then a strip of felt impregnated with asphalt is laid on the wall and coated with asphalt mastic before the panels are placed. The panels are anchored to the



FIGURE 25.—*Transverse load on floor CW*. Load-deflection (open circles) and load-set (solid circles) results for specimens *CW*-*T*1, *T*2, and *T*3 on the span 12 ft 0 in.

wall by bolts, ¹/₂-in. diam, 4 in. long, spaced 4 ft.

Any type of wood flooring may be applied to the flanges of the floor panels, or a concrete slab may be poured on paper-backed floor lath fastened to the flanges by steel clips. The lower face of the panels (ceiling of the room below) may be painted or papered.

2. TRANSVERSE LOAD

The results for floor specimens CW-T1, T2, and T3 under transverse load are shown in table 10 and figure 25.

Under the maximum load, the flanges of each joist in specimen CW-T1 buckled under a loading roller; in specimen T2 the two outside joists buckled under a loading roller and the center joist buckled near a support; and in specimen T3 the center joist buckled under a loading roller and one outside joist buckled between the loading rollers. The subfloor and the finish floor were undamaged.

TABLE 10.--Structural properties of floor CW

[Weight,	hased	on	face	area:	9.16	lb/ft^2]
----------	-------	----	------	-------	------	-------------

Transverse loa 12 ft 0	d; span in.	Impact load; ft 0 in	span 12	Concentrated load	
Specimen	Maxi- mum load	Specimen	Maxi- mum height of drop	Specimen	Maxi- mum load
T1 T2 T3 A verage	$\frac{lb/ft^2}{290}\\ \frac{286}{280}\\ 285$	11 12 13 A verage	ft a 10. 0 a 10. 0 a 10. 0 a 10. 0 a 10. 0	P1 P2 P3 A verage	<i>lb</i> <i>a</i> 1,000 <i>a</i> 1,000 <i>a</i> 1,000 <i>a</i> 1,000 <i>a</i> 1,000

^a Specimen did not fail. Test discontinued.

3. IMPACT LOAD

Floor specimen CW-II during the impact test is shown in figure 26. The results for floor specimens CW-II, I2, and I3 are shown in table 10 and in figure 27.



FIGURE 26.—Floor specimen CW-I1 during the impact test. A, set gage; B, deflectometer.

[20]

The impact loads were applied to the center of the upper face, the sandbag striking the finish floor directly over the center joist. After the 10-ft drop the set in specimen CW-IIwas 0.061 in.; in I2, 0.051.; and in I3, 0.021 in. No other effects were observed.

4. CONCENTRATED LOAD

The results for floor specimens CW-P1, P2, and P3 under concentrated load are shown in table 10 and in figure 28.

The concentrated loads were applied to the finish floor midway between joists and 9 in. from one end of the specimen.

After a load of 1,000 lb had been applied, the set in specimen CW-P1 was 0.043 in.; in P2, 0.069 in.; and in P3, 0.048 in. No other effects were observed.





VIII. ROOF CX

1. Sponsor's Statement

Roof CX consisted of prefabricated sheetsteel channels, joined at the flanges; the webs were the lower face. The upper face was insulating board, wood sheathing, and built-up roofing. The surface of the channels was covered with paint. The channels were similar to those in floor *CW*.

The price of this construction in Washington, D. C., as of July 1937, was \$0.48/ft².



FIGURE 28.—Concentrated load on floor CW. Load-indentation (open circles) and load-set (solid circles) results for specimens CW-P1, P2, and P3.

(a) Description

Each roof specimen, shown in figure 29, was 14 ft 6 in. long, 5 ft 0 in. wide, and 9% in. deep. Each specimen consisted of two full-width channel-shaped roof panels, A; two half-width roof panels, B; insulating board, C; wood sheathing, D; spacer blocks, E; and built-up roofing, F.

Roof panels.—The full-width roof panels, A, were sheet steel, No. 16 U. S. Std. Gage (0.0613 in. thick), 14 ft 6 in. long, 1 ft 8 in. wide, and 8 in. deep. The edges of the flanges were turned in 2 in., as shown in figure 23, for attaching the wood sheathing and to increase the strength of the panel. Adjacent panels were fastened through the flanges by stove bolts, $\frac{1}{4}$ -in. diam, $\frac{1}{2}$ in. long. There were two rows of 16 bolts each, spaced as shown in figure 24. The half-width panels, *B*, were the same as a full-width panel cut along a longitudinal center line. In a house there are no half-width panels.

Fabrication.—Adjacent panels were clamped together and the bolt holes laid off with a rule and marked with a center punch. The holes were drilled with a twist drill, ¼-in. diam, mounted in an electric hand drill.

Paint.—Before assembling, the flanges of each panel were covered with one coat of aluminum paint applied with a brush to the Sheathing paper.—There were three strips of sheathing paper each 5 in. wide and 5 ft 0 in. long. A strip was laid over each joint between the insulating boards. They were held in place by the wood sheathing.

Sheathing.—The wood sheathing, D, was southern yellow pine, ${}^{2}\!\!/_{32}$ in. thick and 5¼ in. face width, tongued and grooved, laid over the insulating board at right angles to the joists. Each piece was fastened at midwidth of the strip to each joist by one 1¾-in. screw nail.



A, full-width roof panels; B, half-width roof panels; C, insulating board; D, wood sheathing; E, spacer blocks; F, built-up roofing.

surfaces which would come into contact with Nails the adjacent panels. After assembling, the sides of panels were covered with two coats of alu-

Insulating board.—The insulating board, C, $\frac{1}{2}$ in. thick, 5 ft 0 in. wide, was four pieces, three 4 ft 0 in. long and one 2 ft 6 in. long, laid with the "burlap texture" surface up. The piece 2 ft 6 in. long was at one end of the specimen. The insulating board was held in place by the wood sheathing.

minum paint applied with a brush.

Nails in successive boards were on alternate sides of the joints between panels and close to the joint to minimize bending of the flanges. A few nails were between the flanges.

Blocks.—The spacer blocks, E, were cypress, $\frac{3}{4}$ by 1% in. by 8 in. long, spaced 1 ft, with 16 along each edge of the specimen. Each block was fastened to the half-width panel by one screw nail, 1 $\frac{3}{4}$ in. long, through the web and into the block and to the upper face by a screw nail, 1 $\frac{3}{4}$ in. long, through the wood sheathing, the insulating board, and into the block. In a house there are no spacer blocks.

Built-up roofing.—The built-up roofing, F, laid over the wood sheathing was two plies of roofing felt and one ply of roofing. Each ply consisted of two strips 3 ft 0 in. wide and 14 ft 6 in. long. The strips overlapped 1 ft 0 in. at midwidth of the specimen. When the builtup roofing was laid, the wood sheathing was covered with roof-coating at room temperature and floated to a uniform thickness. Two strips of 12-lb roofing felt were laid with roof-coating between the overlapping edges. The exposed edge was fastened by roofing nails, 1 in. long, spaced 4¼ in. Roof-coating was then applied. The second ply, consisting of two strips of 12lb felt, was laid, fastened in the same way as the first, and roof-coating again applied. The third ply, consisting of two strips of 55-lb roll roofing, was laid and fastened in the same way as the first and second plies. Finally, the third ply was covered with roof-coating.

(b) Comments

The roof may be either the flat or the gable type. If the roof is flat, the roof panels are

bolted to the angle cap by stove bolts, ¼-in. diam, ½ in. long, spaced 8¼ in. Wall panels placed horizontally and bolted to the roof panels on three sides of the building form a parapet. The fourth side is left open for run off and is fitted with a galvanized sheetsteel gutter. The sheathing is fastened to tapered wood sleepers, which have a slope of $\frac{1}{4}$ in. per foot toward the gutter and are fastened longitudinally to the flanges of the panels by screw nails. A built-up roof is applied over the wood sheathing and is extended up the inside of the parapet wall; it is overlapped by a metal or wood cap. For fireproof construction, the cap is an ornamental steel channel, formed of No. 16 U.S. Std. Gage sheet steel, the flanges extending downward over the roofing and the exterior finish. A wood cap is formed by a 2- by 10-in, piece laid flat on the top of the parapet and extending beyond the roofing and the exterior finish. It is nailed to a line of 2- by 4-in, wood pieces bolted to the upper flange of the panel.

If the building has a gable roof, wall panels are used for the roof and ceiling of the upper story. A wood floor laid on the ceiling panels provides an attic floor. At the ridge, the roof panels are connected by two angles formed of No. 16 U. S. Std. Gage sheet steel. The upper one is bolted to the flanges and the lower one to the webs of the panels. At the eaves the roof panels are joined to the ceiling panels by a Z-shaped section formed from No. 16 U. S. Std. Gage sheet steel. The wood sheathing is fastened to the flanges by screw nails, and any suitable roof covering may be applied.

2. TRANSVERSE LOAD

Roof specimen CX-T2 under transverse load is shown in figure 30. The results for roof specimens CX-T1, T2, and T3 are shown in table 11 and in figure 31.



FIGURE 30.—Roof specimen CX-T2 under transverse load.

TABLE 11.—Structural properties of roof CX

[Weight, based on face area: 9.08 lb/ft²]

Transverse load; span 14 ft 0 in.		Concentrated load		
Specimen	Maximum load	Specimen	Maximum load	
T1 T2 T3	<i>lb/ft</i> ² 183 180 180	P1 P2 P3	/b a 1,000 a 1,000 a 1,000	
Average	181	Average	a 1, 000	

« Specimen did not fail. Test discontinued.



FIGURE 31.—*Transverse load on roof CX*. Load-deflection (open circles) and load-set (solid circles) results for specimens *CX*-*T1*, *T2*, and *T3* on the span 14 ft 0 in.

In specimen CX-T2 the flanges buckled under the loading rollers at 135 lb/ft². Under the maximum load, the flanges of the center and one outside joist in specimen CX-T1 buckled between the loading rollers; and in specimens T2and T3 each joist buckled between the loading rollers.

3. Concentrated Load

The results of the concentrated load on roof specimens CX-P1, P2, and P3 are given in table 11 and figure 32.

The concentrated loads were applied to the upper face on the built-up roofing midway between joists and 1 ft 8 in. from one end of the specimen.

Under a load of 900 lb on each specimen the disk punched through the upper ply of roofing. After the 1,000-lb load had been applied, the set in specimens CX-P1 and P2 was 0.115 in. and in P3 was 0.258 in.

IX. ADDITIONAL COMMENTS BY SPONSOR

Four commercial buildings and three dwellings using the "Mu-Steel" prefabricated panels have been completed or are under contract.

Houses of this construction are built on a reinforced-concrete slab or on masonry walls, with or without basement.





For a two-story house the wall panels are continuous from foundation to eaves. The second-story floor rests on and is bolted to an angle cap or shelf bolted to the inside face of the panels. The roof and attic floor, if any, are fastened to a similar angle cap flush with the top of the wall panels. Details of a typical two-story house with a gable roof are shown in figure 33 and of a one-story house with a flat roof in figure 34.



"Mu-Steel" construction.

Pipes, ducts, and conduits are run between the studs and joists. Chimneys are of brick with tile flue linings or of enameled sheet steel suitably insulated.

The physical properties of the insulating board were determined by C. G. Weber and S. G. Weissburg, of the Paper Section, under the supervision of B. W. Scribner.

The description and drawings of the speciments were prepared by E. J. Schell and G. W. Shaw, of the Building Practice and Specifications Section, under the supervision of V. B. Phelan.

The structural properties were determined by the Engineering Mechanics Section, under the supervision of H. L. Whittemore and A. H. Stang, with the assistance of the following members of the professional staff: E. S. Cohen, A. H. Easton, A. Heiter, W. G. Hoback, A. B. Lanham, D. C. List, M. F. Peck, L. R. Sweetman, H. L. Weiss.

WASHINGTON, July 16, 1940.



FIGURE 34.—Details of a one-story house with a flat roof. "Mu-Steel" construction.

 \bigcirc

BUILDING MATERIALS AND STRUCTURES REPORTS

On request, the Superintendent of Documents, U. S. Government Printing Office, Washington, D. C., will place your name on a special mailing list to receive notices of new reports in this series as soon as they are issued. There will be no charge for receiving such notices.

An alternative method is to deposit with the Superintendent of Documents the sum of \$5.00, with the request that the reports be sent to you as soon as issued, and that the cost thereof be charged against your deposit. This will provide for the mailing of the publications without delay. You will be notified when the amount of your deposit has become exhausted.

If 100 copies or more of any paper are ordered at one time, a discount of 25 percent is allowed. Send all orders and remittances to the Superintendent of Documents, U. S. Government Printing Office, Washington, D. C.

The following publications in this series are available by purchase from the Superintendent of Documents at the prices indicated:

BMS1	Research on Building Materials and Structures for Use in Low-Cost Housing	10¢
BMS2	Methods of Determining the Structural Properties of Low-Cost House Constructions	10¢
BMS3	Suitability of Fiber Insulating Lath as a Plaster Base	10¢
BMS4	Accelerated Aging of Fiber Building Boards	10¢
BMS5	Structural Properties of Six Masonry Wall Constructions	15¢
BMS6	Survey of Roofing Materials in the Southeastern States	15¢
BMS7	Water Permeability of Masonry Walls	10¢
BMS8	Methods of Investigation of Surface Treatment for Corrosion Protection of Steel	10¢
BMS9	Structural Properties of the Insulated Steel Construction Co.'s "Frameless-Steel" Con- structions for Walls, Partitions, Floors, and Roofs	10¢
BMS10	Structural Properties of One of the "Keystone Beam Steel Floor" Constructions Spon- sored by the H. H. Robertson Co	10¢
BMS11	Structural Properties of the Curren Fabrihome Corporation's "Fabrihome" Construc- tions for Walls and Partitions	10¢
BMS12	Structural Properties of "Steelox" Constructions for Walls, Partitions, Floors, and Roofs Sponsored by Steel Buildings, Inc.	15¢
BMS13	Properties of Some Fiber Building Boards of Current Manufacture	10¢
BMS14	Indentation and Recovery of Low-Cost Floor Coverings	10¢
BMS15	Structural Properties of "Wheeling Long-Span Steel Floor" Construction Sponsored by Wheeling Corrugating Co	10¢
BMS16	Structural Properties of a "Tilecrete" Floor Construction Sponsored by Tilecrete Floors, Inc	10¢
BMS17	Sound Insulation of Wall and Floor Constructions	10¢
BMS18	Structural Properties of "Pre-Fab" Constructions for Walls, Partitions, and Floors Sponsored by the Harnischfeger Corporation	10¢
BMS19	Preparation and Revision of Building Codes	15¢
BMS20	Structural Properties of "Twachtman" Constructions for Walls and Floors Sponsored by Connecticut Pre-Cast Buildings Corporation	10¢
BMS21	Structural Properties of a Concrete-Block Cavity-Wall Construction Sponsored by the National Concrete Masonry Association	10¢
BMS22	Structural Properties of "Dun-Ti-Stone" Wall Construction Sponsored by the W. E. Dunn Manufacturing Co	10¢
BMS23	Structural Properties of a Brick Cavity-Wall Construction Sponsored by the Brick Manufacturers Association of New York, Inc.	10¢
BMS24	Structural Properties of a Reinforced-Brick Wall Construction and a Brick-Tile Cavity- Wall Construction Sponsored by the Structural Clay Products Institute	10¢
BMS25	Structural Properties of Conventional Wood-Frame Constructions for Walls, Partitions, Floors, and Roofs	15¢
BMS26	Structural Properties of "Nelson Pre-Cast Concrete Foundation" Wall Construction Sponsored by the Nelson Cement Stone Co., Inc	10¢
BMS27	Structural Properties of "Bender Steel Home" Wall Construction Sponsored by the Bender Body Co	10¢
BMS28	Backflow Prevention in Over-Rim Water Supplies	10¢

[List continued on cover page IV]

BUILDING MATERIALS AND STRUCTURES REPORTS

[Continued from cover page III]

BMS29	Survey of Roofing Materials in the Northeastern States	10¢
BMS30	Structural Properties of a Wood-Frame Wall Construction Sponsored by the Douglas Fir Plywood Association	10¢
BMS31	Structural Properties of "Insulite" Wall and "Insulite" Partition Constructions Spon- sored by The Insulite Co	15¢
BMS32	Structural Properties of Two Brick-Concrete-Block Wall Constructions and a Concrete- Block Wall Construction Sponsored by the National Concrete Masonry Association.	10¢
BMS33	Plastic Calking Materials	10¢
BMS34	Performance Test of Floor Coverings for Use in Low-Cost Housing: Part 1	10¢
BMS35	Stability of Sheathing Papers as Determined by Accelerated Aging	10¢
BMS36	Structural Properties of Wood-Frame Wall, Partition, Floor, and Roof Constructions with "Red Stripe" Lath Sponsored by the Weston Paper and Manufacturing Co	10¢
BMS37	Structural Properties of "Palisade Homes" Constructions for Walls, Partitions, and Floors Sponsored by Palisade Homes	10¢
BMS38	Structural Properties of Two "Dunstone" Wall Constructions Sponsored by the W. E. Dunn Manufacturing Co	10¢
BMS39	Structural Properties of a Wall Construction of "Pfeifer Units" Sponsored by the Wis- consin Units Co	10¢
BMS40	Structural Properties of a Wall Construction of "Knap Concrete Wall Units" Sponsored by Knap America Inc	10¢
BMS41	Effect of Heating and Cooling on the Permeability of Masonry Walls	10 m e
BMS42	Structural Properties of Wood-Frame Wall and Partition Constructions with "Celotex" Insulating Boards Sponsored by the Celotex Corporation	10é
BMS43	Performance Test of Floor Coverings for Use in Low-Cost Housing: Part 2	10¢
BMS44	Surface Treatment of Steel Prior to Painting	10é
BMS45	Air Infiltration Through Windows	10é
BMS46	Structural Properties of "Scot-Bilt" Prefabricated Sheet-Steel Constructions for Walls, Floors, and Roofs Sponsored by The Globe-Wernicke Co	10¢
BMS47	Structural Properties of Prefabricated Wood-Frame Constructions for Walls, Partitions, and Floors Sponsored by American Houses, Inc.	10¢
BMS48	Structural Properties of "Precision-Built" Frame Wall and Partition Constructions Sponsored by the Homasote Co	10¢
BMS49	Metallic Roofing for Low-Cost House Construction	10¢
BMS50	Stability of Fiber Building Boards as Determined by Accelerated Aging	10¢
BMS51	Structural Properties of "Tilecrete Type A" Floor Construction Sponsored by the Tile- crete Corporation	10¢
BMS52	Effect of Ceiling Insulation Upon Summer Comfort	10ϕ
BMS53	Structural Properties of a Masonry Wall Construction of "Munlock Dry Wall Brick" Sponsored by the Munlock Engineering Co	10¢
BMS54	Effect of Soot on the Rating of an Oil-Fired Heating Boiler	10¢
BMS55	Effect of Wetting and Drying on the Permeability of Masonry Walls	10¢
BMS56	A Survey of Humidities in Residences	10¢
BMS57	Roofing in the United States—Results of a Questionnaire	10¢
BMS58	Strength of Soft-Soldered Joints in Copper Tubing	10¢
BMS59	Properties of Adhesives for Floor Coverings	10¢
BMS60	Strength, Absorption, and Resistance to Laboratory Freezing and Thawing of Building Bricks Produced in the United States	15¢
BMS61	Structural Properties of Two Nonreinforced Monolithic Concrete Wall Constructions	10¢
BMS62	Structural Properties of a Precast Joist Concrete Floor Construction Sponsored by the Portland Cement Association	10¢
BMS63	Moisture Condensation in Building Walls	10¢
BMS64	Solar Heating of Various Surfaces	10¢
BMS65	Methods of Estimating Loads in Plumbing Systems	10 m c
BMS66	Plumbing Manual: Report of Subcommittee on Plumbing, Central Housing Committee on Research, Design, and Construction	20¢
BMS67	Structural Properties of "Mu-Steel" Prefabricated Sheet-Steel Constructions for Walls,	
	Partitions, Floors, and Roofs Sponsored by Herman A. Mugler	15 c

23







· ·



