

U. S. DEPARTMENT OF COMMERCE

BUILDING  
MATERIALS  
AND  
STRUCTURES

REPORT BMS77

Properties and Performance  
of Fiber Tile Boards

*by*

DANIEL A. JESSUP,  
HERMAN BOGATY, *and*  
SAMUEL G. WEISSBERG



NATIONAL  
BUREAU OF STANDARDS



The program of research on building materials and structures carried on by the National Bureau of Standards was undertaken with the assistance of the Central Housing Committee, an informal organization of governmental agencies concerned with housing construction and finance, which is cooperating in the investigations through a committee of principal technicians.

CENTRAL HOUSING COMMITTEE  
ON RESEARCH, DESIGN, AND CONSTRUCTION

HUGH L. DRYDEN, *Chairman.*  
National Bureau of Standards.

HOWARD P. VERMILYA, *Vice Chairman.*  
Federal Housing Administration.

STERLING R. MARCH, *Secretary.*

MARY F. TAYLOR, *Assistant Secretary.*

PIERRE BLOUKE,  
Federal Home Loan Bank Board.

JOHN F. DONOVAN,  
Farm Security Administration.

A. C. SHIRE,  
United States Housing Authority.

GEORGE W. TRAYER,  
Forest Service (F. P. Laboratory).

WARREN G. NOLL,  
Public Buildings Administration.

ROLLO H. BRITTEN,  
Public Health Service.

LUTHER M. LEISENRING,  
Construction Division (War).

GEORGE E. KNOX,  
Yards and Docks (Navy).

EDWARD A. POYNTON,  
Office of Indian Affairs.

WILLIAM R. TALBOTT,  
Veterans' Administration.

WALLACE ASHBY,  
Bureau of Agricultural Chemistry and Engineering.

---

NATIONAL BUREAU OF STANDARDS  
STAFF COMMITTEE ON ADMINISTRATION AND COORDINATION

HUGH L. DRYDEN, *Chairman.*  
Mechanics and Sound.

PHAON H. BATES,  
Clay and Silicate Products.

GUSTAV E. F. LUNDELL,  
Chemistry.

HOBART C. DICKINSON,  
Heat and Power.

ADDAMS S. McALLISTER,  
Codes and Specifications.

WARREN E. EMLEY,  
Organic and Fibrous Materials.

HENRY S. RAWDON,  
Metallurgy.

The Forest Products Laboratory of the Forest Service is cooperating with both committees on investigations of wood constructions.

UNITED STATES DEPARTMENT OF COMMERCE · Jesse H. Jones, Secretary

NATIONAL BUREAU OF STANDARDS · Lyman J. Briggs, Director

# BUILDING MATERIALS *and* STRUCTURES

REPORT BMS77

Properties and Performance of Fiber Tile Boards

*by*

DANIEL A. JESSUP, HERMAN BOGATY

*and* SAMUEL G. WEISSBERG



ISSUED AUGUST 8, 1941

The National Bureau of Standards is a fact-finding organization; it does not "approve" any particular material or method of construction. The technical findings in this series of reports are to be construed accordingly.

UNITED STATES GOVERNMENT PRINTING OFFICE · WASHINGTON · 1941

FOR SALE BY THE SUPERINTENDENT OF DOCUMENTS, WASHINGTON, D. C. · PRICE 10 CENTS

# Foreword

Fiber tile board offers considerable promise as a finishing material for installations where much more costly materials are ordinarily used. Samples of this type of board were tested as a part of the research program on building materials and structures.

LYMAN J. BRIGGS, *Director.*

# Properties and Performance of Fiber Tile Boards

by DANIEL A. JESSUP, HERMAN BOGATY, and SAMUEL G. WEISSBERG

## CONTENTS

	Page		Page
Foreword.....	ii	III. Properties and Testing—Continued	
I. Introduction.....	1	4. Thickness of coating.....	3
II. Description of samples.....	1	5. Effect of steam.....	3
III. Properties and testing.....	1	6. Impact tests.....	4
1. Thickness and density.....	2	7. Resistance to abrasion.....	4
2. Linear expansion with change in humidity.....	2	8. Resistance to staining.....	5
3. Flexural properties.....	2	IV. Summary and conclusions.....	5

## ABSTRACT

Performance tests have been made on fiber tile boards by subjecting them to conditions which they might possibly meet in service. The properties examined were resistance to abrasive cleaning powders, resistance to staining by household chemicals, and stability of the boards when subjected to cycles of steaming and drying. In addition, data were obtained on the density, expansivity, and flexural properties of the boards, and on the thickness and impact resistance of the finish coatings.

The resistance of most of the boards to staining, to impact, and to abrasive cleaning powders was good. Most of the surface coatings were damaged by the cycles of steaming and drying, especially at the edges, where moisture had direct access to the base material, and at the score marks, where the coatings in some of the boards were very thin. The density, expansivity, and flexural properties were satisfactory.

## I. INTRODUCTION

In connection with research at the National Bureau of Standards on building materials and structures relative to low-cost housing,<sup>1</sup> it was considered desirable to include a study of the properties of fiber tile boards. This material is made of vegetable-fiber boards in large

<sup>1</sup> NBS Building Materials and Structures Report BMS1 (1938) 10¢. (See page 3 of cover.)

sheets, and has on one side a dense, hard coating, either white or colored. The coated surface is frequently scored to resemble the ceramic wall tile commonly used in more costly structures than those for which the fiber tiles are primarily intended.

## II. DESCRIPTION OF SAMPLES

The samples were commercial products furnished by manufacturers. They consisted of compressed wood-fiber board, coated on one side with a synthetic plastic. Some of the coatings were homogeneous, and others had a top layer over a priming coat. Two of the products had a resinous binding material in the base boards. There was no added material in the other base boards.

## III. PROPERTIES AND TESTING

The samples were tested in their normal condition for the physical properties commonly measured on fiberboards, and for resistance to impact, steam, abrasion, and various liquids since structural tile in use frequently encounters one or more such deteriorative influences. The data are contained in tables 1 and 2, respectively.

TABLE 1.—Properties of fiber-tile boards

Board number	Thick-ness	Dens-ity	Linear expan-sion <sup>b</sup>	Flexural properties <sup>c</sup>				Coating thick-ness <sup>d</sup>	
				Breaking load		Deflection at rupture		Over all	Top-coat
				Ma-chine	Cross	Ma-chine	Cross		
80 <sup>a</sup>	<i>in.</i> 0.140	<i>lb/ft<sup>3</sup></i> 69	% 0.15	<i>lb</i> 47	<i>lb</i> 50	<i>in.</i> 0.21	<i>in.</i> 0.21	<i>in.</i> ( <sup>a</sup> ) 0.0070	<i>in.</i> ( <sup>a</sup> ) 0.0070
10 <sup>a</sup>	.145	85	.20	79	62	.15	.15	.0152	.0026
11 <sup>a</sup>	.140	83	.15	91	74	.15	.15	.0120	.0022
20	.160	76	.10	96	80	.10	.06	.0028	.0012
30	.133	65	.19	42	44	.22	.27	.0048	.0048
40	.144	72	.10	50	53	.21	.23	.0036	.0036
50	.146	73	.13	56	50	.18	.20	.0064	.0060
51	.141	71	.13	51	58	.18	.17	.0071	.0066
52	.143	70	.10	55	66	.18	.20	.0036	.0036
70	.140	71	.15	48	51	.20	.19	.0042	.0018
90	.148	69	.17	56	51	.16	.17	.0054	.0038
91	.148	69	.20	50	53	.13	.15	.0028	.0028
100	.142	70	.25	47	52	.17	.18	.0044	.0020
110	.136	73	.17	50	44	.20	.19	.0062	.0028
111	.140	70	.16	52	48	.19	.19	.0062	.0066
130	.150	67	.15	55	55	.18	.17	.0036	.0036
131	.150	67	.17	57	55	.20	.19	.0042	.0018
140	.139	73	.17	56	57	.20	.18	.0066	.0066
141	.139	73	.14	62	65	.16	.17		

<sup>a</sup> Samples 10 and 11 are compressed wood fiber with a resinous binder. The remainder of the boards are compressed wood fiber with no added material. Sample 80 has no surface coat and is included for comparison.  
<sup>b</sup> For a change in relative humidity of surrounding atmosphere from 50 to 95 percent.  
<sup>c</sup> For specimens 1 inch wide on supports 3 inches apart.  
<sup>d</sup> Identical figures for over-all thickness and topcoat thickness indicate board with a single coat.

TABLE 2.—Resistance of fiber tile boards to deteriorative influences

Board number	Resistance to impact <sup>a</sup>				Resistance to steam			Resistance to abrasion		
	Before steam-ing		After steam-ing		Extent of warping <sup>b</sup>	Color <sup>c</sup>	Gloss	Blistering of surface <sup>c</sup>	Entire coating <sup>d</sup>	Per 0.001 inch of coating
	1-oz. weight	2-oz. weight	1-oz. weight	2-oz. weight						
10 <sup>e</sup>	<i>in.</i> 30	<i>in.</i> 7	<i>in.</i> 34	<i>in.</i> 11	<i>in.</i> 0.400	Good	Poor	<i>B</i>	Thous. of cycles 75	Thous. of cycles 10.7
11 <sup>e</sup>	29	8	39	8	1.12	Poor	do	<i>B</i>	60	3.9
20 <sup>e</sup>	40	34	40	31	.172	Fair	do	None	60	5.0
30 <sup>e</sup>	13	5	39	14	.135	Good	Good	<i>S, L</i>	15	5.4
40	20	8	29	9	.063	do	do	<i>E, B</i>	40	8.3
50	18	8	19	4	.126	do	Poor	<i>S, L</i>	15	4.2
51	23	6	20	5	.004	do	do	<i>E</i>	53	8.3
52	18	7	11	2	.048	do	do	<i>S, L</i>	40	5.6
70	7	4	8	4	.035	do	do	<i>B, E</i>	20	5.6
90	6	4	9	4	.020	do	Good	<i>B, E</i>	15	3.6
91	7	4	7	4	.045	do	do	<i>B, E</i>	15	2.8
100	13	3	20	9	.031	Poor	Fair	<i>B, S</i>	4	1.4
110	14	10	34	12	.033	do	do	<i>B, S</i>	20	4.5
111	16	5	29	10	.050	Good	Good	<i>B, E</i>	15	2.4
130	8	7	24	14	.040	do	Poor	<i>S</i>	6	1.0
131	10	6	25	14	.010	do	do	<i>E</i>	17	4.7
140	10	6	34	14	.022	Poor	do	<i>B, E</i>	8	1.9
141	6	3	15	4	.007	Good	Fair	<i>B, E</i>	24	3.6

<sup>a</sup> Impact tests were made by dropping a cylindrical weight on the surfaces of the boards placed at 30° to the horizontal. The values recorded are the shortest distances required to break the surface.  
<sup>b</sup> Measured at the center of a 12-inch span.  
<sup>c</sup> The letters indicate the places where the blistering effect was noted: *B*=on broken surfaces, *E*=at edges of the board, *S*=at score marks, *L*=loosening of the coating.  
<sup>d</sup> Number of thousands of cycles of scrubbing with a cloth pad, soap and water, and mild household cleanser to wear coating through to base material.  
<sup>e</sup> Samples 10, 11, and 20 were not stained by writing ink, 5 percent acetic acid, tincture of iodine, or hot grease. The remaining samples were stained only by 5 percent acetic acid and by commercial tincture of iodine.  
<sup>f</sup> Samples 10, 40, 50, 51, 52, 70, 90, 91, 130, 131, and 141 had white surfaces; samples 30, 50, 51, 52, 70, 91, 100, 110, and 130 were scored to resemble ceramic tile.

1. THICKNESS AND DENSITY

The density of the tile board is the weight per unit of volume. It was computed from measurements of dimensions and from determination of weight. In most cases specimens about 18 by 18 inches were used. The weight was determined on a torsion balance reading to 0.1 gram, and the thickness was determined by means of a micrometer caliper reading to 0.001 inch.

2. LINEAR EXPANSION WITH CHANGE IN HUMIDITY

The change in dimensions with a change in the relative humidity of the surrounding atmosphere is an important characteristic of interior finishing materials. Low expansivity minimizes the difficulties encountered with waving, buckling, and opening of seams when extreme humidity conditions occur.

The linear-expansion tests were made in accordance with the Federal Specification for fiber insulating board.<sup>2</sup> Test specimens measuring about 12 by 2 inches were conditioned in an atmosphere at 50-percent relative humidity and then conditioned for 48 hours in an atmosphere at 95-percent relative humidity. The changes of length were determined from the displacement of reference marks placed about 8 inches apart on the specimen.

3. FLEXURAL PROPERTIES

Although tile boards are not generally required to contribute to the strength of a structure, the boards must be of sufficient strength to withstand, without undue breakage, handling incidental to installation, and to resist damage after installation. The strength of fiber building boards is generally determined in terms of flexural properties. These were determined by placing a specimen 1 inch wide across two parallel supports 3 inches apart and loading at the midspan. The load is conveniently applied by means of a tensile testing machine with suitable fixtures. The rupturing load and the deflection at instant of rupture are recorded. This method is one developed at the Bureau for use with binders board.<sup>3</sup>

<sup>2</sup> Federal Specification LLL-F-321a Fiber Boards; Insulating.  
<sup>3</sup> Paper Trade J. 95, No. 16, 183 (Oct. 20, 1932).

#### 4. THICKNESS OF COATING

The thickness of the coating was determined by an adaptation of Mesle's chord method. This method has been used successfully for the measurement of the thickness of plated metal coatings.<sup>4</sup>

A precision grinding wheel of known radius,  $R$ , is lowered upon the surface of the tile board with the axis of the wheel parallel to the plane of the board, as illustrated in figure 1. The




FIGURE 1.—Relationship between radius of grinding wheel and thickness of coat.

A, surface coat; B, base material.

surface of thickness,  $T$ , is ground through until the wheel reaches the base material along a line through  $P$ . The width of the cut,  $C$ , is related to the thickness,  $T$ , and the radius of the grinder,  $R$ , as follows:

$$R^2 = (R - T)^2 + \left(\frac{C}{2}\right)^2 \text{ or } 2RT = T^2 + \frac{C^2}{4}$$

As  $T$  is about 0.01 inch,  $R$  about 4 inches, and  $C$  about 0.5 inch,  $T^2$  may be neglected, making  $T = (C^2/8R)$ .

In practice the plane of the specimen is tilted so that it makes an angle of about  $1^\circ$  with the axis of the wheel. This gives a cut with a semielliptical plan (fig. 2). Tilting has the advantage that, when there is more than one layer of coating, all are exposed for measurement with but one grinding operation. Moreover, there is no uncertainty as to the endpoint of the grinding operation. The width of the cut,  $C$ , for a particular coating is measured at the apex of the ellipse formed by the intersection of the wheel with the plane separating the coating under consideration from the next lower layer.

#### 5. EFFECT OF STEAM

A test was devised whereby the surface of the fiber tile was exposed to the action of condensing steam for 7 hours and then allowed to dry for 17 hours. Changes in appearance and properties were determined after five such cycles of steaming and drying. The changes produced in some of the boards as a result of this treatment are shown in figures 3, 4, and 5.

Warping was determined by means of a cylindrometer. This device consists of two rigid feet fixed 12 inches apart and a movable foot attached to a dial micrometer at the center of the span. A zero reading is obtained by holding the instrument on a plate-glass surface. The difference between the micrometer reading on the warped board and the zero reading gives the degree of warping.

The warping was extreme in only two of the samples. The base material of these was compressed wood fiber with a resinous binder.

The resistance of the coating to change of gloss and color after steaming was rated as




FIGURE 2.—Appearance of the cut on the surface of the fiber tile board.

A, surface coatings; B, base material; C, exposed top coat; D, exposed under coat; E, exposed base material; F, grinding wheel.

follows: Good, no change; fair, slight but not objectionable; poor, considerable change.

Most of the boards became less glossy on steaming and many of the colored boards faded (fig. 3). In general the color of the white boards was unaffected by steam.

The coatings of most of the boards underwent some surface change. Steaming caused wheals or blisters to form, generally at the edges, near score marks, or at places where the coating had

<sup>4</sup>J. Research NBS 16, 171 (1936) RP866.



FIGURE 3.—Color change produced by steaming.  
Unexposed portion is so marked

been scratched or broken (fig. 4). In two instances the coating loosened and tended to separate from the base (fig. 5).

#### 6. IMPACT TESTS

Impact tests on the coated surfaces of tile boards were used as a measure of the resistance to chipping by hard blows. Specimens were placed in a metal frame at an angle of  $30^\circ$  with the horizontal, to simulate glancing blows, and weights were allowed to fall on the surfaces. The shortest distance of fall required to break the surface was recorded. The weights were hardened steel cylinders,  $\frac{1}{2}$  inch in diameter, with the edges rounded to a radius of 0.025 inch. The cylinder axis at the moment of impact was vertical. Tests were made with 1- and 2-ounce weights on both the original and the steam-treated boards.

The surface in most cases showed no deterio-

ration after steaming with respect to resistance to impact. The coatings in many instances appeared to be toughened by steaming.

#### 7. RESISTANCE TO ABRASION

The surface was tested for resistance to abrasion by mechanically scrubbing it with a cloth-faced pad moving with a reciprocating motion. A device was constructed whereby a number of specimens could be tested simultaneously. The scrubbing pads were composed of wood blocks  $2\frac{1}{4}$  inches square covered with a piece of wool blanket over which was fastened a piece of sturdy twill cloth. A load of  $1\frac{1}{4}$  pounds was applied to the pads. The stroke of the pads was 4 inches, and the rate of scrubbing was 2,500 cycles per hour. The specimens, fixed in place beneath the moving pads, were moistened from time to time with a 1-percent soap solution



to which a mild household cleaning powder had been added.

Change in gloss could not be used as a measure of resistance to abrasion, because the polishing effect of the scrubbing prevented change of gloss. The best indication of resistance to abrasion appeared to be the number of cycles necessary to cause the coat to wear completely through to the base. This criterion was used since, in practice, the board tiles might not have to be replaced until this occurred. As might be expected, there is a fairly good correlation between the resistance to abrasion and the overall thickness of the coat.

#### 8. RESISTANCE TO STAINING

The resistance of the coating to staining by common household materials was tested by placing  $\frac{1}{2}$  milliliter of the following liquids on the surfaces: a 5-percent solution of washing

soda, 5-percent solution of acetic acid, commercial tincture of iodine, commercial writing ink, hot bacon grease. The drop was allowed to stand for  $\frac{1}{2}$  hour and then wiped with a clean cloth, using soap and water, if necessary, for thorough cleaning. Most of the boards were stained by dilute acid and iodine. The other compounds had no appreciable effect on the coatings.

#### IV. SUMMARY AND CONCLUSIONS

The tests of the fiber tile boards studied showed that they are very dense, have a moderate degree of expansion with change in moisture content, and are strong and rigid. The thickness of the coating varies considerably.

The resistance of the coatings of the boards to abrasion was excellent, particularly for those having double coatings.

Steam did not adversely affect the resistance




FIGURE 4.—Blistering at score marks, caused by swelling of base material when subjected to steam.



FIGURE 5.—*Loosening of surface coat due to failure of bond between surface coat and base material when steamed.*

of the coatings to impact, but the gloss of most of the coatings was dulled and the colored ones faded. The steaming in general did not affect the color of the white coatings. All coatings treated with steam were blistered, this generally occurring at the edges of the board, near score marks, or where the coating had been

scratched. Steam produced excessive warping of two of the boards. The coatings were resistant to staining by writing ink and hot grease, but most of them were stained by weak acetic acid and by tincture of iodine.

WASHINGTON, *May 20, 1941.*

○

## BUILDING MATERIALS AND STRUCTURES REPORTS

On request, the Superintendent of Documents, U. S. Government Printing Office, Washington, D. C., will place your name on a special mailing list to receive notices of new reports in this series as soon as they are issued. There will be no charge for receiving such notices.

An alternative method is to deposit with the Superintendent of Documents the sum of \$5, with the request that the reports be sent to you as soon as issued, and that the cost thereof be charged against your deposit. This will provide for the mailing of the publications without delay. You will be notified when the amount of your deposit has become exhausted.

If 100 copies or more of any report are ordered at one time, a discount of 25 percent is allowed.

Send all orders and remittances to the *Superintendent of Documents, U. S. Government Printing Office, Washington, D. C.*

The following publications in this series are available by purchase from the Superintendent of Documents at the prices indicated:

BMS1	Research on Building Materials and Structures for Use in Low-Cost Housing.....	10¢
BMS2	Methods of Determining the Structural Properties of Low-Cost House Constructions...	10¢
BMS3	Suitability of Fiber Insulating Lath as a Plaster Base.....	10¢
BMS4	Accelerated Aging of Fiber Building Boards.....	10¢
BMS5	Structural Properties of Six Masonry Wall Constructions.....	15¢
BMS6	Survey of Roofing Materials in the Southeastern States.....	15¢
BMS7	Water Permeability of Masonry Walls.....	10¢
BMS8	Methods of Investigation of Surface Treatment for Corrosion Protection of Steel.....	10¢
BMS9	Structural Properties of the Insulated Steel Construction Co.'s "Frameless-Steel" Constructions for Walls, Partitions, Floors, and Roofs.....	10¢
BMS10	Structural Properties of One of the "Keystone Beam Steel Floor" Constructions Sponsored by the H. H. Robertson Co.....	10¢
BMS11	Structural Properties of the Curren Fabrihome Corporation's "Fabrihome" Constructions for Walls and Partitions.....	10¢
BMS12	Structural Properties of "Steelox" Constructions for Walls, Partitions, Floors, and Roofs Sponsored by Steel Buildings, Inc.....	15¢
BMS13	Properties of Some Fiber Building Boards of Current Manufacture.....	10¢
BMS14	Indentation and Recovery of Low-Cost Floor Coverings.....	10¢
BMS15	Structural Properties of "Wheeling Long-Span Steel Floor" Construction Sponsored by the Wheeling Corrugating Co.....	10¢
BMS16	Structural Properties of a "Tilecrete" Floor Construction Sponsored by Tilecrete Floors, Inc.....	10¢
BMS17	Sound Insulation of Wall and Floor Constructions.....	10¢
BMS18	Structural Properties of "Pre-Fab" Constructions for Walls, Partitions, and Floors Sponsored by the Harnischfeger Corporation.....	10¢
BMS19	Preparation and Revision of Building Codes.....	15¢
BMS20	Structural Properties of "Twachtman" Constructions for Walls and Floors Sponsored by Connecticut Pre-Cast Buildings Corporation.....	10¢
BMS21	Structural Properties of a Concrete-Block Cavity-Wall Construction Sponsored by the National Concrete Masonry Association.....	10¢
BMS22	Structural Properties of "Dun-Ti-Stone" Wall Construction Sponsored by the W. E. Dunn Manufacturing Co.....	10¢
BMS23	Structural Properties of a Brick Cavity-Wall Construction Sponsored by the Brick Manufacturers Association of New York, Inc.....	10¢
BMS24	Structural Properties of a Reinforced-Brick Wall Construction and a Brick-Tile Cavity-Wall Construction Sponsored by the Structural Clay Products Institute.....	10¢
BMS25	Structural Properties of Conventional Wood-Frame Constructions for Walls, Partitions, Floors, and Roofs.....	15¢
BMS26	Structural Properties of "Nelson Pre-Cast Concrete Foundation" Wall Construction Sponsored by the Nelson Cement Stone Co., Inc.....	10¢
BMS27	Structural Properties of "Bender Steel Home" Wall Construction Sponsored by The Bender Body Co.....	10¢
BMS28	Backflow Prevention in Over-Rim Water Supplies.....	10¢
BMS29	Survey of Roofing Materials in the Northeastern States.....	10¢
BMS30	Structural Properties of a Wood-Frame Wall Construction Sponsored by the Douglas Fir Plywood Association.....	10¢
BMS31	Structural Properties of "Insulite" Wall and "Insulite" Partition Constructions Sponsored by The Insulite Co.....	15¢
BMS32	Structural Properties of Two Brick-Concrete-Block Wall Constructions and a Concrete-Block Wall Construction Sponsored by the National Concrete Masonry Association.....	10¢

[List continued on cover page IV]

## BUILDING MATERIALS AND STRUCTURES REPORTS

[Continued from cover page III]

BMS33	Plastic Calking Materials.....	10¢
BMS34	Performance Test of Floor Coverings for Use in Low-Cost Housing: Part 1.....	10¢
BMS35	Stability of Sheathing Papers as Determined by Accelerated Aging.....	10¢
BMS36	Structural Properties of Wood-Frame Wall, Partition, Floor, and Roof Constructions With "Red Stripe" Lath Sponsored by The Weston Paper and Manufacturing Co.....	10¢
BMS37	Structural Properties of "Palisade Homes" Constructions for Walls, Partitions, and Floors, Sponsored by Palisade Homes.....	10¢
BMS38	Structural Properties of Two "Dunstone" Wall Constructions Sponsored by the W. E. Dunn Manufacturing Co.....	10¢
BMS39	Structural Properties of a Wall Construction of "Pfeifer Units" Sponsored by the Wisconsin Units Co.....	10¢
BMS40	Structural Properties of a Wall Construction of "Knap Concrete Wall Units" Sponsored by Knap America, Inc.....	10¢
BMS41	Effect of Heating and Cooling on the Permeability of Masonry Walls.....	10¢
BMS42	Structural Properties of Wood-Frame Wall and Partition Constructions With "Celotex" Insulating Boards Sponsored by The Celotex Corporation.....	10¢
BMS43	Performance Test of Floor Coverings for Use in Low-Cost Housing: Part 2.....	10¢
BMS44	Surface Treatment of Steel Prior to Painting.....	10¢
BMS45	Air Infiltration Through Windows.....	10¢
BMS46	Structural Properties of "Scot-Bilt" Prefabricated Sheet-Steel Constructions for Walls, Floors, and Roofs Sponsored by The Globe-Wernicke Co.....	10¢
BMS47	Structural Properties of Prefabricated Wood-Frame Constructions for Walls, Partitions, and Floors Sponsored by American Houses, Inc.....	10¢
BMS48	Structural Properties of "Precision-Built" Frame Wall and Partition Constructions Sponsored by the Homasote Co.....	10¢
BMS49	Metallic Roofing for Low-Cost House Construction.....	10¢
BMS50	Stability of Fiber Building Boards as Determined by Accelerated Aging.....	10¢
BMS51	Structural Properties of "Tilecrete Type A" Floor Construction Sponsored by the Tilecrete Corporation.....	10¢
BMS52	Effect of Ceiling Insulation on Summer Comfort.....	10¢
BMS53	Structural Properties of a Masonry Wall Construction of "Munlock Dry Wall Brick" Sponsored by the Munlock Engineering Co.....	10¢
BMS54	Effect of Soot on the Rating of an Oil-Fired Heating Boiler.....	10¢
BMS55	Effects of Wetting and Drying on the Permeability of Masonry Walls.....	10¢
BMS56	A Survey of Humidities in Residences.....	10¢
BMS57	Roofing in the United States: Results of a Questionnaire.....	10¢
BMS58	Strength of Soft-Soldered Joints in Copper Tubing.....	10¢
BMS59	Properties of Adhesives for Floor Coverings.....	10¢
BMS60	Strength, Absorption, and Resistance to Laboratory Freezing and Thawing of Building Bricks Produced in the United States.....	15¢
BMS61	Structural Properties of Two Nonreinforced Monolithic Concrete Wall Constructions.....	10¢
BMS62	Structural Properties of a Precast Joist Concrete Floor Construction Sponsored by the Portland Cement Association.....	10¢
BMS63	Moisture Condensation in Building Walls.....	10¢
BMS64	Solar Heating of Various Surfaces.....	10¢
BMS65	Methods of Estimating Loads in Plumbing Systems.....	10¢
BMS66	Plumbing Manual.....	20¢
BMS67	Structural Properties of "Mu-Steel" Prefabricated Sheet-Steel Constructions for Walls, Partitions, Floors, and Roofs Sponsored by Herman A. Mugler.....	15¢
BMS68	Performance Test of Floor Coverings for Use in Low-Cost Housing: Part 3.....	15¢
BMS69	Stability of Fiber Sheathing Boards as Determined by Accelerated Aging.....	10¢
BMS70	Asphalt-Prepared Roll Roofings and Shingles.....	15¢
BMS71	Fire Tests of Wood- and Metal-Framed Partitions.....	10¢
BMS72	Structural Properties of "Precision-Built, Jr." Prefabricated Wood-Frame Wall Construction Sponsored by the Homasote Co.....	10¢
BMS73	Indentation Characteristics of Floor Coverings.....	10¢
BMS74	Structural and Heat-Transfer Properties of "U. S. S. Panelbilt" Prefabricated Sheet-Steel Constructions for Walls, Partitions, and Roofs Sponsored by the Tennessee Coal, Iron & Railroad Co.....	10¢
BMS75	Survey of Roofing Materials in the North Central States.....	15¢
BMS77	Properties and Performance of Fiber Tile Boards.....	10¢