

NAT'L INST. OF STAND. & TECH. R.I.C.




A11104 023123

NBS
PUBLICATIONS

CONTAINER BOARD

report no. 116

May 1979



NBS Collaborative Reference
Program for Containerboard

Fourdrinier Kraft Board Group
American Paper Institute, Inc.
and U.S. Department of
Commerce, National Bureau
of Standards

QC
100
.U56
79-1380
1979
C.2

NBS COLLABORATIVE REFERENCE PROGRAMS

TAPPI Paper and Board (6 times per year)

Bursting strength	Smoothness
Tearing strength	Surface pick strength
Tensile breaking strength	K & N ink absorption
Elongation to break	pH
Tensile energy absorption	Opacity
Folding endurance	Blue reflectance (brightness)
Stiffness	Specular gloss, 75°
Air resistance	Thickness
Grammage	Concora (flat crush)
	Ring crush

FKBG-API Containerboard (48 times per year)

Mullen burst of linerboard
Concora test of medium

MCCA Color and Appearance (4 times per year)

Gloss at 60°
Color and color difference

CTS Rubber (4 times per year)

Tensile strength, ultimate elongation and tensile stress
Hardness
Mooney viscosity
Vulcanization properties

CTS Thermal Insulation Materials (2 times per year)

19 test methods for thermal insulation materials covering:
thermal properties; strength properties; dimensions, stability,
and density properties; fire properties; and properties of
vapor barriers

ASTM Cement (2 times per year)

Chemical (11 chemical components)
Physical (8 characteristics)

AASHTO Bituminous

Asphalt cement (2 times per year)
Cutbacks (once a year)

NBS Collaborative Reference Programs
A05 Technology Building
National Bureau of Standards
Washington, DC 20234

National Bureau of Standards
FEB 27 1980
NOT ACC-CIRC
EQ 100
USG
79-1380
1979
c.2

CONTAINER BOARD

Collaborative Reference
Program for
Containerboard

report no. 116
May 1979

J. Horlick
Office of Testing Laboratory
Evaluation Technology,
Office of Engineering Standards,
National Engineering Laboratory

T.L. Cummings
NBS Research Associate
Collaborative Testing
Services, Inc.

U.S. Department of Commerce,
National Bureau of Standards

Fourdrinier Kraft Board Group
American Paper Institute, Inc.



Introduction

The Collaborative Reference Program for Containerboard is sponsored by the Fourdrinier Kraft Board Group (FKBG) of the American Institute of Paper, Inc., with the cooperation of the Technical Association of the Pulp and Paper Industry (TAPPI) and the Collaborative Testing Services, Inc. In this program, samples of three weights of linerboard, nominally 26 lb, 42 lb, and 69 lb and of corrugating medium (26 lb) are randomized separately from uniform narrow rolls and packaged for distribution to the participants. Each month, sufficient test material for four weekly tests, the material for each consisting of 20 test pieces of 42 lb board and 20 test pieces of 26 or 69 lb board, the latter in alternate months, is mailed to participants for Mullen bursting strength, or for each week five sheets of corrugating medium, each sheet for four tests of Concora flat crush strength. The participants return their test results to NBS for analysis and receive two monthly reports from NBS: a "preliminary" (individualized report) comparing a laboratory's results with the industrial mean, and a longer report (as illustrated by this report) showing the data from all participants.



Jeffrey Horlick, Administrator
Collaborative Reference Programs

Office of Testing Laboratory
Evaluation Technology
(301) 921-2946

July 5, 1979




TABLE OF CONTENTS

Page

1	Explanation of Tables
4	Instrument Codes
5	Use of Average Mean as a Reference Standard
6	Bursting Strength, Linerboard 42H11, weeks 1 - 4
8	Bursting Strength, Linerboard 69J1, weeks 1 - 3
10	Bursting Strength, Linerboard 69J2, week 4
12	Concora Flat Crush, Corrugating Medium 26D1



EXPLANATION OF TABLES

Each table shows laboratory test results for Mullen bursting strength of linerboard or Concora flat crush strength of corrugating medium. The data are divided into three time spans. On the left of each table is an analysis for each week of the month. In the center is cumulative data for the month and on the right is cumulative data for up to 16 weeks.

Conservative statistical tests have been used in excluding extreme data from the analyses. Thus, where the mean (average) for one laboratory is compared with the average for many laboratories, limits have been used that would exclude only one laboratory in a hundred if all laboratories followed exactly the same testing procedure. Consequently, laboratories receiving "X" flags should review their testing procedures, instrument calibration, and control processes. Similar conservative criteria were used in flagging within-laboratory standard deviations and other statistics.

	LAB	MEANS THIS MONTH			
<u>WEEKLY VALUES:</u>	CODE V	WK-1	WK-2	WK-3	WK-4

LAB CODE - Confidential laboratory identification number known only to the participant and the Collaborative Reference Program staff.

V - Code for indicating instrument type, units used, and any other variation in test procedure or conditions. A '+' in this column means a non-standard variation. Data marked '+' are not included in the combined averages for all laboratories. (see page 4).

MEANS THIS MONTH - For each laboratory each weekly mean is the average of individual test determinations, usually an average of 20 determinations.

FLAGS (following means and standard deviations) -

X - Data excluded from an AV MEAN or average standard deviation because value deviated from the AV MEAN or average standard deviation by more than 2.576 times the appropriate standard deviation. A laboratory following the prescribed test method could obtain such an extreme value by chance only one time in a hundred. Corrective action is almost certainly required.

* - Data included in the CUMULATIVE AV MEAN but the value deviated from this mean by more than 1.960 and less than 2.576 times the SD CUM MEAN. A laboratory following the prescribed test method could obtain such an extreme value by chance only one time in twenty. Corrective action may be desired.

- S - This is a warning to the laboratory but does not affect inclusion or exclusion of the laboratory's results from the corresponding AV MEAN. This flag indicates an extremely high or low within-laboratory standard deviation (SDR, not shown) that could occur by chance only one time in a hundred if the laboratory is following the prescribed test method.
- AV MEAN - (at bottom of table) - The average for the indicated week of the means for all laboratories, except those laboratories marked '+' in column V and those means marked with an 'X'.
- SDR - (not shown) - The standard deviation of within-laboratory measurements; i.e., the Standard Deviation of the Replicate measurements made at one time in one laboratory on one package of test pieces.
- AV SDR - The average for the indicated week of the SDR's of all the laboratories, except those omitted from the AV MEAN. Also an extremely high or low SDR as compared with the AV SDR based on the remaining laboratories is omitted from the AV SDR and the letter 'S' is placed after the laboratory mean for that week. The AV SDR is an index of the within-laboratory precision for repeated measurements; i.e., a measure of the ability of an average laboratory to repeat its results over a short period of time. It includes measurement error and sample variation.
- SD LABS - For each week the standard deviation of the means about the AV MEAN for that week after omitting those means marked with an 'X' or noted '+' in column V. The SD LABS is an index of the among-laboratory precision of the test method as applied by the participating laboratories; i.e., a measure of the ability of laboratories to get comparable results.
- NO. INCL - The number of laboratory means included in the AV MEAN for that week.
- NO. OMIT - The number of laboratory means reported but omitted from AV MEAN because of non-standard equipment, environment or procedure ('+' in column V) or because of extreme results (X following mean).
- NOT RCD - The number of laboratories failing to report data on time or in usable form for this week (but who reported data for at least one of the other weeks of this month), or who received test pieces from a different sample of material and whose data therefore are shown in another table of this report.
- SD SHTS - (Concora only) The average for the indicated week of the among-sheet within-laboratory standard deviations. The SD SHTS is an index primarily of the variability among sheets.

THIS MONTH

VALUES THIS MONTH: **MEAN SDR SDWKS**

- MEAN - The average for the indicated laboratory of the reported weekly MEANS THIS MONTH.
- SDR - The average for the indicated laboratory of the weekly SDRs for the current month.
- SDWKS - For the indicated laboratory, the standard deviation among the laboratory's weekly MEANS THIS MONTH (including those means marked with an 'X').

CUMULATIVE

CUMULATIVE VALUES: **MEAN SDR SDWKS WKS**

- MEAN - The average for the indicated laboratory of all its weekly means for the number of weeks indicated, including those for the current month. An '*' or 'X' following this CUMULATIVE MEAN indicates the laboratory is running consistently low or high. (See above for explanation of these flags).
- SDR - The average for the indicated laboratory of the weekly SDRs for the indicated number of weeks.
- SDWKS - For the indicated laboratory, the standard deviation among the laboratory's weekly means (including those means marked with an 'X'). SDWKS is an index of the week to week precision; i.e., a measure of the ability of a laboratory to repeat its results from week to week.
- WKS - Number of weeks for which usable results have been reported by that laboratory. At most, 16 weeks of data are included.

GRAND AVERAGES

GRAND AVERAGES: **THIS MONTH CUMULATIVE 12 WEEKS**

- THIS MONTH - Averages for the four weeks of the quantities shown to the left.
- CUMULATIVE - Averages for the indicated number of weeks, including the four weeks of the current month.

- AV SDWKS - The average of the SDWKS for all laboratories excluding those marked '+' in column V or with an 'X' following the corresponding THIS MONTH or CUMULATIVE MEAN or SDWKS.
- SD CUM MEAN - The larger of either (1) the standard deviation of the CUMULATIVE MEANS about the average CUMULATIVE MEAN after omitting those CUMULATIVE MEANS marked with an 'X' or with a '+' in column V, or (2) the CUMULATIVE SD LABS divided by the square root of the number of weeks cumulated. The former will be appreciably larger than the latter only when there are persistent systematic differences among the laboratories.

INSTRUMENT CODES
FOR
MULLEN BURST TESTERS
(Column V)

<u>Code</u>	<u>Description</u>
A	Model A, Manual Clamp
H	Model AH, Hydraulic Clamp
I	Model A, Hydraulic Clamp added
J	Jumbo, Hand Clamp, Hand Driven
L	Lhomargy, Hydraulic Clamp
M	Model AH, Hydraulic Clamp, Transducer
R	Model A, Air Clamp added
X	Other Model, Please Describe Instrument Make and Model

If an incorrect instrument code has been assigned to your laboratory, please inform us.

Use of Average Mean as a Reference Standard

A large supply of linerboard in three weights was randomized and placed in sealed packages ready for shipment. The supply for each weight of board was divided into several narrow "rolls" or cross-machine "positions" of a larger roll, and each position was separately randomized. Each package contains test pieces from one position only. The position is designated by the number following the letter in the code marked on the package. Thus 42H 1 indicates that this package contains 42 lb board from position 1 of lot H. Samples from the first position are distributed until exhausted, then from the second position, and so forth for each weight of board. Thus for short periods of time (several weeks to months), the samples that the participants test are from the same position of a lot, and for a longer period from the same lot.

The three weights of linerboard distributed in this program may be used as reference standards. The best reference values are the cumulative grand AV MEANS in the latest reports. These values are given at the bottom right of each table. For each weight of board, comparisons should be made first for measurements made on the same position, i.e., for checking your current measurement, use grand AV MEANS that have the same position code as on the packages being tested. The position is shown in the upper left corner of the table. If no report is yet available on the current position, grand AV MEANS from previously tested positions of the same lot may be used as approximate reference values.

Similarly a large supply of a 26 lb corrugating medium was randomized, after dividing into several narrow rolls or positions. The above discussion for linerboard also applies to the corrugating medium.

We are currently using the third lot of linerboard and the fourth lot of corrugating medium:

<u>Lot</u>	<u>Material</u>	<u>Codes</u>	<u>Used</u>
1	linerboard	A,B,C	October 1969 - April 1973
2	linerboard	D,E,F	September 1972 - September 1976
3	linerboard	G,H,I,J	October 1976 -
1	corrugating medium	(A)	May 1973 - March 1976
2	corrugating medium	B	April 1976 - February 1977
3	corrugating medium	C	March 1977 - August 1978
4	corrugating medium	D	September 1978 -

LAB CODE	V	MEANS THIS MONTH				THIS MONTH			CUMULATIVE			WKS
		WK-1	WK-2	WK-3	WK-4	MEAN	SDR	SDWKS	MEAN	SDR	SDWKS	
100	H	128.0	124.9	125.2	123.1	125.3	6.6	2.0	125.2	7.8	1.4	10
101	H	123.1	122.6	123.0	124.3	123.2	6.9	.7	121.6	7.2	3.0	10
102	H	130.2	123.7	125.7	128.6	127.0	8.0	2.9	125.9	8.0	2.8	10
103	I	120.9	120.2	119.7	122.5	120.8	6.9	1.2	118.1	7.3	2.5	10
105	M	126.0	120.6	127.7	122.0	124.1	9.1	3.3	123.6	9.5	4.0	10
106	H	127.2	133.9X	125.7	124.0	127.7	9.5	4.3	131.3*	10.8	4.5	10
108	M	128.2	131.4	129.7	132.6	130.5	9.9	1.9	129.8	9.2	2.1	10
109	H	123.1	124.4	130.8	126.5	126.2	9.7	3.4	126.1	10.0	2.7	10
110	M	131.1	131.1	130.3	129.5	130.5	8.8	.7	128.5	9.1	2.4	10
111	M	127.2	124.8	128.4	125.2	126.4	9.5	1.7	124.7	10.4	2.6	10
112	H	121.4	119.9	118.1	115.0	118.6	7.6	2.8	118.4	9.2	3.0	10
113	R	125.3	124.0	124.9	124.0	124.6	8.4	.7	124.8	8.1	1.2	10
114	A	129.1S	124.4	124.2	125.4	125.8	11.9	2.3	125.8	10.5	1.5	10
115	R	125.5	127.2	124.3S	125.6	125.7	4.5	1.2	124.6	6.7	1.3	10
117	H	121.8	119.3	118.0	119.6	119.7	9.8	1.6	121.1	8.5	2.9	9
119	H		116.1	132.6	123.9S	124.2	11.9	8.3	127.1	10.1	5.7X	8
120	R	118.4	124.3	118.0	120.4	120.3	9.9	2.9	119.6	9.1	3.3	10
121	M	127.4	125.9	124.7	125.6	125.9	8.3	1.1	127.1	8.7	3.6	10
123	R	126.3	123.5	128.1	129.4	126.8	9.8	2.5	119.4	9.2	11.8X	9
125	I	130.1	127.3	128.5	131.4	129.3	7.3	1.8	126.7	8.2	3.1	10
127	H	123.6	123.2	124.2	123.5	123.6	6.4	.4	125.0	6.7	1.9	10
128	H	128.4	124.0	129.4	130.6	128.1	9.7	2.9	126.2	9.6	3.0	10
129	R	117.3	123.4S	126.0	110.6X	119.3	5.3	6.9	122.5	6.1	6.3X	9
130	H	128.3	122.4	122.2	121.6	123.6	9.0	3.1	124.8	9.9	3.4	10
131	R	117.0	118.3	129.9	125.3	122.7	10.8	6.1	122.2	11.5	5.6X	10
133	A	123.3		121.6	128.9	124.6	9.9	3.8	123.9	8.7	2.8	9
134	H	119.1	119.2	123.0	121.2	120.6	7.5	1.8	121.2	7.8	1.9	6
135	I	126.3	127.3	134.5X	130.4	129.6	11.0	3.7	130.6	10.8	3.4	10
136	H	117.6	118.4	113.5X	115.5	116.2	7.2	2.2	116.2*	7.2	2.2	4
137	H	120.7	123.0	126.8	124.5	123.8	10.3	2.5	123.2	11.4	2.5	10
138	H	131.6	127.0	129.5	127.0	128.8	9.8	2.2	128.4	10.2	2.1	10
139	R	122.7	121.0	126.2	117.1	121.8	9.7	3.8	121.3	9.4	3.8	10
140	H	117.5	121.9	119.2	119.1S	119.5	7.4	1.8	120.2	7.3	2.9	10
141	H	119.4	137.6X	122.0	120.2	124.8	6.4	8.6	121.0	6.4	6.0X	10
142	A	118.7	118.5	122.1	118.7	119.5	8.9	1.7	122.8	8.6	3.1	10
143	H	124.1		125.7	123.9	124.6	10.4	1.0	125.1	9.9	1.0	9
145	H	114.4	119.0		120.3	117.9	7.5	3.1	119.2	7.3	2.9	7
147	H	123.5	121.9	124.4	125.1	123.7	8.4	1.4	125.9	9.1	3.1	10
149	H	133.8	126.5	131.4	128.9	130.2	9.3	3.2	129.9	10.2	2.6	10
151	H	123.9	124.3	122.8	124.2	123.8	6.4	.7	124.1	6.7	1.1	10
153	H	128.2	121.3			124.8	11.3	4.9	127.5	10.7	3.7	5
155	H	127.3	120.8	125.1S	130.7	126.0	11.3	4.1	127.3	11.2	4.3	10
157	*X	129.7	127.6	120.9	121.7	125.0	8.9	4.3	122.5	7.9	4.7	10
161	*X	123.9	125.0	120.6	121.1	122.7	9.0	2.1	125.0	7.9	3.4	10
163	H	122.4	118.4	120.9		120.6	8.7	2.0	121.6	8.4	2.2	5
165	R	117.7	124.2	124.7	123.1	122.4	9.4	3.2	124.0	8.8	2.4	10
166	H	132.3	121.5	125.0	121.6	125.1	9.5	5.1	122.6	8.5	4.5	8
167	H	126.6	127.7	125.2	127.2	126.7	10.2	1.1	125.8	9.3	1.3	10
169	I			124.6	128.1	126.3	10.5	2.5	126.3	10.5	2.5	2
171	H	122.9		120.0	122.7	121.9	7.9	1.6	122.4	8.8	1.4	9
172	H	123.5	129.0	126.5	132.6	127.9	8.4	3.9	127.2	9.6	4.4	10
173	H	122.1	122.6		123.2	122.7	7.7	.6	123.4	7.9	1.2	9
174	H	120.8	123.0	120.5	125.4	122.5	9.3	2.3	123.7	9.5	2.5	10
175	H	114.4	123.2	118.8	121.9	119.6	9.8	3.9	118.3	9.1	3.5	10
176	H	128.7	121.4	124.1	128.1	125.6	9.9	3.5	126.0	10.1	3.4	10

LAB CODE	V	MEANS THIS MONTH				THIS MONTH			CUMULATIVE			
		WK-1	WK-2	WK-3	WK-4	MEAN	SDR	SDWKS	MEAN	SDR	SDWKS	WKS
177	H	118.8	119.0	118.9	116.4	118.3	7.2	1.3	119.8	8.3	1.6	10
182	H	124.1	123.3	125.0	124.7	124.3	10.4	.8	125.0	10.2	1.1	10
184	H	123.0	125.6	125.8		124.8	9.0	1.6	123.3	8.7	3.8	8
186	I	122.9	117.6	121.5	122.6	121.2	9.4	2.4	121.5	8.2	1.6	10
188	I	120.9	118.7	117.8	118.7	119.0	6.0	1.3	117.4	6.2	3.1	10
250	*L	142.3X	148.8X	139.9X	138.5X	142.4X	10.8	4.6	141.7X	11.7	4.6	9
274	H	122.8	122.5	123.2	123.6	123.0	7.5	.5	122.4	7.1	.9	10
283	H	123.0		121.6	122.6	122.4	5.7	.7	122.8	7.2	3.4	8
287	A	125.1	128.8	129.7	128.9	128.1	10.8	2.1	128.7	9.9	4.0	9
327	M	124.5	126.0	124.9	125.7	125.3	8.3	.7	126.0	9.0	1.9	10
350	H	118.4	127.3	119.7	124.9	122.6	9.3	4.2	122.7	9.7	3.1	10
553	M	130.1	126.6	132.6	134.2	130.9	8.8	3.3	128.3	8.0	3.8	10
562	A	132.1	126.1	127.0	125.9	127.8	10.1	2.9	131.6*	9.7	5.0	10
568	I	122.1	125.9	116.3	121.1	121.4	9.1	4.0	120.8	9.9	3.3	10
569	A	120.1	128.6	125.1	121.9	123.9	7.1	3.8	122.7	7.9	3.2	10
658	H	121.3	120.5	122.0	120.7	121.1	9.4	.7	118.2	6.5	4.4	10
701	H	123.8	124.1	124.9	129.7	125.7	7.7	2.8	125.7	7.7	2.8	4

	WK-1	WK-2	WK-3	WK-4	GRAND AVERAGES	
					THIS MONTH	CUMULATIVE 10 WEEKS
AV MEAN	123.9	123.4	124.5	124.5	AV MEAN	124.1
AV SDR	8.6	8.9	8.8	8.7	AV SDR	8.8
SD LABS	4.5	3.4	3.9	4.2	SD LABS	4.0
NO. INCL	67	62	64	65	NO. INCL	64.5
NO. OMIT	3	5	5	4	AV SDWKS	2.6
NOT RCD	2	5	3	3	SD CUM MEAN	3.5

LAB CODE	V	MEANS THIS MONTH				THIS MONTH			CUMULATIVE			WKS
		WK-1	WK-2	WK-3	WK-4	MEAN	SDR	SDWKS	MEAN	SDR	SDWKS	
100	H	159.6	158.6	156.8		158.3	11.6	1.4	155.7	13.3	2.9	8
101	H	154.9	154.6	154.0		154.5	9.3	.5	155.3	10.8	2.8	8
102	H	161.8	162.0	160.4		161.4	11.8	.8	160.4	11.2	2.1	8
103	I	152.8	154.1	157.7		154.9	12.2	2.5	155.2	12.4	2.1	8
105	M	156.1	151.9	159.9		156.0	16.4	4.0	157.7	15.7	3.5	8
106	H	158.8	156.6	161.0		158.8	15.1	2.2	158.4	14.5	3.7	8
108	M	155.5	156.2	149.8		153.8	13.5	3.5	157.2	13.8	4.2	8
109	H	160.0	161.0	158.2		159.7	16.1	1.4	160.8	16.1	2.2	8
110	M	154.8	160.9	156.5		157.4	14.0	3.1	155.5	14.1	4.9	8
111	M	151.8	156.2	159.4		155.8	14.0	3.8	153.3	14.2	5.9	8
112	H	155.8	150.9	156.1		154.3	10.6	2.9	152.6	12.5	4.3	8
113	R	155.1	156.2	154.6		155.3	11.1	.8	155.7	10.2	1.3	8
114	A	147.1	148.1	148.9		148.0	13.7	.9	152.0	12.0	3.7	8
115	R	158.9	159.38	155.1		157.8	5.1	2.3	156.6	6.6X	2.2	8
117	H	155.7	146.3	144.9		149.0	12.8	5.9	151.7	13.1	4.3	8
119	H		149.4	160.2		154.8	15.8	7.6	154.4	14.8	4.9	7
120	R	152.4	144.18	147.6		148.0	16.9	4.2	147.5X	16.1	3.9	8
121	M	162.6	159.7	159.7		160.7	11.3	1.6	157.0	13.3	5.9	8
123	R	156.4	152.7	157.9		155.7	14.9	2.7	155.3	15.7	4.6	8
125	I	151.5	150.8	157.9		153.4	13.3	3.9	154.5	13.2	4.8	8
127	H	154.7	156.3	156.3		155.8	8.5	1.0	155.0	9.1	2.9	8
128	H	149.8	158.1	157.5		155.1	16.9	4.6	154.4	16.0	4.3	8
129	R	135.5X	152.6S	150.8		146.3	7.4	9.4	150.2	7.4X	8.3X	7
130	H	155.8	146.0S	149.6		150.5	16.8	5.0	151.8	16.5	3.6	8
131	R	149.8	151.7	162.7		154.8	16.9	7.0	150.9	15.4	7.3	8
133	A	153.6		154.5		154.1	11.9	.7	152.8	12.5	1.1	7
134	H	154.1	153.8	154.7		154.2	11.1	.4	154.2	11.1	.4	3
135	I	164.0	158.8	165.5		162.8	17.6	3.5	162.2*	15.9	3.1	5
136	H	138.8X	155.6	147.5		147.3	8.9	8.4	146.7X	10.9	6.6	5
137	H	156.0	166.9X	153.7		158.9	15.3	7.0	158.8	18.1	6.8	8
138	H	154.0	150.4	161.3		155.2	17.0	5.6	157.5	15.4	5.4	8
139	R	157.1	150.6	153.1		153.6	14.4	3.3	158.2	14.6	6.2	8
140	H	151.7	157.4	157.3		155.5	13.2	3.3	157.0	13.1	2.8	8
141	H	156.1	156.4	157.8		156.8	9.9	.9	153.2	10.6	4.1	7
142	A	155.0	150.4	147.7		151.1	11.2	3.7	155.9	12.2	4.8	8
143	H	156.9		159.3		158.1	13.0	1.7	158.1	13.2	1.2	7
145	H	146.7	149.5			148.1	11.3	2.0	150.5	12.8	4.7	5
147	H	154.8	157.2	149.0		153.7	14.6	4.2	156.9	14.3	4.1	8
149	H	156.0	150.3	161.1		155.8	15.1	5.4	153.9	13.6	5.4	8
151	H	154.8	153.7	154.1		154.2	9.5	.6	154.2	10.1	1.6	8
153	H	155.2	146.7			151.0	14.8	6.0	151.0	14.8	6.0	2
155	H	149.5	150.1	156.4		152.0	16.9	3.9	156.3	16.2	6.0	8
157	*X	165.5X	152.8	149.6		156.0	14.1	8.4	153.1	13.8	5.7	8
161	*X	156.6S	153.9	164.7S		158.4	20.5	5.6	157.3	15.7	3.7	8
163	H	153.4	159.2	149.0		153.9	14.5	5.1	154.5	15.1	3.6	8
165	R	149.6	148.9	157.4		152.0	14.4	4.7	152.6	12.9	3.1	8
166	H	159.3	158.5	159.0		159.0	14.3	.4	159.0	14.3	.4	3
167	H	155.0	156.1	160.4		157.2	12.9	2.8	161.2*	13.6	4.6	8
169	I			152.1		152.1	20.1		152.1	20.1X		1
171	H	153.8		155.8		154.8	13.9	1.4	160.2	16.4	5.2	7
172	H	150.6	153.1	150.6		151.5	14.9	1.4	153.4	14.8	3.0	8
173	H	160.6	163.7			162.2	12.3	2.2	158.7	11.3	2.7	7
174	H	159.4	155.4	154.9		156.6	12.8	2.5	153.8	13.9	2.9	8
175	H	149.8	153.5	148.1		150.5	14.6	2.8	147.9X	16.9	8.4X	7
176	H	159.3	155.0	147.8		154.0	18.6	5.8	154.6	15.8	4.6	8

LAB CODE	V	MEANS THIS MONTH				THIS MONTH			CUMULATIVE			WKS
		WK-1	WK-2	WK-3	WK-4	MEAN	SDR	SDWKS	MEAN	SDR	SDWKS	
177	H	153.3	149.7	159.8		154.3	10.4	5.2	156.3	12.3	4.1	8
182	H	157.5	150.3S	158.2		155.3	17.1	4.3	155.2	15.1	3.0	8
184	H	157.0	158.9	161.5		159.2	15.6	2.3	159.9	13.9	1.9	7
186	I	153.0	148.3	153.7		151.7	11.8	2.9	153.7	12.5	2.4	8
188	I	154.5	153.0	155.1		154.2	9.0	1.1	154.0	10.5	1.4	8
250	*L	180.7X	184.4X	183.1X		182.7X	19.2	1.9	174.7X	19.8X	8.7X	7
274	H	156.7	156.7	157.3		156.9	9.9	.3	157.4	10.8	1.0	8
283	H	154.9		157.1		156.0	10.3	1.5	155.9	10.9	1.1	6
287	A	163.3	157.0	149.7		156.7	14.7	6.8	152.9	16.3	6.0	7
327	M	153.1	154.2	153.6		153.6	12.6	.5	154.1	14.1	.9	7
350	H	156.9	158.8	146.8		154.2	14.7	6.5	153.6	14.3	4.4	8
553	M	152.9	157.5	158.7		156.4	13.5	3.0	157.7	13.6	5.4	8
562	A	162.7	161.0	161.0		161.6	16.6	1.0	164.9X	16.3	3.0	8
568	I	155.8	155.2	149.6		153.5	15.3	3.4	151.9	16.1	6.0	8
569	A	152.3	166.0X	160.2		159.5	13.0	6.9	156.0	13.3	5.4	8
658	H	157.4	156.1	159.0		157.5	14.4	1.5	158.6	11.6	3.9	8
701	H	153.6	156.4	154.7		154.9	14.6	1.4	154.9	14.6	1.4	3

	WK-1	WK-2	WK-3	WK-4	GRAND AVERAGES		
					THIS MONTH	CUMULATIVE	8 WEEKS
AV MEAN	155.3	154.4	155.4		AV MEAN	155.0	155.4
AV SDR	13.6	13.5	13.3		AV SDR	13.4	13.5
SD LABS	3.7	4.4	4.7		SD LABS	4.2	4.5
NO. INCL	65	62	66		NO. INCL	64.3	61.6
NO. OMIT	5	5	3		AV SDWKS	3.3	3.6
NOT RCD	2	5	3		SD CUM MEAN		2.8

LAB CODE V	WEEK	MEANS THIS MONTH				THIS MONTH			CUMULATIVE			WKS
		WK-1	WK-2	WK-3	WK-4	MEAN	SDR	SDWKS	MEAN	SDR	SDWKS	
100	H				151.0	151.0	15.8	151.0	15.8		1	
101	H				152.5	152.5	9.4	152.5	9.4		1	
102	H				158.8	158.8	11.7	158.8	11.7		1	
103	I				159.4	159.4	14.3	159.4	14.3		1	
105	M				154.9	154.9	13.3	154.9	13.3		1	
106	H				159.5	159.5	8.9	159.5	8.9		1	
108	M				162.0	162.0	11.9	162.0	11.9		1	
109	H				157.1	157.1	20.9	157.1	20.9		1	
110	M				156.0	156.0	18.7	156.0	18.7		1	
111	M				153.6	153.6	14.9	153.6	14.9		1	
112	H				160.2	160.2	11.6	160.2	11.6		1	
113	R				155.9	155.9	10.4	155.9	10.4		1	
114	A				156.1	156.1	12.0	156.1	12.0		1	
115	R				152.1	152.1	9.5	152.1	9.5		1	
117	H				154.8	154.8	11.1	154.8	11.1		1	
119	H				155.7	155.7	18.5	155.7	18.5		1	
120	R				147.5	147.5	14.7	147.5*	14.7		1	
121	M				165.3	165.3	11.0	165.3*	11.0		1	
123	R				152.8	152.8	14.6	152.8	14.6		1	
125	I				156.4	156.4	10.8	156.4	10.8		1	
127	H				157.6	157.6	9.0	157.6	9.0		1	
128	H				156.3	156.3	17.0	156.3	17.0		1	
129	R				135.8X	135.8X	7.0	135.8X	7.0		1	
130	H				153.0	153.0	15.3	153.0	15.3		1	
131	R				154.1	154.1	14.4	154.1	14.4		1	
133	A				158.2	158.2	16.1	158.2	16.1		1	
134	H				153.5	153.5	10.0	153.5	10.0		1	
135	I				177.3X	177.3X	17.1	177.3X	17.1		1	
136	H				148.0	148.0	10.0	148.0	10.0		1	
137	H				162.9	162.9	19.5	162.9	19.5		1	
138	H				156.3	156.3	14.8	156.3	14.8		1	
139	R				155.2	155.2	15.2	155.2	15.2		1	
140	H				150.5	150.5	8.4	150.5	8.4		1	
141	H				157.0	157.0	7.0	157.0	7.0		1	
142	A				150.4	150.4	15.4	150.4	15.4		1	
143	H				158.9	158.9	13.0	158.9	13.0		1	
145	H				154.4	154.4	11.8	154.4	11.8		1	
147	H				149.3	149.3	15.7	149.3	15.7		1	
149	H				160.2	160.2	20.8	160.2	20.8		1	
151	H				156.3	156.3	13.1	156.3	13.1		1	
155	H				158.2	158.2	18.0	158.2	18.0		1	
157	*X				156.1	156.1	16.5	156.1	16.5		1	
161	*X				154.8	154.8	9.2	154.8	9.2		1	
165	R				149.6	149.6	14.1	149.6	14.1		1	
166	H				159.4	159.4	12.0	159.4	12.0		1	
167	H				166.4	166.4	12.9	166.4*	12.9		1	
169	I				161.9	161.9	16.6	161.9	16.6		1	
171	H				165.7	165.7	20.6	165.7*	20.6		1	
172	H				159.5	159.5	16.1	159.5	16.1		1	
173	H				153.9	153.9	10.9	153.9	10.9		1	
174	H				157.9	157.9	17.5	157.9	17.5		1	
175	H				155.0	155.0	17.5	155.0	17.5		1	
176	H				156.1	156.1	18.4	156.1	18.4		1	
177	H				154.1	154.1	14.8	154.1	14.8		1	
182	H				157.8	157.8	16.5	157.8	16.5		1	

LAB CODE V	MEANS THIS MONTH				THIS MONTH			CUMULATIVE			
	WK-1	WK-2	WK-3	WK-4	MEAN	SDR	SDWKS	MEAN	SDR	SDWKS	WKS
186 I				146.4	146.4	15.0		146.4*	15.0		1
188 I				157.3	157.3	11.3		157.3	11.3		1
250 +L				173.7X	173.7X	16.5		173.7X	16.5		1
274 H				157.9	157.9	10.9		157.9	10.9		1
283 H				156.0	156.0	10.3		156.0	10.3		1
287 A				157.1	157.1	10.3		157.1	10.3		1
327 M				151.2	151.2	17.5		151.2	17.5		1
350 H				157.0	157.0	17.2		157.0	17.2		1
553 M				161.4	161.4	13.9		161.4	13.9		1
562 A				167.3X	167.3X	15.8		167.3X	15.8		1
568 I				151.8	151.8	14.8		151.8	14.8		1
569 A				156.1	156.1	12.0		156.1	12.0		1
658 H				160.1	160.1	11.9		160.1	11.9		1
701 H				149.2	149.2	14.9		149.2	14.9		1

	WK-1	WK-2	WK-3	WK-4	GRAND AVERAGES		
					THIS MONTH	CUMULATIVE	1 WEEKS
AV MEAN				156.1	AV MEAN	156.1	156.1
AV SDR				13.9	AV SDR	13.9	13.9
SD LABS				4.3	SD LABS	4.3	4.3
NO. INCL				63	NO. INCL	63.0	63.0
NO. OMIT				6	AV SDWKS	.0	.0
NOT RCD				0	SD CUM MEAN		4.3

LAB CODE V	MEANS THIS MONTH				THIS MONTH			CUMULATIVE			
	WK-1	WK-2	WK-3	WK-4	MEAN	SDR	SDWKS	MEAN	SDR	SDWKS	WKS
100	72.4	74.3	75.1	74.5	74.1	3.7	1.2	74.2	3.7	1.2	16
102	72.3	71.9	72.6	74.1	72.7	3.2	.9	72.8	3.3	.7	15
105	71.3	70.4	70.2	71.1	70.8	3.4	.5	73.0	3.9	2.3	16
106	72.3	71.6	73.4	71.3	72.2	4.0	1.0	72.8	4.1	2.1	15
110	73.7	73.0	74.3	73.7	73.7	3.4	.5	74.5	3.7	1.3	16
113	71.3	71.9	71.9	72.1	71.8	3.1	.4	72.6	3.2	.6	16
114	70.6	76.2	76.2	75.8	74.7	3.5	2.8	71.3	3.5	2.7	16
115	75.0	73.5	71.5	75.6	73.9	3.7	1.8	72.7	3.8	1.5	16
116	68.7	69.1	69.1	68.8	68.9	3.5	.2	69.7	3.5	2.8	12
119		70.2	71.0		70.6	3.7	.6	71.2	3.7	1.8	13
120	69.5	71.9	70.4	72.3	71.0	3.8	1.3	72.2	3.7	2.1	16
125	73.3	79.5	81.5X	75.5	77.5	4.1	3.7	78.6X	4.3	2.4	16
128	73.0	72.2	72.1	72.0	72.3	3.3	.4	72.1	3.4	.7	16
136	38.9XS	38.2XS	38.6X	39.3X	38.8X	1.6	.5	54.2X	2.7	19.2X	7
138	74.4	75.3	72.8	75.9	74.6	4.0	1.3	75.4	4.4	1.5	16
140	74.7	75.9	77.1	76.2S	76.0	4.7	1.0	73.3	4.1	1.9	16
143	72.1	73.5	73.3	71.6	72.6	3.3	.9	72.8	3.4	1.2	16
161	75.4	75.1	73.1	76.4	75.0	5.1	1.4	73.9	4.6	2.3	15
164	68.9	65.9	71.4	66.4X	68.2	3.6	2.5	73.5	3.6	4.2X	16
167	72.1	73.6	74.6	72.2	73.1	3.7	1.2	73.5	4.0	1.2	16
177	70.8	72.7	69.9	71.2	71.2	3.6	1.2	71.1	3.8	1.4	16
182	76.0	78.4	76.4	77.2	77.0	4.9	1.1	78.2X	4.6	2.0	16
188	78.2	74.7	74.5	73.8	75.3	4.5	2.0	73.2	3.6	1.7	16
237	71.9	71.1	71.8	70.3	71.3	4.2	.8	71.7	3.5	1.4	16
250	68.8	70.4	68.7	69.0	69.2	2.9	.8	69.3	2.6	.8	15
269	71.7	73.1	72.5	72.8	72.6	3.5	.6	71.9	3.6	1.4	16
274	74.1		73.6	73.8	73.9	3.0	.3	73.1	3.2	.6	15
283	70.1		69.5	69.5	69.7	2.7	.3	71.7	2.7	1.2	14
284	70.7	67.8	71.7	72.1	70.6	4.0	1.9	71.3	3.8	1.4	16
287	76.3	77.5	77.7	76.3	76.9	3.9	.8	78.7X	4.3	1.9	16
289	64.5	60.3X	67.4	67.3	64.9X	2.4	3.3	64.5X	2.7	2.4	16
292	75.0	71.1	72.3	70.7	72.3	3.4	1.9	72.4	3.7	2.8	15
327	74.8	75.1	73.5	73.2	74.1	4.3	.9	71.0	2.9	2.7	12
350	82.0X	79.4	79.3	81.7X	80.6X	2.9	1.5	79.8X	3.5	1.5	16
351	70.1	73.2	72.2	71.7	71.8	2.1	1.3	73.0	2.3X	1.5	16
353	73.5		73.3	71.3	72.7	3.9	1.2	73.2	3.5	1.6	15
355	79.4	80.4	73.9	78.0	77.9	4.3	2.9	75.0	3.7	2.4	16
357	66.4	71.0	69.0	71.0	69.3	4.3	2.2	70.2	3.9	2.6	16
363	69.4	73.1	72.5	70.1	71.3	4.4	1.8	70.6	3.2	1.4	16
365	70.7	70.7	69.1	68.9	69.9	3.8	1.0	70.3	3.5	1.4	16
367		72.1	73.6	73.8	73.2	3.7	.9	74.5	4.5	1.9	15
369	72.1	71.1	71.0	71.6	71.5	3.4	.5	71.8	3.5	.8	16
377	78.6	75.1	76.1	73.4	75.8	4.2	2.2	75.1	4.2	1.9	15
379	76.5	74.0	73.8	71.3	73.9	3.4	2.1	73.9	4.0	1.4	16
381		67.8	68.1	72.6	69.5	4.4	2.7	69.5	4.1	1.8	6
383	75.5	73.0	74.2	73.4	74.0	4.0	1.1	73.5	4.0	1.7	15
385	70.6		70.4	72.1	71.0	4.6	.9	71.1	5.1X	2.4	15
387	68.8	69.6	74.4	73.7	71.6	3.9	2.9	72.1	3.7	2.1	16
391	64.7	70.8	66.1	64.7X	66.6	2.4	2.9	67.4X	3.3	3.6X	15
393	66.6	67.6	67.0	68.2	67.4	2.9	.7	69.6	2.7	2.3	16
395	74.5	75.2	74.6	73.8	74.5	3.5	.6	75.5	3.8	1.1	15
397	71.7	72.2	75.1	72.3	72.8	3.1	1.5	75.2	3.6	2.3	16
399	67.3	67.4	69.6	71.0	68.8	3.2	1.8	71.4	3.3	3.1	16
553	72.8	71.2	72.6	72.4	72.3	3.5	.7	71.5	3.7	1.5	15
555	76.3	75.0	75.7	76.9	76.0	3.3	.8	75.4	3.1	1.8	16

