

VI-2
VLC:LJ

U. S. DEPARTMENT OF COMMERCE
NATIONAL BUREAU OF STANDARDS
WASHINGTON
OCTOBER 27, 1937.

Letter
Circular
LG-506

SOUND ABSORPTION COEFFICIENTS OF THE MORE COMMON ACOUSTIC MATERIALS.

The following figures have been obtained at the National Bureau of Standards for the sound absorption coefficients of a number of acoustic materials. It is our intention to publish results only for materials which are on the market. The measurements on some of these materials were made several years ago, but we believe these materials are essentially the same as when the measurements were made. The inclusion of a material in this letter circular is not to be construed as a general approval. Each material should be judged on its merits in any particular case as there are other requirements such as fire resisting qualities; light reflection, appearance, etc. Figures are also given for the absorption of an audience seated in chairs of different kinds. All the results have been obtained by the reverberation method on samples having an area of approximately 72 square feet.

The sound absorption coefficient of a material is defined as the fractional part of the energy of a sound wave which is absorbed at each reflection. Experimental figures such as are given here must be regarded as approximate only. This branch of applied science is new and in a state of development. The methods and formulas used in obtaining these figures are those which, while not entirely satisfactory, are open to the least objection. The uncertainty involved is such that all the coefficients are probably somewhat too large.

The "noise coefficient" given in the table is the average to the nearest multiple of 0.05 of the coefficients for 256, 512, 1024 and 2048 cycles. It has been recommended by many consultants that such a coefficient be used when the problem is one of reducing the noise level, as in offices, restaurants, etc.

Fibrous materials and acoustic tiles may exhibit large variations in coefficient arising from different methods of mounting. The figures here given apply only to cases where the materials are mounted in the same manner as when tested.

Acoustic plasters require special skill in their application, as improper manipulation may reduce the coefficient. Particular attention is called to the fact that a dry base coat is used for most applications. Also the sound absorption coefficients are affected quite materially by the time between the application of the first and second coat of acoustic plaster. Moreover, the figures given for plasters without a base coat will be considerably reduced if a base coat is used.

It is not necessarily the case that the materials of highest coefficient are the most advantageous. When there is room enough to apply the requisite quantity, a material of low coefficient will give better results than one of higher absorption, because of the more uniform distribution of material. Also, in comparing different materials it should be borne in mind that there is some variation in manufacture, hence the sample which was measured may have more or less absorption than the material delivered on the job. Minor differences in coefficients, therefore, should be disregarded in choosing between materials.

For the foregoing reasons it is advisable in drawing up specifications for auditoriums to lay emphasis upon the reverberation time desired rather than upon coefficients of material. See Bureau of Standards Circular No. 396 entitled "Architectural Acoustics", which may be obtained of the Superintendent of Documents, Government Printing Office, Washington, D. C. at 5 cents per copy. Additional details regarding any of the materials mentioned in this letter circular will be furnished on application.

Additional information regarding the absorption coefficients of acoustical materials may be obtained from the Acoustical Materials Association, 919 North Michigan Avenue, Chicago, Illinois.

Sound Absorption Coefficients and Description of Test Samples

Table 1
Acoustical Tiles, Cast Materials, Boards and Blankets

The coefficients given in the following table have been modified to some extent from those given in Letter Circular No. 359 and earlier letter circulars. The reason for these changes is to be found in the August, 1934 number of the Journal of Research of the National Bureau of Standards (Research Paper No. 700) entitled "Dependence of Sound Absorption upon the Area and Distribution of the Absorbent Material".

ACOUSTICAL CORPORATION OF AMERICA

Material	Thickness (See Footnote)	Mounting Coef. Coefficients	Noise Coef.	Size of Unit Wt. (lb.)	Surface Tested sq. ft.	Date
Mutetile (2" Rockwool)	2 1/2"	4 .53 .71 .80 .78 .76 .45 .75	.16 .17 .48 .82 .65 .74 .55	12" x 24"	--	Cast plaster of paris 1932 perforated 2556 holes per sq. ft., dia. 1/16".

ACUSTONE COMPANY, LTD.

ACUSTONE COMPANY, LTD.							
Trutone Tile, cast on 1/4" gypsum wall board	3/4"	4 .22 .31 .60 .82 .74 .76	.16 .17 .48 .82 .65 .74 .65	11 7/8" x 22 7/8"	12.3	Unpainted	1932
Ek-O-less Tile cast on 1" backing.	4 .18 .32 .85 .92 .77 .81	.70 .70 .70 .70 .70 .70 .70	11 7/8" x 22 7/8"	--	Unpainted	1932	
Ek-O-less Tile cast on 1/2" backing.							

AMERICAN ACOUSTIC CORPORATION							
Ek-O-less Tile cast on 1" backing.	4 .18 .32 .85 .92 .77 .81	.70 .70 .70 .70 .70 .70 .70	11 7/8" x 22 7/8"	12.3	Unpainted	1932	
Ek-O-less Tile cast on 1/2" backing.							

ARMSTRONG CORK & INSULATION COMPANY							
Ceramacoustic Tile 1 1/8"	1 .34 .48 .63 .66 .65 .58	.00 .00 .00 .00 .00 .00 .00	4 1/2" x 9"	3.4	Unpainted	1932	
Ceramacoustic Tile 1 1/8"	1 .28 .49 .62 .62 .66 .54	.60 .60 .60 .60 .60 .60 .60	4 1/2" x 9"	3.4	Spray painted 4 coats at N.Y. of S.	1932	
Corkoustic Tile 1 1/2"	1 .08 .23 .70 .61 .52 .50	.36 .47 .36 .36 .36 .36 .36	12" x 12"	.83	painted by mfr.	1936	
Temlock (16" o.c.)	5 .24 .31 .27 .27 .27 .27	.30 .30 .30 .30 .30 .30 .30	-- -- --	--	Unpainted	1931	

ARMSTRONG CORK & INSULATION COMPANY (Cont'd)

Material	Thickness in.	Mounting (See Footnote)	128	256	512	1024	2048	4096	Noise Coef.	Unit Tested	Size of Wt. (1b) sq. ft.	Surface	Date
Temlock Deluxe	1/2"	4	.12	.24	.39	.31	.31	.32	.30	48" x 54"	1.18	Painted by mfr.	1937
Temlock Deluxe	7/8"	4	.22	.45	.35	.32	.39	.57	.40	48" x 54"	1.19	" "	1937
Temlock Deluxe	1 3/8"	4	.32	.45	.37	.39	.45	.63	.40	48" x 54"	1.95	" "	1937

TELE-COMMUNICATIONS PROTECTION

THE CELOTEX CORPORATION (Cont'd)

Material	Thickness	Mounting (See Footnote)	Noise Coefficients	Size of Unit	Wt. (1b) sq ft	Surface	Date
Acousti-Celotex	11/16"	1	.10 .31 .70 .80 .76 .62	.65 12"x 12"	1.10	Unpainted, perforated 441 holes per sq ft, 3/16" dia., 1/2" deep.	1936
Type C2	Slow burning	5/8"	1 .09 .25 .58 .79 .69	.60 12"x 12"	.89	Unpainted, perforated 441 holes per sq ft, 3/16" dia., 1/2" deep.	1937
Acousti-Celotex	Type C2	Slow burning	2 .09 .65 .61 .78 .75	.70 12"x 12"	1.10	Unpainted, perforated 441 holes per sq ft, 3/16" dia., 1/2" deep.	1936
Acousti-Celotex	11/16"	1	.18 .32 .75 .93 .63	.65 12"x 12"	1.11	R.I. Finish, perforated 441 holes per sq ft, 3/16" dia., 1/2" deep.	1935
Type C2	Slow-burning	13/16"	8 .55 .66 .65 .80 .69	.70 12"x 24"	1.09	R.I. Finish, perforated 441 holes per sq ft, 3/16" dia., 5/8" deep.	1936
Acousti-Celotex	Type C3	13/16"	1 .18 .36 .67 .74 .67	.66 12"x 12"	1.35	R.I. Finish, perforated 441 holes per sq ft, 3/16" dia., 5/8" deep.	1936
Acousti-Celotex	Type C3	Slow-burning	8 .45 .58 .67 .91 .71	.65 12"x 24"	1.06	Unpainted, perforated 441 holes per sq ft, 3/16" dia., 5/8" deep.	1937
Acousti-Celotex	13/16"	8	.17 .48 .97 .72 .56	.41 .65 12"x 12"	1.56	R.I. Finish, perforated 441 holes per sq ft, 3/16" dia., 5/8" deep.	1936
Type C3	Slow-burning	1 1/4"					
Acousti-Celotex	Type C4	1 1/4"	8 .53 .68 .96 .73	.50 .75 12"x 24"	1.44	R.I. Finish, perforated 441 holes per sq ft, 3/16" dia., 1 1/16" deep.	1936
Acousti-Celotex	Type C4	Slow-burning	1 .13 .51 .94 .84	.52 .70 12"x 12"	1.80	Unpainted, perforated 441 holes per sq ft, 3/16" dia., 1 1/16" deep.	1936

THE CELLOTEX CORPORATION (Cont'd)

Material	Thickness Mounting (See Footnote)	Coefficients	Noise Coef. Tested	Size of Unit (1b) sq. ft.	Wt. Unpainted	Surface	Date
Acousti-Celotex 1/2"	1 .10 .17 .63	.68 .66 .72	.55	12"x 12"	1.39	Unpainted, not perforated.	1936
Type MU-1							
Acousti-Celotex 9/16"	1 .11 .29 .68	.74	.82	12"x 12"	1.23	Painted by mfr., perforated .076 holes per sq. ft., 5/32" dia., 1/2" deep.	1936
Type M1							
Acousti-Celotex 1 1/4"	1 .15 .50 .93	.89	.74	.69	.75	Painted by mfr., perforated .076 holes per sq. ft., 5/32" dia., 1 1/8" deep.	1936
Type M3							
Calicel Acoustic Tile	3/4"	1 .07 .21 .62	.90	.75	.60	12"x 12"	-
Calicel Acoustic Tile	1"	1 .09 .26 .74	.97	.78	.84	12"x 12"	2.66
Calicel Acoustic Tile	1"	5 .28 .90 .86	.72	.85	.89	12"x 12"	2.66
Calicel Acoustic Tile	(12" o.c.)						
Calicel Acoustic Tile	1 1/4"	1 .14 .43 .90	.90	.82	.80	12"x 12"	3.42
Calicel Acoustic Tile	1 1/4"	5 .38 .95 .76	.78	.89	.87	12"x 12"	3.42
Calicel Acoustic Tile	(12" o.c.)						
Calistone	2"	4 .12 .45 .87	.82	.76	.67	12"x 12"	9.3
Calistone	2"	5 .46 .91 .71	.75	.84	.72	12"x 12"	9.3
Calistone	(12" o.c.)						
Absorbex Type A	4"	4 .38 .59 .60	.63	.62	.60	18"x 24"	17.8
Absorbex Type A	1"	1 - .22 .45 .87	.91	-	.60	9"x 9"	2.5
Absorbex Type A	1"	2 - .27 .65 .92	.77	-	.65	9"x 9"	2.5
Absorbex Type A on 2"	4 (9" o.c.)	- .39 .80 .96	.92	-	.75	9"x 9" tile on 20"x 64" sheets.	-
1" Absorbex Type F (10 gauge)							Spray painted by mfr.
Absorbex Type A	1"	9 .19 .63 .95	.86	.78	.77	18"x 18"	2.6
Absorbex Type A	1"	2 .19 .33 .80	.86	.80	.83	18"x 18"	2.7
	(18" o.c.)						Kerfed, spray painted 4 coats paint at N.B. of S.

THE CELOTEX CORPORATION (Cont'd)

Material	Thickness	Mounting (See Footnote)	Coefficients				Noise Coef. Unit	Size of Wt. (1b) sq. ft.	Surface	Date
			128	256	512	1024				
Absorber Type C	1"	4	.14	.19	.34	.73	.62	.45	20" x 64"	—
Absorber Type C (14 gauge)	1"	2	.14	.21	.67	.69	.59	.55	20" x 64"	—
Absorber Type F (10 gauge)	1"	2	.66	.17	.47	.65	.53	—	20" x 64"	—
Absorber Type F (8 gauge)	2"	7	.13	.47	.98	.70	.78	.70	20" x 64"	—
<hr/>										
CERTAIN-TINED PRODUCTS CORPORATION										
Kalite, cast on 1/4" backing of moulding plaster, Grade D(fine)	1"	4	.09	.30	.49	.54	.47	.48	.45	24" x 36"
Kalite, cast on 1/4" backing of moulding plaster, Grade A(Coarse)	1"	4	.06	.19	.42	.69	.74	.64	.50	24" x 36"
Kalite, cast on 1/4" backing of moulding plaster, Grade A(Fine)	1 1/2"	4	.20	.39	.59	.61	.60	.67	.55	24" x 36"
Kalite, cast on 1/4" backing of moulding plaster, Grade A(Coarse)	1 1/2"	4	.15	.34	.54	.74	.60	.69	.60	24" x 36"
Kalite, cast on 1/4" backing of moulding plaster, Grade D(Fine)	2"	4	.22	.48	.55	.58	.54	.53	.55	24" x 36"
Kalite, cast on 1/4" backing of moulding plaster, Grade A(Coarse)	2"	4	.23	.55	.73	.67	.64	.62	.65	24" x 36"

Spray painted 4 coats paint at N.B. of S.

CERTAIN-TEED PRODUCTS CORPORATION (Cont'd)

Material	Thickness backing of moulding plaster, Grade A(Coarse)	Mounting (See Footnote)	Coefficients	Noise Coef.	Size of Unit Tested	Wt. sq ft	Surface	Date
Kalite, cast on 1/4"	2"	4	.08 .13 .25 .54	.42	.40	--	Unpainted	1930

R. GUASTAVINO COMPANY

Akoustolith Tile	1"	4	.08 .13 .25 .54	.42	.40	--	Unpainted	1930
Grade D	2"	4	.15 .26 .59 .74	.52	.50	.55	--	Unpainted
Akoustolith Tile	1 1/2"	4	.12 .19 .44 .61	.66	.56	.50	Unpainted	1930
Grade C	2"	4	.19 .26 .53 .64	.70	.56	.55	Unpainted	1930
Akoustolith Tile	1"	4	.09 .17 .46 .77	.77	.58	.55	Unpainted	1932
Grade B-2	1 1/2"	4	.14 .30 .67 .87	.82	.57	.65	Unpainted	1932
Akoustolith Tile	2"	4	.21 .50 .85 .81	.70	.70	.65	Unpainted	1932
Grade B-2	2"	5	.42 .75 .67 .75	.80	.78	.75	Unpainted	1936
Akoustolith Tile	2"	(12" o.c.)	Not nailed					
Grade B-1	1 1/4"	5	Not nailed					
Akoustolith Tile	1 1/4"	4	.41 .83 .78 .72	.78	.82	.80	Unpainted	1936
Grade B-1	1 1/4"	4	(12" o.c.)					
Akoustolith Tile	4"	10	Not nailed					
Grade C	4"	4	.54 .70 .78 .85	.88	.81	.80	Unpainted	1937
Akoustolith Tile	4"	4	.32 .82 .90 .77	.79	.81	.80	Unpainted	1937
Grade C	4"	10	.54 .80 .70 .88	.87	.74	.80	Unpainted	1937
Akoustolith Tile	4"	4	.27 .76 .93 .78	.74	.69	.80	Unpainted	1937
Grade D	4"	4	(Grade D)					

Kalite, cast on 1/4"
backing of moulding
plaster, Grade A(Coarse)

Material
Kalite, cast on 1/4"
backing of moulding
plaster, Grade A(Coarse)

Date
1937

Date
1937

HAWAIIAN CANE PRODUCTS, LTD.

Material	Thickness	Mounting (See Footnote)	Noise Coefficients	Wt. Unit Tested	Size of Surface sq ft	Date
Hawaiian Cane Tile	1"	1	.10 .40 .59 .78 .77 .79	.65 11 1/2" x 11 1/2"	0.75 Unpainted	1933
Hawaiian Cane Tile	1"	2	.24 .70 .40 .48 .54 .60	.55 12" x 12"	.81 Unpainted	1935

Insulite Acoustile Type 44	1 3/4"	4	.26 .42 .50 .57 .61 .59	.55	12" x 12"	1.47	Unpainted	1931
----------------------------	--------	---	-------------------------	-----	-----------	------	-----------	------

JOHNS-MANVILLE SALES CORPORATION

Nashkote A	1/2"	1	.05 .13 .25 .26 .20 .15	.20 36" x 48"	--	Painted 2 coats oil paint.	1929
Nashkote A	1/2"	1	.08 .15 .43 .62 .65 .58	.45 36" x 48"	--	Same as above except membrane perforated with fine holes after painting.	1929
Nashkote A	3/4"	1	.09 .16 .27 .30 .23 .23	.25 36" x 48"	--	Painted 2 coats oil paint.	1929
Nashkote A	3/4"	1	.11 .21 .51 .68 .71 .68	.55 36" x 48"	--	Same as above except membrane perforated with fine holes after painting.	1929
Nashkote A	1"	1	.12 .20 .33 .33 .28 .28	.30 36" x 48"	--	Painted 2 coats oil paint.	1929
Nashkote A	1"	1	.13 .26 .58 .73 .77 .71	.60 36" x 48"	--	Same as above except membrane perforated with fine holes after painting.	1929
Nashkote B-332	1/2"	1	.09 .15 .31 .52 .74 .63	.45 36" x 48"	--	Covered with perforated membrane.	1929
Nashkote B-332	3/4"	1	.12 .21 .40 .63 .81 .73	.50 36" x 48"	--	Covered with perforated membrane.	1929
Nashkote B-332	1"	1	.19 .26 .51 .73 .89 .77	.60 36" x 48"	--	Covered with perforated membrane.	1929
Sound Isolation Blanket (Rockwool)	-	4	.11 .58 .85 .83 .81 .83	.75 12" x 12"	1.5 Metal lath.		1932
Transite Acoustical Tile	1 1/8"	4	.19 .39 .77 .74 .70 .55	.65 12" x 12"	3.0 Transite, perforated 576 holes per sq ft, diameter 5 32".		1931

LJUSE STEVENSON CO.

Material	Thickness ness	Mounting (See Footnote)	Coefficients	Noise Coef.	Size of Wt. Unit Tested sq. ft.	Surface	Date
Lusco Hair Felt	1"	4	.06 .27	.57 .77	.81 .60	4'x 9' No surface covering	1934

MAIZEWOOD PRODUCTS CORPORATION

Maizewood Tile	1 1/2"	4	.23 .41	.63 .79	.70 .62	.65 12"x 12"	2.1 12 saw cuts across tile 1" deep,
Maizewood Tile	1 1/2"	4	.21 .41	.64 .73	.70 .58	.60 12"x 12"	2.1 Same sample as above painted 1 coat glue size, 2 coats lead and oil at N.E. of S.

NATIONAL GYPSUM COMPANY							
Acoustolic (Maftex)	1/2"	5	.44 .24	.31 .44	.48 .37	.35	- -
Acoustolic	1/2"	5	- .29	.28 .41	- -	- -	- -
Acoustolic	1/2"	5	- .40	.33 .51	.38 .37	.35	- -
Acoustex	7/8"	4	- .19	.41 .72	- -	- 12"x 12"	2.06 - -
Acoustex	1 1/8"	4	- .25	.53 .79	- -	- 12"x 12"	2.6 - -
Acoustex	1 1/8"	5	- .74	.88 .63	- -	- 12"x 12"	2.6 - -
Acoustex Type 50R	15/16"	2 (1"x 3" furring)	.14 .32	.77 .91	.78 .79	.70 12"x 12"	2.16 Unpainted
Acoustex Type 50R	15/16"	2 (1"x 2" furring)	.10 .34	.84 .95	.75 .98	.70 12"x 12"	2.16 Unpainted
Acoustex Type 50R	15/16"	1	.11 .24	.54 .87	.80 .75	.60 12"x 12"	2.16 Unpainted
Acoustex Type 60R	1"	1	.07 .24	.55 .87	.86 .88	.65 12"x 12"	2.16 Unpainted
Acoustex Type 60R	1"	2	.11 .33	.77 .92	.70 .96	.70 12"x 12"	2.07 Unpainted

THE SPHINX ACOUSTICAL COMPANY

Material	Thickness	Mounting (See Footnote)	Coefficients	Noise Coef.	Wt. Unit Tested	Size of Surface	Date
Sphinxstone	2"	4	.10 .33 .78 .87 .71 .70	.65	18"x 24"	- - Unpainted	1932

UNITED STATES GYPSUM COMPANY

Acoustone Type D	3/4"	1	.10 .36 .73 .78 .75 .76	.65	12"x 12"	1.26	Unpainted
Acoustone Type D	1"	1	.13 .48 .85 .83 .80 .85	.75	12"x 12"	1.73	Unpainted
Quietile Type 80	1"	4	.06 .47 .76 .74 .72 .76	.65	12"x 12"	0.81	Unpainted, brush finish.
Red Top Acoustic Tile	1/2"	1	.14 .22 .40 .48 .52 .51	.40	12"x 12"	0.55	Unpainted
Thermofil	3"	4	.43 .39 .66 .78 .81 .93	.65	— —	—	No surface covering.
U. S. Gypsum Metal Tile, Rockwool pad.	1 1/2"	4	.12 .56 .91 .87 .78 .70	.80	12"x 12"	1.03	Painted by mfr., perforated 2401 holes per sq ft

WOOD CONVERSION COMPANY

Balsam Wool	1"	4	.18 .36 .55 .65 .67 -	.55	- -	.29	Scrim facing
Krexstone Tile (Balsam Wool)	1"	6	.12 .24 .62 .73 .75 .78	.60	12"x 12"	0.85	Screen wire
Nuwood Bevel Lap Tile	1/2"	6	.12 .19 .30 .40 .40 .51	.30	12"x 12"	0.69	Unpainted
Nuwood Bevel Lap Tile	1"	6	.14 .19 .37 .37 .41 .56	.35	12"x 12"	1.41	Unpainted

FOOTNOTES:

1. Cemented to gypsum wall board. This is considered equivalent to cementing to plaster or masonry.
2. Nailed on 13/16" x 2" furring 12" o.c. unless otherwise indicated.
3. Metal supports attached to 13/16" x 2" wood furring.
4. Laid directly on laboratory floor. As a rule the results obtained this way are the same as when the tile is cemented to gypsum wall board.
5. Nailed on 2 x 4's o.c. unless otherwise indicated.
6. Cemented to the floor of the reverberation chamber.
7. Back of sample covered with concrete.
8. Attached to metal suspension system. 4" air space back of tile.
9. Acoustic tile nailed to 13/16" x 2" furring 18" o.c. Space between furring filled with Rockwool.
10. Laid on 2 x 8's 12" o.c.

Table 2
Acoustical Plasters

Unless otherwise stated each sample of acoustical plaster was mixed according to the specifications furnished by the manufacturers and applied by a skilled plasterer on a false ceiling at the N.B.of S. The panels were laid on the floor of the Reverberation Chamber for test.

CERTAIN-TEED PRODUCTS CORPORATION

Material	Thickness	Coefficients	Noise Coef.	No. of Coats	Base Coat		Application	Treatment	Surface Date
					Noise	No. Coats			
Kalite H Coarse Aggregate	1/2"	.36 .33 .45	.70	.68	.55	1st coat 3/8"	Gypsum plaster on metal lath, attached to 1"	1st coat applied to dry base coat. 2nd coat applied 1 hr. after 1st coat.	Finished 1935 with steel trowel.
Kalite H Coarse Aggregate	1/2"	.26 .31 .45	.67	.65	.50	1st coat 3/8"	Same sample as above.	Brush painted 2 coats non- biting lacquer.	1936
Kalite H Coarse Aggregate	5/4"	.43 .38 .63	.78	.65	.50	1st coat 5/8"	Gypsum plaster on metal lath	1st coat applied to dry base coat. 2nd coat applied 1 hr. after 1st coat.	Finished 1935 with steel trowel.
Hus-Lite Acoustic Plaster	1/2"	.13 .24 .45	.71	.56	.49	1st coat 1/4"	Gypsum plaster on metal lath.	1st coat applied to dry base coat. 2nd coat applied 24 hrs. after 1st coat.	Finished 1935 with steel trowel.
Hus-Lite Acoustic Plaster	5/8"	.16 .34 .50	.53	.43	.37	.45	1st coat 3/8"	Gypsum plaster on metal lath.	1st coat applied to dry base coat. 2nd coat applied 24 hrs. after 1st coat.
									1937

CLEVELAND GYPSUM SUPPLY COMPANY

E. GUASTAVINO COMPANY

Material	Thickness	Coefficients			Noise Coef.	No. Coats	Base Coat	Application	Surface Treatment	Date
Akoustolith Plaster	1/4"	.13	.21	.19	.23	.33	.45	.25	1 coat	Gypsum plaster
Akoustolith Plaster	3/4"	.20	.26	.35	.56	.59	.45	.45	1 coat	Gypsum plaster

Akoustolith Plaster
See mfg. directions.
Akoustolith Plaster
See mfg. directions.

HACHMEISTER - LIND COMPANY

Hachmeister-Lind Acoustic Plaster	1/2"	.15	.19	.25	.30	.44	.49	.30	1st coat 2nd coat 1/4"	Gypsum plaster
<hr/>										

NATIONAL GYPSUM COMPANY

Macoustic Plaster (Trowel Finish)	1/2"	.15	.27	.42	.45	.45	.36	.29	.40	1st coat 2nd coat 1/4"	3/4"	1st coat applied to half green base	Finished with steel trowel.
Macoustic Plaster (Trowel Finish)	1/2"	.17	.27	.52	.76	.66	.55	.55	.55	1st coat 2nd coat 1/4"	3/4"	1st coat applied to dry base coat.	Finished with steel trowel.
Macoustic Plaster (Trowel Finish)	3/4"	.25	.41	.67	.63	.52	.47	.55	.55	1st coat 2nd coat 3/8"	3/8"	1st coat applied to dry base cont.	Finished with steel trowel.

NATIONAL GYPSUM COMPANY (Cont'd)

Thickness	Noise Coef.	No.	Base	Coat	Application	Surface Treatment	Date
Material	Coeficients		Coats				
Flockwall Acoustic Plaster	1/2"	.13 .20 .35 .65 .70 .64 .50	2048 4096	1st coat 1/4"	3/4"	1st coat applied to dry base coat.	Finished 1935 with steel trowel.
				2nd coat 1/4"		2nd coat applied on metal 3 hours after lath.	
				1st coat.		1st coat.	

NEWARK PLASTER COMPANY

Acoustic Plaster	1/2"	.09 .23 .47 .77 .71 .75 .55	1st coat 1/4"	3/4"	1st coat applied to dry base coat.	Finished 1937 with steel trowel.
			2nd coat 1/4"		2nd coat applied on metal 24 hours after lath.	
			1st coat.		1st coat.	

PACIFIC PORTLAND CEMENT CO.

Calacoustic Plaster	1/2"	.15 .23 .44 .67 .66 .39	1st coat 1/4"	3/4"	1st coat applied to dry base coat.	Finished 1935 with cork float.
			2nd coat 1/4"		2nd coat applied on metal 72 hrs. after 1st coat.	
			lath.		lath. coat.	

UNITED STATES GYPSUM COMPANY

Sabinite Plaster	1/2"	.14 .24 .27 .38 .49 .64	1st coat 1/4"	.35 .55	Gypsum plaster.	1st coat applied to dry base coat.	Floated 1931 with cork float.
			2nd coat 1/4"			2nd coat applied after 1st coat had set and partly dried.	
			1st coat 1/4"		1st coat applied to dry base coat.	1st coat applied to dry base coat.	Floated 1935 with cork float.
			2nd coat 1/4"		2nd coat applied 24 hrs. after 1st coat.	2nd coat applied 24 hrs. after 1st coat.	

UNITED STATES GYPSUM COMPANY (Cont'd)

Material	Thickness	Coefficients of Noise	No. of Coats	Base Coat	Application	Treatment	Date
Sabbinite Plaster A	$\frac{3}{4}$ "	128 250 512 1024 2048 4096	.60	1st coat applied $\frac{1}{4}$ " Gypsum 2nd coat plaster $\frac{1}{4}$ " 3rd coat lath. $\frac{1}{4}$ "	1st coat applied on dry base coat. 2nd coat applied 48 hrs. after 1st coat. 3rd coat applied 72 hrs. after 2nd coat.	Flocked with cork float.	1935
Sabbinite Plaster F	$\frac{1}{2}$ "	.19 .22 .43 .30 .75 .55	.60	1st coat $\frac{1}{4}$ " Gypsum 2nd coat plaster $\frac{1}{4}$ " on metal lath	1st coat applied on dry base coat. 2nd coat applied 48 hrs. after 1st coat.	Flocked with cork float.	1936

Table 2

Audience seated in chairs of various types

- A - cane seat chairs, open back
- B - theatre chairs, box spring seat, heavily padded back
- C - same as B, but single layer of padding on back
- D - church pews, seating five

Absorption per person *

		128	256	512	1024	2048	Date
Women without coats,	A	0.7	1.3	2.3	3.6	4.6	1930
Women with coats,	A	1.3	2.4	4.0	5.8	6.7	1930
Men without overcoats,	A	1.3	2.1	4.1	5.5	7.4	1930
Men with overcoats,	A	2.3	3.2	4.8	6.2	7.6	1930
Mixed audience,	B			3.9	4.7		1929
Empty seat,	B	3.4	3.0	3.3	3.6	3.6	1929
Mixed audience,	C		3.5	4.1	4.9	4.2	1930
Empty seat,	C	3.0	2.5	2.9	3.1	3.1	1929
Mixed audience.	D	2.7	3.3	3.8	3.6	3.6	1930
Plywood Chair,		0.2	0.3	0.5	0.5	0.5	1930

* These figures are numerically equal to the number of square feet of a material having an absorption coefficient of 1.00, which would absorb the same amount of sound energy.

Suggestions Concerning the Proper Use
of Acoustical Material

As there has been considerable misconception as to the proper use of acoustical material it is considered desirable to call attention to two of the fundamental principles underlying the formulas which are used in acoustical design. It is assumed in all of the formulas that (1) the absorption is proportional to the area of the absorbing material and that (2) there is a uniform distribution of sound energy. As a rule neither one of these assumptions is true.

It has been found from experiment when very small areas are used, such as the panels in a coffered ceiling having areas from 1 to 4 square feet and separated from each other by a foot or more, that the effective absorption of the material in these panels is greater than when the material is installed in one large area. In fact, for materials having large coefficients, this effective absorption may be as much as 50 percent more than one would expect from the coefficient.

It has also been found when all of the acoustical material is applied on one surface of a relatively small room, say 50,000 cubic feet or under, that this creates a non-uniform distribution of sound energy in the following manner. Let us assume that the ceiling of a room is covered with a highly absorbent material. Under these conditions the sound energy which is traveling between the floor and ceiling is absorbed quite rapidly, while that traveling between the untreated wall surfaces, having very little to absorb it, may continue for some considerable time. This persistence of sound energy between the untreated surfaces may cause the measured reverberation time to be considerably longer than would be computed using the ordinary reverberation formula and the coefficient usually given. For this reason, it is essential in small rooms that the acoustical material be distributed on the side walls as well as on the ceiling, if the effective absorption of the material is to be anywhere near that which one would expect from the coefficient of the material.

We also wish to call attention to the fact that a proper distribution of the acoustical material should be worked out in the initial plans of a building, as it is frequently impossible to obtain a satisfactory distribution after the interior design has been completed without taking into account the acoustical treatment.

