

NSRDS-NBS 61, Part V

U.S. DEPARTMENT OF COMMERCE / National Bureau of Standards

NBS PUBLICATIONS



## NATIONAL BUREAU OF STANDARDS

The National Bureau of Standards<sup>1</sup> was established by an act of Congress on March 3, 1901. The Bureau's overall goal is to strengthen and advance the Nation's science and technology and facilitate their effective application for public benefit. To this end, the Bureau conducts research and provides: (1) a basis for the Nation's physical measurement system, (2) scientific and technological services for industry and government, (3) a technical basis for equity in trade, and (4) technical services to promote public safety. The Bureau's technical work is performed by the National Measurement Laboratory, the National Engineering Laboratory, and the Institute for Computer Sciences and Technology.

THE NATIONAL MEASUREMENT LABORATORY provides the national system of physical and chemical and materials measurement; coordinates the system with measurement systems of other nations and furnishes essential services leading to accurate and uniform physical and chemical measurement throughout the Nation's scientific community, industry, and commerce; conducts materials research leading to improved methods of measurement, standards, and data on the properties of materials needed by industry, commerce, educational institutions, and Government; provides advisory and research services to other Government agencies; develops, produces, and distributes Standard Reference Materials; and provides calibration services. The Laboratory consists of the following centers:

Absolute Physical Quantities<sup>2</sup> — Radiation Research — Thermodynamics and Molecular Science — Analytical Chemistry — Materials Science.

**THE NATIONAL ENGINEERING LABORATORY** provides technology and technical services to the public and private sectors to address national needs and to solve national problems; conducts research in engineering and applied science in support of these efforts; builds and maintains competence in the necessary disciplines required to carry out this research and technical service; develops engineering data and measurement capabilities; provides engineering measurement traceability services; develops test methods and proposes engineering standards and code changes; develops and proposes new engineering practices; and develops and improves mechanisms to transfer results of its research to the ultimate user. The Laboratory consists of the following centers:

Applied Mathematics — Electronics and Electrical Engineering<sup>2</sup> — Mechanical Engineering and Process Technology<sup>2</sup> — Building Technology — Fire Research — Consumer Product Technology — Field Methods.

**THE INSTITUTE FOR COMPUTER SCIENCES AND TECHNOLOGY** conducts research and provides scientific and technical services to aid Federal agencies in the selection, acquisition, application, and use of computer technology to improve effectiveness and economy in Government operations in accordance with Public Law 89-306 (40 U.S.C. 759), relevant Executive Orders, and other directives; carries out this mission by managing the Federal Information Processing Standards Program, developing Federal ADP standards guidelines, and managing Federal participation in ADP voluntary standardization activities; provides scientific and technological advisory services and assistance to Federal agencies; and provides the technical foundation for computer-related policies of the Federal Government. The Institute consists of the following centers:

Programming Science and Technology - Computer Systems Engineering.

Headquarters and Laboratories at Gaithersburg, MD, unless otherwise noted;

mailing address Washington, DC 20234.

Some divisions within the center are located at Boulder, CO 80303.

JUL 7 1982

# Physical Properties Data Compilations Relevant to Energy Storage.

V. Mechanical Properties Data on Alloys for Use in Flywheels

N-REL- NRE 101 Part 7

H. M. Ledbetter

Fracture and Deformation Division National Bureau of Standards Boulder, Colorado 80303





U.S. DEPARTMENT OF COMMERCE, Malcolm Baldrige, Secretary NATIONAL BUREAU OF STANDARDS, Ernest Ambler, Director

Issued January 1982

2:武治1 - 【共文:24)。 「清江市長」「明日望」 つ 「「京臣新校で」」

#### Library of Congress Cataloging in Publication Data

Ledbetter, H. M. Mechanical properties data on alloys for use in flywheels.
(Physical properties data compilations relevant to energy storage; V) (NSRDS-NBS; 61, pt. V)
1. Alloys. 2. Fly-wheels. I. Title. II. Series. III. Series: NSRDS-NBS; 61, pt. V.
QC100.U573 no. 61, pt. V 602'.18s 81-14053
[TA460] [620.1'6] AACR2

## NSRDS-NBS 61, Part V

Nat. Stand. Ref. Data Ser., Nat. Bur. Stand. (U.S.), 61, Part V, 42 pages (Jan. 1982) CODEN: NSRDAP

© 1982 by the Secretary of Commerce on Behalf of the United States Government

## U.S. GOVERNMENT PRINTING OFFICE WASHINGTON: 1982

## Foreword

The National Standard Reference Data System provides access to the quantitative data of physical science, critically evaluated and compiled for convenience and readily accessible through a variety of distribution channels. The System was established in 1963 by action of the President's Office of Science and Technology and the Federal Council for Science and Technology, and responsibility to administer it was assigned to the National Bureau of Standards.

NSRDS receives advice and planning assistance from a Review Committee of the National Research Council of the National Academy of Sciences-National Academy of Engineering. A number of Advisory Panels, each concerned with a single technical area, meet regularly to examine major portions of the program, assign relative priorities, and identify specific key problems in need of further attention. For selected specific topics, the Advisory Panels sponsor subpanels which make detailed studies of users' needs, the present state of knowledge, and existing data resources as a basis for recommending one or more data compilation activities. This assembly of advisory services contributes greatly to the guidance of NSRDS activities.

The System now includes a complex of data centers and other activities in academic institutions and other laboratories. Components of the NSRDS produce compilations of critically evaluated data, reviews of the state of quantitative knowledge in specialized areas, and computations of useful functions derived from standard reference data. The centers and projects also establish criteria for evaluation and compilation of data and recommend improvements in experimental techniques. They are normally associated with research in the relevant field.

The technical scope of NSRDS is indicated by the categories of projects active or being planned: nuclear properties, atomic and molecular properties, solid state properties, thermodynamic and transport properties, chemical kinetics, and colloid and surface properties.

Reliable data on the properties of matter and materials are a major foundation of scientific and technical progress. Such important activities as basic scientific research, industrial quality control, development of new materials for building and other technologies, measuring and correcting environmental pollution depend on quality reference data. In NSRDS, the Bureau's responsibility to support American science, industry, and commerce is vitally fulfilled.

E. Ambler.

ERNEST AMBLER, Director

# Preface

This series of publications is aimed at providing physical properties data on materials used in energy storage systems. It was inspired by a requirement in the Department of Energy's Division of Energy Storage Systems for materials property data needed by its contractors in the timely development of energy storage devices. As prime contractor for this program, the Lawrence Livermore Laboratory (LLL) has requested the Office of Standard Reference Data (OSRD) to manage the task of gathering the data, using its established network of data centers and other identified sources of expertise. The OSRD monitors the progress of work, reviews the results, and conveys the numerical data to LLL where the data are converted for entry into an automated data storage and retrieval system. Every effort is made to supply data which have been critically examined in light of the latest knowledge concerning theory and experiment. However it must be recognized that in a rapidly moving technology some of the data via computer terminal as well as publication in this series should help provide the practitioner with timely and useful data which he requires to solve his problems in energy storage. Funding for this series of projects from the Department of Energy, Division of Energy Storage, through the Lawrence Livermore Laboratory, is gratefully acknowledged.

Previous publications in the series "Physical Properties Data Compilations Relevant to Energy Storage":

- Janz, G. J., Allen, C. B., Bansal, N. P., Murphy, R. M., and Tomkins, R. P. T., Physical Properties Data Compilations Relevant to Energy Storage. II. Molten Salts: Data on Single and Multi-Component Salt Systems, Nat. Stand. Ref. Data Ser., Nat. Bur. Stand. (U.S.), 61, Part II, 442 pp. (Apr. 1979).
- Miller, G. R., and Paquette, D. G., Physical Properties Data Compilations Relevant to Energy Storage. III. Engineering Properties of Single and Polycrystalline Sodium Beta and Beta" - Alumina, Nat. Stand. Ref. Data. Ser., Nat. Bur. Stand. (U.S.), 61, Part III, 19 pp. (June 1979).
- Janz, G. J., and Tomkins, R. P. T., Physical Properties DataCompilations Relevant to Energy Storage. 1V. Molten Salts: Data on Additional Single and Multi-Component Salt Systems, Nat. Stand. Ref. Data Ser., Nat. Bur. Stand. (U.S.), 61, Part IV, 870 pp. (July 1981).

Janz, George J., Allen, Carolyn B., Downey, Joseph R., Jr., and Tomkins, R. P. T., Physical Properties Data Compilations Relevant to Energy Storage. I. Molten Salts Eutectic Data, Nat. Stand. Ref. Data Ser., Nat. Bur. Stand. (U.S.), 61, Part I, 244 pp. (March 1978).

# Contents

ł	,	a	υ	P	
1		a	۶	, C	

1.	Introduction	1
2.	Metallurgical Descriptions of Alloys	1
3.	Properties of Interest	7
4.	Data Collection	8
5.	Data Analysis	8
6.	Results	9
7.	Discussion	9
8.	Acknowledgment	9
Table	28	10
Appe	ndix 1	31
Appe	ndix 2	32

# Physical Properties Data Compilations Relevant to Energy Storage. V. Mechanical Properties Data on Alloys for Use in Flywheels H. M. Ledbetter

Fracture and Deformation Division, National Bureau of Standards, Boulder, CO 80303

This report deals with the physical and mechanical properties of 21 commercial alloys that are candidates for flywheel rotors used as inertial-energy-storage systems. Base metals include aluminum, iron, and titanium. Alloys vary in complexity from simple carbon steels to superalloys. Properties include: mass density, Young's modulus, shear modulus, bulk modulus, Poisson's ratio, yield strength, ultimate strength, fatigue strength, fracture toughness, and creep strength. Property values were collected from many types of sources and were analyzed statistically to detect possible outlying values. For each alloy, the report contains typical chemical composition, typical heat treatment, metallurgical descriptions, and typical property values. The report also shows the variations of these properties and the relative abundances of experimental property values.

Key words: alloy; aluminum alloy; elastic constants; flywheel; iron alloy; mass density; mechanical property; titanium alloy.

#### 1. Introduction

Materials considered here are candidate alloys for flywheel rotors used as inertial-energy-storage systems. The purpose of this study was to determine values of particular physical and mechanical properties of alloys. This was done by compiling data from the engineeringscience literature, analyzing the data statistically, discarding "poor" values, and in most cases identifying the trimmed arithmetic mean as the "best" value. In all, 21 commercial alloys were examined:

- (1) aluminum alloy 6061-T6
- (2) aluminum alloy 7075-T6
- (3) titanium-6aluminum-4vanadium
- (4) alloy steel 4340
- (5) maraging steel 18Ni-300
- (6) precipitation-hardened stainless steel 15-7
- (7) aluminum alloy 2024
- (8) carbon steel 1020
- (9) carbon steel 1040
- (10) precipitation-hardenable stainless steel AM 355
- (11) hardenable stainless steel 440C
- (12) wrought stainless steel custom 455
- (13) tool steel H-11
- (14) titanium-6aluminum-6vanadium

- (15) titanium-8molybdenum-8vanadium
- (16) resulfurized carbon steel C1141
- (17) austenitic Cr-Ni stainless steel 316
- (18) iron-based superalloy A286
- (19) maraging steel 18Ni-400
- (20) iron-based superalloy V57
- (21) unitemp 212.

These alloys are described metallurgically in section 2 of this report. Table 1 gives their brief descriptions, chemical compositions, and usual heat treatments.

## 2. Metallurgical Descriptions of Alloys

Aluminum alloy 6061-T6. This alloy has intermediate strength but excellent corrosion resistance and high plane-strain fracture toughness. It is readily welded by either the GTA or GMA process and with 4043 filler reheat treated welds has approximately the same tensile strength as the parent metal. Fusion welds have excellent corrosion resistance. Resistance welding is difficult and requires special care. Typical applications of 6061 are heavy-duty structures requiring high resistance to corrosion such as truck bodies, marine structures, railroad tank cars, and pipelines. The alloy is available

UNS Number <sup>a</sup>	Description	Chemical Composition	Usual Heat Treatment
A96061	Wrought aluminum alloy, heat treatable	Al bal, Cr 0.04-0.35, Cu 0.15-0.40, Fe 0.7 max, Ag 0.8-1.2, Mn 0.15 max, Si 0.40-0.8, Ti 0.15 max, Zn 0.25 max, Others each 0.05 max, total 0.15 max	Solution treat at 529°C (985°F) and artificially age at 160°C (320°F) for 18h (T6 plate)
A97075	Wrought aluminum alloy, heat treatable	Al bal, Cr 0.18-0.35, Cu 1.2-2.0, Fe 0.50 max, Mg 2.1-2.9, Mn 0.30 max, Si 0.40 max, Ti 0.20 max, Zn 5.1-6.1, Others each 0.05 max, total 0.15 max	Solution heat treat at 482°C (900°F) and artificially age at 121°C (250°F) for 24h (T6 plate)
	Wrought titanium alloy, heat treatable	Al 5.5-6.75, C 0.10 max, Fe 0.40 max, H 0.015 max, N 0.07 max, 0 0.30 max, V 3.5- 4.5	Solution treat at 816-941°C (1500-1750°F) 15-30 min, water quench, artificially age at 482-538°C (900-1000°F) for 4-8 h, air cool
G43400	Alloy steel	C 0.38-0.43, Cr 0.70-0.90 Mn 0.60-0.80, Mo 0.20-0.30, M1 1.65-2.00, P 0.035 max, Si 0.20-0.35, S 0.040 max	Austenitized at 829-899°C (1525-1650°F), oil quench, temper at 399-632°C (750- 1170°F)
	18Ni 300 maraging steel	Al 0.10, B 0.003, Ca 0.05, C 0.03 max, Co 9.0, Mn 0.10 Mo 4.80, Ni 18.50, P 0.01 max, Si 0.10 max, S 0.01 max, Ti 0.60, Zr 0.02	Solution anneal at 816°C (1500°F) for lh/in, air cool, age at 482°C (900°F) for 3h
S15700	Precipitation harden- able Cr-Ni-Mo-Al stain- less steel	A1 0.75-1.50, C 0.09 max, Cr 14.00-16.00, Mn 1.00 max, Mo 2.00-3.00, Ni 6.50-7.75, P 0.04 max, Si 1.00 max, S 0.03 max	Austenitize at 760-954°C (1700-1750°F), cool rapidly
A92024	Wrought aluminum alloy, heat treatable	Al ba <sup>1</sup> , Cr 0.10 max, Cu 3.8- 4.9, Fe 0.50 max, Mg 1.2-1.8, Mn 0.30-0.9, Si 0.50 max, Zn 0.25 max, Other each 0.05 max, total 0.15 max	Solution treat at 493°C (920°F and artificially age at 191°C (375°F) for 8-16 h depending on product; cold deformation after solution treatment de- pending on product
G10200	Carbon steel	C 0.18-0.23, Mn 0.30-0.60, P 0.040 max, S 0.050 max, Other sheets and plates, C 0.17-0.23	Hot rolled: 899°C (1650°F) for 1 h, air cool; annealed: 899°C (1650°F) for 1 h, fur- nace cool; quenched and tem- pered: 899°C (1650°F), water quench, temper at 204°C (400°F to 427°C (800°F) for 1 h, air cool
G10400	Carbon steel	C 0.37-0.44, Mn 0.60-0.90, P 0.040 max, S 0.050 max, Other sheets, C 0.36-0.44	Hot rolled: 843°C (1550°F) for 1 h, air cool; annealed: 843°C (1550°F) for 1 h, fur- nace cool
535500	Cr-Ni-Mo stainless steel, precipitation hardenable (AM 355)	C 0.10-0.15, Cr 15.00-16.00, Mn 0.50-1.25, Mo 2.50-3.25, N 0.07-0.13, Ni 4.00-5.00, P 0.040 max, S 0.030 max, Si 0.50 max	Double aged: solution anneal, age at 732°C (1350°F) 1-2 h, air cool, age at 454°C (850°F) 1-2 h
544004	Stainless steel, hardenable (440 C)	C 0.95-1.20, Cr 16.00-18.00, Mn 1.00 max, Mo 0.75 max, P 0.040 max, S 0.030 max, Si 1.00 max	, Solution anneal at 917°C (1700°F) 1 h, oil quench, tem- per 2 h at 316°C (600°F), 538° (1000°F) or 760°C (1400°F), and air cool
545500	Stainless steel, wrought precipitation harden- able (custom 455)	C 0.05 max, Cb 0.10-0.50, Cr 11.00-12.50, Cu 1.50-2.50, Mn 0.50 max, Mo 0.50 max, Ni 7.50-9.50, P 0.040 max, S 0.030 max, Si 0.50 max, Ti 0.80-1.40	Solution treat at 816°C (1500° for 30 min, age at 482°C (900° 510°C (950°F), 538°C (1000°F), or 566°C (1050°F) for 4 h, air cool
T20811	Tool steel, hot-work (H-ll)	C 0.33-0.43, Cr 4.75-5.50, Mn 0.20-0.50, Mo 1.10-1.60, P 0.030 max, S 0.030 max, Si 0.80-1.20, V 0.30-0.60	Solution treat at 1010°C (1850 F), for 1 h, temper twice at 510°C (950°F), 538°C (1000°F), 593°C (1100°F), 621°C (1150°F) or 704°C (1300°F) for 1 to 2 h each, air cool

Table 1.	Description	of	alloys,	chemical	compositions,	and	heat	treatments.
----------	-------------	----	---------	----------	---------------	-----	------	-------------

С

#### Table 1. - Continued

UNS NUMBER <sup>a</sup>	Description	Chemical Composition	Usual Heat Treatment
	Wrought titanium alloy, heat treatable (Ti-6Al-6V)	Al 5.0-6.0, C 0.05 max, (1) Cu 0.35-1.0, Fe 0.35- 1.0, H 0.015 max, N 0.04 max, 0 0.2 max, Sn 1.5- 2.5, Ti bal. V 5.0-6.0 (2)	Solution treat at 816 to $949^{\circ}C$ (1500 to $1740^{\circ}F$ ) $1/2 - 4h$ , water quench or air cool, age at 482 to $871^{\circ}C$ (900 to $1600^{\circ}F$ ) 1 - 8 h, air cool Anneal at 704 to $982^{\circ}C$ (1300 to $1800^{\circ}F$ ) $1 - 8 h$ , air or furnace cool.
	Wrought titanium alloy, heat treatable (Ti-8Mo-8V)	Al 2.5-3.5, C 0.05 max, (1) Fe 1.75-2.25, H 0.015 max, Mo 7.5-8.5, O 0.10- 0.18, V 7.5-8.5 (2)	<pre>Solution treat at 774 to 816°C (1425 to 1500°F) 1/6 - 1 h, air cool or water quench, at 427 to 649°C (800 to 1200°F) 1 - 24 h, air cool ) Cold roll 9 to 50% (usually 25%), solution treat at 760 to 816°C (1400 to 1500°F) for 1/6 - 1/4 h, air cool, age at 427 to 649°C (800 to 1200°F) 8 - 24 h, air cool</pre>
G11410	Resulfurized carbon steel (Cll41)	C 0.37-0.45, Mn 1.35-1.65, P 0.040 max, S 0.08-0.13	Heat to 816 to 843°C (1500 to 1550°F), oil quench, temper at 204 to 704°C (400 to 1300°F)
S31600	Austenitic Cr-Ni stainless steel	C 0.08 max, Cr 16.0-18.0, Mn 2.0 max, Mo 2.0-3.0, Ni 10.0-14.0 max, P 0.045 max, S 0.030 max, Si 1-0 max	Anneal at 1038 to 1177°C (1900 to 2150°F), Cool rapidly
K66286	Iron-base superalloy (A286)	Al 0.35 max, 8 0.001-0.01, C 0.08 max, Cr 13.5-16.0, Mn 2.0 max, Mo 1.0-1.5, Ni 24.0-27.0, P 0.04 max, S 0.03 max, Ti 1.9-2.35, V 0.1-0.5	Solution treat at 899 to 982°C (1650 to 1800°F) 1/2 -1 h, oil quench, age at 704 to 760°C (1300 to 1400°F) 16 h, air cool
	18Ni-400 maraging steel <sup>b</sup>	A1 0.12, B 0.003, Ca 0.05, (1 C 0.01, Co 11.50, Fe bal. M0 4.69, Ni 18.0 Mn 0.01, P 0.004, S 0.005, Si 0.003, Ti 1.33, Zr 0.008 (	<ul> <li>) Solution treat at 760 to 816°C (1400 to 1500°F) 1/4 - 1 h, air cool, age at 510°C (950°F) 3 - 10 h, air cool</li> <li>2) Cold deform 25-60%, solution treat at 760 to 816°C (1400 to 1500°F), 1/4 - 1 h, air cool, age at 454 to 593 °C (850-1100°F) 3 - 8 h</li> <li>3) Solution treat 816°C (1500°F) 1 h, air cool, age at 454 to 482°C (850 to 900°F) 3 h, air cool</li> </ul>
	Iron-base superalloy (V57)	Al 0.25, B 0.008, C 0.06, Cr 15.0, Fe bal. Mn 0.25 Mo 1.25, Ni 25.50, Si 0.55, Ti 3.0, V 0.25	Solution treat at 982°C (1800°F) 2 - 4 h, oil quench, age at 732°C (1350°F) 16 h, air cool
	Iron-base superalloy (unitemp 212)	B 0.01, C 0.05-0.15, Cb 0.6, Cr 15.0-17.0, Ni 23.0-27.0, Si 0.15, Ti 4.0, Zr 0.07, Al 0.15	Solution treat at 1010°C (1850°F) 2 h, water quench, double age at 774°C (1425°F) 2 h, air cool, 677°C (1250°F) 16 h, air cool

<sup>a</sup>Unified Numbering System for Metals and Alloys (Society of Automotive Engineers, Warrendale, Penn., Second Ed., 1977).
 <sup>b</sup> Properties quoted are actually for 350-grade.

in all commercial forms and in various sizes. Sheet and plate are available clad with 7072.

Aluminum alloy 7075-T6. This heat-treatable aluminum alloy contains zinc, magnesium, and copper for hardness and has very high strength under static conditions in the T6 temper. It is available in a large range of forms and sizes. In the annealed-and-solution-treated condition it has good formability at ambient temperatures, and in the T6 condition it has good formability at elevated temperatures. The T6 temper has low fracture toughness at room and cryogenic temperatures. A recently introduced T73 temper has a lower tensile and yield strength but improved fracture toughness combined with better stress-corrosion resistance. The unusually high static strength at ambient temperature is not reflected, however, in corresponding high fatigue resistance. Fatigue strengths are comparable to those of 2024 and 2014, which have lower static strength. The loss of fatigue strength is thought to be due to the progressive breakdown of the hardening particles, which lie in the slip regions, progressively reducing their size until they become unstable and dissolve into the matrix, thus losing their hardening function. At high temperatures the alloy loses its strength advantage over 2024 even under static conditions.

Titanium-Galuminum-4vanadium. This alloy is the most widely used of all the alpha-beta titanium compositions. It may be heat treated to a range of strength levels. In its fully aged conditions it is successfully used in highly stressed welded structures. However, in the maximum strength conditions careful attention must be given to the fracture toughness in design of highly stressed parts. Hardenability is limited and sections exceeding 2.5 cm (1 in) may not develop full properties. The alloy has good strength and high stability up to 672 K (750 °F). Very high strength is obtained at cryogenic temperatures. However, the fracture toughness below 116 K (-250 °F) is extremely poor for the fully heattreated conditions and in the annealed condition inferior to that of 5Al-2.5Sn. Low-temperature applications should use the extra-low-interstitial grades. Welding techniques for sheet have been highly developed and procedures for heavy plate are under development. Forming requires special methods and elevated temperatures.

Alloy steel 4340. 4340, including its variety 4337, which has a slightly lower carbon content, is the preferred common low-alloy steel for air weapons where good strength, high hardenability, and uniformity are desired. It can be heat treated to strength values within a wide range. For low-strength to intermediate-strength applications, other low-alloy steels that have sufficient

hardenability possess nearly the same mechanical and other properties as 4340. For high-strength applications, this steel has been found to be superior to other common low-alloy steels and also to some of the recently developed more complex low-alloy steels. 4340 is available in all wrought forms, and castings in this steel are under development. It possesses a fair formability when properly annealed and can be welded by various methods. Forgings in this alloy, heat treated to high strengths, require special measures in design and fabricating.

Maraging steel 18Ni-300. This steel is one of a class of maraging types that develops yield strengths up to 2400 MPa (350 ksi) primarily as a result of complex precipitation reactions in a very low-carbon Fe-Ni martensite. The maraging steels were designed to have superior resistance to crack propagation at high strength levels. In the 18Ni maraging steels, transformation from austenite to martensite occurs above room temperature. Three composition ranges have been specified corresponding to typical yield-strength grades of 1400, 1700, and 1900 MPa (200, 250, and 280 ksi); the latter grade, considered here, being more frequently designated as 2000 MPa (300 ksi). The various yield-strength grades differ principally in the amounts of titanium, molybdenum, and cobalt in the composition. (Material with yield strength up to 2400 MPa (350 ksi) may be obtained from some producers through further adjustments in composition.) The actual strength and toughness will vary considerably within the composition limits and can also depend strongly on the processing history. High fracture toughness, compared with other types of quenched-and-tempered steels, characterizes a properly processed sheet product. The toughness and impact properties of heavy sections are superior to those of conventional medium-carbon, low-alloy, ultrahighstrength steels heat treated to tensile strength levels exceeding 1700 MPa (250 ksi). However, the fracture properties of heavy sections can be directional and are lowest in the short-transverse direction. This directionability is influenced by the melting and processing conditions.

Corrosion and oxidation resistance are somewhat better than 4340 steel. Resistance to environmentassisted crack propagation is better than 4340 steel at an equivalent level of tensile strength. Hydrogen embrittles the maraging steels, but they exhibit a greater tolerance for hydrogen than conventional low-alloy steels. Formability is excellent in the annealed condition. The steel is readily machined in the annealed condition and can be machined in the fully aged condition. A high degree of dimensional stability is maintained throughout heat treatment. Welding requires special precautions, and the toughness of the weld deposit is generally below that of the parent metal.

Precipitation-hardened stainless steel 15-7. This alloy is a semi-austenite precipitation-hardening stainless steel. It is a modified 17-7PH alloy in which 2 to 3 percent molybdenum is substituted for an equivalent percentage of chromium. Thus, higher strengths can be obtained both at room and elevated temperatures in the various heat treated conditions. The alloy can be considered for use at temperatures up to 811 K (1000 °F). PH 15-7Mo is essentially austenitic at room temperature in either the annealed or solution-treated condition, but can be transformed to martensite by a series of thermal treatments or by cold working. The alloy can then be hardened further by thermal treatment to strengths exceeding 1400 MPa (200 ksi) at room temperature. The alloy is available in sheet, strip, plate, bar, and wire. It can be formed readily in the annealed condition and is welded easily by various methods. Its heat treatment is identical with that of 17-7PH, and much of the information available for the latter alloy applies also to PH 15-7Mo.

Aluminum alloy 2024. This heat-treatable wrought aluminum alloy is the final development of the dural type, which contains copper, magnesium, and manganese as hardeners. Its strength properties in various tempers are among the highest obtainable in aluminum alloys. Including clad 2024, it is still the most used highstrength alloy and it is available in all wrought forms, except forgings. The room-temperature aged conditions of this alloy should not be used where the temperature exceeds 339 K (150 °F) and corrosive conditions exist. The more recently developed artificially aged conditions maintain their strength and corrosion resistance up to a temperature of 422 K (300 °F). The corrosion resistance of the alloy is inferior to that of alloys free from or low in copper. Therefore, where higher corrosion resistance is required, clad 2024 sheet and strip is preferred over the bare material. The alloy is readily formable in either the annealed or solution-treated condition. Limited forming can also be performed in the T4 condition. The machinability of the heat-treated conditions is very good. The alloy may be resistance welded, but fusion welding is not recommended.

*Carbon steel 1020.* This low-carbon, nonalloyed steel finds extensive use in large-scale construction. It machines easily and forges readily. In general, such a steel combines fair strength with high ductility and excellent fabrication properties such as rolling, drawing, and welding. It is used mainly as hot-rolled, normalized, or annealed. Carbon steel 1040. This medium-carbon, nonalloyed steel can be quenched and tempered to produce high toughness and good strength properties useful in engineering applications such as shafts, gears, connecting rods, rails, rail axles, and drop-forging dies.

Precipitation-hardenable stainless steel AM355. This alloy is one of a series of age hardenable steels that combine high strength, at temperatures up to 700 K (800 °F) and higher, with the corrosion resistance of stainless steels. In the annealed condition, the alloy is austenitic. Upon forming at room temperature the alloy work hardens very rapidly because of martensite formation during working. Formation of martensite can be avoided by working at temperatures of about 422 K (300 °F) or higher, in which case the alloy forms in much the same manner as conventional austenitic stainless steels. AM355 is a companion alloy to AM350 differing from it by a slightly lower chromium content and a higher carbon. Although designed primarily to meet the demand for heavier sections including plate, bar, and forgings, it is also available in sheet form, which is the principal field for AM350. While the compositions of the two alloys are very similar, the small differences account for significant changes in structure. For example the AM350 has 5 to 20 percent delta ferrite; AM355 usually has little or none.

Hardenable stainless steel 440C. These 17-percentchromium martensitic stainless steels are produced with various carbon contents. Type 440A contains about 0.70 percent carbon, type 440B about 0.85 percent carbon, and type 440C about 1.10 percent carbon. Type 440F is a free machining grade of type 440C and contains additions of either sulphur or selenium. All these types are used in the hardened condition where a combination of high wear and corrosion resistance is required. Their hardness and wear resistance increase with increasing carbon content, while their shock resistance and ductility decrease.

Wrought stainless steel custom 455. Custom 455 is a versatile, low-carbon, martensitic, age-hardening Cr-Ni stainless steel with good corrosion resistance and favorable fabrication characteristics. It is intended for service up to 700 K (800 °F). A single aging treatment in the range of 755 K (900 °F) to 835 K (1050 °F) develops high tensile and yield strengths. The fracture toughness and ductility in tensile tests decrease with increasing strength level. The  $K_{1SCC}$  values in salt solution decrease with lower aging temperatures and are relatively low for the fully-aged condition. It can be readily cold-formed, welded, and machined in the annealed condition. Typical applications include high-strength aircraft fasteners and forgings, components for

nuclear reactors, springs, valve stems, gears, shafts, ring seals, retaining rings, pressure vessels, and various parts for use at cryogenic temperatures.

Tool steel H-11. This steel is a modification of the martensitic hot-worked die steel type H-11 with minor changes in chemical composition including slightly higher carbon content. This composition permits heat treating the steel to high strength. It is used extensively in the form of sheet, bar, and forgings at various strengths at room temperature. Also, due to its high chromium content, this steel is of the secondary hardening type and requires tempering temperatures exceeding 755 K (900 °F). Therefore, it is suitable in its full-hardness condition for high strength applications at temperatures up to 811 K (1000 °F) when protected from corrosion and oxidation by appropriate surface treatments. The steel has good formability in the annealed condition, is readily welded and exhibits little distortion when heat treated. This tool steel has relatively good toughness because of low carbon content; it has good to excellent hardness and fair wear resistance and machinability.

Titanium-6aluminum-6vanadium. This is a heattreatable alpha-beta alloy similar in many respects to Ti-6Al-4V but containing increased content of beta stabilizing elements, which provide higher strength potential at a sacrifice in both toughness and weldability. In forged sections and plate up to 2.5 cm thick, solution-treated-and-aged material has a guaranteed minimum  $F_{tu} = 1200$  MPa (170 ksi). For forged sections between 8 and 10 cm the corresponding  $F_{\rm tu} = 1000$  MPa (150 ksi). Response to heat treatment may vary from heat to heat and the correct aging temperature is best determined by tests on the heat in question. As is characteristic of other titanium alloys, exposure to stress at elevated temperature produces changes in the retained mechanical properties. The stress and temperature limits below which these changes will not occur have not yet been established for this alloy. Structural applications should be based on a knowledge of the low toughness characterizing the higher strength conditions of this alloy and the limited toughness of welds. Particular attention should be given to the influence of aggressive environments in the presence of cracks. Such environments include aqueous solutions of chlorides and possibly certain organic solvents such as methanol.

*Titanium-8molybdenum-8vanadium.* Ti-8Mo-8V-2Fe-3Al is an ageable, metastable beta alloy developed under U.S. Army Contract DA-30-069-ORD-3743. It was developed primarily as a high-strength, formable sheet alloy. But it also possesses hardenability in 10.2 cm (4 in) sections (possibly in 15.2 cm (6 in) sections) and

potential as a fastener alloy. In common with its competitor, Ti-13V-11Cr-3Al, the alloy's body-centeredcubic phase (high temperature allotrope) is retained on cooling from solution temperatures to ambient temperature at relatively slow rates. The stability of the beta phase, however, is such that the alloy can be subsequently strengthened by reheating above 700 K (800 °F) through the conventional precipitation of alpha phase (close-packed-hexagonal structure). The alloy is superior in aging kinetics, requiring less aging time to achieve high strength levels. Also, the alloy is claimed to have superior notch fatigue strength, modulus of elasticity, stability at 589 K (600 °F), and, in the annealed condition, salt water corrosion resistance. The major disadvantages of this and other beta alloys compared to alpha-beta alloys are high density and relatively poor creep properties at elevated temperatures. This alloy does not apparently possess smooth fatigue resistance commensurate with its higher strength when compared to Ti-6Al-4V. The alloy is a relatively new composition which, in some respects, is still in a state of development. Thus, reported measurements are tentative.

Resulphurized carbon steel C1141. This alloy steel contains high manganese content. Manganese, a carbideforming element, increases its hardenability by shifting the nose of the temperature-time-transformation curve to the right. Compared to the medium-carbon-content steel 1040, C1141 has much higher hardenability.

Cr-Ni-stainless steel 316. These Austenitic molybdenum-bearing grades of austenitic stainless steel, which are normally used in the annealed condition, cannot be hardened by heat treatment; however, they can be hardened by cold work. The molybdenum content of 2 to 3 percent in type 316 provides marked improvements in corrosion resistance, particularly pitting corrosion, and in elevated-temperature strength over the non-molybdenum-bearing austenitic stainlesses. The higher molybdenum content of 3 to 4 percent in the less widely used type 317 results in further improvements in these characteristics. They retain usable strength and oxidation resistance at temperatures up to 1089 K (1500 °F). They are, however, susceptible to carbide precipitation and associated intergranular corrosion as a result of exposure to temperatures in the range 755 K (900 °F) to 1144 K (1600 °F). Low carbon modifications, 316L and 317L, are recommended when exposure in this temperature range is unavoidable, although the lower carbon results in lower strength. In cast form, type 316 is generally designated CF3M, CF8M, and CF12M, corresponding to carbon contents of 0.03, 0.08, and 0.12 percent. respectively. The wrought

and cast forms are readily weldable, and the wrought forms have good formability in the annealed condition. These alloys are used in various jet-engine parts, exhaust manifolds, heat exchangers, boat trim, chemicalprocessing equipment, photographic equipment, furnace parts, and orthopedic implants.

*Iron-based superalloy A286.* This alloy is one of the first and most popular age-hardenable, austenitic, nickelchromium steels and has pioneered the successful application of this type of superalloy for high-temperature use. It is similar to and a development of the German alloy Tinidur. It is used primarily at temperatures up to 978 K (1300 °F). The alloy is available in sheet, plate, bar, tubing, wire, extrusions, and forgings. Investment castings are also produced. It can be formed and welded.

Maraging steel 18Ni-400. This alloy is consumable vacuum melted and relates strongly metallurgically to the 300-series alloy. Containing less than 0.03 C, it combines a yield strength of about 2800 MPa (400 ksi) with exceptional ductility and toughness for that strength level. An annealing treatment places it in the best condition for machining and forming. Subsequent aging increases hardness by a precipitation reaction in the martensite matrix, with corresponding higher strength properties. Designers and users of this alloy find among the many desirable characteristics: very high yield strengths, good ductility and toughness; high notch-to-smooth tensile strength ratios for a material with this strength capability; good formability characteristics, both hot and cold, with low work-hardening tendencies; easy weldability; freedom from decarburization without use of a protective atmosphere; ease of heat treatment; minimum distortion during heat treatment; excellent hardenability; and a low coefficient of expansion.

Iron-based superalloy V-57. This austenitic stainlesssteel alloy has a good combination of tensile and creep rupture properties up to 1089 K (1500 °F) at high stresses. It is a higher titanium and boron modification of A286 stainless steel and is primarily used for some parts of aircraft gas turbines.

Unitemp 212. Because of high chromium content, this alloy is a stainless steel. But it is considered a superalloy because of its superior high-temperature properties. Designed for service to 1033 K (1400 °F), it resists heat and corrosion. At room temperature and above, it has a high strength-to-weight ratio. Its high titanium content causes segregation, which leads to problems in hot working. Its hot-working temperature is relatively low: working above 1339 K (1950 °F) causes cracking. For room-temperature use only, this alloy does not offer the best combination of usual mechanical properties. It has been used for aircraft bolts and for guided-missile components. This alloy was developed and patented by a U.S. steel company as a promising high-strength superalloy. But lack of demand has removed it from production.

### 3. Properties of Interest

The following properties were covered in this study:

#### Physical Properties

(1) mass density.

Elastic Properties

- (2) Young's modulus
- (3) shear modulus
- (4) bulk modulus
- (5) Poisson's ratio.

Mechanical Properties

- (6) yield strength
- (7) ultimate strength
- (8) fatigue strength
- (9) fracture toughness
- (10) creep strength.

Elastic constants are, of course, physical properties. But in this report it is useful to consider them as a separate subclass.

Definitions of the various properties together with their usual SI units are as follows:

g/cm <sup>3</sup>	Mass density: mass per unit
	volume.
GPa	Young's modulus: ratio of uniaxial
	stress to strain along the stress
	axis, in either tension or
	compression.
GPa	Shear modulus: ratio of stress to
	corresponding strain when stress
	is either pure shear or pure
	torsion.
GPa	Bulk modulus: negative ratio of hy-
	drostatic stress (pressure) to
	volume change.
dimensionless	Poisson's ratio: negative ratio of
	transverse strain to axial strain in
	a uniaxially stressed body.
MPa	Yield strength: stress at which a
	material deviates significantly
	from linear stress-strain behavior;
	physically, the onset of plastic
	deformation.
MPa	Tensile strength: maximum tensile
	stress a material can sustain,
	based on original cross-section.

MPa	Fatigue strength: maximum stress a
	material can sustain for a specified
	number of load cycles, N.
$MPa \cdot m^{1/2}$	Fracture toughness: resistance of a
	material to fracture in the
	presence of a sharp crack, under
	plane-strain, expressed as critical
	linear-elastic stress-intensity
	factor, $K_{1e}$ .
MPa	Creep strength: stress that causes a
	given creep strain in a given time.

#### 4. Data Collection

Property data were compiled from the following types of sources:

- 1. handbooks
- 2. books
- 3. reports
- 4. review papers
- 5. manufacturers' literature
- 6. engineering-science literature
- 7. unpublished NBS studies.

Many data were obtained from type-1 sources and from readily available sources. A chronological bibliography of these is given in appendix 1. Type-6 sources were sought only in cases where very limited data were available elsewhere. These type-6 sources were located using:

- 1. NBS Cryogenic Data Center literature searches
- 2. Metals Review
- 3. Metallurgical Abstracts.

From each source, data were recorded on a worksheet (app. 2), which included chemical composition, thermalmechanical treatment, and other relevant observations.

## 5. Data Analysis

Two hundred fifty-two data sets (21 materials, 12 properties) were examined statistically for normal distribution when the data set contained at least 5 entries. Data-set size ranged from 0 to 111. Examples of normal-distribution probability plots are shown in figures 1-2. When data were distributed nearly normally, computations were made for: the mean value, the



FIGURE 1. Normal-distribution test for yield-strength data for Ti-6Al-4V. The straight line represents normally distributed data. For the materials and properties considered in this study, these data represent an excellent fit to a normal distribution.



FIGURE 2. Normal-distribution test for fracture-toughness data for alloy steel 4340. Normally distributed data would fall along a straight line. Excluding the two highest values, these data deviate slightly from a normal distribution.

median value, the standard deviation, and a trimmed mean. Trimming consisted of discarding 7 percent of the highest values and 7 percent of the lowest values. Retaining 86 percent of the values amounts to retaining all values within  $\pm 1.5\sigma$ , where  $\sigma$  is the standard deviation. For a large sample size this corresponds approximately to retaining values within a 90-percent confidence interval. This  $\pm 1.5\sigma$  cutoff is a judgment based on the experience of our laboratory in previous experimental and analytical studies. In a few cases, data were distributed non-normally and other methods were used to ascertain a "best" value. Strong evidence of nonnormal behavior in a probability plot was the exception. Many of these exceptions were for cases where one value was repeated in several references. Such data are best summarized by giving the most prevalent value. Outliers seldom occurred, thus eliminating the need for the trimmed mean in many cases.

#### 6. Results

About 1700 worksheets resulted from the compilation. These worksheets contain 3900 individual data, an average of nearly 200 per alloy, ranging from 14 to 574 per alloy. For brevity, these worksheets are omitted here and the results are summarized by alloy in tables 2-22 in both SI and English units.

#### 7. Discussion

This study suffers from several limitations: reliance principally on secondary sources, neglect of test-variable effects, and use of normal-distribution statistics. Perhaps future related studies will alleviate these limitations.

Despite these drawbacks, this study provides many new insights together with information that may promote further understanding. For the first time, for 21 technological alloys, physical-property and mechanical-property results have been collected from a variety of secondary sources. We see clearly the range of results, the mean value, and the deviation of the mean. The computed standard deviations represent perhaps the most pessimistic statement of uncertainty because the data contain nearly every imaginable uncertainty source: chemical composition, thermomechanical processing, sampling method, test method, experimental error, transcription error, and so on. Where data sets are sufficiently large, we see that practical bounds can be established for the property value. Knowing such bounds is enormously useful and is an essential first step toward determining improved bounds.

That the data may be distributed non-normally seems irrelevant to present purposes. The "errors" may still be random. And, calculating mean values and standard deviations is always valuable for comparing distributions of data, whatever their actual distribution. We chose to exclude extrema from our summary tables because we believe that (in most cases) these represent poor experiments rather than unusual materials.

The veracity of this study can be established partly by comparing its results with the few existing exhaustive studies of property variability. For stainless-steel 316, this is possible because the elastic-property variability was reported recently by Ledbetter (Metal Sci., Dec. 1980, 595-596) and the mechanical-property variability by Sikka (ORNL Report 5384, 1978). Results from neither of these two reports were included in the present study. However, table 23 contains the comparison, which is good for all properties except yield strength, the property with highest uncertainty.

From the data in the tables the average mass-density uncertainty is 0.3 percent, the average elastic-constant uncertainty is 3 percent, and the average mechanicalproperty uncertainty is 19 percent. Mass density is reported infrequently, but it is well known because of the relative simplicity of measurements and the insensitivity to metallurgical variables such as composition and heat treatment.

None of the four elastic constants—Young's modulus, shear modulus, bulk modulus, Poisson's ratio—is systematically better known than the others. Young's modulus is reported more often than the other three constants combined. Direct bulk-modulus measurements are reported seldomly because such measurements are difficult.

Among the four mechanical properties—yield strength, ultimate strength, fatigue strength, and fracture toughness—the yield and ultimate strength have the lowest uncertainties. Fracture toughness is about 25 percent uncertain; this reflects both experimental inaccuracy and material variability. Fatigue-strength data are relatively scarce because of the long testing times involved; the large uncertainty in these data, about 25 percent, is due mainly to material variability.

#### 8. Acknowledgment

R. P. Mikesell was responsible for data collection, M. W. Austin and G. Maerz for data collation, and J. F. LaBrecque for statistical analysis. J. Dahnke assisted in preparing the report.

	Density (g/cm <sup>3</sup> )	Young's Modulus (GPa)	Shear Modulus (GPa)	Bulk Modulus (GPa)	Poisson's Ratio	Yield Strength (MPa)	Tensile Strength (MPa)	10 <sup>4</sup> Cycles	Fatigue - 10 <sup>5</sup> Cycles (MPa	Strength 10 <sup>6</sup> Cycles a)	10 <sup>7</sup> Cycles	Fracture Toughness (MPa /m)
o. Observations	6	17	7	1	4	57	47	11	16	16	14	12
ean Value	2.71	69.6	26.3	72.4	0.331	275	312	303	223	178	151	28
edian Value	2.71	68.9	26.2	I	0.330	276	310	310	214	166	145	29
rimmed Mean	2.71	69.6	26.3	1	0.331	274	311	303	230	175	151	
tandard Deviation	0.006	1.9	0.3	1	0.005	20	46	43	45	>	39	3
ercent Uncertainty	0.2	2.7	1.0	1	1.5	7.3	14.9	14.1	19.5	20.5	25.6	10.5
	Density	Young's Modulus	Shear Modulus	Bulk Modulus	Poisson's Ratio	Yield Strength	Tensile Strength	10 <sup>4</sup> Cycles	Fatigue 10 <sup>5</sup> Cycles	Strength 10 <sup>6</sup> Cycles	10 <sup>7</sup> Cycles	Fractur
	(g/cm <sup>3</sup> )	(GPa)	(GPa)	(GPa)		(MPa)	(MPa)		(MP	a)		(MPa √m
lo. Observations	8	15	9	1	4	111	42	6	16	12	6	75
lean Value	2.79	71.8	26.8	70.7	.330	465	529	409	270	199	173	27
ledian Value	2.80	71.7	26.9	ı	.330	462	531	452	283	214	172	28
rimmed Mean	2.79	71.8	26.8	I	.330	468	530	409	270	199	173	27
standard Deviation	0.03	0.9	0.2	t	0.0	53	47	86	51	50	39	9

			TABLE 4	(SI). SUM	MARY OF PRO	PERTY DATA	FOR TITAN	IUM ALLOY	Ti-6Al-4V			
	Density (g/cm <sup>3</sup> )	Young's Modulus (GPa)	Shear Modulus (GPa)	Bulk Modulus (GPa)	Poisson's Ratio	Yield Strength (MPa)	Tensile Strength (MPa)	10 <sup>4</sup> Cycles	Fatigue 10 <sup>5</sup> Cycles (MP	Strength 10 <sup>6</sup> Cycles	10 <sup>7</sup> Cycles	Fracture Toughness (MPa Vm)
No. Observations	2	15	9	2	9	108	98	5	9	S	2	27
Mean Value	4.43	110.0	42.3	1.05	0.316	994	1143	969	625	508	456	65
Median Value	4.43	110.3	42.4	1.05	0.315	1000	1103	1034	607	490	456	60
Trimmed Mean	4.43	111.0	42.3	1.05	0.316	1000	1085	969	625	508	456	63
Standard Deviation	0.01	3.7	0.5	0.0	0.007	101	103	206	176	160	212	22
Percent Uncertainty	0.25	3.4	1.2	0.0	2.1	1.0	9.5	21.2	28.1	31.7	46.5	35.4
	Density (g/cm <sup>3</sup> )	Young's Modulus (GPa)	Shear Modulus (GPa)	Bulk Modulus (GPa)	Poisson's Ratio	Yield Strength (MPa)	Tensile Strength (MPa)	10 <sup>4</sup> Cycles	Fatigue 10 <sup>5</sup> Cycles (MF	Strength 10 <sup>6</sup> Cycles	10 <sup>7</sup> Cycles	Fracture Toughness (MPa Vm)
No. Observations	9	14	9	0	2	72	37	5	10	11	7	43
Mean Value	7.85	205	76.5	ı	1.93	1494	1733	1168	754	690	613	68
Median Value	7.83	207	75.8	T	1.93	1541	1813	1324	776	724	655	60
Trimmed Mean	7.85	205	76.5	I	1.93	1487	1720	1168	754	690	613	67
Standard Deviation	0.01	9	1.4	I	0.04	240	393	384	25	211	203	21
Dercent Uncertaintv	1	2.0	1.8		0 6	16.1	22.8	33.0	32.4	30.6	33.1	30.9

									Dati and			
	Density (g/cm <sup>3</sup> )	Young's Modulus (GPa)	Shear Modulus (GPa)	Bulk Modulus (GPa)	Poisson's Ratio	Yield Strength (MPa)	Tensile Strength (MPa)	10 <sup>4</sup> Cycles	Cycles (M	Strength 10 <sup>6</sup> Cycles Pa)	10 <sup>7</sup> Cycles	Fracture Toughnes (MPa /m)
No. Observations		4	1	1	5	84	65	3	4	4	4	3,8
Mean Value	8.04	190	66.3	167.6	0.318	1925	1982	1356	831	738		00
Median Value	8.00	188	ı	I	0.318	1940	2034	1310	838	738	703	, ra
Trimmed Mean	8.04	190	I	I	0.318	1917	1980	1356	831	738	707	01 78
Standard Deviation	0.14	14	I	I	0.011	230	206	211	199	183	148	1 2
Percent Uncertainty	1.8	7.5	I	I	3.3	12.0	10.4	15.6	24.0	25.0	20.9	21.8
	Density (g/cm <sup>3</sup> )	Young's Modulus (GPa)	Shear Modulus (GPa)	Bulk Modulus (GPa)	Poisson's Ratio	Yield Strength (MPa)	Tensile Strength (MPa)	10 <sup>4</sup> Cycles	Fatigue 10 <sup>5</sup> Cycles (MPa	Strength 10 <sup>6</sup> Cycles a)	10 <sup>7</sup> Cycles	Fracture Toughnes: (MPa /m)
Vo. Observations	2	4	3	0	1	37	36					
1ean Value	7.67	201	77.9	ı	0.320	1468	15 21	5	7	-	1	7
ledian Value	7.67	200	77.9	I		0011	1/01	ı	1220	1138	1103	63
rimmed Mean	7.67	201	77.9	I		1440 17F0	1055	I	I	I	I	57
tandard Deviation	0.0	1.7	2.4	I		6041 071	1004	ı	I	ı	I	63
ercent Uncertainty	0.0	6.0	۲۷ ۱		1	601	157	ı	I	1	I	14
	2	C*0	1.0		1	11 6	V 0					

		F	ABLE 8(SI)	). SUMMARY	OF PROPERTY	' DATA FOR A	VLUMINUM ALL	0Y 2024				
	Density (g/cm <sup>3</sup> )	Young's Modulus (GPa)	Shear Modulus (GPa)	Bulk Modulus (GPa)	Poisson's Ratio	Yield Strength (MPa)	Tensile Strength (MPa)	10 <sup>4</sup> Cycles	Fatigue : 10 <sup>5</sup> Cycles (M	Strength 10 <sup>6</sup> Cycles Pa)	10 <sup>7</sup> Cycles	Fracture Toughness (MPa 师)
No. Observations	9	=	2	0	7	139	50	0	-	2	2	96
Mean Value	2.77	73.1	27.1	ı	0.332	417.8	454.4	·	220.6	168.9	131.0	24.4
Median Value	2.77	73.1	27.1	I	0.330	441.3	482.6	ı	I	168.9	131.0	24.2
Trimmed Mean	2.77	73.1	27.1	I	0.332	429.6	456.4	ı	I	168.9	131.0	24.4
Standard Deviation	0.0	1.4	0.8	ı	0.006	75.8	86.2	1	I	53.8	39.3	4.9
Percent Uncertainty	0.0	1.8	2.7	ı	1.7	18.1	19.0	ı	ı	31.7	29.8	20.4
	Density (g/cm <sup>3</sup> )	Young's Modulus (GPa)	Shear Modulus (GPa)	Bulk Modulus (GPa)	Poisson's Ratio	Yield Strength (MPa)	Tensile Strength (MPa)	10 <sup>4</sup> Cycles	Fatigue : 10 <sup>5</sup> Cycles (MM	Strength 10 <sup>6</sup> Cycles Pa)	10 <sup>7</sup> Cycles	Fracture Toughness (MPa <i>√</i> m)
No. Observations	2	9	-	0	-	45	42	0	0	0	0	2
Mean Value	7.84	206.2	80.0	ı	0.288	429.6	619.2	ı	I	1	I	95.1
Median Value	7.84	206.2	ı	I	ı	365.4	544.7	ı	1	I	ī	95.1
Trimmed Mean	7.84	206.2	ı	ı	١	439.2	630.9	,	I	I	I	95.1
Standard Deviation	0.0	2.1	I	ı	I	195.1	222.7	ī	I	I	1	7.0
Percent Uncertainty	0.0	1.1	ı	ı	ı	45.5	36.0	ı	I	ı	ı	7.4

	Density (g/cm <sup>3</sup> )	Young's Modulus (GPa)	Shear Modulus (GPa)	Bulk Modulus (GPa)	Poisson's Ratio	Yield Strength (MPa)	Tensile Strength (MPa)	10 <sup>4</sup> Cycles	Fatigue S 10 <sup>5</sup> Cycles (MP	Strength 10 <sup>6</sup> Cycles 'a)	10 <sup>7</sup> Cycles	Fracture Toughness (MPa /皿)
No. Observations	0	-	0	ο	0	10	12	0	0	0	0	_
Mean Value	I	211.7	ı	1	ı	458.5	653.6	,	ı	I	I	114.3
Median Value	I	I	1	I	ł	406.8	634.3	ı	I	I	ı	t
Trimmed Mean	ı	ı	1	I	ı	458.5	653.6	ı	ı	ı	ı	ı
Standard Deviation	ı	1	1	ı	ı	188.2	133.1	ı	ı	I	ı	
Percent Uncertainty	I	I	ı	I	ı	41.1	20.4	ı	I	I	ı	ı
	Density (g/cm <sup>3</sup> )	Young's Modulus (GPa)	Shear Modulus (GPa)	Bulk Modulus (GPa)	Poisson's Ratio	Yield Strength (MPa)	Tensile Strength (MPa)	10 <sup>4</sup> Cycles	Fatigue S 10 <sup>5</sup> Cycles (MF	Strength 10 <sup>6</sup> Cycles <sup>2</sup> a)	10 <sup>7</sup> Cycles	Fracture Toughness (MPa <i>√</i> 邢)
No. Observations	4	9	-	0	0	109	104	-	4	4	4	сл
Mean Value	7.81	200.6	78.6	ł	ı	1201	1362	827.4	815.0	703.3	668.2	75.4
Median Value	7.81	200.0	I	ı	ı	1179	1348	I	817.1	703.3	668.2	81.3
Trimmed Mean	7.81	200.6	ı	l	I	1196	1358	t	815.0	703.3	668.2	75.4
Standard Deviation	0.028	5.5	ı	I	ı	230	219	I	14.5	31.7	55.8	16.2
Percent Uncertainty	0.5	2.6	ı	I	ı	19.2	16.1	I.	1.7	4.5	8.3	21.4

TABLE 10(SI). SUMMARY OF PROPERTY DATA FOR CARBON STEEL 1040

		TARI	IF 12(SI).	SUMMARY	OF PROPERTY	DATA FOR SIV	AINLESS SIEN	EL 4400				
									Fatigue St	trength	٢	
	Density (a/cm <sup>3</sup> )	Young's Modulus (GPa)	Shear Modulus (GPa)	Bulk Modulus (GPa)	Poisson's Ratio	Yield Strength (MPa)	Tensile Strength (MPa)	10 <sup>4</sup> Cycles	10 <sup>5</sup> Cycles (MP;	10 <sup>6</sup> Cycles a)	10 <sup>/</sup> Cycles	Fracture Toughness (MPa /而)
	1						:	c	c	С	0	0
No Observations	2	ę	-	0	-		=	Ð	5	þ	, 1	,
	7.70	203.0	93.1	ı	0.284	1220	1448	ı	1	1	ı	
Mean value		200 0	ı	ı	1	1324	1655	•	1	ı	ı	I
Median Value				1		1220	1448	•	ı	ı	ı	١
Trimmed Mean	7.70	203.0	ı	ı		C T L	6.20	ı	1	ŀ	ı	ı
Standard Deviation	0.0	5.5	ı	ı		8/G	000			,	,	ı
Dovrent Incertaintv	0.7	2.7	ı	I	ı	47.3	37.2	1				
				:	- , ,			401	Fatigue 105	Strength 10 <sup>6</sup>	107	Fracture
	Density	Young's Modulus	Shear Modulus	Bulk Modulus	Poisson's Ratio	Y1eld Strength	Strength	Cycles	Cycles	Cycles	Cycles	Toughness
	(g/cm <sup>3</sup> )	(GPa)	(GPa)	(GPa)		(MPa)	(MPa)		×)	IPa)		(MPa vm)
No. Observations	-	6	-	0	2	51	53	-	2	ъ	ß	4
Mean Value	7.76	197.9	75.8	ı	0.300	1489	1572	617	886.0	701.9	685.4	72.3
Median Value	ı	196.5	ı	T	0.300	1517	1620	I	886.0	1.717	648.1	66.5
Trimmed Mean	ı	197.9	ı	ı	0.300	1480	1564	I	886.0	701.9	685.4	72.3
Standard Deviation	1	4.8	١	ı	0.0	255	204	ı	44.1	79.3	98.6	29.9
	I	2.6	I	1	0.0	17.1	13.0	ł	5.0	11.3	14.4	41.3

2.6

ı

Percent Uncertainty

-			TABLE 14(S	I). SUMMA	RY OF PROPEF	<b>ΚΤΥ DATA FO</b>	r tool stee	L H-11				
	Density (g/cm <sup>3</sup> )	Young's Modulus (GPa)	Shear Modulus (GPa)	Bulk Modulus (GPa)	Poisson's Ratio	Yield Strength (MPa)	Tensile Strength (MPa)	10 <sup>4</sup> Cycles	Fatigue S 10 <sup>5</sup> Cycles (MF	strength 10 <sup>6</sup> Cycles 2a)	10 <sup>7</sup> Cycles	Fracture Toughness (MPa √m)
No. Observations	0	7	0	0	0	72	65	5	10	=	2	12
Mean Value	ı	205.5	ı	ı		1671	1987	1204	935	788	778	30.1
Median Value	I	207.5	ı	I	,	1662	2041	1103	989	883	896	29.1
Trimmed Mean	I	205.5	ı	I	ı	1704	2013	1204	935	788	778	30.1
Standard Deviation	ı	11.7	I	ı	ı	416	423	196	217	221	243	16.7
Percent Uncertainty	I	5.7	I	ı	ı	24.9	21.3	16.3	23.2	28.0	31.2	55.4
	Density (g/cm <sup>3</sup> )	Young's Modulus (GPa)	Shear Modulus (GPa)	Bulk Modulus (GPa)	Poisson's Ratio	Yield Strength (MPa)	Tensile Strength (MPa)	10 <sup>4</sup> Cycles	Fatigue 10 <sup>5</sup> Cycles (N	Strength 10 <sup>6</sup> Cycles 4Pa)	10 <sup>7</sup> Cycle	Fracture s Toughness (MPa /m)
No. Observations	1	16	1	0	1	235	206	11	15	19	20	49
Mean Value	4.539	115.1	44.8	I	0.320	1123.9	1185.9	992.9	820.5	737.7	661.9	310.3
Median Value	I	115.1	I	I	ı	1130.7	1199.7	1034.2	855.0	758.4	675.7	268.9
Trimmed Mean	I	114.5	ł	I	ı	1137.6	1206.6	992.9	848.1	744.6	668.8	303.4
Standard Deviation	I	4.1	I	I	ı	137.9	137.9	103.4	110.3	103.4	103.4	103.4
Percent Uncertainty	I	3.3	I	I	I	12	12	11	14	14	16	34

		T	ABLE 16(SI)	. SUMMARY	OF PROPERT	Y DATA FOR	TITANIUM P	/LLOY Ti-8	40-8V			
	Density (g/cm <sup>3</sup> )	Young's Modulus (GPa)	Shear Modulus (GPa)	Bulk Modulus (GPa)	Poisson's Ratio	Yield Strength (MPa)	Tensile Strength (MPa)	10 <sup>4</sup> Cycles	Fatigue S 10 <sup>5</sup> Cycles (MF	trength 10 <sup>6</sup> Cycles a)	10 <sup>7</sup> Cycles	Fracture Toughness (MPa $\sqrt{\mathrm{m}})$
Ma Observations		20	c	0	0	159	155	-	7	1	0	10
NO. UDSELVALIUNS Moon Value	т 7, 87,7	0,01	> 1	- 1	I	1151.4	1220.4	517.1	551.6	517.1	I	331.0
Median Value		106.9	1	ı	1	1185.9	1248.0	I	ı	I	1	324.1
Trimmed Mean	ı	107.6	I	ı	ı	1144.5	1213.5	I	I	I	I	331.0
Standard Deviation	,	8.3	1	ı	ı	172.4	179.3	I	ı	ı	ı	55.2
Percent Uncertainty	ı	8.0	I	I	I	15	15	I	I	I	I	18
	Density (g/cm <sup>3</sup> )	Young's Modulus (GPa)	Shear Modulus (GPa)	Bulk Modulus (GPa)	Poisson's Ratio	Yield Strength (MPa)	Tensile Strength (MPa)	10 <sup>4</sup> Cycles	Fatigue 10 <sup>5</sup> Cycles (M	Strength 10 <sup>6</sup> Cycles Pa)	10 <sup>7.</sup> Cycles	Fracture Toughness (MPa $\sqrt{m}$ )
	ŀ							<		C	0	T
No. Observations	2	2	0	0	0	5	4 797 9	5 1		) I	I	427.5
Mean Value	7.805	202.0	I	ı	ı	7.61C	827.4	1	1	ı	ι	I
Median Value	7.805	202.0	ı	I	ı	1.00U	797 9	I	1	I	1	ı
Trimmed Mean	7.805	202.0	I	I	1	7.610	131.0	1	I	I	I	1
Standard Deviation	0.0	2.8	1	1 1	1 1	18	17	1	I	I	1	I

1 1

1 I

2.8

0.0

Standard Deviation Percent Uncertainty

	Density (g/cm <sup>3</sup> )	Young's Modulus (GPa)	Shear Modulus (GPa)	Bulk Modulus (GPa)	Poisson's Ratio	Yield Strength (MPa)	Tensile Strength (MPa)	10 <sup>4</sup> Cycles	Fatigue 10 <sup>5</sup> Cycles (	Strength 10 <sup>6</sup> Cycles MPa)	10 <sup>7</sup> Cycles	Fracture Toughness (MPa √m)
No Observations	<u> </u>	11	4	1	3	50	56	1			1	1
Mora Value	7.971	195.1	79.9	177.9	0.294	296.5	627.4	268.9	234.4	213./	4.94.	6.4002
Median Value	7.971	193.1	79.9	I	0.295	284.2	586.1	I	I	ı	ı	I
Trimmed Mean	7.971	195.1	79.9	I	0.294	268.9	620.5	ı	I	'	ł	I
Standard Deviation	0.028	9.7	3.4	ı	0.004	165.5	131.0		I	'	I	I
Percent Uncertainty	0.3	5.1	4.8	I	1.2	56	21		I	I	I	I
	Density (g/cm <sup>3</sup> )	Young's Modulus (GPa)	Shear Modulus (GPa)	Bulk Modulus (GPa)	Poisson's Ratio	Yield Strength (MPa)	Tensile Strength (MPa)	10 <sup>4</sup> Cycles	Fatigue S 10 <sup>5</sup> Cycles (MF	trength 10 <sup>6</sup> Cycles a)	10 <sup>7</sup> Cycles	Fracture Toughness (MPa /m)
No. Observations	7	17	80	1	9	72	86	2	4	4	2	e
Mean Value	7.944	196.5	73.1	154.4	0.301	820.5	7.666	517.1	503.3	393.0	420.6	1013.5
Median Value	7.916	199.9	72.4	ı	0.303	730.8	1048.0	517.1	558.5	420.6	420.6	7.999
Trimmed Mean	7.944	195.8	73.1	ı	0.301	841.2	992.9	517.1	503.3	393.0	420.6	1013.5
Standard Deviation	0.055	0.6	1.4	ı	0.006	255.1	303.4	241.3	137.9	103.4	27.6	234.4
Percent Uncertainty	0.5	4.5	2.2	ı	2.1	31	30	47	28	27	9	23

TABLE 18(SI). SUMMARY OF PROPERTY DATA FOR AUSTENITIC Cr-Ni STAINLESS STEEL 316

		TABL	E 20(SI).	SUMMARY 0	F PROPERTY D	DATA FOR MA	ARAGING STE	EL 18Ni-40	0			
	Density (g/cm <sup>3</sup> )	Young's Modulus (GPa)	Shear Modulus (GPa)	Bulk Modulus (GPa)	Poisson's Ratio	Yield Strength (MPa)	Tensile Strength (MPa)	10 <sup>4</sup> Cycles	Fatigue S 10 <sup>5</sup> Cycles (MF	Strength 10 <sup>6</sup> Cycles	10 <sup>7</sup> Cycles	Fracture Toughness (MPa Vm)
No. Observations Mean Value	1 8.082	2 189.6	0 1	0 1	6 0.300	92 2275.3	94 2337.3	2 1234.2	2 992.9	2 820.5	1 765.3	27
Median Value	I	189.6	I	I	0.295	2316.7	2378.7	1234.2	992.9	820.5	i	272.3
Trimmed Mean	I	189.6	I	I	0.300	2268.4	2337.3	1234.2	992.9	820.5	ı	297.2
Standard Deviation	I	14.5	I	I	0.045	186.2	165.5	6.9	89.6	27.6	ı	89.6
Percent Uncertainty	I	7.7	I	I	15.1	∞	2	1	6	3	I	30
	Density (g/cm <sup>3</sup> )	Young's Modulus (GPa)	Shear Modulus (GPa)	Bulk Modulus (GPa)	Poisson's Ratio	Yield Strength (MPa)	Tensile Strength (MPa)	10 <sup>4</sup> Cycles	Fatigue S 10 <sup>5</sup> Cycles (MP	trength 10 <sup>6</sup> Cycles a)	10 <sup>7</sup> Cycles	Fracture Toughness (MPa /m)
No. Observations	e	2	2	0	1	6	9	0	6	4	.,	0
Mean Value	7.916	196.5	78.6	ı	0.294	868.7	1213.5		703.3	524.0	482 6	
Median Value	7.916	196.5	78.6	ı	I	848.1	1199.7	I	703.3	537.8	482 6	I
Trimmed Mean	7.916	196.5	78.6	I	I	861.9	1213.5	ı	703.3	524.0	482.6	1
Standard Deviation	0.028	0.7	1.4	I	I	62.1	41.4	I	275.8	75.8	75.8	1
Percent Uncertainty	0.2	0.5	1.9	I	I	7	ŝ	1	40		16	I

I.

16

15

40

I

 $\sim$ 

	Density (g/cm <sup>3</sup> )	Young's Modulus (GPa)	Shear Modulus (GPa)	Bulk Modulus (GPa)	Poisson's Ratio	Yield Strength (MPa)	Tensile Strength (MPa)	10 <sup>4</sup> Cycles	Fatigue 10 <sup>5</sup> Cycles	e Strength 10 <sup>6</sup> Cycles MPa)	10 <sup>7</sup> Cycles	Fracture Toughness (MPa /m.)
No. Observations	Г	-	0	0	0	2	e	C	0	c		
Mean Value	7.916	200	I	I	I	930.8	1351.4	) <b>I</b>				
Median Value	I	I	ı	ł	I	930.8	1289.3	I	ı	I		
Trimmed Mean	I	I	I	ı	I	930.8	1351.4	I	I	ı		
Standard Deviation	I	I	I	I	I	6.9	110.3	I	I	I		I
Percent Uncertainty	I	I	I	I	I	1	ø	I	I	I		1
	Density (1b/im <sup>3</sup> )	Young's Modulus (10 <sup>6</sup> psi)	TABLE 2( Shear Modulus (10 <sup>6</sup> psi)	(E). SUMMA Bulk Modulus (10 <sup>6</sup> psi)	ARY OF PROPE	XTY DATA F Yield Strength (10 <sup>3</sup> psi)	OR ALUMINU Tensile Strength (10 <sup>3</sup> bsi)	M ALLOY 60 10 <sup>4</sup> Cycles	61-T6 Fatigue 5 105 Cycles (10 <sup>3</sup> t	itrength 106 Cycles	10 <sup>7</sup> Cycles	Fracture O <sup>3</sup> psi vin)
No. Observations	6	17	7	t.	4	57	47	11	16	16	14	12
Mean Value	0.0979	10.1	3.81	10.5	0.331	40	45	44	34	26	22	26
Median Value	0.0980	10.0	3.80	I	0.330	40	45	45	31	24	21	27
Trimmed Mean	0.0979	10.1	3.81	,	0.331	40	45	44	34	25	22	26
Standard Deviation	0.0002	0.3	0.04	·	0.005	53	7	9	7	S	6	3

10.5

25.6

20.5

19.5

14.1

14.9

7.3

1.5

ı

1.0

2.7

0.2

Percent Uncertainty

TABLE 22(SI). SUMMARY OF PROPERTY DATA FOR UNITEMP 212

			IABLE 3(	E). SUMIVIA	KY UF PKUP	EKTY DATA	FOR ALUMINU	M ALLOY 7	075-T6			
	Density (1b/in <sup>3</sup> )	Young's Modulus (10 <sup>6</sup> psi)	Shear Modulus (10 <sup>6</sup> psi)	Bulk Modulus (10 <sup>6</sup> psi)	Poisson's Ratio	Yield Strength (10 <sup>3</sup> psi)	Tensile Strength (10 <sup>3</sup> psi)	10 <sup>4</sup> Cycles	Fatigue 10 <sup>5</sup> Cycles (10 <sup>3</sup>	Strength 10 <sup>6</sup> Cycles psi)	10 <sup>7</sup> Cycles	Fracture Toughness (10 <sup>3</sup> psi vin)
No. Observations	œ	15	9	1	4	111	42	6	16	12	6	75
Mean Value	0.1007	10.41	3.89	10.3	0.330	67	77	59	39	29	25	25
Median Value	0.1010	10.40	3.90	ı	0.330	67	77	66	41	31	25	25
Trimmed Mean	0.1007	10.42	3.89	ŧ	0.330	68	77	59	39	29	25	25
Standard Deviation	0.0010	Q.13	0.02	ı	0.0	ø	7	13	7	7	6	5
Percent Uncertainty	0.1	1.2	0.6	ı	0.0	11.4	8.9	21.1	18.9	25.3	22.7	21.1
	Density (1b/in <sup>3</sup> )	Young's Modulus (10 <sup>6</sup> psi)	Shear Modulus (10 <sup>6</sup> psi)	Bulk Modulus (10 <sup>6</sup> psi)	Poisson's Ratio	Yield Strength (10 <sup>3</sup> psi)	Tensile Strength (10 <sup>3</sup> psi)	10 <sup>t</sup> Cycles	Fatigue 10 <sup>5</sup> Cycles (10 <sup>3</sup>	Strength 10 <sup>6</sup> Cycles psi)	10 <sup>7</sup> Cycles	Fracture Toughness (10 <sup>3</sup> psi /in)
No. Observațions	Ľ	15	6	5	9	108	98	2	9	2	2	27
Mean Value	0.1601	16.0	6.14	0.152	0.316	144	157	141	91	74	66	60
Median Value	0.1600	16.0	6.15	0.152	0.315	145	160	150	88	71	66	54
Trimmed Mean	0.1601	16.1	6.14	0.152	0.316	145	157	141	91	74	66	57
Standard Deviation	0.0004	0.5	0.07	0.0	0.007	15	15	30	26	23	31	20
Percent Uncertainty	0.25	3.4	1.2	0.0	2.1	10.0	9.5	21.2	28.1	31.7	46.5	35.4

			TABLE 5	(E). SUMMA	ARY OF PROP	ERTY DATA	FOR ALLOY S	TEEL 4340				
	Density (1b/in <sup>3</sup> )	Young's Modulus (106 psi)	Shear Modulus (10 <sup>6</sup> psi)	Bulk Modulus (10 <sup>6</sup> psi)	Poisson's Ratio	Yield Strength (10 <sup>3</sup> psi)	Tensile Strength (10 <sup>3</sup> psi)	10 <sup>4</sup> Cycles	Fatigue 10 <sup>5</sup> Cycles (10 <sup>3</sup>	Strength 10 <sup>6</sup> Cycles psi)	10 <sup>7</sup> Cycles	Fracture Toughness (10 <sup>3</sup> psi vin)
No. Observations	9	. 14	6	0	2	72	37	ß	10	11	7	43
Mean Value	0.283	29.7	11.1	1	0.28	217	251	169	109	100	89	62
Median Value	0.283	30.0	11.0	ı	0.28	224	263	192	113	105	95	55
Trimmed Mean	0.283	29.7	11.1	I	0.28	216	250	169	109	100	89	61
Standard Deviation	0.0004	0.9	0.2	ı	0.06	35	57	56	35	31	29	19
Percent Uncertainty	0.1	3.0	1.8	I	20.4	16.1	22.8	33.0	32.4	30.6	33.1	30.9
	Density (1b/in <sup>3</sup> )	Young's Modulus (10 <sup>6</sup> psi)	Shear Modulus (10 <sup>6</sup> psi)	Bulk Modulus (10 <sup>6</sup> psi)	Poisson's Ratio	Yield Strength (10 <sup>3</sup> psi)	Tensile Strength (10 <sup>3</sup> psi)	10 <sup>tt</sup> Cycles	Fatigue 10 <sup>5</sup> Cycles (10 <sup>3</sup>	Strength 10 <sup>6</sup> Cycles psi)	10 <sup>7</sup> Cycles	Fracture Toughnes <u>s</u> (10 <sup>3</sup> psi vin)
No. Observations	M	4	1	1	2	84	65	м	4	4	4	38
Mean Value	0.290	27.6	9.6	24.3	0.318	279	288	197	121	107	103	70
Median Value	0.289	27.2	ı	ı	0.318	282	295	190	122	107	102	74
Trimmed Mean	0.290	27.6	I	1	0.318	278	287	197	121	107	103	71
Standard Deviation	0.005	2.1	1	ı	0.011	33	30	31	29	27	21	15

21.8

20.9

25.0

24.0

15.6

10.4

12.0

3.3

I.

ı.

7.5

1.7

Percent Uncertainty

		TABLE 7	7(E). SUMM	ARY OF PROP	ERTY DATA I	FOR PRECIPI	ITATION-HARI	DENED STAL	INLESS ST	EEL 15-7		
	Density (1b/in <sup>3</sup>	Young's Modulus 3) (10 <sup>6</sup> psi)	Shear Modulus (10 <sup>6</sup> psi)	Bulk Modulus (10 <sup>6</sup> psi)	Poisson's Ratio	Yield Strength (10 <sup>3</sup> psi)	Tensile Strength (10 <sup>3</sup> psi)	10 <sup>4</sup> Cycles	Fatigue 10 <sup>5</sup> Cycles (10 <sup>3</sup>	s Strengtl 10 <sup>6</sup> Cycle: psi)	h 10 <sup>7</sup> s Cycle:	Fracture s Toughness (10 <sup>3</sup> psi vin)
No. Observations	3	4	3	0	1	37	36	0	1		-	
Mean Value	0.277	29.1	11.3	ı	0.320	213	242	I	177	165	160	57
Median Value	0.277	29.0	11.3	ı	I	210	240	I	ı.	I	I	52
Trimmed Mean	0.277	29.1	11.3	I	I	212	241	ł	ı	I	I	57
Standard Deviation	0.0	0.3	0.4	I	ı	25	23	ı	T	I	1	12
Percent Uncertainty	0.0	0.9	3.1	I	ł	11.6	9.4	ı	I	1	ı	21.9
	Density (1b/in <sup>3</sup> )	Young's Modulus (10 <sup>6</sup> psi)	Shear Modulus (10 <sup>6</sup> psi)	Bulk Modulus (10 <sup>6</sup> psi)	Poisson's Ratio	Vield Strength (10 <sup>3</sup> psi)	Tensile Strength (10 <sup>3</sup> psi)	10 <sup>4</sup> Cycles	atigue S 10 <sup>5</sup> Cycles (10 <sup>3</sup> <sub>1</sub>	trength 10 <sup>6</sup> Cycles osi)	10 <sup>7</sup> Cycles (1	Fracture Toughness 10 <sup>3</sup> psi <i>V</i> in)
No. Observations	9	1	2	0	7	139	50	0	-	2	2	96
Mean Value	0.1000	10.6	3.93	I	0.332	60.6	65.9		32	24.5	19.0	22.2
Median Value	0.1000	10.6	3.93	1	0*330	64.0	70.0	i	I	24.5	19.0	22.0
Trimmed Mean	0.1000	10.6	3.93	I	0.332	62.3	66.2	ı	ł	24.5	19.0	22.2
Standard Deviation	0.0	0.2	0.11	ı	0.006	11.0	12.5	I	,	7.8	5.7	4.5
Percent Uncertainty	0.0	1.8	2.7	ı	1.7	18.1	19.0	I	I	31.7	29.8	20.4

1020
STEEL
CARBON
FOR
DATA
PROPERTY
0F
SUMMARY
Ē
9
TABLE

	Density (1b/in <sup>3</sup> )	Young's Modulus (10 <sup>6</sup> psi)	Shear Modulus (10 <sup>6</sup> psi)	Bulk Modulus (10 <sup>6</sup> psi)	Poisson's Ratio	Yield Strength (10 <sup>3</sup> psi)	Tensile Strength (10 <sup>3</sup> psi)	F 10 <sup>4</sup> Cycles	atigue S 10 <sup>5</sup> Cycles (10 <sup>3</sup>	trength 10 <sup>6</sup> Cycles psi)	10 <sup>7</sup> Cycles	Fracture Toughness (10 <sup>3</sup> psi vin)	1
No. Observations	2	9	1	0	-	45	42	0	0	0	0	2	1
Mean Value	0.283	29.9	11.6	ı	0.288	62.3	89.8	ı	I	ī	ı	86.5	
Median Value	0.283	29.9	ı	ı	ı	53.0	79.0	ł	ı	I	ı	86.5	
Trimmed Mean	0.283	29.9	ı	ı	۱	63.7	91.5	I	ī		I	86.5	
Standard Deviation	0.0	0.3	ı	ı	ı	28.3	32.3	ı	ı	ı	I	6.4	
Percent Uncertainty	0.0	۱.۱	ı	I	I	45.5	36.0	I	ı	ī	ī	7.4	
					ορορερτν. ηΛ.		ON STEEL TO	C					
			LE 10(L/. ,					2		:			
								Ľ		1.1			

Fracture Toughness (10<sup>3</sup> psi ∕in) 104.0 ī ī ī ī 10<sup>7</sup> Cycles 0 ī ī 1 ı I Fatigue Strength 10<sup>4</sup> 10<sup>5</sup> 10<sup>6</sup> Cycles Cycles C<sub>,</sub> (10<sup>3</sup> psi) 0 ī ī I. ī ١ 0 ī ı 1 I ī 0 ı, ī ī ī I Yield Tensile Strength Strength  $(10^3 \text{ psi})$   $(10^3 \text{ psi})$ 94.8 94.8 92.0 19.3 20.4 12 66.5 59.0 66.5 27.3 41.1 20 Poisson's Ratio ī Т ı I 0 Т Bulk Modulus (10<sup>6</sup> psi) 0 ī ı ī ī ī. Shear Modulus (10<sup>6</sup> psi) ī ī ī 0 ī 1 Young's Modulus (10<sup>6</sup> psi) 30.7 ī ī ī ī Density (lb/in<sup>3</sup>) 0 ı ı. ı ī ı Percent Uncertainty Standard Deviation No. Observations Median Value Trimmed Mean Mean Value

	Density (lb/in <sup>3</sup> )	Young's Modulus (10 <sup>6</sup> psi)	Shear Modulus (10 <sup>6</sup> psi)	Bulk Modulus (10 <sup>6</sup> psi)	Poisson's Ratio	Yield Strength (10 <sup>3</sup> psi)	Tensile Strength (10 <sup>3</sup> psi)	10 <sup>4</sup> Cycles	<sup>z</sup> atigue S 10 <sup>5</sup> Cycles (10 <sup>3</sup>	itrength 10 <sup>6</sup> Cycles psi)	10 <sup>7</sup> Cycles	Fracture Toughness (10 <sup>3</sup> psi <i>v</i> in)	
No. Observations	4	Q	-	0	0	109	104	-	4	4	4	5	
Mean Value	0.282	29.1	11.4	I	ı	174.2	197.5	120.0	118.2	102.0	97.0	68.6	
Median Value	0.282	29.0	ı	I	I	171.0	195.5	ı	118.5	102.0	97.0	74.0	
Trimmed Mean	0.282	29.1	ı	ı	I	173.4	197.0	ı	118.2	102.0	97.0	68.6	
Standard Deviation	0.001	0.8		ı	ı	33.4	31.7	ı	2.1	4.6	8.1	14.7	
Percent Uncertainty	0.5	2.6	ı	ı	ı	19.2	16.1	1	1.7	4.5	8.3	21.4	
	Density (lb/in <sup>3</sup> )	Young's Modulus (10 <sup>6</sup> psi)	Shear Modulus (10 <sup>6</sup> psi)	Bulk Modulus (10 <sup>6</sup> psi)	Poisson's Ratio	Yield Strength (10 <sup>3</sup> psi)	Tensile Strength (10 <sup>3</sup> psi)	Fa 10 <sup>4</sup> Cycles	atigue St 10 <sup>5</sup> Cycles (10 <sup>3</sup> p	rrength 10 <sup>6</sup> Cycles si)	10 <sup>7</sup> Cycles	Fracture Toughness (10 <sup>3</sup> psi <i>√</i> in)	1
Vo. Observations	2	e	-	0	-	=	=	0	0	0	0	0	1
1ean Value	0.278	29.5	13.5	I	0.284	177.0	210.0	ı	ī	ī	ı	ı	
1edian Value	0.278	29.0	ł	ı	I	192.0	240.0	ı	ı	ı	,	I	
Trimmed Mean	0.278	29.5	ı	ı	I	177.0	210.0	ı	ı	I		ı	
Standard Deviation	0.0	0.8	ı	I	I	83.8	78.1	ı	ı	ı	ı	ı	
Percent Uncertainty	0.7	2.7	1	I	ı	47.3	37.2	ı		ı	1		

TABLE 11(E). SUMMARY OF PROPERTY DATA FOR STAINLESS STEEL AM355

		TABLE	13(E). SUMI	MARY OF PRO	ΡΕΓΤΥ DATA	FOR STAINLE	SS STEEL CU	STOM 455				
	Density (lb/in <sup>3</sup> )	Young's Modulus (10 <sup>6</sup> psi)	Shear Modulus (10 <sup>6</sup> psi)	Bulk Modulus (10 <sup>6</sup> psi)	Poisson's Ratio	Yield Strength (10 <sup>3</sup> psi)	Tensile Strength (10 <sup>3</sup> psi)	F 10 <sup>4</sup> Cycles	atigue S 10 <sup>5</sup> Cycles (10 <sup>3</sup>	trength 10 <sup>6</sup> Cycles psi)	10 <sup>7</sup> Cycles	Fracture Toughness (10 <sup>3</sup> psi /in)
No. Observations	-	6	-	0	2	51	53	-	2	22	ى ۲	4
Mean Value	0.280	23.7	11.0	ı	0.300	216.0	228.0	133.0	128.5	101.8	99.4	65.8
Median Value	ı	28.5	ı	ı	0.300	220.0	235.0	1	128.5	104.0	94.0	60.5
Trimmed Mean	ı	28.7	ı	I	0.300	214.6	226.9	ı	128.5	101.8	99.4	65.8
Standard Deviation	1	0.7	1	ı	0.0	37.0	29.6	ı	6.4	11.5	14.3	27.2
Percent Uncertainty	1	2.6	ı	1	0.0	17.1	13.0	ı	5.0	11.3	14.4	41.3
	Density (lb/in <sup>3</sup> )	Young's Modulus (10 <sup>6</sup> psi)	Shear Modulus (10 <sup>6</sup> psi)	Bulk Modulus (10 <sup>6</sup> psi)	Poisson's Ratio	Yield Strength (10 <sup>3</sup> psi)	Tensile Strength (10 <sup>3</sup> psi)	F 10 <sup>4</sup> Cycles	catigue S 10 <sup>5</sup> Cycles (10 <sup>3</sup>	strength 10 <sup>6</sup> Cycles psi)	10 <sup>7</sup> Cycles	Fracture Toughness (10 <sup>3</sup> psi <i>v</i> in)
No. Observations	0	7	С	0	0	72	65	£	10	=	7	12
Mean Value	1	29.8	1	ı	I	242.4	288.2	174.6	135.6	114.3	112.9	27.4
Median Value	I	30.1	ı	1	1	241.0	296.0	160.0	143.5	128.0	130.0	26.5
Trimmed Mean	ł	29.8	ı	- 1	ı	247.1	291.9	174.6	135.6	114.3	112.9	27.4
Standard Deviation	I	1.7	ı	١	1	60.3	61.3	28.4	31.5	32.0	35.3	15.2
Percent Uncertainty		5.7	I	ı	ı	24.9	21.3	16.3	23.2	28.0	31.2	55.4

	Density (1b/in <sup>3</sup> )	Young's Modulus (10 <sup>6</sup> psi)	Shear Modulus (10 <sup>6</sup> psi)	Bulk Modulus (10 <sup>6</sup> psi)	Poisson's Ratio	Yield Strength (10 <sup>3</sup> psi)	Tensile Strength (10 <sup>3</sup> psi)	10 <sup>4</sup> Cycles	Fatigue S 10 <sup>5</sup> Cycles (10 <sup>3</sup>	trength 10 <sup>6</sup> Cycles psi)	10 <sup>7</sup> Cycles (1	Fracture Toughness 10 <sup>3</sup> psi /in)
No. Observations	I	16	1	0	П	235	206	11	15	19	20	49
Mean Value	0.164	16.7	6.5	I	0.320	163	172	144	119	107	96	45
Median Value	I	16.7	I	ı	ı	164	174	150	124	110	98	39
Trimmed Mean	ı	16.6	ı	ı	I	165	175	144	123	108	67	44
Standard Deviation	ı	0.6	1	ı	ı	20	20	15	16	15	15	15
Percent Uncertainty	I	3.3	I	I	I	12	12	11	14	14	16	34
	Density (1b/in <sup>3</sup>	Young's Modulus ) (10 <sup>6</sup> psi	Shear Modulus ) (10 <sup>6</sup> psi)	Bulk Modulus (10 <sup>6</sup> psi)	Poisson'. Ratio	s Yield Strength (10 <sup>3</sup> psi)	Tensile n Strength (10 <sup>3</sup> psi)	Cycles	Fatigue 10 <sup>5</sup> Cycles (10	Strength 10 <sup>6</sup> Cycles ) <sup>3</sup> psi)	10 <sup>7</sup> Cycles	Fracture Toughness (10 <sup>3</sup> psi vin)
No. Observations	1	70	0	0	0	159	155	1	]	1	0	10
Mean Value	0.175	15.5	I	I	I	167	177	75	80	75	I	48
Median Value	I	15.5	I	I	I	172	181	I	I	I	I	47
Trimmed Mean	I	15.6	I	I	I	166	176	I	I	I	I	48
Standard Deviation	I	1.2	I	I	I	25	26	I	I	I	I	8
Percent Uncertainty	I	8.0	I	I	I	15	15	I	I	I	I	18

	Density (lb/in <sup>3</sup> )	Young's Modulus (10 <sup>6</sup> psi)	Shear Modulus (10 <sup>6</sup> psi)	Bulk Modulus (10 <sup>6</sup> psi)	Poisson's Ratio	Yield Strength (10 <sup>3</sup> psi)	Tensile Strength (10 <sup>3</sup> psi)	10 <sup>4</sup> Cycles	Fatigue S 10 <sup>5</sup> Cycles (10 <sup>3</sup>	trength 10 <sup>6</sup> Cycles psi)	10 <sup>7</sup> Cycles	Fracture Toughness (10 <sup>3</sup> psi √in)
No. Observations	2	. 2	0	0	0	5	4	0	0	0	C	1
Mean Value	0.282	29.3	I	ı	I	84	115	1	• 1	> 1	> I	- 69
Median Value	0.282	29.3	I	I	I	85	120	I	ı	ı	ı	1 1
Trimmed Mean	0.282	29.3	I	I	I	84	115	I	I	I	I	ı
Standard Deviation	0.0	0.4	I	ı	I	15	19	I	I	I	ı	ı
Percent Uncertainty	0.0	1.2	I	I	I	18	17	I	I	I	I	I
	Density (1b/in <sup>3</sup> )	Young's Modulus (10 <sup>6</sup> psi)	Shear Modulus (10 <sup>6</sup> psi)	Bulk Modulus (10 <sup>6</sup> psi)	Poisson's Ratio	Yield Strength (10 <sup>3</sup> psi)	Tensile Strength (10 <sup>3</sup> psi)	10 <sup>4</sup> Cycles	Fatigue S 10 <sup>5</sup> Cycles (10 <sup>3</sup>	trength 10 <sup>6</sup> Cycles psi)	10 <sup>7</sup> Cycles	Fracture Toughness (10 <sup>3</sup> psi $\sqrt{\mathrm{in}}$ )
No. Observations	7	11	4	1	e	50	56	1	1		1	1
Mean Value	0.288	28.3	11.6	25.8	0.294	43	91	39	34	31	29	343
Median Value	0.288	28.0	11.6	I	0.295	36	85	I	ı	I	I	I
Trimmed Mean	0.288	28.3	11.6	I	0.294	39	90	ı	I	I	I	1
Standard Deviation	0.001	1.4	0.5	1	0.004	24	19	I	I	I	I	1

I.

ī

i.

ī

i

21

56

1.2

I.

4.8

5.1

0.3

Percent Uncertainty

		TABLE 1	9(E). SUMM	ARY OF PROP	ERTY DATA F	FOR IRON BA	ASED SUPERAI	LOY A286				
	Density (1b/in <sup>3</sup> )	Young's Modulus (10 <sup>6</sup> psi)	Shear. Modulus (10 <sup>6</sup> psi)	Bulk Modulus (10 <sup>6</sup> psi)	Poisson's Ratio	Yield Strength (10 <sup>3</sup> psi)	Tensile Strength (10 <sup>3</sup> psi)	10 <sup>4</sup> Cycles	Fatigue S 10 <sup>5</sup> Cycles (10 <sup>3</sup>	Strength 10 <sup>6</sup> Cycles 9 psi)	10 <sup>7</sup> Cycles	Fracture Toughness (10 <sup>3</sup> psi /in)
No. Observations	2	17	œ	1	9	72	86	2	4	4	2	3
Mean Value	0.287	28.5	10.6	22.4	0.301	119	145	75	73	57	61	147
Median Value	0.286	29.0	10.5	ı	0.303	106	152	75	81	61	61	145
Trimmed Mean	0.287	28.4	10.6	1	0.301	122	144	75	73	57	61	147
Standard Deviation	0.002	1.3	0.2	ı	0.006	37	77	35	20	15	4	34
Percent Uncertainty	0.5	4.5	2.2	ı	2.1	31	30	47	28	27	9	23
		Young's	Shear	Bulk	Poisson's	Yield	Tensile	104	Fatigue St 10 <sup>5</sup>	trength 10 <sup>6</sup>	107	Fracture
	Density (lb/in <sup>3</sup> )	Young's Modulus (10 <sup>6</sup> psi)	Shear Modulus (10 <sup>6</sup> psi)	Bulk Modulus (10 <sup>6</sup> psi)	Poisson's Ratio (	Yield Strength (10 <sup>3</sup> psi)	Tensile Strength (10 <sup>3</sup> psi)	10 <sup>4</sup> Cycles	Fatigue St 10 <sup>5</sup> Cycles (10 <sup>3</sup>	trength 10 <sup>6</sup> Cycles psi)	10 <sup>7</sup> Cycles	Fracture Toughness (10 <sup>3</sup> psi /in)
lo. Observations	-	2	0	0	9		64	2	2	6	-	7.6
lean Value	0.292	27.5	1	ł	0.300	330	339	179	- 144	119	111	42.9
ledian Value	I	27.5	I	ı	0.295	336	345	179	144	119	I	39.5

43.1 13.0 30

E E E

119 4 3

144 13 9

179 1 1

339 24 7

329 27 8

0.3000.04515.1

і і і

E E E

27.5 2.1 7.7

1 I E

Standard Deviation Percent Uncertainty

Trimmed Mean

(6)         (15)         (10)         (10)         (10)         (11)         (10)         (11)         (10)         (11)         (10)         (11)         (10)         (11)         (10)         (11)         (10)         (11) <th< th=""><th></th><th>Density</th><th>Young's Modulus</th><th>Shear Modulus</th><th>Bulk Modulus</th><th>Poisson's Ratío</th><th>Yield Strength</th><th>Tensile Strength</th><th>10<sup>4</sup> Cycles</th><th>Fatigue S 10<sup>5</sup> Cycles</th><th>10<sup>6</sup> Cycles</th><th>10<sup>7</sup> Cycles</th><th>Fracture Toughness</th></th<>		Density	Young's Modulus	Shear Modulus	Bulk Modulus	Poisson's Ratío	Yield Strength	Tensile Strength	10 <sup>4</sup> Cycles	Fatigue S 10 <sup>5</sup> Cycles	10 <sup>6</sup> Cycles	10 <sup>7</sup> Cycles	Fracture Toughness
B0: Observations       3       2       2       0       11 $ 0.264$ $0.286$ $33.5$ $11.4$ $ 0.234$ $126$ $176$ $ 102$ $76$ $70$ Rotan Value $0.286$ $23.5$ $11.4$ $  123$ $176$ $ 102$ $76$ $70$ Rotandard bwintion $0.286$ $23.5$ $11.4$ $  123$ $176$ $ 102$ $76$ $70$ Rotandard bwintion $0.001$ $0.1$ $0.2$ $  -$		( UT /0T)	(TSA OT)	(TSd OT)	(TSA DT)		(Ted OT)	(ted ot)			(Ted		(IIIT A ted or)
Real Value         0.286         28.5         11.4         -         0.294         126         176         -         102         76         70           Rudian Value         0.286         28.5         11.4         -         -         123         174         -         102         76         70           Trumed Nam         0.286         28.5         11.4         -         -         123         174         -         102         76         70           Friendel Nam         0.001         0.1         0.1         -         -         123         174         -         102         76         70           Friendel Nam         0.001         0.1         1.9         -         -         7         3         -         40         11         10           Freedel Noertainty         0.0         0.0         1.9         -         7         3         -         40         13         16           Freedel Noertainty         0.0         1.9         -         7         3         -         40         13         16         7           Freede Noertainty         0.0         1.9         Noutis         Nodulus         Nodulus	No. Observations	ĉ	2	2	0	1	9	9	0	2	4	4	0
Median Value         0.286         28.5         11.4         -         -         123         174         -         102         78         70           Trimmed Mean         0.286         28.5         11.4         -         -         123         176         -         102         76         70           Standard Devlation         0.001         0.1         0.2         -         -         7         3         -         40         11         11           Percent Uncertainty         0.2         0.5         1.9         -         -         7         3         -         40         15         16           Percent Uncertainty         0.2         0.5         1.9         -         -         7         3         -         40         15         16         17           Percent Uncertainty         0.2         0.5         1.9         -         7         3         -         40         15         16         17           Percent Uncertainty         0.2         1.9         Strength         Fatigue Strength         10 <sup>4</sup> 10 <sup>4</sup> 10 <sup>7</sup> 10 <sup>7</sup> 10 <sup>7</sup> 10 <sup>7</sup> 10 <sup>7</sup> 10         10 <sup>7</sup> 10 <sup>7</sup>	Mean Value	0.286	28.5	11.4	I	0.294	126	176	I	102	76	70	I
Triamed Mean $0.286$ $28.5$ $11.4$ $  125$ $176$ $76$ $70$ Standard Deviation $0.011$ $0.1$ $0.2$ $   -$ - $-$	Median Value	0.286	28.5	11.4	I	ı	123	174	ı	102	78	70	ı
Standard Deviation         0.001         0.1         0.2         -         -         9         6         -         40         11         11           Percent Uncertainty         0.2         0.5         1.9         -         -         7         3         -         40         15         16           Percent Uncertainty         0.2         0.5         1.9         -         -         7         3         -         40         15         16           Percent Uncertainty         0.2         0.5         1.9         -         -         7         3         -         40         15         16           Percent Uncertainty         0.2         0.5         Strength Value         Strength Stren	Trimmed Mean	0.286	28.5	11.4	I	ı	125	176	ı	102	76	70	I
Percent Uncertainty         0.2         0.5         1.9         -         7         3         -         40         15         16           TABLE 22 (E).         SUMMARY OF PROPERTY DATA FOR UNITEDP         212         -         40         15         16           Image: Strength	Standard Deviation	0.001	0.1	0.2	I	ı	6	9	I	40	11	11	I
TABLE 22 (E). SUMMARY OF PROPERTY DATA FOR UNITED 212         TABLE 22 (E). SUMMARY OF PROPERTY DATA FOR UNITED 212         Density       Young's       Shear       Bulk       Poisson's       Yield       Tarsile       10 <sup>4</sup> 10 <sup>5</sup> 10 <sup>6</sup> 10 <sup>7</sup> Density       Young's       Shear       Bulk       Ratio       Strength       Transile       10 <sup>4</sup> 10 <sup>5</sup> 10 <sup>6</sup> 10 <sup>7</sup> Density       Modulus       Modulus       Modulus       Modulus       Modulus       Ratio       Strength       Transile       10 <sup>4</sup> 10 <sup>5</sup> 10 <sup>6</sup> Density       Modulus       Modulus       Modulus       Modulus       Ratio       Strength       Transile       10 <sup>4</sup> 10 <sup>5</sup> 10 <sup>6</sup> Mean Value       1       1       0       0       0       2       3       10 <sup>6</sup> 10 <sup>7</sup> 10 <sup>7</sup> 10 <sup>7</sup> Mean Value       1       1       0       0       0       2       3       13       1       2       2       2       2       2       2       2       2       2       2       2       2       2       2       2       2       2       2       2	Percent Uncertainty	0.2	0.5	1.9	I	I	7	c	I	40	15	16	I
No. Observations       1       1       0       0       2       3       0       0       0       0       0         Mean Value       0.286       29.0       -       -       -       135       196       -		Density (1b/in <sup>3</sup> )	Young's Modulus (10 <sup>6</sup> psi)	Shear Modulus (10 <sup>6</sup> psi)	Bulk Modulus (10 <sup>6</sup> psi)	Poisson's Ratio	Yield Strength (10 <sup>3</sup> psi)	Tensile Strength (10 <sup>3</sup> psi)	10 <sup>4</sup> Cycles	Fatigue S 10 <sup>5</sup> Cycles (10 <sup>3</sup>	trength 10 <sup>6</sup> Cycles psi)	10 <sup>7</sup> Cycles	Fracture Toughness (10 <sup>3</sup> psi √in)
Mean Value       0.286       29.0       -       -       135       196       -	No. Observations	г	L	0	0	0	2	3	0	0	0	0	0
Median Value       - <t< td=""><td>Mean Value</td><td>0.286</td><td>29.0</td><td>I</td><td>I</td><td>ı</td><td>135</td><td>196</td><td>I</td><td>I</td><td>I</td><td>I</td><td>I</td></t<>	Mean Value	0.286	29.0	I	I	ı	135	196	I	I	I	I	I
Trimmed Mean       - <t< td=""><td>Median Value</td><td>I</td><td>I</td><td>I</td><td>I</td><td>1</td><td>135</td><td>187</td><td>I</td><td>I</td><td>I</td><td>I</td><td>I</td></t<>	Median Value	I	I	I	I	1	135	187	I	I	I	I	I
Standard Deviation     -<	Trimmed Mean	1	ı	ı	I	ı	135	196	I	I	I	I	I
Percent Uncertainty	Standard Deviation	I	I	I	I	ı	1	16	I	I	I	I	I
	Percent Uncertainty	I	1	I	I	1	1	∞	I	I	ı	ı	ı

	Here	There	Ratio
Density (g/cm <sup>3</sup> )	7.971	7.958	1.002
Young's Modulus (GPa)	195.1	194.6	1.003
Shear Modulus (GPa)	79.9	75.2	1.060
Bulk Modulus (GPa)	177.9	157.5	1.130
Poisson's Ratio	0.294	0.294	1.000
Yield Strength (MPa)	297	227	1.308
Tensile Strength (MPa)	627	583	1.075

# TABLE 23. FOR STAINLESS STEEL 316, COMPARISON OF PRESENT RESULTS WITH TWO OTHER VARIABILITY STUDIES.

Represents a single value.

# Appendix 1. Physical and Mechanical Properties of Technological Alloys: A Data-Source Bibliography

Everhart, J. L., Lindlieff, W. E., Kanegio, J., Weissler, P. G., and Siegel, F., *Mechanical Properties of Metals and Alloys*, NBS Circular C447 (U.S. Govt. Print. Off., Washington, DC, 1943).

Hoyt, S. L., Metal Data (Reinhold, New York, 1952).

- Pagonis, G. A., *The Light Metals Handbook* (Van Nostrand, Toronto, 1954).
- Smithells, C. J., Metals Reference Book, Volumes 1-2 (Interscience, New York, 1955).
- Tarr, A. L., and Osborn, J. M., Properties of metallic materials at low temperatures. Unpublished study, The Engineer Center and Fort Belvoir Engineer Research and Development Laboratories, Corps of Engineers, U.S. Army (1956).
- Materials property manual and summary report. North American Aviation report AL-2604 (Oct. 1957).
- AGARD Material Properties Handbook, Volumes 1-3 (The Royal Aeronautical Society, London, 1959).
- Durham, T. F., McClintock, R. M., and Reed, R. P., Cryogenic Materials Data Handbook, Volumes 1-2 (U.S. Department of Commerce, National Bureau of Standards, Boulder, CO, 1960).
- McClintock, R. M., and Gibbons, H. P., Mechanical Properties of Structural Materials at Low Temperatures, NBS Monograph 13 (U.S. Govt. Print. Off., Washington, DC, 1960).
- Lyman, T. (editor), Metals Handbook, Volume 1, Properties and Selection of Metals (Amer. Soc. for Metals, Novelty, OH, 1961).
- Midgley, P., and Thomas, D. F., *The mechanical properties of metals at cryogenic temperatures*, Rocket Propulsion Establishment, Westcott, England, Tech. Memo. No. 237 (Oct. 1961).
- Warren, K. A., and Reed, R. P., Tensile and Impact Properties of Selected Materials from 20 to 300 °K, NBS Monograph 63 (U.S. Govt. Print. Off., Washington, D.C., 1963).
- Schwartzberg, F. R., Osgood, S. H., Keys, R. D., and Kiefer, T. F., Cryogenic Materials Data Handbook, Volumes 1-2 (Air Force

Materials Laboratory, Wright-Patterson Air Force Base, OH, 1964). Available from NTIS, order numbers AD713619, AD713620.

- Materials Properties Data Book, NERVA Program Report 2275 (Aerojet Nuclear Systems Co., Sacramento, CA, 1970).
- Wood, R. A., and Favor, R. J., *Titanium Alloys Handbook* (Battelle Metals and Ceramics Information Center, Columbus, OH, 1972). Available from NTIS, order number AD758335.
- Damage Tolerant Design Handbook (Battelle Metals and Ceramics Information Center, Columbus, OH, 1973).
- Woldman, N. E., and Gibbons, R. C., *Engineering Alloys* (Van Nostrand Reinhold, New York, 1973).
- *Aluminum Standards and Data 1974-75* (The Aluminum Assoc., New York, 1974).
- Matthews, W. T., Typical plane strain fracture toughness of aircraft materials, in Liebowitz, H. (editor), *Fracture Mechanics of Aircraft Structures, AGARDograph No. 176* (North Atlantic Treaty Organization, 1974), pp. 509-579. Available from NTIS, order number AD777641.
- Military Standardization Handbook, Metallic Materials and Elements for Aerospace Vehicle Structares, MIL-HDBK-5B (U.S. Dept. of Defense, Washington, DC, 1975).
- Deel, O. L., Ruff, P. E., and Mindlin, H., Engineering data on new aerospace structural materials, Battelle Columbus Laboratories report AFML-TR-75-97 (June 1975), 267 pp.
- Lynch, C. T. (editor), Handbook of Materials Science, Volume 2: Metals, Composites, and Refractory Materials (CRC Press, Cleveland, OH, 1975).
- Handbook on Materials for Superconducting Machinery (Battelle Metals and Ceramics Information Center, Columbus, OH, 1977).
- Moore, T. D. (editor), Structural Alloys Handbook, Volumes 1-2 (Mechanical Properties Data Center, Traverse City, MI, 1977).
- Wolf, J. (editor), Aerospace Structural Metals Handbook (Mechanical Properties Data Center, Traverse City, MI, 1977).

# Appendix 2.

Min.	Avg.	Max.	Element	Wt	A +
					At.
			······		
Treatment:					
			Form:		
g/cm <sup>3</sup>	lb/in <sup>3</sup>	Comments:			
GPa	10 <sup>6</sup> psi				
GPa	10 <sup>6</sup> psi				
GPa	10 <sup>6</sup> psi				
MPa	ksi				
MPa	ksi	· ·			
MPa	ksi	cycles			
MPa√m	ksi√ in				
MPa	ksi	strain	hours		
			<u></u>		

NBS-114A (REV. 2-80)			
U.S. DEPT. OF COMM.	1. PUBLICATION OR	2. Performing Organ. Report No.	3. Publication Date
BIBLIOGRAPHIC DATA	NCDDC-NRC 61 Part V		January 1982
SHEET (See instructions)			
4. TITLE AND SUBTITLE			
		1	
Physical Properties	s Data Compilations Re	levant to Energy Storag	ge. v.
Mechanical Property	les Data on Alloys for	Use In Flywheels	
5. AUTHOR(S)			
H. M. Ledbetter			
6. PERFORMING ORGANIZA	TION (If joint or other than NBS	, see instructions)	7. Contract/Grant No.
NATIONAL BUREAU OF	STANDARDS		
DEPARTMENT OF COMM	ERCE	8	. Type of Report & Period Covered
WASHINGTON, D.C. 2023	4		N/A
		DDRESS (Streat City State 710)	
9. SPONSORING ORGANIZA	TON NAME AND COMPLETE A	DDRESS (Street, City, State, ZIP)	
Same as Item 6			
10. SUPPLEMENTARY NOTE	S	·····	
Library	y of Congress Catalog	Card Number: 81-14053	
	0 0		
Document describes a	computer program; SF-185, FIP	S Software Summary, is attached.	
11. ABSTRACT (A 200-word o	or less factual summary of most	significant information. If docume	nt includes a significant
bibliography or literature s	survey, mention it here)		
This report of	leals with the physica	1 and mechanical proper	ties of twenty-one
commercial alloys	that are candidates f	or flywheel rotors used	l as inertial-energy-
complexity from a	Base metals include a	luminum, iron, and tita	anium. Alloys vary in
density Young's m	mple carbon steels to	superalloys. Property	les include: mass
strength ultimate	strength fatigue et	, bulk modulus, Poissor	n's ratio, yield
Property values we	are collected from man	v types of sources and	wore analyzed statisti
cally to detect po	ssible outlying value	s For each allow the	were analyzed statisti-
chemical compositi	on, typical heat trea	tment, metallurgical de	e report contains typical
property values.	The report also shows	the variations of thes	se properties and the
relative abundance	s of experimental pro	perty values.	
		-	
12. KEY WORDS (Six to twelv	e entries: alphabetical order: ca	bitalize only proper names; and se	eparate key words by semicolons)
Alloy; aluminum al	lov: elastic constant	s. flywheel, iron allow	. mass density.
mechanical propert	y; titanium alloy.	s, ilywneer, iron arroy	; mass densicy;
	1		
13. AVAILABILITY			14. NO. OF PRINTED PAGES
XXX Unlimited			
For Official Distributi	on. Do Not Release to NTIS		42
Order From Superinten 20402.	ident of Documents, U.S. Govern	ment Printing Office, Washington,	D C 15. Price
X Order From National 3	Technical Information Service (N	TIS), Springfield, VA 22161	
Las order From Mattonal	connear monnation service (N	110/, 0p/mg/1010, 1/1 22101	

USCOMM-DC 6043-P80

Where can you find all the reference data you need? Right in the Journal of Physical and Chemical Reference Data!

Now in its tenth year, this valuable publication has proved that it fills the important gaps for you in the literature of the physical sciences.

physical sciences. Published by the American Institute of Physics and the American Chemical Society for the National Bureau of Standards, this quarterly gives you quantitative numerical data, with recommended values and uncertainty limits chosen by experts in the field.

Critical commentary on methods of measurement and sources of error, as well as full references to the original literature, is an integral part of each of your four issues a year.

Can you afford to be without this prime source of reliable data on physical and chemical properties? To start receiving your copies, just fill in the order form and drop into the mail.

If you do use a purchase order, please attach the printed form as this will help us to expedite your order.

Send for complete list of reprints!

Available in Hard Copy or Microfiche

Journal of Physical and Chemic American Chemical Society 1155 Sixteenth Street, N.W. Washington, D.C. 20036	al Reference Data		1981
Yes. I would like to receive JOURI DATA at the one year rate checke	NAL OF PHYSICAL d below:	AND CHEMICAL P	REFERENCE
	U.S.	Foreign	
ACS Members, AIP Members, and Affiliated Societies Nonmembers	□\$ 34.00 □\$135.00	□\$40.00 □\$141.00	
Bill me Bill company Paymer	t enclosed (Payable to	American Chemica! Societ	y)
Charge my 🗆 MasterCard 🗆 VISA	Account No	Interbank	No
Expire Date	Signature		
Name			
Organization		Title	
City	State/Country	Z	ıp
Journal subscriptions start January 1981.	Allow 90 days for your firs	t copy to be mailed	
Foreign payment must be made in U.S. current	ersonal use only. w. by international money (	order, UNESCO coupons, L	J S. bank draft, or
order through your subscription agency.	,,		1108H

CALL TOLL FREE: (800) 424-6747



For a review copy, write Journal of Research, National Bureau of Standards, U.S. DEPARTMENT OF COMMERCE Washington, D.C. 20234

#### Subscription Order Form

Enter my subscription to NBS Journal of Research at \$17.00. Add \$4.25 for foreign mailing. No additional postage is required for mailing within the United States or its possessions. (SJR—File Code 2Q)

#### Send Subscription to:



# Subscribe now – The new National Bureau of Standards Journal

The expanded Journal of Research of the National Bureau of Standards reports NBS research and development in those disciplines of the physical and engineering sciences in which the Bureau is active. These include physics, chemistry, engineering, mathematics, and computer sciences. Papers cover a broad range of subjects, with major emphasis on measurement methodology, and the basic technology underlying standardization. Also included from time to time are survey articles on topics closely related to the Bureau's technical and scientific programs. As a special service to subscribers each issue contains complete citations to all recent NBS publications in NBS and non-NBS media. Issued six times a year. Annual subscription: domestic \$17.00; foreign \$21.25. Single copy, \$3.00 domestic; \$3.75 foreign.

• Note: The Journal was formerly published in two sections: Section A "Physics and Chemistry" and Section B "Mathematical Sciences."

NBS Board of Editors Churchill Eisenhart, Executive Editor (Mathematics) John W. Cooper (Physics) Donald D. Wagman (Chemistry) Andrew J. Fowell (Engineering) Joseph O. Harrison (Computer Science) Stephen J. Smith (Boulder Labs.)

> Remittance Enclosed (Make checks payable to Superintendent of Documents)

\_\_\_\_\_

Charge to my Deposit Account No.

MAIL ORDER FORM TO: Superintendent of Documents Government Printing Office Washington, D.C. 20402

. . . the monthly There's magazine of the National Bureau of Standards. Still featured are special aranew ticles of general interest on current topics such as consumer product safety and building look technology. In addition, new sections are designed to . . . PROVIDE **SCIENTISTS** with illustrated discussions of recent technical developments and work in progress . . . INFORM INDUSTRIAL MANAGERS of technology transfer activities in Federal and private labs. . . DESCRIBE TO MAN-UFACTURERS advances in the field of voluntary and mandatory standards. The new DIMENSIONS/NBS also carries complete listings of upcoming conferences to be held at NBS and reports on all the latest NBS publications, with information on how to order. Finally, each issue carries a page of News Briefs, aimed at keeping scientist and consumer alike up to date on major developments at the Nation's physical sciences and measurement laboratory.

(please detach here)

STATE

ZIP CODE

#### SUBSCRIPTION ORDER FORM

Send Subscription to:

Enter my Subscription To DIMENSIONS/NBS at \$11.00. Add \$2.75 for foreign mailing. No additional postage is required for mailing within the United States or its possessions. Domestic remittances should be made either by postal money order, express money order, or check. Foreign remittances should be made either by international money order, draft on an American bank, or by UNESCO coupons.

STREET ADDRESS

- Remittance Enclosed (Make checks payable to Superintendent of Documents)
- Charge to my Deposit Account No.

MAIL ORDER FORM TO: Superintendent of Documents Government Printing Office Washington, D.C. 20402

PLEAS	E PR	INT

## Announcement of New Publications in National Standard Reference Data Series

Superintendent of Documents, Government Printing Office, Washington, D.C. 20402

Dear Sir:

Please add my name to the announcement list of new publications to be issued in the series: National Standard Reference Data Series – National Bureau of Standards.

Name			
Company			
Address			
City	State	Zip Code	

(Notification Key N-519)



# **NBS TECHNICAL PUBLICATIONS**

#### PERIODICALS

**JOURNAL OF RESEARCH**—The Journal of Research of the National Bureau of Standards reports NBS research and development in those disciplines of the physical and engineering sciences in which the Bureau is active. These include physics, chemistry, engineering, mathematics, and computer sciences. Papers cover a broad range of subjects, with major emphasis on measurement methodology and the basic technology underlying standardization. Also included from time to time are survey articles on topics closely related to the Bureau's technical and scientific programs. As a special service to subscribers each issue contains complete citations to all recent Bureau publications in both NBS and non-NBS media. Issued six times a year. Annual subscription; domestic \$18; toreign \$22.50. Single copy \$4.25 domestic; \$5.35 foreign.

**DIMENSIONS/NBS**—This monthly magazine is published to inform scientists, engineers, business and industry leaders, teachers, students, and consumers of the latest advances in science and technology, with primary emphasis on work at NBS. The magazine highlights and reviews such issues as energy research, fire protection, building technology, metric conversion, pollution abatement, health and safety, and consumer product performance. In addition, it reports the results of Bureau programs in measurement standards and techniques, properties of matter and materials, engineering standards and services, instrumentation, and automatic data processing. Annual subscription: domestic \$11; foreign \$13.75.

#### **NONPERIODICALS**

**Monographs**—Major contributions to the technical literature on various subjects related to the Bureau's scientific and technical activities.

Handbooks—Recommended codes of engineering and industrial practice (including safety codes) developed in cooperation with interested industries, professional organizations, and regulatory bodies.

**Special Publications**—Include proceedings of conferences sponsored by NBS, NBS annual reports, and other special publications appropriate to this grouping such as wall charts, pocket cards, and bibliographies.

Applied Mathematics Series—Mathematical tables, manuals, and studies of special interest to physicists, engineers, chemists, biologists, mathematicians, computer programmers, and others engaged in scientific and technical work.

National Standard Reference Data Series—Provides quantitative data on the physical and chemical properties of materials, compiled from the world's literature and critically evaluated. Developed under a worldwide program coordinated by NBS under the authority of the National Standard Data Act (Public Law 90-396). NOTE: The principal publication outlet for the foregoing data is the Journal of Physical and Chemical Reference Data (JPCRD) published quarterly for NBS by the American Chemical Society (ACS) and the American Institute of Physics (AIP). Subscriptions, reprints, and supplements available from ACS, 1155 Sixteenth St., NW, Washington, DC 20056.

**Building Science Series**—Disseminates technical information developed at the Bureau on building materials, components, systems, and whole structures. The series presents research results, test methods, and performance criteria related to the structural and environmental functions and the durability and safety characteristics of building elements and systems.

**Technical Notes**—Studies or reports which are complete in themselves but restrictive in their treatment of a subject. Analogous to monographs but not so comprehensive in scope or definitive in treatment of the subject area. Often serve as a vehicle for final reports of work performed at NBS under the sponsorship of other government agencies.

Voluntary Product Standards—Developed under procedures published by the Department of Commerce in Part 10, Title 15, of the Code of Federal Regulations. The standards establish nationally recognized requirements for products, and provide all concerned interests with a basis for common understanding of the characteristics of the products. NBS administers this program as a supplement to the activities of the private sector standardizing organizations.

**Consumer Information Series**—Practical information, based on NBS research and experience, covering areas of interest to the consumer. Easily understandable language and illustrations provide useful background knowledge for shopping in today's technological marketplace.

Order the **above** NBS publications from: Superintendent of Documents, Government Printing Office, Washington, DC 20402.

Order the following NBS publications—FIPS and NBSIR's—from the National Technical Information Services, Springfield, VA 22161.

Federal Information Processing Standards Publications (FIPS PUB)—Publications in this series collectively constitute the Federal Information Processing Standards Register. The Register serves as the official source of information in the Federal Government regarding standards issued by NBS pursuant to the Federal Property and Administrative Services Act of 1949 as amended, Public Law 89-306 (79 Stat. 1127), and as implemented by E:. ecutive Order 11717 (38 FR 12315, dated May 11, 1973) and Part 0 of Title 15 CFR (Code of Federal Regulations).

**NBS Interagency Reports (NBSIR)**—A special series of interim or final reports on work performed by NBS for outside sponsors (both government and non-government). In general, initial distribution is handled by the sponsor; public distribution is by the National Technical Information Services, Springfield, VA 22161, in paper copy or microfiche form.

# U.S. DEPARTMENT OF COMMERCE National Bureau of Standards

Washington, DC 20234

OFFICIAL BUSINESS

Penalty for Private Use, \$300

POSTAGE AND FEES PAID U.S. DEPARTMENT OF COMMERCE COM-215



THIRD CLASS