NATIONAL BUREAU OF STANDARDS REPORT

8510

Quarterly Report

on

EVALUATION OF REFRACTORY QUALITIES OF

CONCRETES FOR JET AIRCRAFT WARM-UP, POWER CHECK

MAINTENANCE APRONS, AND RUNWAYS

BY

J. V. Ryan, E. C. Tuma and W. H. Bettum

U. S. DEPARTMENT OF COMMERCE
NATIONAL BUREAU OF STANDARDS

THE NATIONAL BUREAU OF STANDARDS

The National Bureau of Standards is a principal focal point in the Federal Government for assuring maximum application of the physical and engineering sciences to the advancement of technology in industry and commerce. Its responsibilities include development and maintenance of the national standards of measurement, and the provisions of means for making measurements consistent with those standards; determination of physical constants and properties of materials; development of methods for testing materials, mechanisms, and structures, and making such tests as may be necessary, particularly for government agencies; cooperation in the establishment of standard practices for incorporation in codes and specifications; advisory service to government agencies on scientific and technical problems; invention and development of devices to serve special needs of the Government; assistance to industry, business, and consumers in the development and acceptance of commercial standards and simplified trade practice recommendations; administration of programs in cooperation with United States business groups and standards organizations for the development of international standards of practice; and maintenance of a clearinghouse for the collection and dissemination of scientific, technical, and engineering information. The scope of the Bureau's activities is suggested in the following listing of its four Institutes and their organizational units.

Institute for Basic Standards. Electricity. Metrology. Heat. Radiation Physics. Mechanics. Applied Mathematics. Atomic Physics. Physical Chemistry. Laboratory Astrophysics.* Radio Standards Laboratory: Radio Standards Physics; Radio Standards Engineering.** Office of Standard Reference Data.

Institute for Materials Research. Analytical Chemistry. Polymers. Metallurgy. Inorganic Materials. Reactor Radiations. Cryogenics.** Office of Standard Reference Materials.

Central Radio Propagation Laboratory.** Ionosphere Research and Propagation. Troposphere and Space Telecommunications. Radio Systems. Upper Atmosphere and Space Physics.

Institute for Applied Technology. Textiles and Apparel Technology Center. Building Research. Industrial Equipment. Information Technology. Performance Test Development. Instrumentation. Transport Systems. Office of Technical Services. Office of Weights and Measures. Office of Engineering Standards. Office of Industrial Services.

---

* NBS Group, Joint Institute for Laboratory Astrophysics at the University of Colorado.
** Located at Boulder, Colorado.

NATIONAL BUREAU OF STANDARDS REPORT

NBS PROJECT		NBS REPORT
42102-12-4210472	July 23, 1964	8510

Quarterly Report

on

EVALUATION OF REFRACTORY QUALITIES

of

CONCRETES FOR JET AIRCRAFT WARM-UP, POWER CHECK

MAINTENANCE APRONS, AND RUNWAYS

by

J. V. Ryan, E. C. Tuma and W. H. Bettum
Fire Research Section
Building Research Division

Sponsored by:

Department of the Navy
Bureau of Yards and Docks

Reference: Task Y-F015-15-102

NBS File No. 10.02/10472

U. S. DEPARTMENT OF COMMERCE
NATIONAL BUREAU OF STANDARDS

Quarterly Report

on

EVALUATION OF REFRACTORY QUALITIES OF CONCRETES FOR JET AIRCRAFT WARM-UP, POWER CHECK MAINTENANCE APRONS, AND RUNWAYS

by

J. V. Ryan, E. C. Tuma and W. H. Bettum

1. Introduction

The purpose of this project is the development of criteria for the fabrication of jet exhaust resistant concretes. Concretes under study are evaluated by exposure to hot gases from a combustion chamber. The combustion chamber delivers these gases at velocities and temperatures approaching field conditions.

2. Present Plan of the Investigation

The experimental work has been completed in the present Fiscal Year. A summary report on the whole project will be prepared promptly in Fiscal Year 1965.

3. Activities

Two sets of specimens were prepared during this quarter, one containing diabase aggregate, the other blast furnace slag. Both sets of specimens were conditioned in the fog room for one week. One-half of each set was oven dried for one week before testing.

3.1 Minimal Conditioning

The curing and drying time was again reduced on two sets of specimens in an attempt to determine the minimum fog-room and oven-drying time required so the specimens would still develop the required strength and resistance to jet impingement. The first set, Di-6, consisted of six 12-in. diameter by 6-in. thick cylindrical specimens plus nine 3 x 4 x 16 in. beams. The cylindrical specimens were instrumented with thermocouples at the surface, 1/8 in., 1/4 in., 3/8 in., and 1/2 in., and with two pressure tubes at 1/2-in. depth. All the specimens in each set were put in the fog room as soon as the forms were removed. At seven days, three cylinders and three beams were put in an oven and heated to 110°C; another three beams were conditioned at 73°F and 50 percent Rh. At the end of the oven drying period (7 days) all six of the cylindrical specimens were exposed to the jet impingement test. The beam specimens were broken in flexure and compressive strength measurements made on the beam ends.

The second set of specimens were made of blast furnace slag aggregate (BF-3), and were conditioned and instrumented in the same manner as the Di-6 specimens described in the first paragraph.

The results are given in Tables 1 & 2.

3.2 Conclusions

The five sets of specimens tested after various times of fog-room curing and accelerated drying show little or no adverse effects in strength or resistance to spalling in comparison to the specimens conventionally cured and dried.

USCOMM-NBS-DC

Table 1. Results From Specimens After Short Conditioning Periods

	Oven Dried			Fog Room		
Di-6	12 x 6	Spall Volume	Max. Pressure	12 x 6	Spall Volume	Max Pressure
	No. 1	0	50 psi	No. 2	160 cc	232 psi
	3	0	51 psi	4	150 cc	160 psi
	5	0	54 psi	6	170 cc	236 psi
	Avg.	0	52 psi	Avg.	160 cc	209 psi
BF-3						
	No. 1	0	54 psi	No. 2	130 cc	78 psi
	3	0	36 psi	4	180 cc	224 psi
	5	0	46 psi	6	124 cc	102 psi
	Avg.	0	45 psi	Avg.	145 cc	135 psi

Table 2. Supplementary Tests on Specimens After Short Conditioning Periods.

	Modulus of Rupture, psi		Compressive Strength, psi		Moisture Content, %	
	Avg[a/]	Max.	Avg[a/]	Max	Avg[a/]	Max
Di-6						
Oven Dried	790	820	8690	9060	0	0
73°F/50% Rh	750	790	8910	9140	4.4	4.6
Fog Room	885	910	9370	9420	5.5	5.6
BF-3						
Oven Dried	905	915	8170	8500	0	0
73°F/50% Rh	605	625	7440	8500	5.6	5.9
Fog Room	970	1010	7300	7690	7.1	7.4

a/ Of 3 specimens


DEPARTMENT OF COMMERCE
NATIONAL BUREAU OF STANDARDS