

AFOSR Scientific Report

AFOSR 68-1625

NATIONAL BUREAU OF STANDARDS REPORT

9803

PRELIMINARY REPORT
ON THE THERMODYNAMIC PROPERTIES OF
SELECTED LIGHT-ELEMENT AND
SOME RELATED COMPOUNDS

(The previous semiannual reports in this series have the NBS Report Nos. 6297, 6484, 6645, 6928, 7093, 7192, 7437, 7587, 7796, 8033, 8186, 8504, 8628, 8919, 9028, 9389, 9500, and 9601.)



U.S. DEPARTMENT OF COMMERCE
NATIONAL BUREAU OF STANDARDS

This document is subject to special export controls and each transmittal to foreign governments or to foreign nationals may be made only with prior approval of the AFOSR (SRGL).

Qualified requestors may obtain additional copies from the Defense Documentation Center.

NATIONAL BUREAU OF STANDARDS

The National Bureau of Standards¹ was established by an act of Congress March 3, 1901. Today, in addition to serving as the Nation's central measurement laboratory, the Bureau is a principal focal point in the Federal Government for assuring maximum application of the physical and engineering sciences to the advancement of technology in industry and commerce. To this end the Bureau conducts research and provides central national services in three broad program areas and provides central national services in a fourth. These are: (1) basic measurements and standards, (2) materials measurements and standards, (3) technological measurements and standards, and (4) transfer of technology.

The Bureau comprises the Institute for Basic Standards, the Institute for Materials Research, the Institute for Applied Technology, and the Center for Radiation Research.

THE INSTITUTE FOR BASIC STANDARDS provides the central basis within the United States of a complete and consistent system of physical measurement, coordinates that system with the measurement systems of other nations, and furnishes essential services leading to accurate and uniform physical measurements throughout the Nation's scientific community, industry, and commerce. The Institute consists of an Office of Standard Reference Data and a group of divisions organized by the following areas of science and engineering:

Applied Mathematics—Electricity—Metrology—Mechanics—Heat—Atomic Physics—Cryogenics²—Radio Physics²—Radio Engineering²—Astrophysics²—Time and Frequency.²

THE INSTITUTE FOR MATERIALS RESEARCH conducts materials research leading to methods, standards of measurement, and data needed by industry, commerce, educational institutions, and government. The Institute also provides advisory and research services to other government agencies. The Institute consists of an Office of Standard Reference Materials and a group of divisions organized by the following areas of materials research:

Analytical Chemistry—Polymers—Metallurgy — Inorganic Materials — Physical Chemistry.

THE INSTITUTE FOR APPLIED TECHNOLOGY provides for the creation of appropriate opportunities for the use and application of technology within the Federal Government and within the civilian sector of American industry. The primary functions of the Institute may be broadly classified as programs relating to technological measurements and standards and techniques for the transfer of technology. The Institute consists of a Clearinghouse for Scientific and Technical Information,³ a Center for Computer Sciences and Technology, and a group of technical divisions and offices organized by the following fields of technology:

Building Research—Electronic Instrumentation — Technical Analysis — Product Evaluation—Invention and Innovation—Weights and Measures — Engineering Standards—Vehicle Systems Research.

THE CENTER FOR RADIATION RESEARCH engages in research, measurement, and application of radiation to the solution of Bureau mission problems and the problems of other agencies and institutions. The Center for Radiation Research consists of the following divisions:

Reactor Radiation—Linac Radiation—Applied Radiation—Nuclear Radiation.

¹ Headquarters and Laboratories at Gaithersburg, Maryland, unless otherwise noted; mailing address Washington, D. C. 20234.

² Located at Boulder, Colorado 80302.

³ Located at 5285 Port Royal Road, Springfield, Virginia 22151.

NATIONAL BUREAU OF STANDARDS REPORT

NBS PROJECT

221-0404
221-0405
221-0426
222-0423
223-0426
223-0513
313-0430

1 January 1968

NBS REPORT

9803

PRELIMINARY REPORT

ON THE THERMODYNAMIC PROPERTIES OF SELECTED LIGHT-ELEMENT AND SOME RELATED COMPOUNDS

(The previous semiannual reports in this series have the NBS Report Nos. 6297, 6484, 6645, 6928, 7093, 7192, 7437, 7587, 7796, 8033, 8186, 8504, 8628, 8919, 9028, 9389, 9500, and 9601.)

Technical Summary Report
on the Thermodynamic Properties
of Light-Element Compounds

Reference: U. S. Air Force, Office of Scientific Research,
Order No. ISSA 67-6

IMPORTANT NOTICE

NATIONAL BUREAU OF STANDARDS
for use within the Government
and review. For this reason, the
whole or in part, is not authorized
Bureau of Standards, Washington
the Report has been specifically

Approved for public release by the
Director of the National Institute of
Standards and Technology (NIST)
on October 9, 2015

These accounting documents intended
be subjected to additional evaluation
the listing of this Report, either in
the Office of the Director, National
by the Government agency for which
copies for its own use.




U.S. DEPARTMENT OF COMMERCE
NATIONAL BUREAU OF STANDARDS

ABSTRACT

Thermodynamic and related properties of substances important in current high-temperature research and development activities are being investigated under contract with the U. S. Air Force Office of Scientific Research (USAF Order No. ISSA 67-6) and the Advanced Research Projects Agency (ARPA Order No. 20). This research program is a direct contribution to the Interagency Chemical Rocket Propulsion Group (Working Group on Thermochemistry) and, simultaneously, to other organizations oriented toward acquiring the basic information needed to solve not only the technical problems in propulsion but also those associated with ballistics, reentry, and high-strength high-temperature materials. For given substances this needed basic information comprises an ensemble of closely related properties being determined by an extensive array of techniques. Some of these techniques, by relating thermodynamic properties to molecular or crystal structure, make it possible to tabulate these properties over far wider ranges of temperature and pressure than those actually employed in the basic investigations.

This report presents the results and interpretation of five recent NBS experimental studies of thermodynamic properties, two reviews which refine data treatment and evaluation, and one new critical assessment of published heats of formation. The heat capacity of beryllium nitride, Be_3N_2 , was precisely measured from 0 to 315 K; after judicious correction for the irreducible impurities, the data led to the common thermodynamic properties from 0 to 315 K, complementing earlier NBS measurements from 273 to 1173 K. Precise high-temperature calorimetry gave the heat capacity of tungsten from 1100 to 2600 K (showing no detectable difference between two samples, one triple-zone-refined and 99.999% pure); finally corrected results are given also for solid and liquid beryllium aluminate, BeAl_2O_4 , from 1200 to 2400 K. A mass-spectrometric investigation of Al_2O_3 containing 5.8% BeO identified the high-temperature gas species and gave values for their standard

heats of formation. As part of the current NBS microwave and infrared investigation of the alkali-hydroxide molecules, the high-temperature microwave spectra of four isotopic varieties of RbOH were observed and analyzed to give their molecular constants; like CsOH (studied earlier), RbOH is linear, with a low-frequency bending vibration of large amplitude. Two reviews deal with reaction calorimetry involving fluorine compounds: One documents the inadequacy of estimation rules for unmeasured inorganic fluorides, and recommends a systematic cataloging of results to achieve better consistency; while the other describes a new computer subroutine for the automatic reduction of bomb-calorimetry data on organic fluorine compounds. As the result of an up-to-date critical evaluation of the published data giving $\Delta H_f^\circ_{298}$, $\Delta G_f^\circ_{298}$, and S°_{298} of magnesium compounds, values are documented and tabulated for 60 species of interest in "light-element" applications.


Thomas B. Douglas
Project Leader



Charles W. Beckett
Assistant Division Chief for Thermodynamics
Heat Division, Institute for Basic Standards

TABLE OF CONTENTS

	<u>Page</u>
Abstract	i
Chap. 1. <u>THE THERMOCHEMISTRY OF INORGANIC FLUORINE COMPOUNDS. THE NEED FOR A CATALOG OF THERMOCHEMICAL PROCESSES</u> (by George T. Armstrong)	1
1. Estimates of Heats of Formation	1
Table 1. Accuracy of Estimates of Heats of Formation of Some Fluorine Compounds	2
2. Some Sources of Experimental Difficulty in Measurements	3
Table 2. Successive Determinations, $\Delta H_f[Al_2O_3(c, \alpha)]$	3
3. Cataloging the Calorimetric Processes	6
References to the General Text	9
Table 3. Thermochemical Studies Involving Tetrafluoromethane	11
Notes to Table 3	12
References to Table 3	15
Table 4. Process for $\Delta H_f[CH_4(g)]$ from Reactions of Table 3	16
Fig. 1. Recent information on the heat of formation of aqueous hydrofluoric acid	17
Chap. 2. <u>HEAT CAPACITY AND THERMODYNAMIC PROPERTIES OF BERYLLIUM NITRIDE, Be_3N_2, FROM 20 TO 315K</u> (by George T. Furukawa and Martin L. Reilly).	19
Abstract	19
I. Introduction	19
II. Apparatus and Method	19
III. Sample	20
IV. Results	23
V. References	25
Table 1. Summary of Spectrochemical Analysis of the Sample of Beryllium Nitride, Be_3N_2	27
Table 2. Chemical Analysis of the Sample of Beryllium Nitride, Be_3N_2	28
Table 3. Thermodynamic Functions for Beryllium Nitride (Be_3N_2)	29

TABLE OF CONTENTS (Continued)

	<u>Page</u>
Fig. 1. Percentage Deviation of the Empty Sample Vessel Heat Capacities	30
Fig. 2. Percentage Deviation of the Beryllium Nitride Sample Heat Capacities	31
Fig. 3. Percentage Deviation of the Beryllium Nitride Sample Heat Capacities	32
Fig. 4. Percentage Deviation of the Initial Measurements from the Beryllium Nitride Sample Heat Capacities	33
 Chap. 3. <u>AUTOMATIC DATA REDUCTION APPLIED TO BOMB CALORIMETRY OF ORGANIC FLUORINE COMPOUNDS</u> (by George T. Armstrong)	 34
Abstract	34
1. Introduction	35
2. New variables in the program	36
Table 1. Table of Thermochemical Variables Expanded for FARMST Subroutine	38
3. Subroutine FARMST	51
4. Modifications to the main program and subroutines	52
5. Debugging	54
6. Input Data Cards	55
Table 2.	56
7. Output Data	59
Table 3.	60
References	62
 Chap. 4. <u>STRUCTURE OF THE ALKALI HYDROXIDES. III.</u> <u>MICROWAVE SPECTRUM OF GASEOUS RbOH</u> (by David R. Lide, Jr., and Chi Matsumura)	 63
Table I. Observed frequencies in ⁸⁵ RbOH and ⁸⁵ RbOD	64
Table II. Observed frequencies in ⁸⁷ RbOH and ⁸⁷ RbOD	66

TABLE OF CONTENTS (Continued)

	<u>Page</u>
Table III. Effective rotational constants and nuclear quadrupole coupling constants for various vibrational states of RbOH and RbOD	67
Table IV. ℓ -Doubling constants	68
Table V. Fit of $\text{BOv}_2^{20}\text{O}$ to power series	69
Table VI. Variation of rotational constants with V_1	70
Table VII. Structural parameters of rubidium hydroxide	71
 Chap. 5. <u>MASS SPECTROMETRIC STUDY AT HIGH TEMPERATURES OF THE Al_2O_3-BeO SYSTEM</u>	
(by J. Efimenko)	72
Introduction	72
Experimental	72
Results	72
Discussion	73
Table 1. Ion Intensities Over Eutectic $\text{BeO}:\text{Al}_2\text{O}_3$ (94.2% Al_2O_3)	75
Table 2. Auxiliary Data	77
Table 3. Equilibria Constants	78
Table 4. Reaction Enthalpies	79
 Chap. 6. <u>THE ENTHALPY OF TUNGSTEN FROM 1100 to 2600°K</u>	
(by E. D. West and S. Ishihara)	80
Method and Apparatus	80
Materials	81
Results	82
Discussion	83
References	84
Table 1. Experimental Data for the Enthalpy of Tungsten	85
 Chap. 7. <u>THE ENTHALPY OF SOLID AND LIQUID $\text{BeO}\cdot\text{Al}_2\text{O}_3$ FROM 1200° TO 2400°K--REVISION</u>	
(by S. Ishihara and E. D. West)	88

TABLE OF CONTENTS (Continued)

	<u>Page</u>
Chap. 8. <u>THE STATUS OF THE THERMOCHEMICAL DATA</u> <u>ON SOME Mg COMPOUNDS</u>	
(by Vivian B. Parker)	90
I. Introduction	90
II. Discussion of Data	90
Mg(c), Mg(g)	90
Mg ⁿ⁺ (g), Mg ²⁺ (aq), MgO(macrocr.), MgO(microcr.)	91
MgO(g)	92
MgH ₂ (c), MgOH ⁺ (aq), Mg(OH) ₂ (c)	93
Mg(OH) ₂ (ppt), Mg(OH) ₂ (aq), Mg(OH) ₂ (g), MgF(g)	94
MgF ₂ (c), MgF ₂ (g)	95
Table I	96
MgCl(g), MgCl ₂ (c)	96
MgCl ₂ (g)	97
MgCl ₂ (aq), MgCl ₂ ·H ₂ O(c), MgCl ₂ ·2H ₂ O(c)	98
Table II	99
MgCl ₂ ·4H ₂ O(c)	99
MgCl ₂ ·6H ₂ O(c), Mg(ClO ₄) ₂ (c), Mg(ClO ₄) ₂ (aq), Mg(ClO ₄) ₂ ·6H ₂ O(c)	100
MgOHCl(c), MgBr ₂ (c), MgBr ₂ (g)	101
MgBr ₂ (aq), MgBr ₂ ·6H ₂ O(c), MgI ₂ (c), MgI ₂ (g), MgI ₂ (aq)	102
MgI ₂ (aq), MgSO ₄ (c), MgSO ₄ (aq)	103
MgSO ₄ ·H ₂ O(c), MgSO ₄ ·H ₂ O(amorph), MgSO ₄ ·2H ₂ O(c), MgSO ₄ ·4H ₂ O(c), MgSO ₄ ·6H ₂ O(c)	104
MgSO ₄ ·7H ₂ O(c), Mg ₃ N ₂ (c,α)	105
Mg(NO ₃) ₂ (c)	106
Mg(NO ₃) ₂ (aq), Mg(NO ₃) ₂ ·2H ₂ O(c), Mg(NO ₃) ₂ ·6H ₂ O(c)	107
MgC ₂ (c), Mg ₂ C ₃ (c), MgCO ₃ (c)	108
Mg ₂ Si(c), MgSiO ₃ (c), Mg ₂ SiO ₄ (c)	109
Mg ₃ Si ₂ O ₅ (OH) ₄ (c), Mg ₃ Si ₄ O ₁₀ (OH) ₂ (c), MgB ₁₂ (c), MgAl ₂ O ₄ (c)	110
Mg ₂ Al ₄ Si ₅ O ₁₈ (c)	111
Bibliography	112
Table III. Selected Values for Some Mg Compounds at 298°K	120

Chapter 1

THE THERMOCHEMISTRY OF INORGANIC FLUORINE COMPOUNDS THE NEED FOR A CATALOG OF THERMOCHEMICAL PROCESSES¹

George T. Armstrong

Heat Division, Institute for Basic Standards
National Bureau of Standards, Washington, D. C., 20234

1. ESTIMATES OF HEATS OF FORMATION

Some years ago we reviewed (see for example [1]) the effectiveness of estimates of the heats of formation of inorganic fluorine compounds by a procedure which we have not seen used elsewhere. We compared estimates of heats of formation for which no measured value existed at the time of the estimate, with later values measured experimentally. The estimates were, thus, a priori in a sense. By this tactic we hoped to avoid the possibility of (no doubt unpremeditated) influence of the measured value upon the quality of the estimate. We considered, for instance, that if a measured value were available the author of an estimate might be influenced favorably in his decision to publish by good agreement of his estimate; or, contrariwise, unfavorably and decide not to publish if agreement were poor; thus we would anticipate that estimates made after the availability of experimental data might tend to be better than estimates made prior to such availability.

Some new information has been added and the comparisons are shown in Table 1. The average error (without regard to sign) is 44 kcal mol^{-1} , and the average bias is 26 kcal mol^{-1} positive, as compared with our earlier finding of 30 and 17 kcal mol^{-1} , respectively. Thus, the ability to estimate heats of formation was not particularly good, and recent data have continued to show large deviations. The tendency is for the compounds of fluorine to be more stable than estimated.

The difficulty may be due in part to the extreme position of fluorine in the periodic system, which causes all attempts to estimate on the basis of the properties of neighboring elements to be extrapolations rather than interpolations.

¹ Prepared for presentation at the Thermodynamic Symposium of the IUPAC Commission on Thermodynamics and Thermochemistry, Heidelberg, West Germany, September 1967.

Table 1

Accuracy of Estimates of Heats of Formation of Some Fluorine Compounds

Compound	ΔH_f kcal mol ⁻¹		Error
	Estimate	Later Measurement	
AcF ₃ (c)	-420	-477	+57
	-395		+82
AlF ₃ (c)	-311	-361.0	+50
	-323		+38
AuF ₃ (c)	-100	- 83.3	-17
BeF ₂ (c)	-227	-245.3	+18
	-220		+25
HfF ₄ (c)	-435	-461.4	+26
MoF ₆ (l)	-405	-388.6	-16
NF ₂ (g)	17	8.9	+ 8
NbF ₅ (c)	-342	-432	+90
PF ₅ (g)	-315	-381.4	+66
	-420		-39
RuF ₅ (c)	-300	-213.4	-87
SF ₄ (g)	-156	-171.7	+16
TaF ₅ (c)	-300	-455	+155
	-360		+95
ThF ₄ (c)	-477	-482	+ 5
TiF ₄ (c)	-370	-394.2	+24
TlF(c)	- 65	- 74.0	+ 9
TlF ₃ (c)	-175	-136.9	-38
ZrF ₄ (c)	-445	-456.8	+12
Average error			44 kcal mol ⁻¹
Average bias			26 kcal mol ⁻¹

Estimates are selected from a review by Armstrong and Krieger [2].

We have not made a general study of the problem of predictions of binding energies or of the relative effectiveness of the different methods that have been used. This is a worthwhile exercise, and possibly if we had done so we would have somewhat less of a blunderbuss approach to the results. However, our concerns up to now at least have been primarily in other directions. The information which has been presented to you was enough to persuade us to adopt a skeptical attitude toward estimates. It is apparent that competent and well established reviewers have on the whole shown a lack of ability to predict a priori with reasonable accuracy the heats of formation of inorganic fluorine compounds.

2. SOME SOURCES OF EXPERIMENTAL DIFFICULTY IN MEASUREMENTS

The unusual bias of predictions, together with a curious regularity observed in successive experimental determinations of certain heats of formation, led to the formulation of a rather general rule, that members of our laboratory have rather facetiously termed Armstrong's rule: as time goes by heats of formation tend to become more negative. In the denouement we hold no brief for this rule, but point it out as an interesting interlude in our examination of the findings of experimental thermochemistry.

An example that led to this attitude is the heat of formation of aluminum oxide (Table 2) which became significantly more negative over a period of 30 years. The heat of formation of AlF_3 has followed roughly this rule, we see semblances of it also in the heats of formation of $BeO(c)$, $BeF_2(c)$, $CF_4(g)$, and $HF(aq)$.

Table 2

Successive Determinations $\Delta H_f[Al_2O_3(c,\alpha)]$	
	kcal mol ⁻¹
Moose and Parr (1924) [3]	-376.9
Roth and Muller (1929) [4]	-380.1
Snyder and Seltz (1945) [5]	-399.09
Oketani and Maebashi (1950) [6]	-381.03
Holley and Huber (1951) [7]	-400.29
Schneider and Gattow (1954) [8]	-400.6 (-402) ^a
Mah (1957) [9]	-400.4

^a The number in parenthesis included a questionable correction made by the authors for partial formation of a less stable phase.

When we examine these tendencies in greater detail, however, we find, perhaps not surprisingly, that the picture was oversimplified. Still, certain regularities of behavior do persist, and lead us to believe there is some rational explanation of these regularities. The explanations which finally appear to emerge are not the same in every case. That is, a variety of influences is apparently at work. An examination of a few of them may assist us in planning future experimental work.

We return to the heat of formation of Al_2O_3 briefly and note that each value quoted resulted from combustion of the metal in oxygen. With a little imagination we realize that probably the cause of progressively more negative heats of formation was better control of the amount of reaction as time passed. The less negative values probably represent smaller amounts of reaction than the experimenter presumed. There may be two reasons for this bias: (1) the sample metal may have contained larger amounts of inert impurities than were revealed by analysis; (2) the metal may have reacted less completely than presumed. The first source of error is rendered plausible by the finding of relatively large amounts of oxygen and nitrogen (probably as a surface coating) in metals even supposedly highly pure on the basis of spectrographic analysis. The second source of error is rendered plausible by the fact that the combustion product may completely cover small amounts of unburned metal and preclude further oxidation. On the basis of an argument like the above, we would anticipate in the combustion of refractory substances giving solid products, a bias in the direction of low heat of reaction which might be substantial in some cases. A notorious example of this is the combustion of boron in oxygen, for which the two processes may both be presumed to be severe. Let us turn to a more complicated and informative example, the heats of formation of CF_4 and HF.

A few years ago, apparently valid but inconsistent experiments were reported by Jessup [10] on the one hand and by Good, Scott and Waddington [11] and by Neugebauer and Margrave [12] on the other hand, all of which gave values for the heat of formation of CF_4 . See Table 3. In an attempt to reconcile them we observed the opposing sense in which the heat of formation of HF occurred in the relationships between the heats of reaction and the heat of formation of CF_4 . These relationships are shown in Table 4, referring to reactions 2, 3b, and 4c. This led us to make the

suggestion that possibly the heat of formation used for HF in the calculation was in error, and it was no problem then to figure a reasonable change in the heat of formation of HF that would reconcile these inconsistent sets of experiments.

In Table 3 we list all the reactions involving CF_4 for which we have found calorimetric studies.

If we restrict ourselves to the reactions from which the heat of formation of CF_4 is derived by its difference from HF (rather than from its sum with HF) as in reactions 3(a,b,d), 4(a,b,c), 5(a,b,c) and possibly 8, and 9, we find a rather nice consistency between the calculated values for CF_4 no matter what value is selected for $\text{HF}(\text{aq})$. An illustration of this is given by Cox, Gundry, and Head [13], using an extreme value for the heat of formation of $\text{HF}(\text{aq})$.

The heat of formation of CF_4 as inferred from these experiments is inextricably bound to the heat of formation of $\text{HF}(\text{aq})$. It is evident that we shall not learn anything further about it from them alone, so long as there is fluctuating information about the heat of formation of HF.

We may turn to the experiments that do not involve HF. Here we find ourselves in reaction sets 1, 6, and possibly 8 and 9, immediately faced with the same problems or at least similar problems to that mentioned earlier in the case of Al_2O_3 . For instance, in reactions (8) and (9), involving the reduction of an organic compound and the formation of a solid residue carbon, the question arises, "to what extent has this reaction gone to completion?" Completion here includes two concepts: (1) has all of the F been extricated from the C residue? and (2) has the C residue been reduced to a recognizable, well defined standard state, or does it retain active centers (as a result of a large surface area, for example)? The experimental evidence, particularly with respect to the latter problem, as outlined in the notes to Table 1 is dishearteningly unsatisfactory. One is left with the feeling that the observed heat processes will tend to be biased toward the low side of the true heat of reaction.

Only by the most careful experimentation can one be sure that the observed heat actually corresponds to the expectation for a complete reaction described exactly by the equation.

Somewhat peripheral to our subject, the analysis of these equations led us to an understanding:

- (1) That the heat of formation of CF_4 is best represented by the experiments on direct combustion of graphite in fluorine; and by a combination of the combustion of "Teflon" in oxygen and in fluorine, the only products being gaseous CO_2 and CF_4 .
- (2) That other reactions not involving HF do not provide any conflicting evidence, but that the positive information they provide is limited by the lack of characterization of the reaction.
- (3) That reactions involving $\text{HF}(\text{aq})$ do not provide conflicting evidence, but that the positive information they supply is limited by uncertainty in the heat of formation of $\text{HF}(\text{aq})$.

(Incidentally, the reaction by Jessup et al. [10] which was an initiator of the line of thought described here, turns out now to be inconsistent in the opposite sense from what it was at the outset, and no means of reconciliation is now apparent.).

- (4) That the reactions involving $\text{HF}(\text{aq})$ can be combined with independently arrived at values for heats of formation of CF_4 as well as BF_3 and NF_3 to arrive at new "consensus" values for the heat of formation of $\text{HF}(\text{aq})$. Figure 1 shows the apparently most consistent value for heat of formation of $\text{HF}(\text{aq})$.
- (5) That the explanation of the observed discrepancies in measurements of the heat of formation of $\text{HF}(\text{g})$ or $\text{HF}(\text{aq})$ by various means may involve subtle arguments. The large deviation of the work of Cox and Harrop [19], for instance, may be due not to experimental error but to a residual entropy of $\text{LiHF}_2(\text{c})$ at absolute zero, or to use of an inappropriate value for the heat of formation of gaseous HF . In the latter event, the heat of formation of gaseous HF is still a problem.

3. CATALOGING THE CALORIMETRIC PROCESSES

A feature is present in Table 1 which, undoubtedly, is not new but suggests to us what we believe is a new concept of the appropriate forms for presenting calorimetric (and other thermodynamic) data.

We have no question in our mind that the most useful form of thermodynamic information for the general user — the theoretician interested in energies of substances, and the engineer interested in design parameters — is a set of tables of values of thermal functions of the substances in the style of NBS Circular 500 [20] (now Technical Note 270-1) [21] or of the JANAF Thermochemical Tables [22] from the U.S.A. or the Thermal Constants of Substances [23] and Thermodynamic Properties of Individual Substances [24] from the Academy of Sciences of the USSR. However, for the thermochemist, the experimental calorimetrist, or the selector of best values, another form seems at least as desirable, and in the latter case almost a necessary adjunct to his work. This form is a catalog of thermochemical processes.

We have seen in Section 2 that a set of equations together with the heat values associated with them is a flexible tool for attempting to determine true values of the heats of formation, and to appraise sources of errors. It is also apparent that critical substances for further study would be discernible in such a set of equations.

A catalog can be conceived of as a tabulation of observed processes — chemical reactions, phase changes, and so on — listed as equations, with the value of the thermal effect observed. Limited amounts of selected information concerning the conditions of the experiment are also included. The tabulation of equations is indexed with respect to all substances and phases present, so that all processes involving a given substance can be located.

The limited list of equations involving CF_4 given in Table 3 represents a skeleton of a limited segment of such a catalog. To prepare a complete catalog including all the chemical substances for which measurements have been made is a very large task. In the following paragraphs we indicate certain special features of such a compilation and suggest the long term benefits which it might be expected to provide.

There is ample evidence that several groups now have essentially the framework of such a catalog. These are the groups which have been for some years compiling and critically evaluating thermodynamic data. The awkward feature of the present situation is that the information, except for the end result after it has been critically evaluated and released in tables of selected values, is essentially in the form of private files. In this form it is inaccessible to the general investigator; in the event of the

formation of a new critical evaluation group, they must acquire their own file of such working information; in the event of the demise of one of these groups, its literature files would probably revert to inutility.

We suggest that much of the intermediate information gleaned from the thermochemical literature is of permanent value, subject to reuse in various ways, and susceptible to augmentation as time goes on without loss of any of the original body of information. In this respect, particularly it is more useful than a collection of selected values of thermodynamic functions, whose values change as new data are added.

A catalog in the form described can be looked upon as a set of mathematical equations or expressions of which a selection is given in Table 4. In general, most of the thermodynamic relationships involving heats of formation can be described as linear equations. The set of possible chemical reactions involving all the chemical substances may be looked upon as a set of simultaneous equations. Experimental enthalpy changes can be expressed in terms of the numerical coefficients and heats of formation of the substances present.

Because of the complexity and number of these equations, and the difficulty of finding simultaneous solutions which offer the best values of the heats of formation, the practice has been adopted of evaluating heats of formation sequentially, starting with certain "key" substances, to which values of heat of formation are assigned on the basis of carefully selected equations.

In principle, if the experimental enthalpy equations are known for any given set of substances, a set of best values can be selected which minimizes the ensemble of errors without predetermining any one key substance. This minimization is ordinarily not done because of its difficulty.

It is to be presumed that the use of high speed computers will ultimately allow selections of best values in this sense for the whole body of chemical substances for which data exist. A catalog of the type described above is a critical development if such a calculation is to be achieved. The catalog will essentially provide the input data for such a selection of best values.

With a workable program for making such selections, it should be possible to make selected best values annually, or more frequently; it should be possible to study the relative importances of various substances; and also to find those substances whose present values appear to be out of line and require redetermination.

Thus a catalog provides three services:

- (1) A resource for experimental calorimetrists for planning their work.
- (2) Source material for groups preparing best values of thermodynamic properties.
- (3) Input data for computerized selection of best values and other computerized analysis of data.

References to the General Text

- [1] G. T. Armstrong, J. Chem. Ed. 41, 297-307 (1964).
- [2] G. T. Armstrong and L. A. Krieger, in "Progress in International Research on Thermodynamic and Transport Properties," J. F. Masi and D. H. Tsai, Editors, (Academic Press, N. Y. 1962), pp. 8-78.
- [3] J. E. Moose and S. W. Parr, J. Am. Chem. Soc. 46, 2656-61 (1924).
- [4] W. A. Roth and D. Muller, Z. Physik. Chem. (Leipzig), A144, 253-8, (1929).
- [5] P. E. Snyder and H. Seltz, J. Am. Chem. Soc. 67, 683-5 (1945).
- [6] S. Oketani and Y. Maebashi, J. Japan. Inst. Metals 14B, No. 2, 27-31, (1950).
- [7] C. E. Holley, Jr. and E. J. Huber, Jr., J. Am. Chem. Soc. 73, 5577-9, (1951).
- [8] A. Schneider and G. Gattow, Z. Anorg. u. Allgem. Chem. 277, 41-8, (1954).
- [9] A. D. Mah, J. Phys. Chem. 61, 1572-3 (1957).
- [10] R. S. Jessup, R. E. McCoskey, and R. A. Nelson, J. Am. Chem. Soc. 77, 244-5 (1955).
- [11] W. D. Good, D. W. Scott, and G. Waddington, J. Phys. Chem. 60, 1080-9 (1956).
- [12] C. A. Neugebauer and J. L. Margrave, J. Phys. Chem. 60, 1318-21 (1956).
- [13] J. D. Cox, H. A. Gundry, and A. J. Head, Trans. Faraday Soc. 60, 653-65 (1964).
- [14] E. S. Domalski and G. T. Armstrong, J. Res. Nat. Bur. Std. 71A (1967) (In press).

- [15] G. K. Johnson, H. M. Feder, and W. N. Hubbard, J. Phys. Chem. 70, 1-6 (1966).
- [16] G. H. Sinke, J. Phys. Chem. 71, 359 (1967).
- [17] E. S. Domalski and G. T. Armstrong, J. Res. Nat. Bur. Std 71A, 105-18 (1967).
- [18] R. C. King and G. T. Armstrong, Unpublished data.
- [19] J. D. Cox and D. Harrop, Trans. Faraday Soc. 61, 1328-37 (1965).
- [20] F. D. Rossini, D. D. Wagman, W. H. Evans, S. Levine, and I. Jaffe, "Selected Values of Chemical Thermodynamic Properties," Nat. Bur. Std. (U.S.), Circ. 500, (U. S. Government Printing Office, Washington, D. C., 1952, 1961).
- [21] D. D. Wagman, W. H. Evans, I. Halow, V. B. Parker, S. M. Bailey, and R. H. Schumm, National Bureau of Standards Technical Note 270-1, (U.S. Government Printing Office, Washington, D. C., 1965).
- [22] JANAF Thermochemical Tables, Dow Chemical Company, Midland, Michigan (1960-67).
- [23] V. P. Glushko, et al., Thermal Constants of Substances (Akad. Nauk SSSR, Moskva 1965, 1966).
- [24] V. P. Glushko, et al. "Thermodynamic Properties of Individual Substances (Akad. Nauk SSSR, Moskva 1962).

Table 3. Thermochemical Studies Involving Tetrafluoromethane

	Reaction	ΔH_{298}° Kcal mol ⁻¹	References*
1.	$C(c, \text{graphite}) + 2F_2(g) = CF_4(g)$	-162 ± 2^a	[1]
		$(-183.5 \pm 2)^b$	[3]
		-222.87 ± 0.38	[6]
2.	$CH_4(g) + 4F_2(g) = CF_4(g) + 4HF(g)$	-459.3 ± 9	[7]
3(a)	$C_2F_4(g) = CF_4(g) + C(c, \text{graphite})$	-61.43 ± 1.4	[8]
		-65.4 ± 0.42	[9]
	$(b) C_2F_4(g) + 2H_2(g) + 4[118.2H_2O](l) = 4[HF + 118.2H_2O](l) + 2C(c, \text{graphite})$	-150.8 ± 1.1	[9]
	$(c) C_2F_4(g) + 2H_2(g) = 4HF(l) + 2C(c, \text{graphite})$	-132.72 ± 0.7	[8]
	$(d) 4[HF + 118.2H_2O](l) + C(c, \text{graphite}) = CF_4(g) + 2H_2(g) + 4[118.2H_2O](l)$	$+85.4 \pm 1.5$	
	$(e) 4HF(l) + C(c, \text{graphite}) = CF_4(g) + 2H_2(g)$	$+67.32$	
4(a)	$C_2F_4(\text{solid polymer}) + O_2(g) = CO_2(g) + CF_4(g)$	-118.8 ± 0.5	[10,11]
	$(b) C_2F_4(\text{solid polymer}) + O_2(g) + 42H_2O(l) = 2CO_2(g) + 4[HF + 10H_2O](l)$	-160.3 ± 0.9	[10,11]
	$(c) CO_2(g) + 4[HF + 10H_2O](l) = CF_4(g) + 42H_2O(l)$	$+41.5 \pm 1.0$	[10,11]
5(a)	$C_{12}F_{22}(l) + 6.5O_2(g) + 401.8H_2O(l) = 0.6CF_4(g) + 11.4CO_2(g) + 19.6[HF + 20H_2O](l)$	$-4067.9/4.184$	[12]
	$(b) C_{12}F_{22}(l) + 6.5O_2(g) + 131.2H_2O(l) = 3.9CF_4(g) + 8.1CO_2(g) + 6.4[HF + 20H_2O](l)$	$-3496.5/4.184$	
	$(c) CO_2(g) + 4[HF + 20H_2O](l) = CF_4(g) + 82H_2O(l)$	$+41.38 \pm 0.32$	[12]
6(a)	$C_2F_4(\text{solid polymer}) + F_2(g) = 2CF_4(g)$	$-247.85(-247.43) \pm 0.30$	[5,6]
		-246.84 ± 0.07	[17]
	$(b) C_2F_4(\text{solid polymer}) + O_2(g) = CO_2(g) + CF_4(g)$	-118.8	[10,11]
	$(c) CO_2(g) + F_2(g) = O_2(g) + CF_4(g)$	$-129.05(128.63)$	
7.	H_2, O_2, CO, CF_4	-220.1 ± 1.4	[13]
8.	$CF_4(g) + 4K(c) = 4KF(c) + C(\text{graphite})$	-307 ± 4	[2,4]
		-320 ± 2	[15]
9.	$CF_4(g) + 4Na(c) = 4NaF(c) + C(\text{graphite})$	-325.5 ± 2.2	[16]

* See separate set of references for Table 3.

Notes to Table 3

1. a. The original authors made an adjustment of $2.4 \text{ kcal mol}^{-1}$ for the estimated heat of formation of the Norite (activated wood charcoal) they burned. They obtained $-165.0 \pm 1.5 \text{ kcal mol}^{-1}$ for the combustion of Norite in fluorine. When adjusted by $+2.4 \text{ kcal mol}^{-1}$ this gives $-162.6 \text{ kcal mol}^{-1}$ which they apparently rounded to $-162 \text{ kcal mol}^{-1}$, increasing the uncertainty to 2 kcal mol^{-1} .
b. This is an adjustment by Ruff and Bretschneider [3] of the work of von Wartenberg and Schuette [1], taking into account the formation of several percent of higher fluorocarbons in the combustion of Norite. The recalculation changes the original data far too little. A recalculation using a more current value for the fluorination of a C-C bond ($142.7 \text{ kcal mol}^{-1}$, instead of $107 \text{ kcal mol}^{-1}$ as was used by Ruff and Bretschneider) leads to $\Delta H_r = -190.5 \text{ kcal mol}^{-1}$. Hence it appears that the formation of other products would have to be greater than was suggested by Ruff and Bretschneider. The uncertainty in amount of products seems to preclude further consideration of the work of von Wartenberg and Schuette.
2. As a part of its uncertainty the work of Jessup, McCoskey, and Nelson [7] contains an uncertain correction of 1.5 to $2.0 \text{ kcal mol}^{-1}$ (of CF_4) for nonideality of HF. This now appears to have been an excessive correction. In the extreme case, if this correction is reduced to zero, the heat of reaction becomes $-461.2 \text{ kcal mol}^{-1}$. The large uncertainty assigned by the authors is apparently a 95 percent confidence limit.
3. a. The carbon formed in the reaction by Duus [8] was weakly crystalline. Duus made no adjustment to the heat for the physical state of the graphite. An adjustment of the magnitude made by Neugebauer and Margrave [9] would bring Duus' value to $-63.3 \text{ kcal mol}^{-1}$. Neugebauer and Margrave [9] measured the heat of reaction, with the formation of amorphous carbon, to be $-63.5 \text{ kcal mol}^{-1}$, and measured the heat of formation of the amorphous carbon to be $1.9 \text{ kcal mol}^{-1}$. We have combined their measurements to give the heat of decomposition to form graphite, $-65.4 \text{ kcal mol}^{-1}$.

b,c. Neugebauer and Margrave [9] measured the heat of hydrogenation of $C_2F_4(g)$, with the formation of $HF(aq)$ and amorphous carbon, to be $-147.8 \text{ kcal mol}^{-1}$, and measured the heat of formation of the amorphous carbon to be $3.0 \text{ kcal mol}^{-1}$. We have combined their measurements to give the heat of hydrogenation to form $HF(aq)$ and graphite, $\Delta H = -150.8 \text{ kcal mol}^{-1}$. Their reaction is definitely superior to reaction 3(c) as carried out by Duus, who was forced to make large corrections for the presence of $HF(g)$, and did not attempt any correction for the physical state of the carbon formed. Neither reaction 3(b) nor 3(c) can be used by themselves to calculate the heat of formation of CF_4 , but are included because they can be combined with other work done in the same laboratory to obtain a relationship leading to the desired value.

d. This reaction is obtained by subtracting 3(b) from 3(a). The heat value cited was obtained using the heat of reaction 3(a) determined by Neugebauer and Margrave [9].

e. The heat of this reaction was determined by combining the energy of reaction 3(c) with that for 3(a) determined by Duus [8] and reported in the same paper.

4. a,b. The energies of these reactions were obtained by Good, et al. [10], [11] by extrapolating respectively to $x = 1$ and $x = 0$ from measurements covering the range $x = 0.0285$ to $x = 0.8162$ of the reactions $C_2F_4(\text{solid polymer}) + O_2(g) + 42(1-x)H_2O(l) = (2-x)CO_2(g) + xCF_4 + 4(1-x)[HF + 10H_2O](l)$. The experiments are carefully described.
- c. The heat of this reaction was obtained by combining the heats of reactions 4(a) and 4(b) determined in the same laboratory.
5. a. The heat of this reaction was obtained by Cox, Gundry, and Head [12] by appropriately combining reactions 5(a) and 5(b).
6. a. An earlier (in parentheses) and a more recent and more amply substantiated value are listed.
- b. The heat of this reaction is obtained by combining the heats of reaction 6(a) and 4(a). This reaction does not in any way involve the heat of formation of HF , but in order for it to be valid, the $C_2F_4(\text{solid polymer})$ used in the two different experiments must be similar.

7. Baibuz and Medvedev [14] recalculated the work of Baibuz [13] and reported $\Delta H_f[\text{CF}_4(\text{g})] = -220.6$. The work of Baibuz is not available to us in sufficient detail to allow us to write the equation for the reaction or to know the dependence of the reported heat of formation of CF_4 on other auxiliary data.
8. Von Wartenberg [2,4] reported $\Delta H = -307 \text{ kcal mol}^{-1}$, and although he indicated the carbon was graphite, the evidence from other sources is that probably only a slight amount of graphite was present. On the basis of information supplied by Neugebauer and Margrave (1.5 to 1.9 kcal mol^{-1}) [9], von Wartenberg and Schuette (2.4 kcal mol^{-1}) [1], and Kirkbride and Davidson (2.5 kcal mol^{-1}) [15] if we assume the heat of formation of the carbon residue to be $+2 \pm 1 \text{ kcal mol}^{-1}$ and apply a correction, the heat of reaction to that in which graphite is formed would be -307, which is still far less negative than the result of Kirkbride and Davidson.
- Kirkbride and Davidson [15] reported $\Delta H_f[\text{CF}_4(\text{g})] = -218 \pm 2 \text{ kcal mol}^{-1}$, together with auxiliary data for KF(c) and amorphous carbon. We have back calculated to obtain $\Delta H_x = -320 \pm 2 \text{ kcal mol}^{-1}$.
9. Vorob'ev and Skuratov [16] reported $\Delta H_x = -325.5 \pm 2.2 \text{ kcal mol}^{-1}$ and that their reaction led to formation of β -graphite. If we presume, on the basis of the work of Kirkbride and Davidson [15], that only a small amount of crystalline material was present and apply a correction of 2 kcal mol^{-1} for the heat of formation of amorphous carbon, the heat of reaction 9 would be $-327.5 \text{ kcal mol}^{-1}$. See 8 above.

References to Table 3

- [1] Wartenberg, H. v., and Schutte, R., Z. Anorg. Allgem. Chem. 211, 222-6 (1933).
- [2] Wartenberg, H. von, Z. Anorg. Chem. 258, 356-60 (1949).
- [3] Ruff, O. and Bretschneider, O., Z. Anorg. Allgem. Chem. 210, 173-83 (1933).
- [4] Wartenberg, H. von, Nachr. Akad. Wiss. Goettingen, Math. Physik. Kl., 1946, 57.
- [5] Domalski, E. S. and Armstrong, G. T., J. Res. Nat. Bur. Std. 69A, 137-47 (1965).
- [6] Domalski, E. S. and Armstrong, G. T., J. Res. Nat. Bur. Std. 71A, 105-118 (1967).
- [7] Jessup, R. S., McCoskey, R. E., and Nelson, R. A., J. Am. Chem. Soc. 77, 244-5 (1955).
- [8] Duus, H. C., Ind. Eng. Chem. 47, 1445-9 (1955).
- [9] Neugebauer, C. A. and Margrave, J. L., J. Phys. Chem. 60, 1318-21 (1956).
- [10] Good, W. D., Scott, D. W., and Waddington, G., J. Phys. Chem. 60, 1080-9 (1956).
- [11] Scott, D. W., Good, W. D., and Waddington, G., J. Am. Chem. Soc. 77, 245-6 (1955).
- [12] Cox, J. D., Gundry, H. A., and Head, A. J., Trans. Faraday Soc. 60, 653-65 (1964).
- [13] Baibuz, V. F., Doklady Akad. Nauk S.S.S.R. 140, 1358-60 (1961).
- [14] Baibuz, V. F. and Medvedev, V. A., Tr. Gos. Inst. Prikl. Khim., No. 49, 84 (1942).
- [15] Kirkbride, F. W., and Davidson, F. G., Nature 174, 79-80 (1954).
- [16] Vorob'ev, A. F., and Skuratov, S. M., Zh. Fiz. Khim. 32, 2580-5 (1958).
- [17] Wood, J. L., Lagow, R. J., and Margrave, J. L., J. Chem. Eng. Data, 1967. In press.


Table 4

Process for $\Delta H_f[\text{CF}_4(\text{g})]$ from Reactions of Table 3.

Reaction

1	$\Delta H_r(1)$
2	$\Delta H_r(2) + \Delta H_f[\text{CH}_4(\text{g})] - 4\Delta H_f[\text{HF}(\text{g})]$
3(a)	$\Delta H_r(3a) + \Delta H_f[\text{C}_2\text{F}_4(\text{g})]$
3(b)	$\Delta H_r(3a) - \Delta H_r(3b) + 4\Delta H_f[\text{HF in } 118.2 \text{ H}_2\text{O}](\ell)$
3(c)	$\Delta H_r(3a) - \Delta H_r(3c) + 4\Delta H_f[\text{HF}](\ell)$
3(d)	$\Delta H_r(3d) + 4\Delta H_f[\text{HF in } 118.2 \text{ H}_2\text{O}](\ell)$
3(e)	$\Delta H_r(3e) + 4\Delta H_f[\text{HF}(\ell)]$
4(a)	$\Delta H_r(4a) + \Delta H_f[\text{C}_2\text{F}_4(\text{solid polymer})] - \Delta H_f[\text{CO}_2(\text{g})]$
4(b)	See 4(c)
4(c)	$\Delta H_r(4c) + \Delta H_f[\text{CO}_2(\text{g})] + 4\Delta H_f[\text{HF in } 10 \text{ H}_2\text{O}](\ell)$
5(a)	See 5(c)
5(b)	See 5(c)
5(c)	$\Delta H_r(5c) + \Delta H_f[\text{CO}_2(\text{g})] + 4\Delta H_f[\text{HF in } 20 \text{ H}_2\text{O}](\ell)$
6(a)	$\frac{1}{2}[\Delta H_r(6a) + \Delta H_f[\text{C}_2\text{F}_4(\text{solid polymer})]]$
6(b)	See 6(c)
6(c)	$\Delta H_r(6c) + \Delta H_f[\text{CO}_2(\text{g})]$
7	-
8	$4\Delta H_f[\text{KF}(\text{c})] - \Delta H_r(8)$
9	$4\Delta H_f[\text{NaF}(\text{c})] - \Delta H_r(9)$

Figure 1. Recent information on the heat of formation of aqueous hydrofluoric acid. Upper curve, Cox and Harrop [19]; Lower curve, Wagman, et al. [21]; A cycle for $\text{BF}_3\text{-HF}$ set up by Johnson, Feder and Hubbard [15] gives point (1) when applied to data of Domalski and Armstrong [14], and point (2) when applied to data of Johnson, Feder, and Hubbard [15] for BF_3 . The heat of formation of CF_4 determined by Domalski and Armstrong [17] by combustion of graphite in fluorine is applied to data relating CF_4 to HF of Good, Scott and Waddington [11] to obtain point (3); to the data of Cox, Gundry, and Head [13] to obtain point (4); and to the data of Neugebauer and Margrave [12] to obtain point (5). A study relating NF_3 to HF reported by Sinke [16] is used to obtain point (6). A study of the $\text{H}_2\text{-F}_2\text{-H}_2\text{O}$ reaction by King and Armstrong [18] gives point (7). The central solid curve shows an estimate of the probable best values for $\Delta H_f[\text{HF}(\text{aq})]$. The dashed curve differs from the solid central curve by an amount showing the effect of using the heat of formation of CF_4 determined from the combustion of "Teflon" in fluorine [17] on the calculations.



HEAT CAPACITY AND THERMODYNAMIC PROPERTIES OF BERYLLIUM NITRIDE, Be_3N_2 , FROM 20 TO 315 K.

George T. Furukawa and Martin L. Reilly

Abstract

The heat capacity of beryllium nitride, Be_3N_2 , was determined from 20 to 315 K and the thermodynamic properties calculated from 0 to 315 K. The entropy at 298.15 K was found to be 34.4 ± 0.3 J deg⁻¹ mol⁻¹ (8.23 ± 0.08 cal deg⁻¹ mol⁻¹).

I. Introduction

The results of heat-capacity measurements on beryllium nitride, Be_3N_2 , presented between 20 and 315 K in this paper have been obtained in connection with a research program at the National Bureau of Standards to provide thermodynamic data on light-element compounds. In connection with this program, the high-temperature enthalpy measurements have previously been reported by Douglas and Payne [1]. Earlier, Satoh [9] reported relative enthalpy measurements at three temperatures in the range 273 to 773 K on a sample of 98.13 percent purity, the impurities being 0.78, 0.87, and 0.22 percent BeO , Fe_2O_3 , and SiO_2 , respectively. Recently Justice [2] reported measurements in the range 25 to 310 K on a sample of 96.7 purity.

II. Apparatus and Method

The low-temperature heat-capacity measurements were made from about 20 to 315 K in an adiabatic calorimeter of a design similar in principle to that described previously [10]. (The measurements were made initially from about 80 K, but the measurements above 315 K were discontinued when small heat effects were observed above 320 K. The results presented in this paper are based on the data obtained subsequent to heating above 320 K.)

The calorimeter vessel, after filling with the Be_3N_2 sample, was sealed by means of a specially designed gold-gasket closure [7] and suspended within the adiabatic shield by means of a Nylon string instead of the filling tube shown in the above reference. The average temperature of the adiabatic shield was sensed relative to that of the

outer surface of the double-walled sample vessel by means of four-junction constantan-Chromel-P thermocouples and was controlled automatically by means of a combination of electronic and electromechanical equipment. Heater wires were wound bifilarly in grooves on the cylindrical surface and on the conical ends of the adiabatic shield to achieve good thermal contact. Details of the design of the calorimeter used, its operation, and the automatic adiabatic control system will be described in a later publication.

The platinum resistance thermometer (laboratory designation: 1057849) used in the measurements was calibrated in accordance with the International Practical Temperature Scale of 1948 [11]. The temperatures in degrees Kelvin (K) were obtained by adding 273.15 deg to the temperatures in degrees Celsius (C). Below 90 K, the thermometer was calibrated on the NBS-1955 provisional scale which is numerically 0.01 deg lower than the former NBS-1939 provisional scale [8]. The NBS-1939 provisional temperature scale is based on a set of platinum-resistance thermometers that were compared against a helium gas thermometer. The thermometer resistance measurements were made to the nearest 0.00001 ohm. Initially a manual Mueller bridge was used and later an automatic Mueller bridge. The resistance-time observations obtained with the automatic bridge were analyzed by means of a computer to calculate the heat capacity. The observations with the manually operated bridge were processed by means of a desk calculator.

The electrical power introduced into the calorimeter heater (100 Ω) was measured by means of a Wenner potentiometer in conjunction with a volt box, standard resistor, and saturated standard cells, which were all calibrated at the National Bureau of Standards. A constant-current power supply stable to 10 ppm or better was used to facilitate the power measurements. The duration of each heating interval was measured by means of a high-precision interval timer operated on the 60-Hz frequency standard provided at the National Bureau of Standards. The 60-Hz frequency standard is based on a 100-kHz quartz oscillator which is stable to 0.5 ppm. An electronic counter containing a 1-MHz interval quartz oscillator was used simultaneously in the measurement of the heating interval. The estimated uncertainty in the determination of the heating interval was not greater than ± 0.01 sec for any heating period, none of which was less than 2 min in these experiments.

III. Sample

The Be_3N_2 sample was specially prepared for the measurements by the Brush Beryllium Company, Cleveland, Ohio, by reacting pure nitrogen and beryllium powder at elevated temperatures and crushing the product to particle sizes between 20 and 50 mesh (0.8 and 0.3 mm sieve openings, respectively). The material received was thoroughly mixed in a


controlled-atmosphere box containing dry argon (dew-point: -40°C) and samples were apportioned for chemical analysis, for the high-temperature relative enthalpy measurements [1], and for the low-temperature heat-capacity measurements described in this paper. The samples for the chemical analysis and the high-temperature enthalpy measurements were sealed in test tubes under dry argon. The sample that was poured into the low-temperature calorimeter vessel weighed 97.415g. The calorimeter vessel containing the sample was pumped at high vacuum and purged with dry helium gas several times and finally, helium gas at a pressure of 70 torr was sealed in the container with the sample. After completion of the measurements the calorimeter vessel was opened in the controlled-atmosphere box and the sample was divided and sealed in polyethylene bags for chemical analysis. The sealed polyethylene bags were placed individually in screw-cap jars which were in turn placed in desiccators, the whole operation being done in the controlled-atmosphere box.

The results of spectrochemical analysis of the sample are summarized in Table 1. Only the impurity elements that were detected are listed. The results of the chemical analyses on the material before and after the calorimetric measurements are given in Table 2. For the nitrogen and total beryllium analyses about 0.3 g samples were first dissolved in dilute hydrochloric acid and the solution diluted to 250 cc in a volumetric flask. A 10-cc aliquot was analyzed for nitrogen using the Kjeldahl method, the ammonia being titrated with 0.01 N hydrochloric acid that had been standardized against ammonium dihydrogen phosphate by means of the Kjeldahl procedure. The total beryllium was determined by precipitating the beryllium hydroxide in a 100-cc aliquot with ammonium hydroxide. The beryllium hydroxide was filtered, ignited, and weighed as BeO . The free beryllium was determined by dissolving 2-g samples in hydrochloric acid. The hydrogen formed was dried, converted to water, and weighed.

The analysis for water represents all forms of hydrogen present in the sample. Samples (20 mg) were heated at 1050°C in a carbon-hydrogen-nitrogen analyzer and the amount of water driven off was determined. The oxygen was determined by a non-destructive 14-Mev neutron activation technique. Five determinations were made using 6-g samples.

The results of the chemical analysis were found to be inconsistent and unexpected. The decrease in the free beryllium content in the samples before and after the measurements can not be attributed to chemical reactions at temperatures of the measurements. (Small heat effects were observed above about 320°K . See later parts of this section for further details.) The difference is probably due to non-homogeneity in the material, although relatively large samples (2-g) were used in this determination.

The decrease in the total beryllium content because of a chemical reaction during the heat measurements does not seem possible. If the observed heat effects resulted from a chemical reaction within the sample, the expected reaction would be:



This should lead to an increase in the apparent beryllium content, since the ammonia would be lost on opening the sample vessel.

For the material removed from the calorimeter vessel after the heat measurements, the mass balance for beryllium found is not consistent in terms of the analyses obtained. The analyses for N, O, and total Be sum to 100.01 percent and the addition of H (0.13 percent) found as water makes the total weight percent 100.14. This is within the expected limits of accuracy of the chemical analyses. However, inconsistencies arise when these analyses are used to obtain mass balance among the chemical species that are expected to be present (Be_3N_2 , BeO, $\text{Be}(\text{OH})_2$, and Be metal). On the basis of the results of the oxygen and water analyses (2.38 and 1.14 percent, respectively), the percentage of beryllium as BeO and $\text{Be}(\text{OH})_2$ sums to 0.77 percent. When the Be metal (0.04 percent) and beryllium (47.22 percent) as Be_3N_2 , based on the nitrogen analysis, are added to 0.77 percent, the total beryllium becomes 48.03 percent. This is considerably lower than the total beryllium (48.70 percent) from the chemical analysis. The masses of the substances present also sum to considerably less than 100 percent (96.15% - Be_3N_2 , 2.72% - $\text{Be}(\text{OH})_2$, 0.56% - BeO, and 0.04% - Be metal; 99.47% - total mass). These inconsistencies can be resolved if the Be metal analysis were higher (about 0.7 percent), but this is not possible since the estimated error in the chemical analysis for Be metal is much less than this value.

On the other hand, if the analysis shown in Table 2 for water is ignored, the remaining analyses would become consistent on the basis that the substances present are only Be_3N_2 , BeO, and Be metal. All of the oxygen (2.38 percent) would then be taken to be present as BeO, which corresponds to 3.73 percent BeO or 1.34 percent Be. When the percentages of Be as Be_3N_2 and as Be metal are added to 1.34 percent, the total "calculated" Be is 48.61 percent. This is within the limits of chemical analysis found for total Be (48.70 percent). When the 96.15 percent Be_3N_2 , based on the nitrogen analysis, is added to the percentages of BeO and Be metal, the total weight percent is 99.92 percent. The analyses for total beryllium, nitrogen, and oxygen, as mentioned earlier, sum to 100.01 percent. These values are all within the limits of the chemical analysis.

The source of heat effects observed during the measurements can not be explained in terms of the known possible chemical reaction within the sample. The possible chemical reaction depicted by equation (1), in which the water from $\text{Be}(\text{OH})_2$ reacts with Be_3N_2 to form BeO and NH_3 , is not consistent with the chemical analyses. The reaction is obviously not possible if the water is securely held at the temperatures of the heat measurements. Duval and Duval [3] interpreted their thermal gravimetric analysis work to indicate that the decomposition of $\text{Be}(\text{OH})_2$ starts around 150 C and that complete decomposition of $\text{Be}(\text{OH})_2$ to BeO and H_2O occurs only on heating to 951 C. The observed loss in mass at temperatures below 150 C was attributed to adsorbed water in their sample. If any moisture were present in the sample that was used in the work reported here, it was adsorbed between the times the samples was removed from the furnace and received from the supplier.

After careful consideration of the various possibilities that could be selected on the basis of the chemical analyses and the estimated uncertainties that would arise from them, the choice was made to ignore the analysis obtained for water in the reduction of the heat-capacity measurements. The sample was taken to be 96.23 percent Be_3N_2 , 3.73 percent BeO , and 0.04 percent Be metal and corrections were applied to the observed values of heat capacity for BeO [5] and Be metal [6].

IV. Results

Two series of measurements were made, one on the calorimeter vessel with sample (gross) and the other on the empty vessel (tare). The measured energy increments (Q) and the corresponding thermometer resistances (R) before and after heating were analyzed on the high-speed digital computer to obtain dQ/dR of the sample as a function of the thermometer resistance [4]. The values of heat capacity (dQ/dT) were then calculated at even temperatures from the dR/dT and the R-T calibration for the thermometer using the relation:

$$dQ/dT = (dQ/dR)(dR/dT) . \quad (2)$$

Briefly, the procedure was to obtain first the best polynomial equation of the form

$$dQ/dR = \sum a_n R^n \quad (3)$$

to represent the experimental data on the empty calorimeter vessel (tare) [12]. The polynomial equation was then evaluated at the thermometer resistances observed for the gross measurements in order to obtain the energy increments for sample only from the observations in the calorimeter vessel plus sample experiments. The best polynomial equation giving dQ/dR for the sample only was then obtained.

Figure 1 shows the deviation of the experimental data on the empty container from corresponding values calculated from the polynomial equation fitted by the method of least squares to the energy-resistance observations. The range of the polynomial is from $n = -4$ to $n = +10$ (see eq. 3). Due to increasingly poorer precision at the lowest experimental temperatures the sample data were fitted with two overlapping equations. Figure 2 shows the deviation of the sample data from the polynomial (n ranging from 0 to 4) fitted to the data over the temperature range 20 to 110 K and figure 3 the deviation of the data from the polynomial (n ranging from -2 to +10) fitted over the temperature range 60 to 315 K. Heat capacity values calculated from the two equations agreed within 0.02% over the temperature range 80 to 100 K. The heat capacity values obtained from the two equations were joined at 90 K. Figures 2 and 3 show the precision of the measurements and the effect on the final smooth values of a change of 0.025 percent in the values of the heat-capacity measurements for the empty and filled sample vessel.

As mentioned earlier heat effects were observed during the measurements of the heat capacity above about 320 K, and the results that are presented are based on the data obtained between 20 and 315 K subsequent to heating above 320 K. In figure 4 are shown values of heat capacity initially obtained between 80 and 315 K prior to heating above 320 K. Above 150 K, the values of the initial measurements and those after heating above 320 K are shown to be essentially the same. Below 150 K, the values of the initial measurements are somewhat higher. Since no data were obtained initially below 80 K, no comparison can be made below 80 K between the values before and after heating above 320 K. In the range 80 to 315 K, however, the heating above 320 K did not make a large change in the heat capacity of the sample, at most about 0.5 percent at 110 K. The comparison shows that the heat capacity of the sample was not affected grossly when heated above 320 K.

The values of heat capacity of Be_3N_2 , that were generated at evenly spaced temperatures from dQ/dR in accordance with eq (2) were corrected for BeO [5] and Be metal [6] and converted to molal basis. The molecular weight was taken to be 55.05 g. These molal values were analyzed further for extrapolation to 0 K. The final selected values below 20 K are based on the extrapolation of the experimental heat capacity using the Debye heat-capacity function:

$$C = 1943.73 (705/T)^3 \quad (4)$$

$$(\text{J deg}^{-1} \text{mol}^{-1})$$

The values of heat capacity from 0 to 315 K were applied in the usual thermodynamic relations:

$$H_T - H_{0K}^O = \int_0^T C \, dt, \quad (5)$$

$$S_T = \int_0^T (C/T) \, dT, \quad (6)$$

and

$$G_T - H_{0K}^O = (H_T - H_{0K}^O) - T S_T, \quad (7)$$

to obtain the thermodynamic properties. The values are given in Table 3.

Justice [2] recently reported heat-capacity measurements on α -Be₃N₂ of 96.7 percent purity. The significant impurities were BeO - 2.7%, Be metal - 0.2%, C - 0.1%, and Fe - 0.3%. The entropy at 298.15 K that Justice [2] reported is 8.157 cal deg⁻¹ mol⁻¹, which is in good agreement with that (8.23 \pm 0.08 cal deg⁻¹ mol⁻¹) found in this investigation. The values of heat capacity obtained also join satisfactorily, in both the magnitude of heat capacity and its slope, with those derived from the high temperature relative enthalpy measurements reported by Douglas and Payne [1]. A combined table of thermodynamic properties from 0 to 1200 K will be submitted in the next report.

V. References

- [1] T. B. Douglas and W. H. Payne, "Be₃N₂ and BeO·Al₂O₃: High-temperature thermodynamic functions based on recent measurements of heat capacity at the National Bureau of Standards", Preliminary Report on the Thermodynamic Properties of Selected Light-Element and Some Related Compounds, NBS Report 7587, 1 July 1962.
- [2] Dow Chemical Company, JANAF Thermochemical Tables, Quarterly Supplement No. 25, March 31, 1967, under USAF Contract No. F04611-67-C-0009.
- [3] T. Duval and C. Duval, Anal. Chim. Acta, 2, 53 (1948).
- [4] G. T. Furukawa and M. L. Reilly, J. Res. NBS 69A (Phys. and Chem.) No. 1, 5 (1965).
- [5] G. T. Furukawa and M. L. Reilly, unpublished measurements on BeO.
- [6] G. T. Furukawa and M. L. Reilly, unreported results of analysis of literature heat-capacity data on beryllium.

- [7] G. T. Furukawa, M. L. Reilly, and J. H. Piccirelli, J. Res. NBS 68A (Phys. and Chem.) No. 4, 381 (1964).
- [8] H. J. Hoge and F. G. Brickwedde, J. Res. NBS 22, 351 (1939), RP1188.
- [9] S. Satoh, Sci. Papers Inst. Phys. Chem. Research (Tokyo) 34, 888 (1938).
- [10] R. B. Scott, C. H. Myers, R. D. Rands, Jr., F. G. Brickwedde, and N. Bekkedahl, J. Res. NBS 35, 39 (1945), RP1661.
- [11] H. F. Stimson, J. Res. NBS 65A (Phys. and Chem.) No. 3, 139 (1961).
- [12] P. Walsh, Comm. ACM 5, 511 (1962).

Table 1. Summary of Spectrochemical Analysis of the Sample of Beryllium Nitride, Be_3N_2 . Impurity Elements that were Detected.

<u>Element</u>	<u>Wt. %</u>	<u>Element</u>	<u>Wt. %</u>
Al	0.001 - 0.01	Mg	0.001 - 0.01
Ca	< 0.001	Mn	< 0.001
Cr	0.001 - 0.01	Ni	0.001 - 0.01
Cu	< 0.001	Si	0.01 - 0.1
Fe	0.01 - 0.1	Ti	0.001 - 0.01

Analysis by: Elizabeth K. Hubbard
Spectrochemical Analysis Section

Table 2. Chemical Analysis of the
Sample of Beryllium Nitride, Be_3N_2 .

Original Sample

	Wt. %		Wt. %
Be (total)	49.06	N	49.45
	49.09		49.52
			49.84
mean ...	49.08		
		mean ...	49.60
Be (free)	0.09	Cl	<0.02
	0.11		
	0.09		
		F	<0.01
mean ...	0.10		

Sample Removed from Calorimeter Vessel

Be (total)	48.72	N	48.97
	48.68		48.89
mean ...	48.70	mean ...	48.93
Be (free)	0.04	H_2O	1.16
	0.04		1.12
mean ...	0.04	mean ...	1.14
O	2.38 (average of 5 determinations)		

Chemical analysis by: R. A. Paulson
Microchemical Analysis Section

Oxygen analysis by activation method: S. Nargolwalla
Activation Analysis Section

TABLE 3

THERMODYNAMIC FUNCTIONS FOR BERYLLIUM NITRIDE (Be_3N_2)

SOLID PHASE

GRAM MOLECULAR WT.=55.0500 GRAMS

CAL=4.1840 ABS J

$$T \text{ DEG K} = 273.15 + T \text{ DEG C}$$

T	$-(G_T^0 - H_0^C)/T$	$(H_T^0 - H_0^C)/T$	$(S_T^0 - S_0^C)$	$(H_T^0 - H_0^C)$	C_P^0	$-(G_T^0 - H_0^C)$
DEG K	<u>CAL</u> DEG MOLE	<u>CAL</u> DEG MOLE	<u>CAL</u> DEG MOLE	<u>CAL</u> MOLE	<u>CAL</u> DEG MOLE	<u>CAL</u> MOLE
.00	.000	.000	.000	.000	.000	.000
5.00	.000	.000	.000	.000	.000	.000
10.00	.000	.000	.000	.003	.001	.001
15.00	.000	.001	.001	.017	.004	.006
20.00	.009	.003	.003	.053	.011	.018
25.00	.002	.005	.007	.129	.021	.043
30.00	.003	.009	.012	.267	.035	.089
35.00	.005	.014	.019	.490	.055	.165
40.00	.007	.021	.028	.828	.081	.280
45.00	.010	.029	.039	1.314	.115	.446
50.00	.014	.040	.053	1.991	.158	.676
55.00	.018	.053	.071	2.910	.212	.985
60.00	.023	.069	.092	4.133	.280	1.390
65.00	.029	.088	.118	5.736	.364	1.913
70.00	.037	.111	.148	7.900	.464	2.575
75.00	.045	.139	.184	10.411	.584	3.404
80.00	.055	.171	.226	13.671	.724	4.427
85.00	.067	.208	.275	17.685	.886	5.677
90.00	.080	.251	.331	22.557	1.066	7.186
95.00	.095	.299	.393	28.379	1.266	8.994
100.00	.111	.352	.464	35.248	1.485	11.134
105.00	.130	.412	.542	43.265	1.725	13.645
110.00	.151	.478	.628	52.531	1.984	16.568
115.00	.173	.549	.722	63.138	2.261	19.941
120.00	.198	.626	.825	75.172	2.555	23.805
125.00	.226	.710	.935	88.715	2.865	28.202
130.00	.255	.799	1.054	103.84	3.188	33.172
135.00	.287	.893	1.181	120.52	3.525	38.755
140.00	.321	.994	1.315	139.12	3.874	44.991
145.00	.358	1.099	1.457	159.38	4.234	51.919
150.00	.397	1.210	1.607	181.47	4.602	59.576
155.00	.439	1.325	1.764	205.42	4.978	68.000
160.00	.483	1.445	1.928	231.26	5.362	77.228
165.00	.529	1.570	2.099	259.04	5.750	87.292
170.00	.578	1.699	2.276	288.77	6.143	98.228
175.00	.629	1.831	2.460	320.47	6.538	110.07
180.00	.682	1.968	2.650	354.15	6.935	122.84
185.00	.738	2.107	2.845	389.83	7.334	136.58
190.00	.796	2.250	3.046	427.49	7.732	151.30
195.00	.857	2.396	3.252	467.14	8.129	167.05
200.00	.919	2.544	3.463	508.78	8.525	183.83
205.00	.984	2.695	3.678	552.39	8.919	201.69
210.00	1.051	2.847	3.898	597.96	9.310	220.63
215.00	1.119	3.002	4.122	645.48	9.698	240.67
220.00	1.190	3.159	4.349	694.93	10.083	261.85
225.00	1.263	3.317	4.580	746.31	10.465	284.17
230.00	1.338	3.476	4.814	799.58	10.843	307.65
235.00	1.414	3.637	5.051	854.73	11.216	332.31
240.00	1.492	3.799	5.291	911.73	11.585	358.17
245.00	1.572	3.962	5.534	970.57	11.950	385.23
250.00	1.654	4.125	5.779	1031.2	12.309	413.51
255.00	1.737	4.289	6.026	1093.7	12.664	443.02
260.00	1.822	4.453	6.275	1157.8	13.012	473.78
265.00	1.909	4.618	6.527	1223.8	13.355	505.78
270.00	1.996	4.783	6.779	1291.4	13.693	539.05
273.15	2.053	4.887	6.939	1334.9	13.902	560.55
275.00	2.086	4.948	7.034	1360.7	14.024	573.58
280.00	2.176	5.113	7.289	1431.6	14.350	609.39
285.00	2.258	5.278	7.546	1504.2	14.670	646.47
290.00	2.352	5.442	7.804	1578.3	14.985	684.85
295.00	2.456	5.607	8.063	1654.0	15.294	724.52
298.15	2.516	5.710	8.226	1702.5	15.486	750.17
300.00	2.552	5.771	8.322	1731.3	15.598	765.48
305.00	2.648	5.934	8.583	1810.0	15.897	807.74
310.00	2.746	6.097	8.844	1890.2	16.187	851.31
315.00	2.845	6.260	9.105	1971.9	16.468	896.18

 H_0^C AND S_0^C APPLY TO THE REFERENCE STATE OF THE SOLID AT ZERO DEG K.




Fig. 1. Percentage Deviation of the Empty Sample Vessel Heat Capacities.




Fig.2. Percentage Deviation of the Beryllium Nitride Sample Heat Capacities.




Fig. 3. Percentage Deviation of the Beryllium Nitride Sample Heat Capacities.




Fig. 4. Percentage Deviation of Initial Measurements from the Beryllium Nitride Sample Heat Capacities.

Chapter 3

AUTOMATIC DATA REDUCTION APPLIED TO BOMB CALORIMETRY OF ORGANIC FLUORINE COMPOUNDS*

George T. Armstrong
Thermochemistry Section

Abstract

Subroutine FARMST, to calculate the combustion energy of organic fluorine compounds from oxygen-bomb calorimetric data, has been prepared following the computational procedure of Good and Scott. The subroutine is written in FORTRAN IV and conforms to the more general program of Shomate for C-H-O-N-S compounds. The Shomate program has been modified to allow introduction of subroutine FARMST, and to change the calculations in several procedural ways including presentation of the result in joules.

* This work was supported, in part, by funds from the Department of the Navy.

1. Introduction

Shomate [1] prepared a general program for reduction of the data from bomb combustion of organic compounds containing the elements C-H-O-N-S, following the computational procedure of Hubbard, Scott, and Waddington [2]. He recently [1a] modified his program to FORTRAN IV, and segmented it into subroutines. We have made additional modifications in order to improve the versatility of the program, to render the results in joules, and to introduce the new subroutine FARMST.

We have written subroutine FARMST to allow the reduction of data involving fluorine as well as C-H-O-N. For this reduction a procedure for hand computation was previously reported by Good and Scott [3]. This procedure is followed in FARMST. The procedure does not make provision for handling compounds containing both S and F together.

2. New variables in the program

In order to make the general modifications outlined above new variables were defined in the program. Many of these took the form of additions to the array W. It is useful to place variables here because W has the property that it can be modified by the input data cards, and the values in it are available for a memory print-out associated with any experiment. Array W has 999 terms, of which some 673 are used. A complete listing of the variables in this array is given in Table 1. Of these W(1) to W(22), W(109), W(206), W(226), W(246), W(266), W(286), and W(591) to W(673) have not previously been defined. In addition the definitions of W(572) and W(573) were changed. Tables of data needed in subroutine FARMST were introduced into DATA as block data. These are W51AF, a table of solubilities of CO₂ in aqueous HF solutions, obtained from Cox and Head [4]; W87AF, a table of energies of solution of CO₂ in aqueous HF solutions, also obtained from Cox and Head [4]; W71AF, a table of dilution energies for aqueous HF, taken from Wagman, et al. [5]; W72A, W73A, W74A, and W75A, tables of properties of aqueous HF solutions taken from Good and Scott [3]. Unfortunately the latter tables are given only at 25°C, so that the computation is limited in the adequacy with which it can be applied to other temperatures.

Values for the solubility of CO₂ are given by Cox and Head [4] for concentrations of HF from 0 to 5%. Values at 6% were estimated by extrapolation and inserted in the array of data in order to allow use of the quadratic interpolation formulas given in the program for interpolation in the region from 4 to 5 percent. The data for the energy of solution of CO₂ was similarly extrapolated.

Data from Wagman, et al. [5] were smoothed. The point at HF-10H₂O appears to be somewhat irregular and a fictitious value must be used at 0% HF, in order to allow reasonable interpolation from 1 to 2%.

Values at 1 percent intervals were taken from the smooth curve to form the data array to be used in the computations. In all the above cases quadratic interpolation is used. Where temperature is known as a variable, a two-fold quadratic interpolation is used. Table W71AF is not suitable for interpolation in the region 0 to 1% HF.

Table 1.

TABLE OF THERMOCHEMICAL VARIABLES
EXPANDED FOR FARMST SUBROUTINE

Term of the W array	Value or meaning, and units
1	1. The constant unity
2	273.15 The ice point temperature, °K
3	298.15 The standard reference temperature, 25°C.
4	101325 The standard atmosphere, Nm ⁻²
5	22413.6 The standard molar volume of a gas, cm ³
6	4.184 The thermochemical calorie, J
7	
8	The gas constant, $R = 8.314325 \text{ J mol}^{-1}$, defined by $R = 0.000001 * W(4)/W(2)$.
9	The gas constant, $R = 1.9871715 \text{ cal mol}^{-1}$, defined by $R = W(8)/W(6)$
10	The gas constant, $R = 0.0820560 \text{ cm}^3 \text{ atm}$, defined by $R = W(5)/W(2) * 0.001$
11	Molecular weight of water, defined by $W(11) = 2. * W(559) + W(560)$
12	Molecular weight of carbon dioxide, defined by $W(12) = W(558) + 2. * W(560)$
13	Molecular weight of nitrous acid, defined by $W(13) = W(559) + W(561) + 2. * W(560)$
14	Molecular weight of nitric acid, defined by $W(14) = W(559) + W(561) + 3. * W(560)$
15	Molecular weight of sulfuric acid, defined by $W(15) = 2. * W(559) + W(562) + 4. * W(560)$
16	Molecular weight of HF, defined by $W(16) = W(559) + W(563)$
17	
18	
19	
20	

Table 1. (continued).

21	$T_h - 25.$, defined by $W(21) = W(148) - 25.$
22	$T_h + 273.15$, defined by $W(22) = W(148) + W(2)$
23	Mass of substance
24	Mass of substance
25	Moles of substance
26	$V_i[\text{bomb}]$, dm^3
27	$V_i[\text{H}_2\text{O}(\text{total})]$, dm^3
28	$P_i[\text{gas}]$, atm
29	$M_i[\text{H}_2\text{O}(\text{total})]$, g
30	$N_i[\text{H}_2\text{O}(\text{total})]$, mol
31	$V_i[\text{gas}]$, dm^3
32	$N_i[\text{H}_2\text{O}(\text{vapor})]$, mol
33	$N_i[\text{H}_2\text{O}(\text{liquid})]$, mol
34	$N_i[\text{gas}]$, mol
35	$N_i[(\text{O}_2 + \text{N}_2) (\text{dissolved})]$, mol
36	$N_i[\text{O}_2 + \text{N}_2] (\text{total})]$, mol
37	$N_f[\text{HNO}_3]$, mol
38	$N_f[\text{HNO}_2]$, mol
39	$N_f[\text{H}_2\text{SO}_4]$, mol
40	$N_f[\text{H}_2\text{O}(\text{liquid})]$, mol
41	$M_f[\text{solution}]$
42	(Weight per cent) $_f [\text{H}_2\text{SO}_4]$
43	(Weight per cent) $_f [\text{HNO}_3 + \text{HNO}_2]$
44	(Density) $_f [\text{solution}]$, g dm^{-3}
45	$V_f [\text{solution}]$
46	(Normality) $_f [\text{H}_2\text{SO}_4]$, mol dm^{-3}
47	(Normality) $_f [\text{HNO}_3 + \text{HNO}_2]$, mol dm^{-3}
48	$N_f [\text{H}_2\text{O} (\text{liquid})]/N_f [\text{H}_2\text{SO}_4]$
49	$V_f [\text{Gas}]$, dm^3
50	$N_f [\text{CO}_2] (\text{total})]$, mol
51	$K_f [\text{CO}_2]$
52	$D_f [\text{CO}_2]$
53	$K_f^* [\text{CO}_2]$
54	$N_f [\text{CO}_2 (\text{dissolved})]$, mol
55	$N_f [\text{CO}_2 (\text{gas})]$, mol

Table 1. (continued).

56	$N_f [(O_2 + N_2) \text{ (total)}] , \text{ mol}$
57	$K_f [O_2]$
58	$D_f [O_2]$
59	$K_f^* [O_2]$
60	$N_f [(O_2 + N_2) \text{ (dissolved)}] , \text{ mol}$
61	$N_f [(O_2 + N_2) \text{ (gas)}] , \text{ mol}$
62	$N_f [\text{gas}] , \text{ mol}$
63	$X_f [CO_2] , \text{ (mole fraction)}$
64	$U_f [\text{gas}]$
65	$P_f [\text{gas}] , \text{ atm}$
66	G
67	$N_f [H_2O \text{ (vapor)}] , \text{ mol}$
68	--
69	$[(dE/dp)_T]_f [\text{solution}] , \text{ J mol}^{-1} \text{ deg}^{-1}$
70	$\Delta E (\text{dilution})[HNO_3 + HNO_2] , \text{ J mol}^{-1}$
71	$\Delta E (\text{dilution})[H_2SO_4] , \text{ J mol}^{-1}$
72	--
73	--
74	$E [\text{calorimeter}] , \text{ J deg}^{-1}$
75	$E_i [\text{contents}] , \text{ J deg}^{-1}$
76	$E_f [\text{contents}] , \text{ J deg}^{-1}$
77	$\Delta E (\text{ignition}) , \text{ J}$
78	$T_i , \text{ deg C}$
79	$T_f , \text{ deg C}$
80	$\Delta T (\text{correction}) , \text{ deg}$
81	$[\Delta E (\text{vaporization})]_i [H_2O] , \text{ J}$
82	$\Delta E_i [H_2O] \text{ from } 1 \text{ to } P_i , \text{ J}$
83	$\Delta E_i [\text{substance}] \text{ from } 1 \text{ to } P_i , \text{ J}$
84	$[\Delta E (\text{solution})]_i [O_2 + N_2] , \text{ J}$
85	$\Delta E_i (\text{gas}) \text{ from } 0 \text{ to } P_i , \text{ J}$
86	$\Delta E (\text{isothermal bomb process}) , \text{ J}$
87	$[\Delta E (\text{solution})]_f [CO_2] , \text{ J}$
88	$[\Delta E (\text{solution})]_f [O_2 + N_2] , \text{ J}$
89	$\Delta E_f [\text{solution}] \text{ from } 1 \text{ to } P_f , \text{ J}$
90	$[\Delta E (\text{dilution})]_f [HNO_3 + HNO_2] , \text{ J}$
91	$[\Delta E (\text{dilution})]_f [H_2SO_4] , \text{ J}$

Table 1. (continued).

92	$[\Delta E \text{ (decomposition)}]_f [\text{HNO}_3 + \text{HNO}_2]$, J
93	ΔE_f [gas] from P_f to 0 , J
94	$[\Delta E \text{ (vaporization)}]_f [\text{H}_2\text{O}]$, J
95	Sum of W (81) to W (94) inclusive, J
96	Combustion energy from auxiliary material , J
97	Combustion energy from fuse , J
98	Combustion energy from compound , J
99	$\Delta E_c/M$ [compound] at T_h , J
100	ΔE_c [compound] at T_h , J
101	ΔH_c [compound] at T_h , J
102	ΔH_c [compound] at 25 deg C , J
103	ΔH_f [compound] at 25 deg C , J
104	A subscript (C_A) in empirical formula of bomb contents
105	B " (H_B) " " " " " "
106	C " (O_C) " " " " " "
107	D " (N_D) " " " " " "
108	E " (S_E) " " " " " "
109	F " (F_F) " " " " " "
110	() " () " " " " " "
111	() " () " " " " " "
112	() " () " " " " " "
113	N_f [N_2^*] , extra nitrogen , mol
114	Weight of platinum in air , g
115	Weight of glass in air , g
116	Weight of other materials in air , g
117	Mass of platinum (weight in vacuum) , g
118	Mass of glass (weight in vacuum) , g
119	Mass of other materials (weight in vacuum) , g
120	Volume of platinum , dm^3
121	Volume of glass , dm^3
122	Volume of other materials , dm^3
123	Free space in rigid glass bulb , dm^3
124	Nitrogen in free space , mol
125	Initial period rate , deg min^{-1}
126	Final period rate , deg min^{-1}

Table 1. (continued).

127	X [O ₂ + N ₂] , mole fraction
128	X [N ₂ [*]] , mole fraction
129	Mu [O ₂] , see item W(64)
130	A (C _p of solution) , see item W(76) , cal deg ⁻¹
131	E [calorimeter] * (T _i - T _f - ΔT (correction)) , J
132	E _i [contents] * (T _i - T _h) , J
133	E _f [contents] * (T _h - T _f + ΔT (correction)) , J
134	ΔH (vaporization) [H ₂ O] , for W(81) and W(94) ,
135	Cooling constant , min ⁻¹
136	Area under Temperature vs. Time curve , deg min
137	Time (start of main period) , min
138	Time (end of main period) , min
139	Temperature (start of main period) , deg
140	Temperature (start of main period) , deg
141	Mid-time (time after start of main period) , min
142	Rotation time , min
143	Heat of bomb rotation , deg min ⁻¹
144	Sum of terms W(81) , W(82) , W(84) , W(85) , W(88) , W(89), W(93) , W(94) , W(83) , J
145	Corrected temperature rise , deg
146	Pressure to which the bomb was filled , atm
147	Temperature at which the bomb was filled , deg C
148	T _h , the selected temperature , deg C
149	T _h , predetermined value of T _h , deg C
150	Pressure of N ₂ in glass bulb , atm
151	{ Coefficients used to calculate values of items at
152	
153	
154	Selected ratio N _f [H ₂ O]/N _f [H ₂ SO ₄]
155	Actual ratio N _f [H ₂ O]/N _f [H ₂ SO ₄]
156	ΔH _f [H ₂ SO ₄] at selected ratio , cal mol ⁻¹
157	ΔH _f [H ₂ SO ₄] at actual ratio , cal mol ⁻¹
158	Combustion energy from 1st impurity , J
159	Combustion energy from 2nd impurity , J
160	Density of air (if zero , item 567 is used) , g cm ⁻³

Table 1. (continued).

161	C_p of H_2SO_4 solution (selected concentration) , cal g^{-1} deg $^{-1}$
162	$\Delta C_p/\Delta T$ of H_2SO_4 solution (selected concentration) , cal g^{-1} deg $^{-2}$
163	Density of H_2O , g dm $^{-3}$
164	Reference ratio $N_f [H_2O]/ N_f [HF]$
165	
166	
167	
168	
169	
170	
171	
172	
173	
174	
175	
176	
177	
178	
179	
180	
181	
182	
183	
184	
185	
186	
187	
188	
189	
190	
191	
192	
193	
194	

Table 1. (continued).

195	
196	
197	
198	
199	
200	
201	Number of C atoms in compound
202	" " A " " "
203	" " O " " "
204	" " N " " "
205	" " S " " "
206	" " F " " "
207	" " () " " "
208	" " () " " "
209	" " () " " "
210	Mass of compound (weight in vacuum) , g
211	Molecular weight of compound
212	Moles of compound
213	Density of compound , g cm^{-3}
214	Volume of compound , dm^3
215	Weight of compound (in air) , g
216	C_p of compound , $\text{cal g}^{-1} \text{deg}^{-1}$
217	$(\Delta V/\Delta T)_p$ of compound , $\text{dm}^3 \text{deg}^{-1} \text{g}^{-1}$
218	$(\Delta E/\Delta P)_T$ of compound , $\text{J atm}^{-1} \text{g}^{-1}$
219	ΔE_c [compound] , J g^{-1}
220	ΔE_c [compound] , J mol^{-1}
221	Number of C atoms in auxiliary material
222	" " H " " "
223	" " O " " "
224	" " N " " "
225	" " S " " "
226	" " F " " "
227	" " () " " "
228	" " () " " "
229	" " () " " "

Table 1. (continued).

230	Mass of auxiliary material (weight in vacuum) , g
231	Molecular weight of auxiliary material
232	Moles of auxiliary material
233	Density of auxiliary material , g cm^{-3}
234	Volume of auxiliary material , cm^3
235	Weight of auxiliary material (in air) , g
236	C_p of auxiliary material, $\text{cal g}^{-1} \text{deg}^{-1}$
237	$(\Delta V/\Delta T)_p$ of auxiliary material , $\text{dm}^3 \text{deg}^{-1} \text{g}^{-1}$
238	$(\Delta E/\Delta P)_T$ of auxiliary material , $\text{J atm}^{-1} \text{g}^{-1}$
239	ΔE_c [auxiliary material] , J g^{-1}
240	ΔE_c [auxiliary material] , J mol^{-1}
241	Number of C atoms in fuse
242	" " H " " "
243	" " O " " "
244	" " N " " "
245	" " S " " "
246	" " F " " "
247	" " () " " "
248	" " () " " "
249	" " () " " "
250	Mass of fuse (weight in vacuum) , g
251	Molecular weight of fuse
252	Moles of fuse
253	Density of fuse , g cm^{-3}
254	Volume of fuse , dm^3
255	Weight of fuse (in air) , g
256	C_p of fuse , $\text{cal g}^{-1} \text{deg}^{-1}$
257	$(\Delta V/\Delta T)_p$ of fuse, $\text{dm}^3 \text{deg}^{-1} \text{g}^{-1}$
258	$(\Delta E/\Delta P)_T$ of fuse, $\text{dm}^3 \text{atm}^{-1} \text{g}^{-1}$
259	ΔE_c [fuse] , J g^{-1}
260	ΔE_c [fuse] , J mol^{-1}
261	Number of C atoms in first impurity
262	" " H " " "
263	" " O " " "
264	" " N " " "

Table 1. (continued).

265	Number of S atoms in first impurity
266	" " F " " " "
267	" " () " " " "
268	" " () " " " "
269	" " () " " " "
270	Mass of first impurity (weight in vacuum) , g
271	Molecular weight of first impurity
272	Moles of first impurity
273	Density of first impurity , g cm ⁻³
274	Volume of first impurity , dm ³
275	Weight of first impurity (in air) , g
276	C _p of first impurity , cal g ⁻¹ deg ⁻¹
277	($\Delta V/\Delta T$) _p of first impurity , dm ³ deg ⁻¹ g ⁻¹
278	($\Delta E/\Delta P$) _T of first impurity , J atm ⁻¹ g ⁻¹
279	ΔE_c [first impurity] , J g ⁻¹
280	ΔE_c [first impurity] , J mol ⁻¹
281	Number of C atoms in second impurity
282	" " H " " " "
283	" " O " " " "
284	" " N " " " "
285	" " S " " " "
286	" " F " " " "
287	" " () " " " "
288	" " () " " " "
289	" " () " " " "
290	Mass of second impurity (weight in vacuum) , g
291	Molecular weight of second impurity
292	Moles of second impurity
293	Density of second impurity , g cm ⁻³
294	Volume of second impurity , dm ³
295	Weight of second impurity (in air) , g
296	C _p of second impurity , cal g ⁻¹ deg ⁻¹
297	($\Delta V/\Delta T$) _p of second impurity , dm ³ deg ⁻¹ g ⁻¹
298	($\Delta E/\Delta P$) _T of second impurity , J atm ⁻¹ g ⁻¹
299	ΔE_c [second impurity] , J g ⁻¹

Table 1. (continued).

300	ΔE_c [second impurity] , J mol ⁻¹
301 - 400	Recorded times at which corresponding temperature readings in locations 401-500 were taken, minutes
401-500	Recorded temperatures of the initial, main, and final periods, introduced in ohms and converted by the program to degrees C.
501-550	Bridge dial corrections , ohms
551	Ten-ohm dial setting, nominal value, ohms
552	Ten-ohm dial setting correction , ohms
553	Average correction to convert N-only or R-only readings to (N + R) /2.
554	Bridge-zero correction
555	
556	
557	
558	Atomic weight of C (12.01115)
559	Atomic weight of H (1.00797)
560	Atomic weight of O (15.9994)
561	Atomic weight of N (14.0067)
562	Atomic weight of S (32.064)
563	Atomic weight of F (18.9984)
564	Atomic weight of
565	Atomic weight of
566	Atomic weight of
567	Density of Air , 0.0012 g cm ⁻³
568	Density of weights , 8.4 g cm ⁻³
569	Density of platinum , 21.45 g cm ⁻³
570	Density of glass , 2.24 g cm ⁻³
571	Density of other material , 1.0 g cm ⁻³
572	Density of water g/1000 cm ³
573	
574	0.0
575	$\Delta E_c/M$ for benzoic acid calculated by program , J g ⁻¹
576	$\Delta E_c/M$ for benzoic acid, certified value = 26.434 kJ g ⁻¹
577	C_p of platinum = 0.0325 cal g ⁻¹
578	C_p of glass = 0.17 cal g ⁻¹

Table 1. (continued).

579	C_p of other material , = 0.0 cal g^{-1}
580	C_p of CO_2 , gas, at 25°C , 0.20163 cal g^{-1} deg $^{-1}$
581	$\Delta C_p / \Delta T$ of CO_2 = 0.0 cal g^{-1} deg $^{-2}$
582	C_p of O_2 , gas, at 25°C , 0.219375 cal g^{-1} deg $^{-1}$
583	$\Delta C_p / \Delta T$ of O_2 = 0.0 cal g^{-1} deg $^{-2}$
584	C_p of N_2 , gas, at 25°C, 0.248465 cal g^{-1} deg $^{-1}$
585	$\Delta C_p / \Delta T$ of N_2 = 0.0 cal g^{-1} deg $^{-2}$
586	C_p of H_2O , liquid, at 25°C , 0.99895 cal g^{-1} deg $^{-1}$
587	$\Delta C_p / \Delta T$ of H_2O = 0.0 cal g^{-1} deg $^{-2}$
588	$\Delta C_p / \Delta T$ of sample = 0.0 cal g^{-1} deg $^{-2}$
589	$\Delta H_f [CO_2 \text{ (gas)}] = -2137.0552$ cal g^{-1}
590	$\Delta H_f [H_2O \text{ (l)}] = -3\,792.04$ cal g^{-1}
591	$\Delta H \text{ vap } [H_2O] = 10\,177$ cal mol^{-1}
592	$\Delta E \text{ decomp } [HNO_3] = 14\,074$ cal mol^{-1}
593	$\Delta E \text{ decomp } [HNO_2] = -6\,600$ cal mol^{-1}
594	$\Delta E \text{ vap } [HF \text{ from HF (aq)}] = 11\,000$ cal mol^{-1}
595	$\Delta E_f [HF \text{ in } 10H_2O] = -76\,235$ cal mol^{-1}
596	ΔH or ΔE hydrolysis [CF_4] = -41 500 cal mol^{-1}
597	$C_p [CF_4] = 14.7$ cal mol^{-1} deg $^{-1}$
598	$\Delta C_p / \Delta T [CF_4] = 0$
599	--
600	--
601	$C_i [HF \text{ (vap)}]$
602	(Normality) $_i [HNO_3]$, m $mol \text{ cm}^{-3}$
603	$K_i [O_2]$
604	$N_i [HF \text{ (vap)}]$, mol
605	$D_i [O_2]$
606	$N_f [HF \text{ (total)}]$, mol
607	$N_f [CF_4 \text{ (total)}]$, mol
608	$N_i [HF \text{ (total)}]$, mol
609	$N_f [H_2O \text{ (total)}]$, mol
610	(Weight per cent) $_f [HNO_3]$
611	(Weight per cent) $_f [HF]$
612	$N_f [HF \text{ (ag)}]$, mol
613	$N_f [H_2O] / N_f [HF]$, actual ratio

Table 1. (continued).

614	$N_f [H_2O] / f [HF]$, selected ratio
615	$C_f [HF (vap)]$
616	$(dE/dp)_i [solution]$, cal atm ⁻¹
617	$(dE/dp)_f [solution]$, cal atm ⁻¹
618	$\Lambda_i [solution]$
619	$\Lambda_f [solution]$
620	$N_f [HF (gas)]$, mol
621	$(Normality)_f [HF]$, mmol cm ⁻³
622	$\Delta E_f [CO_2] / N_f [CO_2]$ cal
623	Mole fraction (X) $[CF_4]$
624	ΔE dilution $[HF (final)]$, cal
625	$N_f [H_2O] / N_f [HF]$, selected ratio
626	Weight per cent HF at selected ratio
627	Weight per cent HF at $N_f [H_2O] / N_f [HF] = 10$
628	$\Delta H_f [HF (aq, \text{selected ratio})]$, cal mol ⁻¹
629	$N_i [H_2O]$, mol
630	$\Delta H_f [HF (aq, \text{selected ratio})] - \Delta H_f [HF (aq, 10H_2O)]$, cal mol ⁻¹
631	$\Delta H_f [HF (aq, 10H_2O)] - \Delta H_f [HF (aq, \text{actual ratio})]$, cal mol ⁻¹
632	$M_i [solution]$, g
633	$(\Delta E \text{ vap})_i [HF]$, cal mol ⁻¹
634	$(\Delta E \text{ vap})_f [HF]$, cal mol ⁻¹
635	ΔE dilution $[HF (total)]$, cal mol ⁻¹
636	$M_i [HF]$, g
637	Molar coefficient of CF_4 in equation
638	--
639	Correction for CF_4 hydrolysis , cal
640	$C_p [HF (aq, \text{selected ratio})]$, cal g ⁻¹
641	Molar coefficient of O_2 in equation
642	Molar coefficient of H_2O adjusted for hydrolysis of CF_4 .
643	Molar coefficient of CO_2 adjusted for hydrolysis of CF_4
644	Molar coefficient of N_2 in equation
645	Molar coefficient of HF adjusted for hydrolysis of CF_4
646	--
647	--

Table 1. (continued).

648	$\Delta N[\text{gas}]$, mol
649	$\Delta H_f [\text{CO}_2 (\text{g})]$, cal mol ⁻¹
650	$\Delta H_f [\text{H}_2\text{O} (\text{l})]$, cal mol ⁻¹
651	Moles idealized actual HF (aq, selected ratio)
652	Moles idealized actual H ₂ O
653	Moles idealized actual CO ₂
654	Moles H ₂ O reacted (excludes water in HF (aq, selected ratio))
655	$M_i [\text{HNO}_3]$, g
656	(Weight per cent) _i [HF]
657	(Weight per cent) _i [HNO ₃]
658	ρ_i [solution] , g cm ⁻³
659	V_i [solution] , 1000 cm ³
660	g_i
661	ΔH at 25° C [adjusted reaction] , J mol ⁻¹
662	ΔE at 25° C [adjusted reaction] , J mol ⁻¹
663	ΔE at 25° C [unadjusted reaction] , J mol ⁻¹
664	ΔH_f [compound] at 25° C, J mol ⁻¹
665	ΔE_f [compound] at 25° C, J mol ⁻¹
666	$\Delta H_f [\text{H}_2\text{SO}_4 (\text{aq, selected ratio})]$, J mol ⁻¹ , = W(156) * W(6)
667	$\Delta H_f [\text{H}_2\text{SO}_4 (\text{aq, actual ratio})]$, J mol ⁻¹ , = W(157) * W(6)
668	ΔH [Reaction] at 25° C , adjusted for hydrolysis of CF ₄ , cal mol ⁻¹
669	ΔE [Reaction] at 25° C , ' ' ' ' ' ' ' ' ' ' cal mol ⁻¹
670	ΔE [Reaction] at 25° C , unadjusted , cal mol ⁻¹
671	ΔH_f [Compound] at 25° C , cal mol ⁻¹
672	ΔE_f [Compound] at 25° C , cal mol ⁻¹
673	ΔH [Reaction] at 25° C, unadjusted , cal mol ⁻¹

3. Subroutine FARMST

The practice initiated by Shomate, of numbering variables in the W array, so far as possible, to conform to the number of the calculational step given by Hubbard, et al. [2] is continued here by numbering them to conform to the computational steps given by Good and Scott [3]. These authors have made their work mutually consistent to a large degree. It is not possible to follow this practice throughout, however, because in order to retain mutual consistency with Hubbard, et al., Scott and Good introduced multiple variables of the same step number. We have assigned some of these variables higher numbers (above W(590)) more or less as they are encountered in the calculation. The subroutine begins with the calculation of W(29), as all prior steps are identical in the two programs. The subroutine then bypasses the major part of the program called HOWARD, following a parallel but different set of calculations to arrive at final energy values. Where an identity could be established between a variable of FARMST and a variable of HOWARD, i.e. as to meaning, the same variable designation was used in FARMST.

In calculating the composition of the initial bomb contents and the final bomb contents, the program assigns temporary values to the amounts of water and HF present in the liquid phase, and of $\text{CO}_2(\text{g})$, $[\text{N}_2 + \text{O}_2](\text{g})$, $\text{H}_2\text{O}(\text{g})$, and total gas, present in the gas phase. These are then adjusted after one pass through the calculation, and the calculation of the quantities is repeated.

In mathematical expressions used at various stages of the computations, Good and Scott [3] used expressions valid at 25°C , whereas in similar instances Hubbard, et al. [2] used expressions containing terms with temperature as a parameter. Where the correspondence between equations used showed that the equation used by Hubbard, et al. reduced at 25°C to that used by Good and Scott, we used the more general expression of Hubbard, et al., as did Shomate [1, 1a].

4. Modifications to the main program and subroutines

The modifications made in the main program HOWARD and subroutines INPUT, CONVRT, MIDTIM, OUTPUT, and DATA, may be classified as (1) those necessary to introduce an additional subroutine, which do not modify the mode of calculation, and (2) those which are matters of convenience or preference in causing the calculations to have certain desirable features.

In classification (1) we refer to changes such as program statements necessary to allow the program to recognize the new variables introduced in the subroutine. These are matters of programming technique and include definitions of certain variables at suitable times, in the program or in block DATA subroutine, transfer statements dependent on the presence of F in the compound, and suitable output statements to give the appropriate point out.

In classification (2) changes were introduced in order to change the details of the calculation in certain ways.

Calculations were put in terms of joules wherever practicable, Where input data, such as tables, were in calories in the original sources, these were converted to joules before finally being added as energy terms. The program was restated so that the energy equivalent of the calorimeter would be in joules per degree, the energies of combustion of fuse, auxiliary materials, and impurities were in joules per gram, the ignition energy was in joules, and so on. Output statements were modified to indicate the new units. A certain number of output variables were expressed in both joules and calories, and so new variables were introduced to allow this.

Universal constants and defined constants were introduced in the block data program where possible, rather than as terms in the numerical coefficients of equations throughout the program and subroutines. The algebraic variables were then used in the equations. The reason for this is to permit ready change of a constant throughout the program, if it should ever be desirable. Thus the value of the standard molar volume of a gas, $22413.6 \text{ cm}^3 \text{ mol}^{-1}$, is given the name W(5), and the

variable W(5) is used wherever the standard molar volume occurs in an equation. A change in the selected value of W(5) is thus readily accomplished. Other universal constants introduced in this way include the ice point, 273.15°K , the standard reference temperature, 298.15°K , the standard atmosphere, 101325 Nm^{-2} , the ratio of the calorie to the joule, 4.184 J cal^{-1} , and the atomic weights of the elements. Derived quantities such as the gas constant, R, and the molecular weights of compounds involved in the calculations are calculated at an early stage of the program HOWARD.

The molar coefficients of the reactions involved and the change in moles of gas present were calculated early in the main program.

In INPUT subroutine a statement is introduced causing the machine to test whether T_i , T_f and ΔT (corr) have been specified. If all three are specified, as by means of a "9" card the program omits their calculation, thus bypassing subroutines CONVRT and MIDTIM.

5. Debugging

Subroutine FARMST and the whole program were "debugged" by running the sample calculation given by Good and Scott [3]. In order to do this, the data used by Good and Scott were carefully examined for conformity to the program requirements. Several adjustments in the program were made temporarily to assure that the program would duplicate the results obtained by Good and Scott. These included setting the density of air equal to zero for the buoyancy correction so that masses instead of weights in air could be used for the amounts of substances introduced. A small discrepancy in the bomb volume (apparently due to neglecting the platinum volume) was discovered. An adjusted bomb volume was then selected. Values of the CO₂ solubility and heat of solution were dubbed in to allow the calculation to simulate Good and Scott's.

6. Input Data Cards

Table 2 gives a printout of the input data cards for a run on perfluoropiperidine. Each card is coded in column 1 with a digit from 1 to 9 which defines the class of information found in it, following Shomate's practice. The "1" card contains data concerning the fuse and auxiliary material. The only deviation from Shomate's practice in the "1" card is the use of energies of combustion of these two substances in joules per gram instead of calories per gram. These values are found in columns 30-35 and 66-72 respectively. The "2" card contains the name of the compound, the numbers of C, H, O, N and S atoms in it, and some bomb conditions. The number of F atoms is introduced later in a "9" card. (Table 2 approximates the card format).

The "3" card contains data on the amounts of substances present. The format of this card has been slightly modified to permit weights to be expressed to micrograms. The revised format is as follows:

<u>Column</u>	<u>Format</u>	<u>Quantity</u>
1		3
2-3	A2	Run Number
4-11	F8.0	Weight of compound (in air), g
12-18	F7.0	Weight of fuse (in air), g
19-25	F7.0	Weight of auxiliary material (in air), g
26-32	F7.0	Weight of platinum (in air), g
33-39	F7.0	Weight of glass (in air), g
40-43	3PF4.0	Volume of water placed in bomb, cm ³
44-48	OPF5.0	Ignition energy, J
49-53	6PF7.0	Moles of HNO ₃ formed (X 10 ⁶)
54	F1.0	Moles of HNO ₂ formed (X 10 ⁶)
55-59	10PF5.0	Pressure to which bomb is filled, atm

Table 2

1	11.774.887	1.5	.4	0.	16945.10	8.	4	1.38	.315.11	22842.2
2	PERFLUOROPIPERIDINE				5	1	1.730.2514.955	25.		
3	1 5.77703	.00114	.12864		19.592	0.0	9.983.72	1149.	40.0025.00	
4	28948 1.	1	.		328948	20.				
7	THIS IS A SAMPLE OF THE PRINT-OUT OBTAINED FROM THE COMBUSTION PROGRAM.									
7	TEST OF FARMST SUBROUTINE USING DATA FROM WD GOOD AND DW SCOTT EXAMPLE									
7	TEST OF SHOMATE PROGRAM USING TI, TF, AND DT(CORR) SUPPLIED ON '9' CARD									
8	001673									
81	001673									
9	026 .3538134	074	16746.38		567	0.0				
9	078 22.89480	079	24.89078		080	0.00903				
9	649-94051.		650-68317.							
9	614 10.							606	.045037	
9	558 12.010	559	1.008		560	16.000	561	14.008	563	19.00
9	206 11.	226	0.		246	0.	266	0.	286	0.

60-64	F5.0	Temperature at which bomb is filled, °C
65-71	F7.0	Density of air, for reducing weights to vacuum, g cm ⁻³
72	F1.0	Free space, if any, in rigid glass sample bulb, cm ³

The moles of HNO₂ formed and the volume of free space in the bulb are usually zero, so those have been reduced to a single column each.

Card "4" contains temperature-time data points. The illustration shows a possible format if Ti, Tf and ΔT (corr) are given. A single temperature and time are given in the initial field (terminated by 1 in column 16) and in the final field (initiated by 3 in column 30). These may not be necessary. The actual values of Ti, Tf and ΔT (corr) are introduced later in a "9" card.

Cards "5" and "6" are not used in this program. Card "7" gives commentary which appears in the printout (see Table 3).

Cards "8" and "81" call for memory printout of the W array, as fixed point and floating point format, respectively. In the example, the W array from W(001) to W(673) inclusive is called for.

Cards "9" are used for direct introduction of values into the W array. The element of the W array is first indicated by its number, then the value to be introduced is listed. In the example, the bomb volume is given in W(026). (This value differs from that used by Good and Scott, by the volume of platinum, which they apparently ignored). The energy equivalent of the calorimeter in joules per degree is given in W(074). A fictitious density of air is given in W(567) to permit masses (weight in vacuum) of the various substances in the bomb to be used as given by Good and Scott.

Ti, Tf, and ΔT (corr) are introduced in W(078), W(079), and W(080), respectively. Enthalpies of formation of carbon dioxide (g), and water (l) are introduced in cal mol⁻¹ in W(649) and W(650). W(614) is given the value for the selected ratio of H₂O/HF to be used in the calculations.

Atomic weights used by Good and Scott are introduced in W(558) to W(563). The number of F atoms in the compound of interest is placed in W(206). Other quantities can be introduced at will for checking or other purposes.

7. Output Data

Table 3 is the format of the summary printout of the results of the calculation. Some changes are made from the format suggested by Shomate. The number of decimal figures and the units of several of the quantities are different. Equations are given for the idealized bomb reaction and for the reaction adjusted for hydrolysis of any CF_4 formed. Certain corresponding energy changes are given. In the program these are calculated in joules first and then converted to calories. Values are given at T_h and at 298.15°K , which in this case are the same. The results give for the internal energy change of the idealized reaction the value $-354.54 \text{ kcal mol}^{-1}$, which may be compared with the value -354.51 given by Good and Scott.

The calculations were compared with those illustrated by Good and Scott at several stages in the development of the program. Only minor differences occur, mostly due to rounding. The difference of the value 354.54 from $354.51 \text{ kcal mol}^{-1}$ is apparently due to (1) an error in the value for item 93 listed by Good and Scott, and (2) the use of a different solution energy for CO_2 and a different dilution energy for HF (aq) . (Table 3 approximates the actual format).

TABLE 3

PERFLUOROPIPERIDINE

C5	N1	F11	RUN NO. 1	
WEIGHT OF SAMPLE (IN AIR) 5.77030 (IN VACUO) 5.777030 GRAMS				
INITIAL TEMPERATURE			22.89480	DEG. CENT.
FINAL TEMPERATURE			24.89078	DEG. CENT.
CORRECTION ON TEMPERATURE RISE			.00903	DEG. CENT.
CORRECTED TEMPERATURE RISE			1.98695	DEG. CENT.
COOLING CONSTANT X 10 EXP 3			.000000	PER MIN.
ENERGY EQUIVALENT USED			16746.38	J/DEG
COEFFICIENTS OF IDEALIZED REACTION EXCEPT N2				
COMPOUND	+ O2	+ H2O	= CO2	+ HF . 10H2O + CF4
1.0000000	2.2500000	23.1701900	2.8016713	2.2066847 2.1983288
STANDARD ENERGY CHANGES OF ABOVE REACTION				
INTERNAL ENERGY CHANGE (298.15 DEG K)			-30275.05	JOULES
			-5240.59	JOULES/GRAM
ENTHALPY CHANGE (298.15 DEG K)			-1475.33	KJ/MOLE
ENTHALPY CHANGE (298.15 DEG K)			-1475.33	KJ/MOLE
INTERNAL ENERGY CHANGE (298.15 DEG K)			-1483.39	KJ/MOLE
COEFFICIENTS OF REACTION ADJUSTED FOR HYDROLYSIS OF CF4				
COMPOUND	+ O2	+ H2O	= CO2	+ HF. 10H2O + N2
1.0000000	2.2500000	115.4999990	5.0000000	10.9999999 .5000000
STANDARD ENERGY CHANGES OF ABOVE REACTION				
ENTHALPY CHANGE (298.15 DEG K)			-1857.04	KJ/MOLE
INTERNAL ENERGY CHANGE (298.15 DEG K)			-1865.10	KJ/MOLE
			-443.84	KJ/MOLE
			-445.77	KJ/MOLE

Table 3 (continued)

STANDARD ENTHALPY OF FORMATION (298.15 DEG K)	-2047.03	-489.25
STANDARD INTERNAL ENERGY OF FORMATION (298.15)	-2076.78	-496.36
CORRECTION FOR AUXILIARY MATERIAL(S)	-2938.42	JOULES
CORRECTION FOR FUSE	-19.32	JOULES
CORRECTION FOR CARBON DIOXIDE	21.08	JOULES
CORRECTION FOR NITRIC ACID	67.66	JOULES
CORRECTION FOR DILUTION	1.71	JOULES
CORRECTION FOR OTHER REDUCTIONS	74.02	JOULES
CHANGE OF INTERNAL ENERGY FOR ISOTHERMAL BOMB PROCESS IS		
-33274.22 -133.88 + 7.12 + 3.72, OR -33397.26		JOULES
MIDTIME .000		

THIS IS A SAMPLE OF THE PRINT-OUT OBTAINED FROM THE COMBUSTION PROGRAM

TEST OF FARMST SUBROUTINE USING DATA FROM WD GOOD AND DW SCOTT EXAMPLE

TEST OF SHOMATE PROGRAM USING TI, TF, AND DT (CORR.) SUPPLIED ON '9' CARD.

References

- [1] C. H. Shomate, "Computer Calculation of Combustion Bomb Calorimetric Data," U. S. Naval Ordnance Test Station Technical Report 327, China Lake, California, August, 1963.
- [1a] C. H. Shomate, "Fortran IV Computer Program for Reduction of Heat of Combustion Calorimetric Data," Code 5052 (U. S. Naval Ordnance Test Station, China Lake, California, January 1967).
- [2] W. N. Hubbard, D. W. Scott, and Guy Waddington, "Standard States and Corrections for Combustions in a Bomb at Constant Volume," pp. 75-128. "Experimental Thermochemistry," F. D. Rossini, editor, (Interscience Publishers, New York 1956).
- [3] W. D. Good and D. W. Scott, "Combustion in a Bomb of Organic Fluorine Compounds," pp. 15-39. "Experimental Thermochemistry, Volume 2," H. A. Skinner, editor (Interscience Publishers, New York 1962).
- [4] J. D. Cox and A. J. Head, "Solubility of Carbon Dioxide in Hydrofluoric Acid Solutions," Trans. Faraday Soc. 58, 1839-45 (1962).
- [5] D. W. Wagman, W. H. Evans, V. B. Parker, I. Halow, S. M. Bailey, and R. H. Schumm. "Selected Values of Chemical Thermodynamic Properties," NBS Technical Note 270-1 (U. S. Government Printing Office, Washington, D. C. 1967). (See also NBS Technical Note 270-3, 1968).

Chapter 4

STRUCTURE OF THE ALKALI HYDROXIDES. III. MICROWAVE SPECTRUM OF GASEOUS RbOH

David R. Lide, Jr. and Chi Matsumura

National Bureau of Standards, Washington, D. C.

The microwave spectrum of gaseous RbOH and RbOD have been studied in a high temperature microwave spectrometer. The spectrum indicates a linear or very near linear molecule with a large amplitude, low-frequency bending vibration. The RbO bond length is 2.30 \AA and the OH bond distance is 0.97 \AA . The observed frequencies and their assignments for $^{85}\text{RbOH}$ and $^{85}\text{RbOD}$ are given in Table 1. Similar data for $^{87}\text{RbOH}$ and $^{87}\text{RbOD}$ are given in Table 2. The effective rotational constants and nuclear quadrupole coupling constants for various vibrational states of $^{85}\text{RbOH}$ and $^{87}\text{RbOD}$ are found in Table 3. Table 4 gives the values of q for excited vibrational states involving ν_2 . A fit of $B_0 \nu_2^l$ to a power series for $^{85}\text{RbOH}$ and $^{87}\text{RbOD}$ is given in Table 5. Variation of rotational constants with ν_1 is shown in Table 6, while the structural parameters found for the species is given in Table 7.

Table I
Observed frequencies in $^{85}\text{RbOH}$ and $^{85}\text{RbOD}$

J = 2 → 3				
State	F → F'	⁸⁵ RbOH	⁸⁵ RbOD	
(00 ⁰ 0)	5/2 5/2	37744.8		
	7/2 (7/2, 9/2)	37741.2	}	34324.6
	9/2 11/2			
	5/2 7/2	37738.3		34321.6
	3/2 5/2	37734.9	}	34317.9
	1/2 3/2			
	9/2 (7/2, 9/2)	37728.6		34311.9
(01 ¹ 0) ℓ+	5/2 3/2	37600.7	}	
	3/2 1/2			
	5/2 5/2	37594.3	}	34301.9
	9/2 11/2			
	7/2 (7/2, 9/2)	37591.3		34299.0
	5/2 7/2	37589.4	}	34297.3
	3/2 5/2			
9/2 (7/2, 9/2)	37584.7		34292.3	
(01 ¹ 0) ℓ-	5/2 3/2	37541.0	}	
	3/2 1/2			
	5/2 5/2	37534.9	}	34242.9
	9/2 11/2			
	7/2 (7/2, 9/2)	37532.0		34240.1
	5/2 7/2	37530.6	}	34238.5
	3/2 5/2			
9/2 (7/2, 9/2)	37525.5		34233.5	
(02 ⁰ 0)	7/2 (7/2, 9/2)	37430.5	}	34242.8
	9/2 11/2			
	5/2 7/2	37417.1	}	34240.0
	3/2 5/2			
	1/2 3/2			(34236.0)
(02 ² 0)	1/2 (1/2, 3/2)	37394.0	}	34228.8
	3/2 (1/2, 3/2, 5/2)			
	9/2 (7/2, 9/2, 11/2)	37385.2		34220.1
	5/2 (3/2, 5/2, 7/2)	37375.6		34210.4
	7/2 (5/2, 7/2, 9/2)	37372.2		34207.1
(03 ¹ 0) ℓ+	5/2 5/2	37362.2	}	34278.3
	9/2 11/2			
	7/2 (7/2, 9/2)	37358.9		34275.4
	5/2 7/2	37357.2	}	34273.5
	3/2 5/2			
	9/2 (7/2, 9/2)	37352.5		

Table I - cont.

(03 ¹ 0) ℓ^-	5/2 5/2 }	37238.1	34152.2
	9/2 11/2 }		
	7/2 (7/2, 9/2)	37235.0	34149.3
	5/2 7/2 }	37233.0	34147.8
(04 ² 0)	1/2 (1/2, 3/2)	37179.4	
	3/2 (1/2, 3/2, 5/2)		
	9/2 (7/2, 9/2, 11/2) }	37170.7	34189.2
	5/2 (3/2, 5/2, 7/2)	37160.9	34179.2
	7/2 (5/2, 7/2, 9/2)	37157.8	34174.8
(10 ⁰ 0)	7/2 (7/2, 9/2) }		
	9/2 11/2 }	37479.1	34095.4
	3/2 5/2 }		
	1/2 3/2 }	37472.7	34089.0
	9/2 7/2 }		
	9/2 9/2 }	37466.7	34082.9
(11 ¹ 0) ℓ^+	5/2 5/2 }		
	9/2 11/2 }	37333.6	34071.0
	7/2 (7/2, 9/2)	37330.8	34068.2
	5/2 7/2 }	37329.0	34066.4
	3/2 5/2 }		
	9/2 (7/2, 9/2)	37324.1	
(11 ¹ 0) ℓ^-	5/2 5/2 }		
	9/2 11/2 }	37269.2	34010.2
	7/2 (7/2, 9/2)	37266.4	34007.5
	5/2 7/2 }	37264.9	34006.1
	3/2 5/2 }		
	9/2 (7/2, 9/2)	37260.0	
(12 ⁰ 0)	7/2 (7/2, 9/2) }		
	9/2 11/2 }	37164.5	34010.5
	5/2 7/2 }		34007.6
(12 ² 0)	1/2 (1/2, 3/2)	37140.7	33995.2
	3/2 (1/2, 3/2, 5/2)		
	9/2 (7/2, 9/2, 11/2) }	37132.0	33986.8
	5/2 (3/2, 5/2, 7/2)	37122.3	33977.3
	7/2 (5/2, 7/2, 9/2)	37119.2	33974.1
(200)	7/2 (7/2, 9/2) }		
	9/2 11/2 }	37216.9	33866.8
	5/2 7/2 }	37213.9	33863.9
	3/2 5/2 }	37210.8	33860.7
	1/2 3/2 }		
	9/2 (7/2, 9/2)	37204.8	

Table II
Observed frequencies in $^{87}\text{RbOH}$ and $^{87}\text{RbOD}$

$J = 2 \rightarrow 3$

State	$F \rightarrow F'$	$^{87}\text{RbOH}$	$^{87}\text{RbOD}$
(00^0_0)	$7/2 \quad 9/2 \quad \}$	37597.8	34188.4
	$5/2 \quad 7/2 \quad \}$		
	$3/2 \quad 5/2 \quad \}$	37595.6	34186.6
	$1/2 \quad 3/2 \quad \}$		
$(01^1_0) \ell_+$	$3/2 \quad 3/2$	37455.1	
	$7/2 \quad 9/2 \quad \}$	37450.8	34165.1
	$1/2 \quad 3/2 \quad \}$		
	$5/2 \quad 7/2 \quad \}$	37448.7	34163.4
	$3/2 \quad 5/2 \quad \}$		
	$7/2 \quad 7/2$	37444.0	
$(01^1_0) \ell_-$	$7/2 \quad 9/2 \quad \}$	37391.7	34106.9
	$1/2 \quad 3/2 \quad \}$		
	$5/2 \quad 7/2 \quad \}$	37389.7	34105.1
	$3/2 \quad 5/2 \quad \}$		
(02^0_0)	$7/2 \quad 9/2 \quad \}$	37287.5	34106.9
	$5/2 \quad 7/2 \quad \}$		
	$3/2 \quad 5/2 \quad \}$	37285.6	34105.2
	$1/2 \quad 3/2 \quad \}$		
(02^2_0)	$1/2 \quad 3/2$	37246.8	
	$7/2 \quad (5/2, 7/2, 9/2)$	37241.1	34082.5
	$3/2 \quad (3/2, 5/2)$	37238.3	
	$5/2 \quad (3/2, 5/2, 7/2)$	37232.8	34074.2
(10^0_0)	$7/2 \quad 9/2 \quad \}$	37337.1	33960.8
	$5/2 \quad 7/2 \quad \}$		
	$5/2 \quad 7/2 \quad \}$		33959.0
	$3/2 \quad 5/2 \quad \}$		

Table III

Effective rotational constants and nuclear quadrupole coupling constants for various vibrational states of RbOH and RbOD.

State		$B_v (^{85}\text{RbOH})$	$B_v (^{85}\text{RbOD})$	eqQ
00^0_0	Σ	6290.15	5720.77	-67.9
01^1_0	π	6260.55	5711.69	-67.6
02^0_0	Σ	6238.37	5707.08	(-67.9)
02^2_0	Δ	6230.13	5702.57	-67.4
03^1_0	π	6216.43	5702.34	(-67.6)
04^2_0	Δ	6194.38	5697.42	-67
10^0_0	Σ	6246.45	5682.50	-65.9
11^1_0	π	6216.70	5673.24	-67
12^0_0	Σ	6194.03	5668.37	(-66)
12^2_0	Δ	6187.95	5663.75	-66.3
20^0_0	Σ	6202.75	5644.40	-64.2

State		$B_v (^{87}\text{RbOH})$	$B_v (^{87}\text{RbOD})$	eqQ
00^0_0	Σ	6266.35	5698.13	-35
01^1_0	π	6236.84	5689.32	-33
02^0_0	Σ	6214.63	5684.53	-31
02^2_0	Δ	6206.48	5680.02	-32
10^0_0	Σ	6222.90	5660.18	(-33)

Table IV

 ℓ -Doubling constants

State	$q(^{85}\text{RbOH})$	$q(^{85}\text{RbOD})$	$q(^{87}\text{RbOH})$	$q(^{87}\text{RbOD})$
(01^1_0)	9.87	9.82	9.85	9.70
(03^1_0)	10.33	10.51		
(11^1_0)	10.73	10.12		

Table V

Fit of BOv_2^2O to power series

State	$^{85}\text{RbOH}$	Obs - calc	$^{85}\text{RbOD}$	Obs - calc
	calc $\text{BOv}_2^{\ell}\text{O}$		calc $\text{BOv}_2^{\ell}\text{O}$	
00^0_0	6290.10	0.05	5720.77	0.00
01^1_0	6260.38	0.17	5711.70	-0.01
02^0_0	6238.57	-0.20	5707.09	-0.01
02^2_0	6230.38	-0.25	5702.49	-0.08
03^1_0	6216.48	-0.05	5702.34	0.00
04^2_0	6194.10	0.28	5697.45	-0.03

Table VI

Variation of rotational constants with V_1

V_2^{ℓ}	$BOv_2^{\ell}O$	$Blv_2^{\ell}O$
<hr/>		
<hr/>		
$^{85}\text{RbOH}$		
0^0	47.70	43.70
1^1	43.85	
2^0	44.34	
2^2	42.18	
<hr/>		
$^{85}\text{RbOD}$		
0^0	38.27	38.10
1^1	38.45	
2^0	38.71	
2^2	38.82	
<hr/>		
$^{87}\text{RbOH}$		
0^0	43.45	
<hr/>		
$^{87}\text{RbOD}$		
0^0	37.95	
<hr/>		

Table VII

Structural parameters of Rubidium Hydroxide

	From BOO ⁰ O	From "B _e " ^a
r (RbO)	2.316	2.305
r (ON)	0.913	0.965

a) The first terms in equations (1) were used as "B_e".

Chapter 5

MASS SPECTROMETRIC STUDY AT HIGH TEMPERATURES OF THE Al_2O_3 -BeO SYSTEM

by

J. Efimenko

INTRODUCTION

Data have been obtained for the vapor species existing at high temperatures for a number of selected compositions in the Al_2O_3 -BeO system (Report No. 8628, 9028, 9389). This report presents data and calculated thermodynamic quantities for the eutectic mixture, BeO: Al_2O_3 (94.2% Al_2O_3), melting point $1890 \pm 10^\circ\text{C}$, S. M. Lang, C. L. Fillmore, and L. H. Maxwell, J. Res. NBS 48, 301 (1952). The initial purpose of these investigations was to observe and study any complex vapor species in this system. The following is a preliminary report of these data.

EXPERIMENTAL

The procedure followed is similar to that used previously, Report No. 9389. The mass spectrometer had been disassembled completely and reassembled in the new laboratory previous to this experiment. Before the eutectic mixture was placed in the instrument a blank run was carried out. It was necessary to check whether contamination from previously used materials was serious. In addition, a silver calibration was performed in the same effusion cell before the experiment with this eutectic mixture was concluded.

RESULTS

Experimental data are shown in Table 1 and auxiliary data used for computation in Table 2. Equilibria considered for this system are the following:

- (1) $\text{Al}(\text{g}) + \text{O}(\text{g}) + \text{Be}(\text{g}) \rightleftharpoons \text{AlOBe}(\text{g})$
- (2) $2\text{Al}(\text{g}) + \text{O}(\text{g}) \rightleftharpoons \text{Al}_2\text{O}(\text{g})$
- (3) $\text{Al}_2\text{O}(\text{g}) + \text{Be}(\text{g}) \rightleftharpoons \text{AlOBe}(\text{g}) + \text{Al}(\text{g})$
- (5) $\text{Al}_2\text{O}_3 \cdot \text{BeO}(\text{l}) \rightleftharpoons 2\text{Al}(\text{g}) + \text{Be}(\text{g}) + 4\text{O}(\text{g})$

Equilibria constants corresponding to these reactions were computed and are presented in Table 3. A second law treatment, ($\ln K$ vs $1/T$)

yielded enthalpies as shown in Table 4. For comparison, enthalpies for the same equilibria, observed over the compound, $\text{Al}_2\text{O}_3 \cdot \text{BeO}$ (80.3% Al_2O_3), are presented. On the basis of the reaction enthalpy for (1) this experiment indicates a value of $\Delta H_f^\circ = -41$ kcal/mol for the standard heat of formation of AlOBe . The earlier experiments gave a value of -6.2 kcal/mol.

DISCUSSION

In the temperature range investigated, 2177-2562°K, the only complex specie which appeared in addition to the species from the individual reactants was AlOBe . At the higher end of the temperature range, tungsten oxides appeared also but their intensities were minor in comparison to the species Be^+ , O^+ , Al^+ .

During the period that the data in Table 1 were obtained, two shut-downs occurred. One was to replace the electron bombardment heating filaments that failed and the second was to introduce a weighed quantity of silver for a calibration. The data collected in any one run are indicated by the sequence in the index number and the separate runs by the tens series.

From Table 1 it is observed that there are 34 rows of data to compute enthalpies for reactions 1 and 5, while only eight rows for reactions 2 and 3. Since the specie of interest was AlOBe , more time was spent accumulating data for reactions 1 and 5. One set of data, index numbers 50-57, does not have a temperature cycle.

The computed equilibrium constants for reaction 1 show a rather large scatter for check temperature points. Two factors can be responsible for such a scatter. The effusion cell may have had a serious temperature gradient, before or after changing the bombardment filaments and secondly, temperature equilibrium may not have been established inside the effusion cell. Whenever a temperature cycle was performed during a run, the down temperature data do not always follow the same line as the up temperature data. Attainment of constancy of ion intensity may not be a true indication of thermal equilibrium after intentionally changing temperature. The equilibrium constants for reactions 2 and 3 show much less scatter because no temperature cycle was performed for the data, index numbers 50-57.

Since no composition analysis was made of the condensed phase with time and temperature, reaction 5 will not be discussed here. Using the eutectic composition $\text{BeO}:\text{Al}_2\text{O}_3$ (94.2% Al_2O_3) gave a starting composition with specific properties at equilibrium. Reaction 3, which is not independent but is obtainable from combination of reactions 1 and 2, is included as a check. These enthalpies need to be re-examined because of the indicated discrepancies. Reaction 2 has been studied independently by other workers, reporting values

ΔH° , -254 ± 7 and -243 ± 7 kcal/mol. A third law computation will be made for the enthalpies of these reactions for analysis and comparison. As pointed out previously, the data points for reactions 2 and 3 were taken without a temperature cycle and include much fewer readings. Data were obtained on two other eutectic compositions, $\text{BeO}:\text{Al}_2\text{O}_3$ (85.9% Al_2O_3) and $\text{BeO}:\text{Al}_2\text{O}_3$ (75% Al_2O_3), as well as another compound, $\text{BeO} \cdot \text{Al}_2\text{O}_3$ (80.3% Al_2O_3). This additional data will be analyzed for the same gaseous equilibria.

TABLE 1

Ion Intensities Over Eutectic $\text{BeO}:\text{Al}_2\text{O}_3$ (94.2% Al_2O_3)

(intensities in volts)

Index No.	T, °C	I_{Be}^+	I_{O}^+	I_{Al}^+	I_{AlOBe}^+	I_{AlO}^+	$I_{\text{Al}_2\text{O}}^+$
57	2190	99×10^{-3}	49×10^{-2}	42×10^{-1}	18×10^{-3}	28×10^{-2}	28×10^{-2}
56	2135	67×10^{-3}	28×10^{-2}	22×10^{-1}	11×10^{-3}	13.5×10^{-2}	14×10^{-2}
55	2085	43×10^{-3}	15.6×10^{-2}	12×10^{-1}	57×10^{-4}	67.5×10^{-3}	73×10^{-3}
54	2030	28×10^{-3}	81×10^{-3}	60.5×10^{-2}	31×10^{-4}	33×10^{-3}	34×10^{-3}
53	1980	16×10^{-3}	38×10^{-3}	27.3×10^{-2}	15×10^{-4}	15×10^{-3}	14×10^{-3}
52	1895	64×10^{-4}	13×10^{-3}	77×10^{-3}	4.5×10^{-4}	14×10^{-4}	32×10^{-4}
51	1855	41×10^{-4}	57×10^{-4}	36.5×10^{-3}	3.5×10^{-4}	9×10^{-4}	12×10^{-4}
50	1850	46.5×10^{-4}	51×10^{-4}	42×10^{-3}	6×10^{-4}	9×10^{-4}	10×10^{-4}
10	1860	33×10^{-4}	8×10^{-3}	39×10^{-3}	72×10^{-4}		
11	1840	27×10^{-4}	51×10^{-4}	21×10^{-3}	45×10^{-4}		
12	1892	51×10^{-4}	81×10^{-4}	61×10^{-3}	57×10^{-4}		
13	1890	45×10^{-4}	93×10^{-4}	63×10^{-3}	45×10^{-4}		
14	2000	14.4×10^{-3}	35×10^{-3}	27×10^{-2}	90×10^{-4}		
15	2050	23×10^{-3}	72×10^{-3}	61×10^{-2}	14×10^{-3}		
16	1985	10×10^{-3}	33×10^{-3}	23×10^{-2}	57×10^{-4}		
17	1930	57×10^{-4}	16×10^{-3}	10×10^{-2}	33×10^{-4}		
18	1880	27×10^{-4}	78×10^{-4}	41×10^{-3}	20×10^{-4}		
20	1860	30×10^{-4}	45×10^{-4}	24×10^{-3}	20×10^{-4}		
21	1920	66×10^{-4}	11×10^{-3}	70×10^{-3}	22×10^{-4}		
22	1880	35×10^{-4}	63×10^{-4}	37×10^{-3}	19×10^{-4}		
23	1850	28×10^{-4}	42×10^{-4}	23×10^{-3}	13×10^{-4}		
30	2055	35×10^{-3}	11.4×10^{-2}	88×10^{-2}	84×10^{-4}		
31	1990	19×10^{-3}	54×10^{-3}	36×10^{-3}	42×10^{-4}		
32	1928	85.5×10^{-4}	19×10^{-3}	12×10^{-2}	20×10^{-4}		
33	1880	54×10^{-4}	10×10^{-3}	54×10^{-3}	14×10^{-4}		

TABLE 1 (continued)

48	1935	59×10^{-4}	24×10^{-3}	11.4×10^{-2}	12×10^{-4}
47	2035	19×10^{-3}	91×10^{-3}	47×10^{-2}	42×10^{-4}
46	2200	10×10^{-2}	67×10^{-2}	55×10^{-1}	28×10^{-3}
45	2150	69×10^{-3}	34×10^{-2}	27×10^{-2}	16×10^{-3}
44	2080	44×10^{-3}	16×10^{-2}	12×10^{-2}	90×10^{-4}
43	2040	26×10^{-3}	80×10^{-3}	61×10^{-2}	52×10^{-4}
42	1975	13×10^{-3}	34×10^{-3}	23×10^{-2}	25×10^{-4}
41	2025	23×10^{-3}	63×10^{-3}	46×10^{-2}	47×10^{-4}
40	1920	72×10^{-4}	17×10^{-3}	89×10^{-2}	11×10^{-4}

TABLE 2

Auxiliary Data

Sensitivity, S_{Ag}	1.7796×10^{-8} amp/mmHg
Temp. - Silver Calib.	1305K
Window + Prism Transmissivity	$1.40 \times 10^{-5} K^{-1}$

Specie	Ionization Cross Section σ_1 (1)	Multiplier Sensitivity γ_1 (2)
Ag	34.8	296
Be	6.3	276
O	3.3	288
Al	15.4	292
Al ₂ O	34.1	226
AlOBe	25.0	93

(1) J. W. Otvos and D. P. Stevenson, J. Am. Chem. Soc. 78, 546-551 (1956).

(2) Experimental values, author.

TABLE 3

Equilibria Constants

 K_1 subscripts refer to the reactions listed below

Index No.	1/T, °K	K_1	K_2	K_3	$K_5 \times 10^{20}$
57	3.9201	1.2730	3.6402	3.4971	5.7040×10^{-30}
56	4.0128	4.0242	1.2165	3.3082	9.5881×10^{-32}
55	4.1009	1.1166	3.9963	2.7941	1.5154×10^{-33}
54	4.2022	3.7407	1.4808	2.5261	1.5368×10^{-35}
53	4.2985	1.5657	6.6793	2.3441	7.3905×10^{-38}
52	4.4725	1.3175	6.0730	2.1694	2.4400×10^{-41}
51	4.5592	7.9974	2.4020	3.3294	1.1349×10^{-43}
50	4.5703	1.1798	1.6978	6.9490	1.0738×10^{-43}
10	4.5482	1.3564			4.1156×10^{-43}
11	4.5926	3.0777			1.5066×10^{-44}
12	4.4789	4.2548			1.8209×10^{-42}
13	4.4832	3.2166			2.9582×10^{-42}
14	4.2595	1.1251			4.9912×10^{-38}
15	4.1648	2.2541			8.5291×10^{-36}
16	4.2887	1.2952			1.8948×10^{-38}
17	4.3993	6.5663			9.4411×10^{-41}
18	4.5047	4.4072			3.5974×10^{-43}
20	4.5482	1.1973			1.4185×10^{-44}
21	4.4200	7.9299			1.1580×10^{-41}
22	4.5047	4.4311			1.6163×10^{-43}
23	4.5703	9.0211			9.7115×10^{-45}
30	4.1555	3.8737			1.7242×10^{-34}
31	4.2789	1.9521			6.4258×10^{-39}
32	4.4034	1.8653			4.0287×10^{-40}
33	4.5047	9.1351			3.3718×10^{-42}
48	4.3890	1.3427			6.5356×10^{-40}
47	4.1928	8.5192			1.0185×10^{-35}
46	3.9037	1.0857			3.5567×10^{-29}
45	3.9871	3.7652			3.3823×10^{-33}
44	4.1099	1.6873			1.6897×10^{-35}
43	4.1834	6.7253			1.4244×10^{-35}
42	4.3084	4.2802			2.6880×10^{-38}
41	4.2116	1.1728			2.6290×10^{-36}
40	4.4200	1.8497			1.1650×10^{-38}

1. $\text{Al} + \text{O} + \text{Be} = \text{AlOBe}$, K_1
2. $2\text{Al} + \text{O} = \text{Al}_2\text{O}$, K_2
3. $\text{Al}_2\text{O} + \text{Be} = \text{AlOBe} + \text{Al}$, K_3
5. $\text{Al}_2\text{O}_3 \cdot \text{BeO}(\ell) = \text{Be} + 2\text{Al} + 4\text{O}$, K_5

TABLE 4

Reaction Enthalpies

Results from eutectic $\text{BeO}:\text{Al}_2\text{O}_3$ (94.2 wgt % Al_2O_3 , melting point $1890 \pm 10^\circ\text{C}$)

Reaction	ΔH_{2350}° , kcal/mol	ΔH_0° , kcal/mol
(1)	-260	-254
(2)	-262	-256
(3)	+1.82	+1.89
(5)	+980	

Results* from compound $\text{BeO}.\text{Al}_2\text{O}_3$ (80.3 wgt % Al_2O_3 , melting point $1870 \pm 10^\circ\text{C}$)

Reaction	ΔH_{2350}° , kcal/mol	ΔH_0° , kcal/mol
(1)	-222 ± 4.6	-216
(2)	-257 ± 6	-252
(3)	$+35.5 \pm 4$	+36.2
(5)	$+952 \pm 71$	

* From Report No. 9028.

Chapter 6

THE ENTHALPY OF TUNGSTEN FROM 1100 TO 2600°K

E. D. West and S. Ishihara

The high-temperature enthalpy of tungsten is important not only because of its use in high-temperature engineering applications but also because of its use as a container material in the high-temperature enthalpy measurements of other materials and its possible use as a reference material for these measurements to permit a check on the capabilities of various laboratories.

In earlier work in this program [1,2], tungsten was used as a container for liquid Al_2O_3 and liquid $BeO \cdot Al_2O_3$. Revised results for the latter are reported in a subsequent chapter in this report.

The work reported in this chapter was carried out as part of a National Bureau of Standards program related to work done for AFOSR.

Method and Apparatus

The method and apparatus have been described briefly [1,2,3]. Essentially, the apparatus consists of a furnace, in which a specimen in a capsule is held at various high temperatures, and an adiabatic calorimeter, operating near room temperature, which measures the heat given up when the hot specimen is lifted into it. Heat lost by the container in the transfer process is accounted for by separate experiments with the empty capsule. If all the heat lost comes from the capsule wall in both experiments, it is accounted for when the difference in heats is ascribed to the specimen.

The temperature in the furnace is measured by a Leeds & Northrup automatic photoelectric pyrometer sighted on the bottom of the capsule. The output signal from the pyrometer is used in a control loop to maintain a selected constant temperature while the capsule is in the furnace. Some improvements have been made in the pyrometry since the earlier report [1]. Frequent balancing of the integrator circuit has apparently improved the precision of the temperature measurement. Reported temperatures are based on a calibration made by the NBS Radiation Thermometry Section in 1967. The conditions of this calibration are closer to the conditions of use than those of the 1965 calibration although the maximum difference between the two is 0.2% at 1108°K. Four spot checks between these two calibrations do not show any consistent trend. They differ from the 1967 calibration by -0.16, -0.95, +0.31 and +0.66°K.

At high temperatures, there is considerable risk of contamination or mechanical damage to both specimen and container. With tungsten we found it helpful to use a smaller specimen for higher temperatures to reduce breakage of the suspension wire. To minimize the risk and permit this flexibility, we use a method which yields in one day's work all the information required for the calculation of the enthalpy at the operating temperature for that day. Usually four experiments are made at the same temperature in a day--two with the capsule alone and two with the capsule plus specimen. For some higher temperatures, only two experiments are made because of the time required for additional weighing. Weights of the capsule and the specimen can be made after each experiment to check for contamination or vaporization. Allowance for variations in the heat for the capsule can be made by correlating weight gains and observed heats for the empty capsule.

A principal advantage of this method is that loss of a capsule or container on one day does not invalidate data taken previously as would be the case if all the data were obtained for the empty capsule before any measurements were made with the specimen. In this case, loss of the capsule might mean loss of the data taken with it. In experiments at 2700°K, a tungsten capsule developed a crack which allowed contamination of specimen D with carbon from the furnace atmosphere, but experiments at lower temperatures were not affected.

Another advantage of the method is that it facilitates inter-comparison of different specimens under nearly identical conditions. At 1613°K, for example, two different specimens were used the same day.

Materials

Four specimens were used in this work. These are described below with the same designations used in table 1. All machining was done by grinding with aluminum oxide wheels.

Specimen A: Commercial "pure", nominally 99.95% tungsten. Spectrochemical analysis of another piece of the same rod for 51 elements found a maximum of 0.01% impurity. Surface was cleaned by rinsing in carbon tetrachloride. Weight (corrected for buoyancy) 23.0134 g, constant to 0.2 mg, which is about the limit of the balance used.

Specimen B: Triple zone-refined tungsten nominally 99.999% tungsten, in the form of one-eighth inch diameter rods. The rods were cut to length, but not otherwise machined. The surface was treated with one part 48% HF and two parts concentrated HNO₃ for one minute. The weight was 13.3911 g constant \pm within 0.2 mg.

Specimen C: Same as A but surface treated with one part HF and three parts HNO_3 . Weight 13.8482 g constant within 0.2 mg until it gained 0.6 mg in the experiment at 2403°K.

Specimen D: Same as C, except weight 10.6807 g. The specimen gained 0.4 mg at 2450°K, 0.4 and 2.9 mg at 2600, 15.5 mg at 2700°K and 20.6 mg at 2800°K. Analysis in a carbon-hydrogen combustion train found 0.74% carbon in a sample 1 mm long cut from the ends of the specimen. A second sample 2 mm long adjacent to the first showed 0.12% carbon. The analysis indicates that carbon vapor reached the specimen through the crack in the capsule wall near one end.

The atomic weight used for tungsten was 183.85.

Results

The corrected experimental data for the enthalpy of tungsten are shown in table 1. Three capsules and four specimens were used, as indicated in the last column. The specimens are described above.

The temperature in the first column has been corrected for the loss of radiation in a prism in the optical path. Corrections made for variation in room temperature in earlier work [1] are no longer necessary.

The quantity of heat in the second column includes corrections for the enthalpy of the capsule and specimen between the actual final calorimeter temperature and 298.15°K. Data required for this correction are taken from Stull and Sinke [4]. Corrections made in the earlier work [1] for small variations in the furnace temperature are no longer required. The enthalpy calculated from one experiment with the capsule and one with the capsule and specimen are shown in the third column.

The data for the enthalpy of tungsten in kilojoules per gram-atomic weight are represented by the equation

$$H_T - H_{298.15} = -7.115 + (23.041)10^{-3}T + (2.9836)10^{-6}T^2 - (.82203)10^{-9}T^3 \\ + (.21967)10^{-12}T^4 \quad \text{kJ/gaw} \quad (1)$$

The standard deviation is 0.17%. Deviations are shown in the fourth column of table 1.

The table contains data for very pure tungsten (sample B) at four temperatures. The percentage deviations are -0.03, -0.20, +0.09, -0.23, and -0.12. We regard these differences as insignificant and the data for sample B have been used in obtaining equation (1).

One point at 2353°K was omitted in determining equation (1) because it differs by more than three times the standard deviation from the corresponding value from equation (1), although the experiment does not have any apparent defect.

Equation (1) was obtained by the method of least squares, minimizing the sum of the squares of the percentage deviations. This procedure is preferable to working with the deviations themselves because the uncertainty in temperature measurements increases with the temperature. Such a procedure would tend to give too much weight to the experiments at high temperatures.

Discussion

Kirillin, et al. [5] summarize the measurements made before 1963, including their own. They represent the data of several observers with two smoothing equations, one for the range from 250 to 385°K and one from 385 to 3100°K. The maximum difference between their equation and equation (1) is 0.59% at 2050°K. For their data for the range 1275 to 2600°K, the standard deviation is 0.46%. From the deviation plot given [5], it appears that the data in this range are more precise than the standard deviation indicates. For this reason, we have obtained equation (2) for the enthalpy in kilojoules/gram-atomic weight which fits their data for the range 630 to 3093°K with a standard deviation of 0.33%:

$$H_T - H_{298.15} = -3.854 + (25.848)10^{-3}T + (0.72405)10^{-6}T^2 \\ + (.30599)10^{-9}T^3 - .68886 \ln T \text{ kJ/gaw} \quad (2)$$

The difference between equations (1) and (2) is +0.15% at 1100°K, decreasing to -.22% at 1900°K, then increasing to +0.29% at 2500 and 0.51% at 2600°K.

The agreement between the two equations is quite good except at the highest temperature. That agreement is better between equations (1) and (2) than between equation (1) and the equation of Kirillin, et al. [5] indicated that the latter may have given too much weight to older data in the temperature range below 1100°K.

Since tungsten is used as a container for liquid oxides, the data for the enthalpy of tungsten affect the liquid data obtained for Al_2O_3 and $BeO \cdot Al_2O_3$ previously reported [1,2]. Revisions of those data are presented in subsequent chapters.

References

- [1] E. D. West and S. Ishihara, NBS Report 9028 to AFOSR, 1 January 1966, p. 71.
- [2] S. Ishihara and E. D. West, NBS Report 9601 to AFOSR, 1 July 1967, p. 55.
- [3] E. D. West and S. Ishihara in "Advances in Thermophysical Properties at High Temperatures and Pressures," Am. Soc. Mech. Engr. 1965, p. 146.
- [4] D. R. Stull and G. C. Sinke, Thermodynamic Properties of the Elements, Am. Chem. Soc., Washington, D.C. (1956).
- [5] V. A. Kirillin, A. E. Sheindlin, V. Ya. Chekhovskoi, and V. A. Petrov, J. Phys. Chem. USSR 37, 1212, 1963, translated from Zh. Fiz Khim 37, 2249 (1963).
- [6] V. Ya. Chekhovskoi, B. Ya. Shumyatskii, and K. A. Yakimovich, Inzh. Fiz. Zh. Akad. Nauk Belorussk SSR 5, 13 (1962).

Table 1. Experimental Data for the Enthalpy of Tungsten^a

Furn. temp.°K Date of run	Heat to Calorim- eter at 298.15°K Joules	$H_T - H_{298.15}$ kJoules/at.wt.	% Deviations Obs-Calc. from eq (1)	Specimen and Capsule Material
1108.8 3-16-66	4599.4 1933.3 1933.3 4599.6	21.299 21.301	.02 .03	A, Mo A, Mo
1183.8 2-23-66	2129.6 5056.6 5055.9 2125.2	 23.383 23.413 	 -.11 .02 	 A, Mo A, Mo
1183.8 2-16-66	2121.4 5050.9 5052.0 2119.7	 23.403 23.426 	 -.03 .07 	 A, Mo A, Mo
1333.6 2-14-66	2508.3 5967.8 5970.0 2510.6	 27.638 27.637 	 -.09 -.09 	 A, Mo A, Mo
1405.9 3-7-66	6427.7 2705.1 2706.7 4872.9	29.739 29.741	-.03 -.03	A, Mo B, Mo
1514.3 2-11-66	3001.6 7136.7 7142.9 3008.8	 33.035 33.027 	 .35 .33 	 A, Mo A, Mo
1613.2 3-18-66	7758.5 3283.9 3285.9 5892.3	35.747 35.784	-.30 -.20	A, Mo B, Mo
1726.8 2-9-66	3605.4 8529.1 8531.2 3607.2	 39.335 39.337 	 .12 .12 	 A, Mo A, Mo
1815.7 3-11-66	9127.9 3860.3 3866.2 9109.9	42.082 41.891	.13 -.32	A, Mo A, Mo

Table 1 (Cont'd)

Furn. temp. °K Date of run	Heat to Calorimeter at 298.15 °K Joules	H _T -H _{298.15} kJoules/at.wt.	% Deviations Obs-Calc. from eq (1)	Specimen and Capsule Material
1915.4 3-14-66	4166.9 9812.0 9827.3 4163.8	45.097 45.245	-.10 .23	A, Mo A, Mo
1998.1 3-21-66	4400.6 7883.8 7893.2 4421.4	47.821 47.665	.09 -.23	B, W(1) B, W(1)
2107.4 3-23-66	8615.3 4753.7 4764.4 8502.1	51.268 51.317	-.12 -.03	B, W(1) C, W(1)
2107.5 4-18-66	8874.4 5021.0 5023.9 8891.8	51.155 51.347	-.35 -.02	C, W(1) C, W(1)
2210.0 3-31-66	5059.4 9186.0 9215.1 5095.0	54.785 54.700	.08 -.08	C, W(1) C, W(1)
2209.1 4-4-66 (Slow lift time)	5078.5 9215.6 9232.3 5102.6	54.924 54.825	.38 .20	C, W(1) C, W(1)
2267.7 4-14-66	3473.0 6770.5	56.761	.11	D, W(2)
2300.8 4-6-66	9803.9 5451.5	57.783	-.09	C, W(1)
2403.3 4-8-66	5944.5 10569.2	61.394	-.02	C, W(1)

Table 1 (Cont'd)

Furn. temp. °K	Heat to Calorimeter at 298.15 °K	$H_T - H_{298.15}$ kJoules/at.wt.	%Deviations Obs-Calc. from eq (1)	Specimen and Capsule Material
Date of run	Joules			
2460.8	4101.4			
4-21-66	7799.1	63.649	.30	D, W(2)
2503.1	7741.8	64.671	-.48	D, W(2)
4-12-66	3984.8			
2604.4	5167.1			
4-25-66	9171.6	68.931	.31	D, W(2)
	8896.6	68.577	-.20	D, W(2)
	4912.7			
2353.11*	7126.2	59.232	-.70	D, W(2)
4-15-66	3685.1			

^a Atomic wt. of tungsten 183.85.

* This point was given zero weight for determining the smoothed curve.

Chapter 7

THE ENTHALPY OF SOLID AND LIQUID $\text{BeO} \cdot \text{Al}_2\text{O}_3$ FROM 1200° TO 2400°K - REVISION

S. Ishihara and E. D. West

The data presented¹ for the enthalpy of solid and liquid $\text{BeO} \cdot \text{Al}_2\text{O}_3$

¹ Ishihara and West, NBS Report 9601 to the AFOSR, 1 July 1967.

have been revised slightly as a result of a calibration of the automatic pyrometer carried out following completion of the measurements and also as a result of new data for the enthalpy of tungsten, which affects only the data for the liquid. The revisions affect the enthalpy relative to 298.15°K by less than 0.1%. They are therefore probably not important in engineering calculations, but may be useful in checks of consistency of thermodynamic data.

The enthalpy of solid $\text{BeO} \cdot \text{Al}_2\text{O}_3$ from 1180 to 2143°K relative to 298.15°K is given by the equation:

$$\begin{aligned} H_T - H_{298.15} = & -(0.255187)T + (3.46055)10^{-4}T^2 - (1.44123)10^{-7}T^3 \\ & + (2.43189)10^{-11}T^4 + 72.2028 \ln T - 362.433 \text{ kJ/M} \end{aligned} \quad (1)$$

The enthalpy calculated from equation (1) will be approximately 0.05% lower than that calculated from the earlier equation.* With the increased precision from the new calibration, an additional constant is warranted (F test at 95% confidence level).² The constants in

² M. G. Natrella, Experimental Statistics NBS Handbook 91 (U.S. Dept. of Commerce, 1963).

equation (1) are therefore quite different from those in the earlier equation, but the difference in enthalpy calculated is small. Equation (1) fits the data with a standard deviation for an individual measurement of 0.16%, which is very slightly smaller than that given earlier.

* In the earlier report a minus sign was omitted for the logarithmic term.

The enthalpy of liquid $\text{BeO} \cdot \text{Al}_2\text{O}_3$ has been corrected for new data for tungsten, which was used as a container material, and also for the new pyrometer calibration. The enthalpy for the range 2143 to 2400°K is given by the equation:

$$H_T - H_{298.15} = 1299 - (0.9376)T + (0.2637)10^{-3}T^2 \text{ kJ/M} \quad (2)$$

The enthalpy calculated from (2) will differ by less than 0.1% from the enthalpy calculated by the earlier equation. The root-mean-square deviation from equation (2) for a single determination consisting of three experiments is 0.03%.

The heat of fusion at 2143°K calculated from the difference between equations (1) and (2) is 172.3 kJ/mole, lower by 1.5 kJ/mole than the value reported earlier. This value depends slightly on the temperature taken for the melting point and increases 0.04 kJ/mole for each degree decrease in the melting point.

Chapter 8

THE STATUS OF THE THERMOCHEMICAL DATA ON SOME Mg COMPOUNDS

by Vivian B. Parker

I Introduction

As part of the revision of NBS Circular 500 "Selected Values of Chemical Thermodynamic Properties", we have completed a review of the available data on all magnesium compounds. We present here a summary of values selected from this review for substances pertinent to the Light Element Thermodynamics Program. We are including also a brief discussion of the sources from which these values have been calculated. It is hoped that this report will indicate where additional research is required. We will appreciate it if data that have been overlooked or errors in the values are brought to our attention before the final tables are published.

All auxiliary data and constants used in the calculations are given in NBS Technical Note 270-3 [1]. All values of ΔH° and ΔG° are in kcal/mol for the molecular formula written and at 298°K, unless otherwise specified. Caution should be exercised if these values must be combined with data taken from other compilations or sources, in order to avoid errors caused by a lack of consistency between the tables.

II Discussion of Data

Mg(c) This is taken as the standard state. The thermal functions were taken from the evaluation of Hultgren et al. [2,3].

Mg(g) The $\Delta H^\circ(\text{subl}) = 35.3$ kcal has been taken from the tabulations of Hultgren et al. [2,3], as have the thermal functions of the ideal monatomic gas. Hultgren et al. [3] revised their original selection of 35.3 to 35.0 kcal. We prefer 35.3.

Mgⁿ⁺(g) The successive ionization energies were taken from Moore [4].

Mg²⁺(aq, std. state, m = 1) See MgCl₂(aq), Mg(ClO₄)₂(aq, std. state, m = 1) and Mg(NO₃)₂(aq).

Let us first consider ΔH_f° from the aqueous MgCl₂ system. The values given in Table II were corrected to ΔH_f° . Representative values from the MgCl₂·6H₂O system are: Samoilov -191.17 kcal; Voskresenskaya and Ponomareva -191.10; Thomsen -191.42; Mishchenko and Yakovlev -191.17. From the MgCl₂·4H₂O(c) and MgCl₂·2H₂O(c) systems we obtain from Thomsen's measurements -191.77 and -191.20. From MgCl₂(c) we obtain: Mishchenko and Yakovlev -190.92; Mishchenko et al. -191.17; Thomsen -190.28. From Richards et al. we obtain -189.56. A tentative "best" value for ΔH_f° MgCl₂ is -191.22 kcal with ΔH_f° Mg²⁺(aq, std. state, m = 1) = -111.32 kcal.

For Mg(ClO₄)₂ ΔH_f° is -173.63 kcal from which we obtain ΔH_f° Mg²⁺ = -111.81 kcal.

From the Mg(NO₃)₂ system, we obtain for ΔH_f° : Pickering -210.67; Thomsen -211.00; Ewing et al. -210.57 and -210.72. These result in a ΔH_f° = -210.74 and ΔH_f° Mg²⁺ = -111.62 kcal.

We have selected as "best" value for ΔH_f° Mg²⁺ -111.58 kcal.

From the solubilities given by Linke [5] and the activity coefficients and osmotic coefficients given by Robinson and Stokes [6] we obtain $\Delta G^\circ_{\text{soln}}$ MgCl₂·6H₂O(c) = -6.09 kcal and $\Delta G^\circ_{\text{soln}}$ MgSO₄·6H₂O(c) (metastable at 25°C) = +2.18 kcal. Combined with the appropriate heat of solution data we obtain $\Delta S^\circ_{\text{soln}}$ = +6.70 e.u. and -10.64 e.u., respectively. These result in S° Mg²⁺ = -33.1 and -32.5 e.u. We have selected S° = -33.0, with ΔG_f° Mg²⁺ = -108.7 kcal.

MgO(macrocrystal) and MgO(microcrystal)

The thermal functions for the macrocrystal were taken from the tabulation of the Dow Chemical Co. [7]; those for the microcrystal from the evaluation of Furukawa et al. [8].

There are many determinations for ΔH_f° MgO(c); however, very few of them distinguish between the macro and micro crystal forms. The following values were reported without any indication which form was

obtained or the percent of each obtained in the direct combustion of Mg(c); Muthman and Weiss [9], -143.0 kcal; Moose and Paar [10] -146.1; von Wartenberg [11] -143.9; Rogers [12] -146.4; Vorob'ev and Skuratov [13] -143.9; Shchukarev et al. [14] -143.23; Holley and Huber [15] -143.65 kcal.

Shomate and Huffman [16] measured the heats of solution of Mg(c) and MgO in aqueous HCl, from which we obtain $\text{Mg(c)} + \text{H}_2\text{O(l)} \rightarrow \text{MgO(c)} + \text{H}_2\text{(g)}$, $\Delta H^\circ = -75.494$ kcal and $\Delta \text{Hf}^\circ = -143.81$. No mention is made of the crystal size of MgO; however, the MgO used was made from igniting $\text{Mg(OH)}_2\text{(c)}$ at high temperature; the macro crystal form is usually obtained by this method. We are therefore adopting this value as the ΔHf° of the macro form. It is the only definite one for all macro MgO(c).

Giauque [17] showed that finely divided MgO prepared from the reduction of Mg(OH)_2 at low temperature gives a different S° and ΔH soln in HCl. He reported $\Delta H^\circ = 0.89$ kcal for $\text{MgO(macro)} \rightarrow \text{MgO(micro)}$. This results in $\Delta \text{Hf}^\circ = -142.92$ kcal.

MgO(g) Brewer and Porter [18] from their vapor pressure measurements have shown that the solid vaporizes mainly into molecular species. They gave spectroscopic evidence that the $^1\Sigma$ electronic state is not the principal vaporizing species. From their measurements and a $^3\Sigma$ ground state we obtain a 3rd law $\Delta H^\circ_{\text{subl}} = 129$ kcal, and a $\Delta \text{Hf}^\circ = -15$ kcal. From Alexander et al.'s [19] $\text{H}_2\text{O(g)}$ transpiration study we obtain a 2nd law $\Delta \text{Hf}^\circ = -4$ and a 3rd law $\Delta \text{Hf}^\circ = +5$ kcal. Altman's [20] Knudsen effusion and O_2 transpiration studies indicate that MgO(g) is of little importance at 2000°K (in contrast to Brewer and Porter) but from the experiments in which $\text{O}_2\text{(g)}$ is passed over MgO(c) the 3rd law $\Delta H^\circ_{\text{subl}} = 162$ kcal and $\Delta \text{Hf}^\circ = +18$ kcal. From Porter et al. [21] we obtain $\Delta H^\circ_{\text{subl}} > 148.6$ and $\Delta \text{Hf}^\circ > 4.8$ kcal.

Bulewicz and Sugden [22] and Veits et al. [23] reported $D^\circ_0 = 98$ and 100 kcal for a $^3\Sigma$ and $^1\Sigma$ ground state, respectively. These result in $\Delta \text{Hf}^\circ = -4$ kcal and -2 kcal (corrected to a $^3\Sigma$ ground state).

Drowart et al. [24] used the Knudsen effusion-mass spectrometer technique to determine relative ion intensities and enthalpies for the

reactions $\text{MgO(g)} + \text{O(g)} \rightarrow \text{Mg(g)} + \text{O}_2\text{(g)}$, and $\text{MgO(g)} + \text{WO}_2\text{(g)} \rightarrow \text{Mg(g)} + \text{WO}_3\text{(g)}$. We obtain, corrected for a $^3\Sigma$ ground state, $\Delta\text{Hf}^\circ = +12$ and $+20$ kcal from the two reactions.

As is evident, the values are very discordant. We are taking $\Delta\text{Hf}^\circ = +4$ kcal. The uncertainty is large, ± 20 kcal.

Brewer and Trajmor [25] feel that for the purposes of high temperature calculations, the most reliable calculations are obtained by the assumption of a $^3\Pi$ ground state for MgO(g) . This would increase ΔHf° approximately 3 kcal.

The thermal functions used in the calculations were obtained from the Dow Chemical Co. [7].

$\text{MgH}_2\text{(c)}$ The thermal functions were obtained from the Dow Chemical Co. [26] which also cites the references and values obtained for ΔHf° . We have taken $\Delta\text{Hf}^\circ = -18.0$ kcal.

In addition Pepekin et al. [27] reported $\Delta\text{H}^\circ = -190.4$ kcal for the oxidation of MgH_2 to $\text{MgO(c)} + \text{H}_2\text{O(liq)}$. This results in $\Delta\text{Hf}^\circ = -21.7$ kcal.

$\text{MgOH}^+\text{(aq, std. state, m = 1)}$ From Sillen and Martell [28] we obtain $\log K = 2.58$ for $\text{Mg}^{2+}\text{(aq)} + \text{OH}^- \rightarrow \text{MgOH}^+$. Hostetler's [29] value is in agreement.

$\text{Mg(OH)}_2\text{(c)}$ The thermal functions were obtained from the Dow Chemical Co. [30].

Wells and Taylor [31] measured the heats of solution of $\text{Mg(OH)}_2\text{(c)}$ and MgO(macro) in 2N HCl. We obtain for $\text{MgO(c)} + \text{H}_2\text{O(liq)} \rightarrow \text{Mg(OH)}_2\text{(c)}$, $\Delta\text{H}^\circ = -9.02$ kcal and $\Delta\text{Hf}^\circ = -221.15$ kcal. Similarly, from Taylor and Wells' [32] measurements, we obtain $\Delta\text{H}^\circ = -9.07$, using macro MgO and brucite ($\Delta\text{Hf}^\circ = -221.20$) and -8.83 kcal using macro MgO and synthetic Mg(OH)_2 ($\Delta\text{Hf}^\circ = -220.96$ kcal). From Giauque and Archibald [33] we obtain $\Delta\text{H}^\circ = -9.735$ kcal, using micro MgO, and $\Delta\text{Hf}^\circ = -220.97$. Torgeson and Sahama [34] measured $\Delta\text{H} = -26.95$ kcal for the solution of synthetic Mg(OH)_2 in 1N HCl. Using the results of Shomate and

Huffman [16] on the solution of macro MgO, we obtain $\Delta H^\circ = -8.84$ kcal for the formation of $\text{Mg}(\text{OH})_2$ from macro MgO and $\text{H}_2\text{O}(\text{liq})$ and $\Delta \text{Hf}^\circ = -220.97$ kcal. From Roth and Chall's [35] measurements we obtain $\Delta H^\circ = -7.96$ kcal and $\Delta \text{Hf}^\circ = -220.1$ kcal (this is assuming macro $\text{MgO}(\text{c})$ is used). We have selected a "best" value of -220.97 kcal.

Giauque and Archibald's decomposition pressure measurements are in agreement with this value. The Dow Chemical Co. [30] cites other decomposition vapor pressure measurements.

$\text{Mg}(\text{OH})_2$ ppt. From Thomsen's [36] measurements we obtain $\Delta H = 31.3$ kcal for $\text{MgSO}_4(400 \text{ H}_2\text{O}) + 2\text{H}_2\text{O}(\text{liq}) \rightarrow \text{Mg}(\text{OH})_2 \text{ ppt.} + \text{H}_2\text{SO}_4(400 \text{ H}_2\text{O})$, and 0.7 kcal for $\text{MgSO}_4(400 \text{ H}_2\text{O}) + 2\text{KOH}(200 \text{ H}_2\text{O}) \rightarrow \text{K}_2\text{SO}_4(800 \text{ H}_2\text{O}) + \text{Mg}(\text{OH})_2 \text{ ppt.}$ These reactions result in $\Delta \text{Hf}^\circ = -220.5$ and -219.8 kcal. From Berthelot's [37] measurements we have $\Delta H = 0.4$ kcal for $\text{MgSO}_4(400 \text{ H}_2\text{O}) + 2\text{NaOH}(200 \text{ H}_2\text{O}) \rightarrow \text{Mg}(\text{OH})_2 \text{ ppt.} + \text{Na}_2\text{SO}_4(800 \text{ H}_2\text{O})$ and $\Delta H = 1.5$ kcal for $\text{MgCl}_2(400 \text{ H}_2\text{O}) + 2\text{NaOH}(200 \text{ H}_2\text{O}) \rightarrow \text{Mg}(\text{OH})_2 \text{ ppt.} + 2\text{NaCl}(400 \text{ H}_2\text{O})$. ΔHf° , then, is -220.1 and -219.5 kcal.

$\text{Mg}(\text{OH})_2$ (aq, std. state, $m = 1$) ions. The values were obtained from the

$\text{Mg}(\text{OH})_2$ (g) Alexander et al. [19] determined the K_p 's (from 1780°K to 2010°K by the transpiration method) of the reaction $\text{MgO}(\text{c}) + \text{H}_2\text{O}(\text{g}) \rightarrow \text{Mg}(\text{OH})_2(\text{g})$. $\Delta H_{1900^\circ\text{K}} = 66.8$ kcal from which we obtain $\Delta H^\circ = 67.6$ kcal and $\Delta \text{Hf}^\circ = -134$ kcal.

The values of $H - H_{298}$ used in correcting ΔH to 298°K were taken from the estimated functions of the Dow Chemical Co. [30].

$\text{MgF}(\text{g})$ Ehlert et al. [38] reported the K 's of the reactions, $\text{AlF}_3(\text{g}) + 2\text{Mg}(\text{g}) \rightarrow \text{AlF}(\text{g}) + 2\text{MgF}(\text{g})$ (1238°K to 1301°K), and $2\text{MgF}(\text{g}) \rightarrow \text{Mg}(\text{g}) + \text{MgF}_2(\text{c})$ (1205°K to 1242°K). Third law values for ΔH° are 47.5 kcal and -126.65 kcal, which lead to -54.1 and -53.3 kcal for ΔHf° . An additional reaction, studied in Ehlert's Dissertation,

is $2\text{MgF}(\text{g}) \rightarrow \text{Mg}(\text{g}) + \text{MgF}_2(\text{g})$ for which the Dow Chemical Co. [30] reported $\Delta H^\circ = -34.76$ kcal. This results in $\Delta H_f^\circ = -51.5$ kcal.

Gaydon [39] and Herzberg [40] report $D_0^\circ = 3.2$ ev and 4.2 ev, respectively or $\Delta H_f^\circ = -21$ and -41 kcal.

We have taken $\Delta H_f^\circ = -53.0$ kcal.

The thermal functions were taken from the Dow Chemical Co. [30].

MgF₂(c) The thermal functions were taken from the Dow Chemical Co. [41].

Rudzitis et al. [42], from fluorine bomb calorimetry, reported $\Delta H_f^\circ = -268.7$ kcal. Gross et al. [43] reported $\Delta H^\circ = -109.5$ kcal for $\text{Mg}(\text{c}) + \text{PbF}_2(\text{c}) \rightarrow \text{MgF}_2(\text{c}) + \text{Pb}(\text{c})$ which results in $\Delta H_f^\circ = -268.2$ kcal. From Kapustinskii and Samplavskaya [44] we obtain $\Delta H = -94.8$ kcal for $\text{Mg}_2\text{SiO}_4(\text{c}) + 725.2(\text{HF} + 4.442 \text{H}_2\text{O}) \rightarrow 2\text{MgF}_2(\text{c}) + \text{H}_2\text{SiF}_6 + 4\text{H}_2\text{O} + 715.2(\text{HF} + 4.510 \text{H}_2\text{O})$ and $\Delta H_f^\circ = -266.3$ kcal.

From Guntz' [45,46] reactions we obtain $\Delta H = 2.8$ kcal for $\text{MgSO}_4(440 \text{H}_2\text{O}) + 2\text{KF}(220 \text{H}_2\text{O}) \rightarrow \text{MgF}_2(\text{c}) + \text{K}_2\text{SO}_4(880 \text{H}_2\text{O})$ and $\Delta H = -30.2$ kcal for $\text{MgO} + 2\text{HF}(110 \text{H}_2\text{O}) \rightarrow \text{MgF}_2(\text{c}) + \text{H}_2\text{O}$. These result in $\Delta H_f^\circ = -266.7$ and -257.5 kcal, respectively. von Wartenberg [47] reported $\Delta H = -109.6$ kcal for the solution of Mg in aqueous HF, from which we calculate $\Delta H_f^\circ = -262.0$ kcal. Petersen's [48] ΔH for $\text{MgCl}_2(440 \text{H}_2\text{O}) + 2\text{AgF}(220 \text{H}_2\text{O}) \rightarrow 2\text{AgCl}(\text{c}) + \text{MgF}_2(\text{c})$ results in $\Delta H = -28.1$ kcal and $\Delta H_f^\circ = -265.2$ kcal. Torgeson and Sahama's [34] reaction of $\text{Mg}(\text{OH})_2(\text{c}, 25^\circ\text{C})$ with $\text{HF}(4.44 \text{H}_2\text{O})$ at 73.7°C results in $\Delta H = -30.9$ kcal and $\Delta H_f^\circ = -267.5$ kcal. We have taken $\Delta H_f^\circ = -268.5$ kcal.

MgF₂(g) The thermal functions used were obtained from the Dow Chemical Co. [30].

There have been many measurements of the vapor pressure over the crystal and liquid. Table I summarizes the 2nd and 3rd law $\Delta H^\circ_{\text{subl}}$ obtained. The "best" value is 95.5 kcal and $\Delta H_f^\circ = -173.0$ kcal.

Table I

<u>Investigator</u>	<u>Temperature °K</u>	<u>Method</u>	<u>$\Delta H^\circ_{\text{subl}}$</u>	
			<u>2nd Law</u>	<u>3rd Law</u>
Berkowitz and Marquart [49]	1450	Torsion effusion	91.3	94.68
Green et al. [50]	1241-1492	Knudsen effusion	93.8	96.1
Hammer and Pask [51]	1451-1533(c)	" "	98.8	96.1
	1568-1613(liq)	" "	90.4	96.2
	1413-1518	Torsion effusion	92.9	96.2
	1539-1614	" "	96.4	96.2
	1273-1513	" "	84.0	91.5
Greenbaum et al. [52]	1273-1513	" "	84.0	91.5
Margrave [53]	1241-1492	Knudsen effusion	93.8	96.1
Le Boucher [54]	1934-2129	Manometric	99.9	96.0
Hildenbrand et al. [55]	1425-1533(c)	Torsion effusion	104.8	96.0
	1540-1606(liq)	" "	102.8	95.9
Hildenbrand and Theard [56]	1326-1527(c)	" "	91.5	93.3
	1544-1604(liq)	" "	82.4	95.1
Gunther [57]	1284-1530	Knudsen effusion	95.4	95.6

MgCl(g) Herzberg [40] and Gaydon [39] select D°_0 to be 3.2 ev and 2.7 ev, respectively. These result in $\Delta H_f^\circ = -10$ and $+1$ kcal.

The thermal functions were obtained from the Dow Chemical Co. [41].

MgCl₂(c) The thermal functions were obtained from the Dow Chemical Co. [58].

Bommer and Hohman [59] measured the ΔH at 293°K for Mg(c) and MgCl₂(c) in 0.1N HCl to be -112.5 and -37.85 kcal, respectively. We obtain $\Delta H = -74.3$ kcal for $\text{Mg(c)} + 2\text{HCl(0.1N)} \rightarrow \text{MgCl}_2\text{(c)} + \text{H}_2\text{(g)}$ and $\Delta H_f^\circ = -153.9$ kcal. Similarly Shomate and Huffman [16] obtained, in solutions involving $77.2\text{HCl} \cdot 4190 \text{H}_2\text{O}$, $\Delta H = -111.285$ and -36.560 kcal, respectively, or $\Delta H = -74.725$ kcal for $\text{Mg(c)} + 77.2(\text{HCl} + 54.275) \rightarrow \text{MgCl}_2\text{(c)} + 75.2(\text{HCl} + 55.718 \text{H}_2\text{O}) + \text{H}_2\text{(g)}$ and $\Delta H_f^\circ = -153.28$ kcal.

Sano [60] measured the equilibrium $\text{MgCl}_2\text{(c)} + \text{H}_2\text{O(g)} \rightarrow \text{MgO(c)} + 2\text{HCl(g)}$ in the range 796°K to 894°K. We obtain 2nd and 3rd law $\Delta H^\circ = 19.7$ and 23.14 kcal/mol MgCl₂ and $\Delta H_f^\circ = -149.9$ and -153.28 kcal.

Treadwell [61,62] and Sano [63] measured the equilibrium for $\text{MgCl}_2(\text{c}) + \frac{1}{2}\text{O}_2 \rightarrow \text{MgO}(\text{c}) + \text{Cl}_2(\text{g})$ in the temperature ranges 820°K to 976°K and 865°K to 943°K, respectively. The 2nd and 3rd law ΔH° 's are 9.0 and 9.42 kcal, from Treadwell's measurements, and 8.3 and 9.72 kcal from Sano's, which lead to $\Delta H_f^\circ = -152.8$ and -153.23 , and -152.1 and -153.6 kcal, respectively. Similarly from the results of Tsuchiya [64] in the temperature range 823°K to 973°K we obtain $\Delta H_f^\circ = -151.6$ and -153.6 kcal from the 2nd and 3rd law approaches. In the temperature range 1013°K to 1153°K ($\text{MgCl}_2(\text{liq})$) we obtain $\Delta H_f^\circ = -161.6$ and -157.6 kcal, respectively. Reznikov's [65] measurements at 1023°K to 1223°K lead to 2nd law and 3rd law ΔH_f° 's = -160.3 and -152.1 kcal, respectively.

Egan et al. [66] from EMF measurements on the reaction $\text{Mg}(\text{c}) + 2\text{AgCl}(\text{NaCl}) \rightarrow \text{MgCl}_2(\text{c}) + 2\text{Ag}(\text{c})$ combined with other data on the $\text{Ag}/(\text{AgCl} - \text{NaCl})$ half cell obtain the ΔG_f° of $\text{MgCl}_2(\text{c})$ at 673°, 723° and 773°K. Their values lead to a 3rd law $\Delta H_f^\circ = -154.14$ kcal. From the cell measurements of Treadwell et al. [67], Markov et al. [68], Lorenz and Velde [69], and Takahashi [70] on the reaction $\text{Mg}(\text{c}, \text{liq}) + \text{Cl}_2(\text{g}) \rightarrow \text{MgCl}_2(\text{liq})$ we obtain 3rd law ΔH_f° 's = -159.9 , -154.9 , -152.96 , and -153.18 kcal, respectively.

$\text{MgCl}_2(\text{g})$ The estimated thermal functions used in the calculations were obtained from the Dow Chemical Co. [7].

Schrier and Clark [71] have shown that the gaseous species over $\text{MgCl}_2(\text{liq})$, in the range 1200°K to 1400°K, is about 30% dimer. They have also measured the total vapor pressure. Correcting for the dimerization we obtain 2nd and 3rd law $\Delta H^\circ_{\text{subl}} = 57.6$ kcal and 58.0 kcal, respectively. Using their equilibrium constants for the dimerization process we have corrected the measurements of Kushkin et al. [72] (1173°K to 1323°K) to 43.6 and 57.1 kcal, respectively, the measurements of Fischer et al. [73] (1136°K to 1435°K) to 58.0 and 56.9 kcal, Maier [74] (1056°K to 1400°K) to 50.6 and 57.2 kcal.

Berkowitz and Marquart [49], from Knudsen effusion-mass spectroscopy measurements, reported a monomer pressure at 921°K of 3.84×10^{-5} atm.

and $\Delta H_{\text{subl}} = 54.6$ kcal at 800°K. These measurements result in a 3rd law $\Delta H^\circ = 56.4$ kcal and a 2nd law $\Delta H^\circ = 55.4$ kcal.

Hildenbrand et al. [55] reported vapor pressure results from torsion effusion measurements over the temperature range 800°K to 985°K. Monomeric vapor was assumed. Second and third law ΔH° 's of 61.8 kcal and 57.8 kcal are obtained. We have selected $\Delta H^\circ_{\text{subl}} = 57.6$ kcal.

MgCl₂(aq, std. state, m = 1) The final values were obtained from the ions. See Mg²⁺(aq, std. state), MgCl₂(aq), Mg(ClO₄)₂(aq, std. state, m = 1), and Mg(NO₃)₂(aq).

MgCl₂(aq) Lange and Streek [75], Zdanovskii and Deryabina [76], Thomsen [36], and Fricke [77] measured ΔH_{diln} of aqueous MgCl₂. Mishchenko and Yakovlev [78] measured the ΔH_{soln} at varying concentrations.

Measurements of the ΔH_{soln} MgCl₂·rH₂O(c) lead to the following values for ΔH_f (aq, nH₂O), where n is the final concentration. Corrections to 25°C have been made. (See Table II.)

MgCl₂·H₂O(c) The Cp° and S° were obtained from Kelley and King [85].

From Shomate and Huffman's [16] measurements on the solution of Mg(c) and MgCl₂·H₂O(c) we obtain $\Delta H = -84.157$ kcal for Mg(c) + H₂O(liq) + 77.2(HCl + 54.275H₂O) → MgCl₂·H₂O(c) + 75.2(HCl + 55.718H₂O) + H₂(g), and $\Delta H_f^\circ = -231.02$ kcal.

MgCl₂·2H₂O(c) The Cp° and S° were obtained from Kelley and King [85].

As for MgCl₂(c) and MgCl₂·H₂O(c) we obtain, from the measurements of Shomate and Huffman [16] $\Delta H = -90.675$ kcal for Mg(c) + 97.2(HCl + 54.275) + 2H₂O(liq) → MgCl₂·2H₂O(c) + 75.2(HCl + 55.718H₂O) + H₂(g) and $\Delta H_f^\circ = -305.86$ kcal.

Auzhbikovich [86] reported $\Delta H^\circ = 16.4$ kcal/mol H₂O for the decomposition of the dihydrate to the anhydrous salt, or $\Delta H_f^\circ = -306.3$ kcal.

Table II

System	Investigator	ΔH_f kcal/mol	nH_2O	t °C of Meas.
$MgCl_2 \cdot 6H_2O$	1. Samoilov [79]	-190.79	1110	25
	2. Voskresenskaya and Ponomareva [80]	-190.52	333	25
	3. Thomsen [36]	-190.88	400	18
	4. Richardson and Wells [81]	-188.30	22	22.8
	5. Berthelot and Ilosvay [82]	-190.49	200	12.7
	6. Mishchenko and Yakovlev [78]	-190.79	1176	2
		-189.95	52	2
		-187.15	11.45	2
$MgCl_2 \cdot 4H_2O(c)$	1. Thomsen [36]	-191.23	400	18
$MgCl_2 \cdot 2H_2O(c)$	1. Thomsen [36]	-190.66	400	18
$MgCl_2(c)$	1. Mishchenko and Yakovlev [78]	-190.92	2270	2
	2. Mishchenko et al. [83]	-190.8	1110	25
	3. Thomsen [36]	-189.85	800	18
Mg(c) + equiv.				
am't. $HCl \cdot 200 H_2O$	1. Richards et al. [84]	-189.56	400	20

$MgCl_2 \cdot 4H_2O(c)$ The Cp° and S° were obtained from Kelley and King [85].

As for $MgCl_2 \cdot 2H_2O(c)$, we obtain, from Shomate and Huffman's [16] measurements $\Delta H = -102.056$ kcal for $Mg(c) + 77.2(HCl + 54.275) + 4H_2O(liq) \rightarrow MgCl_2 \cdot 4H_2O(c) + 75.2(HCl + 55.718 H_2O)$ and $\Delta H_f^\circ = -453.87$ kcal.

Kondirev and Berezovskii [87], Derby and Yngve [88], Sano [89], and Auzhnikov [86] measured the decomposition pressure of the hexahydrate to the tetrahydrate. A $\log p$ vs $1/T$ plot of the data results in $\Delta H_f^\circ = -453.99$ kcal.

Kondirev and Berezovskii [87] and Sano [90] measured the decomposition pressures of the tetrahydrate to the dihydrate. A log p vs 1/T plot results in $\Delta H_f^\circ = -454.05$. Auzhikov's measurements result in $\Delta H_f^\circ = -457.1$.

$MgCl_2 \cdot 6H_2O(c)$ The C_p° and S° were obtained from Kelley and King [85].

As for $MgCl_2 \cdot 4H_2O(c)$ we obtain from Shomate and Huffman's [16] measurements $\Delta H = -108.836$ kcal for $Mg(c) + 77.2(HCl + 54.275) + 6H_2O(liq) \rightarrow MgCl_2 \cdot 6H_2O(c) + 75.2(HCl + 55.718 H_2O)$ and $\Delta H_f^\circ = -597.28$ kcal.

$Mg(ClO_4)_2(c)$ Vorob'ev et al. [91] reported ΔH_{soln} in 800 H_2O to be -37.08 kcal. This results in $\Delta H_f^\circ = -135.97$ kcal. Drakin and Chzhan [92] reported four measurements in the range from $m = .02$ to $.09$ (where m is the molality), which lead to $\Delta H_f^\circ = -135.68$ kcal. Smeets' [93] measurements for $m = 0.12$ result in $\Delta H_f^\circ = -135.53$ kcal. Measurements have also been reported by Smith et al. [94]. We have selected the first mentioned value.

$Mg(ClO_4)_2(aq, \text{std. state}, m = 1)$ The final values were obtained from the ions. See $Mg^{2+}(aq, \text{std. state}, m = 1)$, $MgCl_2(aq)$ and $Mg(NO_3)_2(aq)$.

Jongenburger and Wood [95] measured the ΔH diln from 3.2 to .0018 molal.

Vorob'ev et al. [91] reported $\Delta H = -36.11$ kcal for the reaction, $MgO(c) + 2HClO_4 \cdot 800 H_2O \rightarrow Mg(ClO_4)_2 \cdot 800 H_2O + H_2O$. This results in $\Delta H_f = -173.28$ kcal for $Mg(ClO_4)_2 \cdot 800 H_2O$ and $\Delta H_f^\circ = -173.63$ kcal.

$Mg(ClO_4)_2 \cdot 6H_2O(c)$ Smeets [93] reported measurements of ΔH_{soln} at $18^\circ C$ for the hexahydrate and the anhydrous salt. We obtain $\Delta H^\circ = -38.71$ kcal for $Mg(ClO_4)_2(c) + 6H_2O(liq) \rightarrow Mg(ClO_4)_2 \cdot 6H_2O(c)$ and $\Delta H_f^\circ = -584.57$ kcal. Similarly from Smith et al. [94] we obtain $\Delta H^\circ = -32.7$ kcal and $\Delta H_f^\circ = -578.6$ kcal. Their value for $\Delta H_{soln} = 0.8$ kcal for the hexahydrate leads to $\Delta H_f^\circ = -583.8$ kcal. Nosova [96] reported ΔH_{soln} to a final concentration of $0.07 m = 1.45$ kcal, from which we obtain $\Delta H_f^\circ = -584.39$ kcal.

Linke [5] lists the saturation concentration to be 4.48 molal. Using this and the activity coefficient and osmotic coefficient from Robinson and Stokes [6] we obtain $\Delta G^\circ_{\text{soln}} = -7.60$ kcal, which results in $\Delta G^\circ_f = -445.34$ kcal and $S^\circ = 124.5$ e.u.

MgOHCl(c) Kelley [97] evaluated the data on the MgOHCl(c) system and obtained for $\text{MgCl}_2 \cdot \text{H}_2\text{O(c)} \rightarrow \text{MgOHCl(c)} + \text{HCl(g)}$ $\Delta H^\circ = 17.82$ and $\Delta G^\circ = 8.34$ kcal. These lead to $\Delta H^\circ_f = -191.1$ kcal, $\Delta G^\circ_f = -174.9$, and $S^\circ = 20.0$ e.u.

Savinkova and Dagtyareva [98] reported the equilibrium from 743°K to 1023°K for $\text{MgCl}_2(\text{solid soln}) + \text{H}_2\text{O(g)} \rightarrow \text{MgOHCl(solid soln)} + \text{HCl(g)}$. The K's include the activities. Their results give $\Delta H^\circ = -1.5$ kcal and $\Delta H^\circ_f = -191.1$ kcal. Vel'nyanskii and Savinkova [99] do not give the activities; hence, their values have not been used.

MgBr₂(c) Beketov [100] reported ΔH_{soln} in 800 H₂O = -43.30 kcal, from which we obtain $\Delta H^\circ_f = -125.26$ kcal. Finch et al. [101] report $\Delta H = -35.23$ kcal for the reaction of MgO(c) in excess HBr(m = 0.5) to form $\text{MgBr}_2 \cdot 2000 \text{ H}_2\text{O}$, and $\Delta H = -43.14$ kcal for the solution of $\text{MgBr}_2(\text{c})$ in excess HBr(m = 0.5) to form $\text{MgBr}_2 \cdot 9000 \text{ H}_2\text{O}$. Correcting for the concentration change, we obtain $\Delta H = 7.78$ kcal for $\text{MgO(c)} + 2\text{HBr(aq)} \rightarrow \text{MgBr}_2(\text{c}) + \text{H}_2\text{O(liq)}$, and $\Delta H^\circ_f = -125.36$ kcal.

Toguri et al. [102] reported $\Delta G^\circ_{1073^\circ\text{K}} = 0.267$ kcal for $\frac{1}{2}\text{MgBr}_2(\text{liq}) + \text{HCl(g)} \rightarrow \frac{1}{2}\text{MgCl}_2(\text{liq}) + \text{HBr(g)}$. Using estimated thermal functions from the Dow Chemical Co. [58] we obtain $\Delta H^\circ = -2.3$ kcal and $\Delta H^\circ_f = -121.9$ kcal.

S° has been estimated as 28.0 e.u. by Kelley and King [85].

MgBr₂(g) Berkowitz and Marquart [49] obtained the vapor pressure by the mass spectroscopy-Knudsen effusion method. A 3rd law ΔH° from measurements at 798°K and 842°K is 49.7 kcal. The 2nd law value, at 727°K, results in $\Delta H^\circ = 52.2$ kcal. We have taken $\Delta H^\circ_{\text{subl}} = 51.3$ kcal and $\Delta H^\circ_f = -74.0$ kcal.

MgBr₂(aq, std. state, m = 1) The values were obtained from the ions.

MgBr₂(aq) Lange and Streek [75] measured the heats of dilution.

MgBr₂·6H₂O(c) The saturation solubility was obtained from Linke [5]; the activity and osmotic coefficients at saturation from Robinson and Stokes [6]. The resultant $\Delta G^\circ_{\text{soln}} = -7.13$ kcal. We have estimated $S^\circ = 95$ e.u. This results in $\Delta H_f^\circ = -575.9$ kcal. A value of 40.7 kcal is obtained for the ΔH° for the reaction $\text{MgBr}_2 \cdot 6\text{H}_2\text{O}(\text{c}) \rightarrow \text{MgBr}_2(\text{c}) + 6\text{H}_2\text{O}(\text{liq})$. This appears high in relation to $\Delta H^\circ = 34.1$ for the comparable chloride system; however, from the differential ΔH soln (obtained from the solubility measurements), which was corrected to infinite dilution we obtain $\Delta H^\circ_{\text{soln}} = -3.4$ kcal and $\Delta H_f^\circ = -576.2$ kcal.

MgI₂(c) From Beketov's [100] measured ΔH soln in 880 H₂O, we have $\Delta H_f^\circ = -87.1$ kcal. Finch et al. [101] report $\Delta H = -35.10$ kcal for the reaction of MgO(c) in excess HI (m = 0.5) to form $\text{MgI}_2 \cdot 2000 \text{ H}_2\text{O}$; and $\Delta H = -49.75$ kcal for the solution of $\text{MgBr}_2(\text{c})$ in HI to form $\text{MgBr}_2 \cdot 9000 \text{ H}_2\text{O}$. Correcting for the concentration change, we obtain $\Delta H = 14.50$ kcal for $\text{MgO}(\text{c}) + 2\text{HI}(\text{aq}) \rightarrow \text{MgBr}_2(\text{c}) + \text{H}_2\text{O}(\text{liq})$ and $\Delta H_f^\circ = -87.0$ kcal.

Kelley and King [85] have estimated $S^\circ = 31.0$ e.u.

MgI₂(g) Berkowitz and Marquart [49] measured the vapor pressure by the mass spectroscopy-Knudsen effusion method. A 3rd law ΔH° from measurements at 757°K and 734°K is 45. kcal (the $\Delta(G^\circ - H^\circ_{298})/T$ was estimated). The 2nd law value at 640°K results in 46.4 kcal. We have taken $\Delta H^\circ_{\text{subl}} = 46$ kcal from which we obtain $\Delta H_f^\circ = -41$ kcal.

MgI₂(aq, std. state, m = 1) The values were obtained from the ions.

MgI₂(aq) The values were estimated from a consideration of the ΔH_{dil} of $MgCl_2$ and $MgBr_2$, and the Cl-Br-I system of the monovalent electrolytes.

MgSO₄(c) The C_p° and S° were obtained from Kelley and King [85].

The following values for ΔH_{soln} have been obtained: Thomsen [36] -20.7 kcal ($nH_2O = 420$); Berthelot and Ilosvay [82] -20.8 ($nH_2O = 100$); Pickering [103] -20.9 and [104] -20.8 kcal ($nH_2O = 420$). These result in $\Delta H_f^\circ = -307.1, -306.8, -307.0$, and -307.1 kcal, respectively.

Kelley [105] evaluated the data on the equilibrium $2MgSO_4 \rightarrow 2MgO(c) + 2SO_2(g) + O_2(g)$ and obtained $\Delta H^\circ = 196.0$ kcal, which leads to $\Delta H_f^\circ = -312.8$ kcal. The results of Dewing and Richardson [106] yield $\Delta H^\circ = 189.6$ kcal and $\Delta H_f^\circ = -309.6$ kcal.

From Knopf and Staude's [107] equilibrium measurements for $MgSO_4(c) \rightarrow MgO(c) + SO_3(g)$ we obtain $\Delta H^\circ = 58.3$ kcal and $\Delta H_f^\circ = -296.7$ kcal.

MgSO₄(aq, std. state, m = 1, undissociated) Sillen and Martell [28] list the K 's and ΔH° for $Mg^{2+} + SO_4^{2-} \rightarrow MgSO_4(aq, undissoc)$. Using the measurements of Nair and Nancollas [108], $\Delta H^\circ = 4.84$ kcal and $\log K = 2.25$, we obtain $\Delta H_f^\circ = -324.1$ kcal and $\Delta G_f^\circ = -289.74$ kcal.

MgSO₄(aq, std. state, m = 1) The final values were obtained from the ions. See $Mg^{2+}(aq, std. state, m = 1)$.

MgSO₄(aq) The heats of dilution were measured by Lange [109], Lange and Streeck [110], Lange and Messner [111,112], Plake [113], and Thomsen [36]. Kaganovich and Mishchenko [114] measured ΔH_{soln} of $MgSO_4 \cdot 7H_2O(c)$ as a function of the concentration. From Thomsen's [36] reported values for the reactions: (1) $MgCl_2(200 H_2O) + H_2SO_4(200 H_2O) \rightarrow MgSO_4(200 H_2O) + 2HCl(100 H_2O)$; (2) $MgCl_2(800 H_2O) + H_2SO_4(400 H_2O) \rightarrow MgSO_4(400 H_2O) + 2HCl(400 H_2O)$; and (3) $MgSO_4(400 H_2O) + 2HNO_3(400 H_2O) \rightarrow Mg(NO_3)_2(800 H_2O) + H_2SO_4(400 H_2O)$, we obtain (1) $\Delta H = -3.82$ kcal, (2) $\Delta H = -3.76$ kcal, and (3) $\Delta H = +3.99$ kcal, which result in (1) $\Delta H_f(200 H_2O) = -327.70$, (2) $\Delta H_f(400 H_2O) = -327.92$ and (3) $\Delta H_f(400 H_2O) =$

-328.12 kcal. These are in good agreement with the values obtained from the use of the heats of diln and the ions.

MgSO₄·H₂O(c) The Cp° and S° were obtained from Kelley and King [85].

Thomsen [36] and Pickering [103] measured ΔH soln in 400 H₂O. Their results lead to ΔHf° = -382.5 and -384.0 kcal. Jamieson and Frost [115] reported ΔH (soln, ∞) = -14.26 kcal which results in ΔHf° = -382.9 kcal.

Kohler and Zaske [116] reported ΔH = 15.0 kcal for the decomposition to the anhydrous sulfate and H₂O(g). This results in ΔHf° = -379.9 kcal.

MgSO₄·H₂O(amorph) Jamieson and Frost [115] reported ΔH (soln, ∞) = -20.8 kcal; ΔHf°, then, is -376.4 kcal

Frost et al. [117] report S° = 33.0 e.u.

MgSO₄·2H₂O(c) Thomsen's [36] ΔH soln in 400 H₂O is -11.4 kcal, or ΔHf° = -453.2 kcal.

Kohler and Zaske [116] reported ΔH = 25.3 kcal for the decomposition to the anhydrous salt and H₂O(g); this results in ΔHf° = -455.8 kcal.

MgSO₄·4H₂O(c) Thomsen's [36] ΔH soln in 400 H₂O is -4.45 kcal or ΔHf° = -596.7 kcal.

Kohler and Zaske [116] reported ΔH = 25.8 kcal for the decomposition of the hexahydrate to the tetrahydrate and H₂O(g). ΔHf°, then, = -597.4 kcal.

MgSO₄·6H₂O(c) The Cp° and S° were taken from Kelley and King [85].



Thomsen [36] reported ΔH soln in 400 H₂O to be +0.02 kcal from which we obtain ΔHf° = -737.8 kcal.

Carpenter and Jette [118], Rolla and Accame [119], Bell [120], and Kohler and Zaske [116], reported values for ΔH for decomposition of the heptahydrate to the hexahydrate and H₂O(g). Their values are 14.0, 14.6, 14.1, and 14.7 kcal, or ΔHf° = -738.1, -737.5, -738.0, and -737.5 kcal, respectively.

$\text{MgSO}_4 \cdot 7\text{H}_2\text{O}(\text{c})$ Kaganovich and Mishchenko [114] measured ΔH_{soln} from $m = .25$ to $m = 2.2$. Their values at these concentrations are 3.12 and 4.54 kcal. The 21 measurements result in $\Delta H_f^\circ = -809.92$ kcal. Kapustin-skii and Samoilov [121] reported $\Delta H_{\text{soln}} = 1.82$ kcal at $m = .03$. This results in $\Delta H_f^\circ = -808.20$ kcal. From Perreu's [122] ΔH_{soln} measurements at 284°K, from $n\text{H}_2\text{O} = 75$ to $n\text{H}_2\text{O} = 21$, we obtain $\Delta H = 4.0$ to 4.5 kcal or $\Delta H_f^\circ = -809.74$ to -809.88 kcal. From Thomsen's [36] and Pickering's [103] ΔH_{soln} , 400 H_2O we have $\Delta H = 3.74$ and 3.90 kcal or $\Delta H_f^\circ = -809.8$ and -810.00 kcal.



From the solubility given by Linke[5] and the activities and osmotic coefficients given by Robinson and Stokes [6] we obtain $\Delta G^\circ_{\text{soln}} = 2.29$ kcal and $\Delta G_f^\circ = -685.8$ kcal. Using this value for ΔG_f° and a $\Delta H_f^\circ = -809.92$ we obtain $S^\circ = 87$ e.u. which appears low. From the decomposition pressure measurements of the heptahydrate to the hexahydrate of Bell [120] we obtain $\Delta H^\circ = 14.1$ and $\Delta G^\circ = 2.42$ kcal from which we obtain $S^\circ = 89.0$ e.u. Kohler and Zaske's [116] decomposition pressure is in agreement.

$\text{Mg}_3\text{N}_2(\text{c}, \alpha)$ Mitchell [123] reported the values of ΔH for the following reactions to be -287.89 kcal and -32.08 kcal, respectively.



Using the ΔH of Shomate and Huffman [16] for the reaction of $\text{Mg}(\text{c})$ in $\text{HCl}(\text{aq})$ and the ΔH_{vap} of $\text{NH}_3(\text{liq})$, he obtains $\Delta H^\circ = -88.05$ kcal for $3\text{Mg} + 2\text{NH}_3(\text{g}) \rightarrow \text{Mg}_3\text{N}_2(\text{c}) + 3\text{H}_2(\text{g})$ from which we obtain $\Delta H_f^\circ = -110.09$ kcal.

Neumann et al. [124] reported the values of ΔH for the following to be -284.8 and -336.0 kcal, respectively.



Using the $\Delta H = 4.14$ kcal from Juza et al. [125] for the solution of $\text{NH}_4\text{Cl}(\text{c})$ in $\text{HCl}(\text{aq})$ they obtain $\Delta H = -42.9$ kcal for $3\text{Mg}(\text{c}) + 2\text{NH}_4\text{Cl}(\text{c}) \rightarrow \text{Mg}_3\text{N}_2(\text{c}) + 2(\text{HCl} + 20 \text{H}_2\text{O}) + 3\text{H}_2(\text{g})$ from which $\Delta H_f^\circ = -114.9$ kcal.

Neumann et al. [126] directly determined the value of ΔH_f° to be -116.6 kcal.

The results of Brunner are cited by Neumann et al. [124]. $\Delta H = -177.0$ kcal for $Mg_3N_2(c) + 6H_2O(c) \rightarrow 3Mg(OH)_2(ppt.) + 2NH_3(aq)$ from which we obtain $\Delta H_f^\circ = -111.4$ kcal. Matignon [127] and Moser and Herzner [128] measured the $\Delta H = -279.7$ and -269.9 kcal, respectively for the reaction of Mg_3N_2 with $H_2SO_4 \cdot 200 H_2O$. The values for ΔH_f° are -133.0 and -143.0 kcal.



Dreger [129] measured the decomposition pressure to $Mg(g)$ and $N_2(g)$ from 1118° to $1254^\circ K$, and obtained a ΔH° apparent = 295.0 kcal, or a $\Delta H_f^\circ = -189.1$ kcal. Blank [130] obtained nonequilibrium values from Torsion effusion measurements in the range 1000 - $1250^\circ K$ of 286.3 and 218.7 kcal/mol Mg_3N_2 for the 3rd law and 2nd law values, respectively. Hildenbrand and Theard [56], in similar measurements, obtained a 2nd law non equilibrium $\Delta H^\circ = 309$ kcal. These values lead to $\Delta H_f^\circ = -180.4$, -112.8 , and -203.1 kcal. Both Blank and Hildenbrand determined the condensation coefficients and corrected their vapor pressures to obtain equilibrium values. Blank's results now yield $\Delta H^\circ = 242.3$ kcal (3rd law) and 239.1 kcal (2nd law) and $\Delta H_f^\circ = -136.4$ and -133.2 kcal, respectively. Hildenbrand's measurements result in an equilibrium $\Delta H^\circ = 243.5$ kcal and a $\Delta H_f^\circ = -137.6$ kcal. The latter three values are in good agreement; however, as Hildenbrand points out, there is a possibility that there is a secondary reaction going on that would interfere with the decomposition reaction. Until there is further evidence supporting this, we have selected the first mentioned $\Delta H_f^\circ = -110.1$ kcal.

The Dow Chemical Co. [131] tabulates the thermal functions.


$Mg(NO_3)_2(c)$ The C_p° and S° were obtained from Kelley and King [85].

Young [132] measured the ΔH 's of the following reactions:

- (1) $2HNO_3 \cdot 26.5 H_2O + MgCl_2 \cdot 75.2HCl \cdot 4190 H_2O \rightarrow$
 $Mg(NO_3)_2 \cdot 77.2HCl \cdot 4216.5 H_2O$; $\Delta H = 0.198$ kcal
- (2) $Mg(NO_3)_2 \cdot 77.2HCl \cdot 4190 H_2O + 26.5 H_2O(liq) \rightarrow$
 $Mg(NO_3)_2 \cdot 77.2HCl \cdot 4216.5 H_2O$; $\Delta H = -.113$ kcal



Using the reaction of Shomate and Huffman [16], $\text{Mg}(\text{c}) + 77.2\text{HCl} \cdot 4190 \text{H}_2\text{O}$



$\text{Mg}(\text{NO}_3)_2(\text{aq}, \text{std. state}, m = 1)$ The final values were obtained from the ions. See $\text{Mg}^{2+}(\text{aq}, \text{std. state}, m = 1)$

$\text{Mg}(\text{NO}_3)_2(\text{aq})$ Lange and Streeck [110], Hammerschmid and Lange [133], Ewing et al. [134], and Thomsen [36] measured ΔH diln.

Pickering [135], Thomsen [36], and Ewing et al. [134] measured ΔH soln. of the hexahydrate. Their results lead to $\Delta H_f = -210.25 \text{ kcal}$ (400 H_2O), -210.58 kcal (400 H_2O), and -210.04 kcal (130 H_2O), respectively. Ewing also measured the ΔH soln. of the anhydrous salt, from which we obtain $\Delta H_f(130 \text{H}_2\text{O}) = -210.20 \text{ kcal}$.

$\text{Mg}(\text{NO}_3)_2 \cdot 2\text{H}_2\text{O}(\text{c})$ Ewing et al. [134] measured the ΔH soln. of the anhydrous salt and that of the dihydrate. We obtain $\Delta H = -11.18 \text{ kcal}$ for $\text{Mg}(\text{NO}_3)_2(\text{c}) + 2\text{H}_2\text{O}(\text{liq}) \rightarrow \text{Mg}(\text{NO}_3)_2 \cdot 2\text{H}_2\text{O}(\text{c})$ and $\Delta H_f^\circ = -336.8 \text{ kcal}$.

$\text{Mg}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}(\text{c})$ Young [132] measured the ΔH soln. of the hexahydrate and anhydrous salt in aqueous HCl (See $\text{Mg}(\text{NO}_3)_2(\text{c})$). The results lead to $\Delta H^\circ = -25.729 \text{ kcal}$ for $\text{Mg}(\text{NO}_3)_2(\text{c}) + 6\text{H}_2\text{O}(\text{liq}) \rightarrow \text{Mg}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}(\text{c})$ or $\Delta H_f^\circ = -624.59 \text{ kcal}$. Similarly, from Ewing et al.'s [134] ΔH soln. in H_2O we obtain $\Delta H = -25.88 \text{ kcal}$ or $\Delta H_f^\circ = -624.74 \text{ kcal}$.

Lloyd et al. [136] reported decomposition pressure measurements to the anhydrous salt in the temperature range from 293°K to 333 °K. We obtain $\Delta H_f^\circ = -618.3 \text{ kcal}$.

From the solubility given by Linke [5] and the activity coefficients and osmotic coefficients given by Robinson and Stokes [6] we obtain $\Delta G^\circ \text{soln} = -4.11 \text{ kcal}$ or $\Delta G_f^\circ = -497.93 \text{ kcal}$. This results in $\Delta S_f^\circ =$



-425.3 e.u. and $S^\circ = 109.5$ e.u. This appears a little high. We have estimated $S^\circ = 108$ e.u. and have adjusted ΔG_f° accordingly.

$\text{MgC}_2(\text{c})$ Irmann [137] reported $\Delta H = -78$ kcal for the reaction $\text{MgC}_2(\text{c}) + 180 \text{HCl}(\text{m} = 2.53, m_{\text{NaCl}} = 3.16) \rightarrow \text{MgCl}_2(\text{aq}) + 178 \text{HCl}(\text{m} = 2.50, m_{\text{NaCl}} = 3.16) + \text{C}_2\text{H}_2(\text{g})$. This results in $\Delta H_f^\circ = 20$ kcal.

$\text{Mg}_2\text{C}_3(\text{c})$ Irmann [137] reported $\Delta H = -198$ kcal for the reaction $\text{Mg}_2\text{C}_3(\text{c}) + 360 \text{HCl}(\text{m} = 2.53, m_{\text{NaCl}} = 3.16) \rightarrow 2\text{MgCl}_2(\text{aq}) + 356 \text{HCl}(\text{m} = 2.51, m_{\text{NaCl}} = 3.16) + \text{C}_3\text{H}_4(\text{g})$. Using $\Delta H_f^\circ \text{C}_3\text{H}_4(\text{g}) = 44.3$ kcal, we obtain $\Delta H_f^\circ = 17$ kcal.

$\text{MgCO}_3(\text{c})$ The C_p° and S° were obtained from Kelley and King [85]; the high temperature functions from Kelley [138].

Kapustinskii and Stakhanova [139] measured the following ΔH 's:



This results in $\Delta H = +23.52$ kcal for $\text{MgCO}_3(\text{c}) \rightarrow \text{CO}_2(\text{g}) + \text{MgO}(\text{c})$, or $\Delta H_f^\circ = -261.4$ kcal.

Roth [140] reported the $\Delta H^\circ_{\text{decomp.}} = +23.6$ kcal or $\Delta H_f^\circ = -261.5$ kcal. Berthelot [141] reported $\Delta H = 2.7$ kcal for the precipitation of MgCO_3 from $\text{K}_2\text{CO}_3(220 \text{H}_2\text{O})$ and $\text{MgSO}_4(220 \text{H}_2\text{O})$. We obtain $\Delta H_f^\circ = -268.1$ kcal. Ellis and Mortland [142] and Foldvari-Vogl and Kliburszky [143] obtained $\Delta H^\circ_{\text{decomp.}}$ from differential thermal analysis methods, to be 27.6 kcal and 27.0 kcal, respectively, or $\Delta H_f^\circ = -265.5$ and -264.9 kcal.

We obtain from Marc and Simek's [144] vapor pressure measurements $\Delta H^\circ_{\text{decomp.}} = 28.2$ kcal (3rd law) and 26.4 kcal (2nd law) or $\Delta H_f^\circ = -266.1$ kcal and -264.3 kcal.

Langmuir [145] reviews the above data as well as the solubility measurements and the derived ΔG_f° values and points out the inconsistencies in the stability relationships in the $\text{MgO-CO}_2\text{-H}_2\text{O}$ system. We have accepted his interpretation and calculations to obtain $\Delta G^\circ = 0.665$ kcal for $\text{MgCO}_3 \cdot 3\text{H}_2\text{O}(\text{c}) \rightarrow \text{MgCO}_3(\text{c}) + 3\text{H}_2\text{O}(\text{liq})$. Using our value for ΔG_f° for the trihydrate = -412.6 kcal, we obtain $\Delta G_f^\circ = -241.9$ kcal.

Mg₂Si(c) Kubaschewski and Villa [146] reported $\Delta H_f^\circ = -18.6$ kcal. Eremenko and Lukashenko [147], from EMF measurements obtained $E(\text{in ev}) = 0.2075 - 0.77 \times 10^{-4} T$ for the range 673°K to 873°K, from which we obtain $\Delta H_f^\circ_{773^\circ\text{K}} = -19.1$ kcal. This corrects to $\Delta H_f^\circ = -18.7$ kcal. Grjotheim et al. [148] measured the decomposition pressure in the range 1130 to 1273°K by the transpiration technique. We obtain $\Delta H^\circ = 41.1$ kcal/mol Mg(g) or $\Delta H_f^\circ = -11.6$ kcal.

From Eremenko and Lukashenko we also obtain a $\Delta S_f^\circ(773^\circ\text{K}) = -7.1$ e.u. which, assuming a $\Delta C_p = -1$ cal/mol deg, corrects to $\Delta S_f^\circ = -6.1$ and $S^\circ = 14.0$ e.u. This value appears low. Mannchen and Jacobi [149] reported C_p measurements from 12°K to 300°K on Mg_{2.12}Si(c) and $S^\circ = 19.8$ cal/mol. Assuming their reported S° is for Mg_{2.12}Si(c) we obtain $S^\circ \text{ Mg}_2\text{Si(c)} = 18.6$ e.u. and a $\Delta S_f^\circ = -1.5$ e.u.

For the corresponding Ge compound ($S^\circ_{\text{Ge}}(\text{c}) = 7.43$ e.u.) we have $S^\circ = 20.7$ e.u. and $\Delta S_f^\circ = -2.35$ e.u. In comparison with these figures we feel 18.6 e.u. is high (and -1.5 e.u. too positive). We have therefore adjusted S° to = 18.0 e.u.

MgSiO₃(c) Furukawa and Reilly [150] evaluated the low temperature C_p and high temperature heat content and have tabulated the thermal functions up to 2000°K.

Torgeson and Sahama [34] by HF soln. calorimetry of Mg(OH)₂(c), SiO₂(c, quartz), and MgSiO₃(c) obtained $\Delta H = 0.16$ kcal for $\text{Mg(OH)}_2(\text{c}) + \text{SiO}_2(\text{c}) \rightarrow \text{MgSiO}_3(\text{c}) + \text{H}_2\text{O}(\text{liq})$. This results in $\Delta H_f^\circ = -370.22$ kcal.

Henderson and Taylor [151] reported $\Delta G^\circ_{1823^\circ\text{K}} = -5.1$ kcal for the formation from the oxides. This results in $\Delta H_f^\circ = -368.5$ kcal.

Mg₂SiO₄(c) Furukawa and Reilly [150] tabulated the thermal functions up to 2000°K.

Torgeson and Sahama [34] by HF soln. calorimetry of Mg(OH)₂(c), SiO₂(c, quartz), and Mg₂SiO₄(c) obtained $\Delta H = 2.58$ kcal for $2\text{Mg(OH)}_2(\text{c}) + \text{SiO}_2(\text{c}) \rightarrow \text{Mg}_2\text{SiO}_4(\text{c}) + 2\text{H}_2\text{O}(\text{liq})$, from which we obtain $\Delta H_f^\circ = -520.45$ kcal.

King et al. [152] from HF soln. calorimetry obtained $\Delta H^\circ = -13.86$ kcal for $2\text{MgO}(c) + \text{SiO}_2(c) \rightarrow \text{Mg}_2\text{SiO}_4(c)$ which leads to $\Delta H_f^\circ = -519.20$ kcal. Henderson and Taylor [151] reported $\Delta G^\circ_{1823^\circ\text{K}} = -9.4$ kcal for the formation of $\text{Mg}_2\text{SiO}_4(c)$ from the oxides. This results in $\Delta H_f^\circ = -515.4$ kcal.

$\text{Mg}_3\text{Si}_2\text{O}_5(\text{OH})_4(c)$ King et al. [152] from HF soln. calorimetry obtained $\Delta H^\circ = -39.86$ kcal for $3\text{MgO}(c) + 2\text{SiO}_2(c) + 2\text{H}_2\text{O}(l) \rightarrow \text{Mg}_3\text{Si}_2\text{O}_5(\text{OH})_4(c)$ from which we obtain $\Delta H_f^\circ = -1043.4$ kcal.

The Cp° and S° were also obtained from King et al.

$\text{Mg}_3\text{Si}_4\text{O}_{10}(\text{OH})_2(c)$ Barany [153] from HF soln. calorimetry obtained $\Delta H^\circ = -44.9$ kcal for $3\text{MgO}(c) + 4\text{SiO}_2(c) + \text{H}_2\text{O}(l) \rightarrow \text{Mg}_3\text{Si}_4\text{O}_{10}(\text{OH})_2(c)$ from which we obtain $\Delta H_f^\circ = -1415.5$ kcal.

The Cp° and S° were obtained from Robie and Stout [154].

$\text{MgB}_{12}(c)$ The thermal functions were obtained from Germaidze et al. [155] who also measured the $\text{Mg}(g)$ pressure over the MgB_{12} to be 10^{-5} atm. at 1700°K . This results in $\Delta H_f^\circ = -53.4$ kcal.

$\text{MgAl}_2\text{O}_4(c)$ The Dow Chemical Co. [156] tabulated the thermal functions. Navrotsky and Kleppa [157] measured the ΔH soln. of $\text{MgO}(c)$, $\text{Al}_2\text{O}_3(c, \alpha)$ and $\text{MgAl}_2\text{O}_4(c)$ in $9\text{PbO} \cdot 3\text{CdO} \cdot 4\text{B}_2\text{O}_3$ (melt) and obtained $\Delta H_{970^\circ\text{K}} = -8.72$ kcal for the formation from the component oxides. This results in $\Delta H^\circ = -8.6$ kcal and $\Delta H_f^\circ = -552.9$ kcal.

Altman [20] from Knudsen effusion decomposition pressure measurements [$\text{MgAl}_2\text{O}_4(c) \rightarrow \text{Mg}(g) + \frac{1}{2}\text{O}_2(g) + \text{Al}_2\text{O}_3(c)$], supports a $\Delta H^\circ = -5$ kcal for the formation from the oxides. Altman [158] from transpiration experiments on the Al-MgO and Al-MgAl₂O₄ systems obtained $\Delta H^\circ = -7$ kcal. Grjotheim et al. [159], by the transpiration method, measured the K 's for $4\text{MgO}(c) + 2\text{Al}(l) \rightarrow \text{MgAl}_2\text{O}_4(c) + 3\text{Mg}(g)$. They considered the system ideal. On this basis we obtain $\Delta H^\circ = 7.3$ kcal (2nd law) and -7.6 kcal (3rd law). Altman [20] corrects their results for the activity

of Al. Using the thermal functions mentioned above we obtain a 3rd law $\Delta H^\circ = -8.2$ kcal and $\Delta H_f^\circ = -552.5$ kcal. Grjotheim et al. [160] repeat their measurements and obtain a $\Delta H^\circ = +1.1$ kcal. In a later series of measurements on the Al-Mg-SiO system they [161] obtain the activity of Al and pressure of Mg(g) for the equilibrium process, $4\text{MgO(c)} + 2\text{AlSi(liq)} \rightleftharpoons \text{MgAl}_2\text{O}_4\text{(c)} + 3\text{Mg(g)}$. This results in $\Delta H^\circ = -7.4$ kcal for formation from the oxides and $\Delta H_f^\circ = -551.7$ kcal. In a reaction involving MgO(c) and $\text{Al}_4\text{C}_3\text{(c)}$ they [162] obtain $\Delta H^\circ = -11.1$ kcal and $\Delta H_f^\circ = -555.4$ kcal. Rao and Dadape [163] measured the K's of the reaction, $4\text{MgO(c)} + 3\text{AlCl(g)} \rightleftharpoons \text{MgAl}_2\text{O}_4\text{(c)} + \text{AlCl}_3\text{(g)} + 3\text{Mg(g)}$ in the range 1298°K to 1465°K. We obtain $\Delta H_f^\circ = -554.0$ kcal (3rd law) and a $\Delta H^\circ = -9.7$ kcal for formation from the oxides and $\Delta H_f^\circ = -554.7$ kcal (2nd law) and a $\Delta H^\circ = -10.4$ kcal.

Zaionchovskii and Rubal'skaya [164] reported $\Delta H_f^\circ = -567.1$ kcal.

The first mentioned ΔH_f° was selected.

$\text{Mg}_2\text{Al}_4\text{Si}_5\text{O}_{18}\text{(c)}$ The Cp° and S° were obtained from Weller and King [165]; the high temperature heat content from Pankratz and Kelley [166].

Henderson and Taylor [151] reported $\Delta G^\circ_{1733^\circ\text{K}} = -12.5$ kcal for $2\text{MgO(c)} + 2\text{Al}_2\text{O}_3\text{(c)} + 5\text{SiO}_2\text{(c)} \rightarrow \text{Mg}_2\text{Al}_4\text{Si}_5\text{O}_{18}\text{(c)}$ from which we obtain $\Delta H_f^\circ = -2177$ kcal.

BIBLIOGRAPHY

1. D. D. Wagman, W. H. Evans, V. B. Parker, I. Halow, S. Bailey, and R. Schumm, Selected values of chemical thermodynamic properties, Natl. Bur. Standards Technical Note 270-3, 264 pp (U. S. Govt. Printing Office, Jan. 1968).
2. R. Hultgren, R. L. Orr, P. D. Anderson, and K. K. Kelley, Selected values of thermodynamic properties of metals and alloys, 963 pp (John Wiley and Sons, Inc. 1963).
3. R. Hultgren, R. L. Orr, and K. K. Kelley, Supplement to Selected values of thermodynamic properties of metals and alloys; Mg, Oct. 1966.
4. C. E. Moore, Atomic energy levels, Vol. 1 and 3, Natl. Bur. Standards Circ. 467, (U.S. Govt. Printing Office, 1949-1958).
5. W. F. Linke, Solubilities of inorganic and metal organic compounds, Vol. II, 4th edition, (American Chemical Society, Wash., D. C., 1965).
6. R. A. Robinson and R. H. Stokes, Electrolyte Solutions, 2nd edition, 559 pp, (Academic Press, Inc. New York, 1959).
7. Dow Chemical Company - JANAF Thermochemical Tables, Dec. 31, 1965.
8. G. T. Furukawa, M. L. Reilly, J. M. Henning, T. B. Douglas, A. C. Victor, and A. R. Beaudoin, Natl. Bur. Standards Report 6484, p. 17 and table 2 - 10 (1959).
9. W. Muthmann and L. Weiss, Ann. 331, 1 (1904).
10. J. E. Moose and S. W. Parr, J. Am. Chem. Soc. 46, 2656 (1924).
11. H. von Wartenburg, Z. Elektrochem. 15, 866 (1909).
12. F. J. Rogers, Am. J. Sci. 143, 301 (1892).
13. A. F. Vorob'ev and S. M. Skuratov, Zhur. Fiz. Khim. 32, 2580 (1958).
14. S. A. Shchukarev, I. V. Vasil'kovà, and B.N. Sharupin, Vestnik Leningrad. Univ. 15, No. 10, Ser. Fiz. i Khim. No. 2, 112 (1960).
15. C. E. Holley and E. J. Huber, J. Am. Chem. Soc. 73, 5577 (1951).
16. C. H. Shomate and E. H. Huffman, J. Am. Chem. Soc. 65, 1625 (1943).
17. W. F. Giauque, J. Am. Chem. Soc. 71, 3192 (1949).
18. L. Brewer and R. F. Porter, J. Chem. Phys. 22, 1867 (1954).

19. C. A. Alexander, J. S. Ogden, and A. Levy, J. Chem. Phys. 39, 3057 (1963).
20. R. L. Altman, J. Phys. Chem. 67, 366-369 (1963).
21. R. F. Porter, W. A. Chupka, and M. G. Inghram, J. Chem. Phys. 23, 1347 (1955).
22. E. Bulewicz and T. Sugden, Trans. Faraday Soc. 55, 720 (1959).
23. I. Veits, L. Gurvitch, N. P. Rtishcheva, Zhur. Fiz. Khim. 32, 2532 (1958).
24. J. Drowart, G. Exsteen, and G. Verhaegen, Trans. Faraday Soc. 60, 1920 (1964).
25. L. Brewer and S. Trajmar, J. Chem. Phys. 36, 1585 (1962).
26. Dow Chemical Company - JANAF Thermochemical Tables, Sept. 30, 1963.
27. V. I. Pepekin, T. N. Dymova, Yu. A. Libeder, and A. Yu. Apin, Zhur. Fiz. Khim. 38, 1024 (1964).
28. L. G. Sillen and A. E. Martell, Stability constants of metal-ion complexes, Soc. London, Spec. Publ. No. 17, 754 pp (London 1964).
29. P. B. Hostetler, Am. J. Sci. 261, 238 (1963).
30. Dow Chemical Company - JANAF Thermochemical Tables, Mar. 31, 1967.
31. L. S. Wells and K. Taylor, J. Research Natl. Bur. Standards 19, 215 (1937).
32. K. Taylor and L. S. Wells, J. Research Natl. Bur. Standards, 21, 133 (1938).
33. W. F. Giaque and R. C. Archibald, J. Am. Chem. Soc. 59, 561 (1937).
34. D. R. Torgeson and T. G. Sahama, J. Am. Chem. Soc. 70, 2156 (1948).
35. W. A. Roth and P. Chall, Z. Elektrochem. 34, 185 (1928).
36. J. Thomsen, Thermochemische untersuchungen, Vols. I, II, III, and IV, (J. A. Barth, Leipzig, 1882-1886).
37. M. Berthelot, Ann. chim. et phys. (6) 11, 310 (1887).
38. T. C. Ehlert, G. D. Blue, J. W. Green, and J. L. Margrave, J. Chem. Phys. 41, 2250 (1964).
39. A. G. Gaydon, Dissociation energies and spectra of diatomic molecules (Chapman and Hall, Ltd., London, 1953).

40. G. Herzberg, Molecular spectra and molecular structure. I. Spectra of diatomic molecules, 2nd ed., (D. Van Nostrand Company, New York, 1950).
41. Dow Chemical Company - JANAF Thermochemical Tables, Mar. 31, 1966.
42. E. Rudzitis, H. M. Feder, and W. N. Hubbard, J. Phys. Chem. 68, 2978 (1964).
43. P. Gross, C. Hayman, and D. L. Levi, Trans. Faraday Soc. 50, 477 (1954).
44. A. F. Kapustinskii and K. K. Samplavskaya, Zhur. Neorg. Khim. 6, 2237 (1961).
45. A. Guntz, Ann. chim. et phys. (6) 3, 39 (1884).
46. A. Guntz, Compt. rend. 98, 819 (1884).
47. H. von Wartenberg, Z. anorg. u. allgem. Chem. 249, 100 (1942).
48. E. Petersen, Z. physik. Chem. 4, 384 (1889).
49. J. Berkowitz and J. R. Marquart, J. Chem. Phys. 37, 1853 (1962).
50. J. W. Green, G. D. Blue, T. C. Ehlert, and J. L. Margrave, J. Chem. Phys. 41, 2245 (1964).
51. R. R. Hammer and J. A. Pask, J. Am. Ceram. Soc. 47, 264 (1964).
52. M. A. Greenbaum, H. C. Ko, M. Wong, and M. Farber, J. Phys. Chem. 68, 965 (1964).
53. J. L. Margrave, CPIA Publication No. 54U I 43 (Aug. 1964).
54. L. Le Boucher, Anales soc. esp̃an. fis. y quim. 32, 1142 (1934).
55. D. L. Hildenbrand, W. F. Hall, F. Ju, and N. D. Potter, J. Chem. Phys. 40, 2882 (1964).
56. D. L. Hildenbrand and L. P. Theard, U. S. Dept. Comm. Office Tech. Serv. AD 258, 410 24 pp (1961).
57. K. G. Gunther, Glastech. Ber. 31, 9 (1958).
58. Dow Chemical Company - JANAF Thermochemical Tables, June 30, 1966.
59. H. Bommer and E. Hohmann, Z. anorg. u. allgem. Chem. 248, 357 (1941).
60. K. Sanō, Nippon Kagaku Zasshi, 57, 1019 (1936).

61. W. D. Treadwell, Schweiz Arch. angew. Wiss. u. Tech. 6, 69 (1940).
62. W. D. Treadwell and A. Cohen, Helv. Chim. Acta 22, 433 (1939).
63. K. Sano, Kinzoku - no-Kenkyu 12, 247 (1935).
64. R. Tsuchiya, Sci. Repts Tohoku Imp. Univ. (I) 37, 9 (1953).
65. I. L. Reznikov, Zhur. Priklad. Khim. 23, 897 (1950).
66. J. J. Egan, W. McCoy and J. Bracker, Symp. thermodyn. Nucl. Mtls., Vienna 1962, 14 pp.
67. W. D. Treadwell, A. Ammann, and T. Zurrer, Helv. Chim. Acta 19, 1255 (1936).
68. B. F. Markov, Yu. K. Delimarskii, and I. D. Panchenko, Zhur. Fiz. Khim. 29, 51 (1955).
69. R. Lorenz and H. Velde, Z. anorg. u. allgem. Chem. 183, 81 (1929).
70. M. Takahashi, J. Elektrochem. Soc. Japan, Overseas Ed. 29, E54 (1961).
71. E. E. Schrier and H. M. Clark, J. Phys. Chem. 67, 1259 (1963).
72. B. N. Kushkin, V. V. Rodyakin, and S. I. Kuznetsov, Zhur. Neorg. Khim. 12, 791 (1967).
73. W. Fischer, T. Petzel, and S. Lauter, Z. anorg. u. allgem. Chem. 333, 226 (1964).
74. C. G. Maier, U. S. Bur. Mines, Tech. Papers 360 54 pp. (1925).
75. E. Lange and H. Streeck, Z. physik. Chem. A152, 1 (1931).
76. A. B. Zdanovskii and L. D. Deryabina, Zhur. Fiz. Khim. 39, 678 (1965).
77. R. Fricke, Z. Elektrochem. 35, 361 (1929).
78. K. P. Mishchenko and I. F. Yakovlev, Zhur. Obshchei. Khim. 29, 1761 (1959).
79. O. Ya. Samoilov, Izvest. Akad. nauk S.S.S.R., Otdel. Khim. Nauk 1952, 627; Doklady Akad. Nauk S.S.S.R. 81, 641 (1951).
80. N. K. Voskresenskaya and K. S. Ponomareva, Zhur. Fiz. Khim. 20, 433 (1946).
81. L. T. Richardson and R. C. Wells, J. Wash. Acad. Sci. 21, 243 (1931).
82. M. Berthelot and L. Ilosvay, Ann. chim. et phys. (5) 29, 295 (1883).
83. K. P. Mishchenko, I. L. Reznikov, M. L. Klyueva, V. V. Sokolov, and Yu. A. Polyakov, Zhur. Priklad. Khim. 38, 1939 (1965).

84. T. W. Richards, A. W. Rowe, and L. L. Burgess, J. Am. Chem. Soc. 32, 1176 (1910).
85. K. K. Kelley and E. G. King, Contributions to the data on theoretical metallurgy. XIV. Entropies of the elements and inorganic compounds, U. S. Bur. Mines, Bull. 592, 149 pp (1961).
86. A. E. Auzhikov, Zhur. Priklad. Khim. 12, 1595 (1939).
87. H. V. Kondirev and G. V. Berezovskii, Zhur. Obshchei Khim. 5, 1246 (1935).
88. I. H. Derby and V. Yngve, J. Am. Chem. Soc. 38, 1439 (1916).
89. K. Sano, Sci. Repts. Tohoku Univ. (1) 25, 184 (1936).
90. K. Sano, Nippon Kagaku Zasshi, 59, 1145 (1938).
91. A. F. Vorob'ev, N. M. Privalova, A. S. Monaenkova, and S. M. Skuratov, Doklady Akad. Nauk S.S.S.R. 135, 1388 (1960).
92. S. Drakin and Ch. Yu. Chzhan, Zhur. Fiz. Khim. 38, 2800 (1964).
93. C. Smeets, Natuurw. Tijdschr. (Ghent) 15, 105 (1933).
94. G. F. Smith, O. W. Rees, and V. R. Hardy, J. Am. Chem. Soc. 54, 3513 (1932).
95. H. S. Jørgensen and R. H. Wood, J. Phys. Chem. 69, 4231 (1965).
96. T. A. Nosova, Zhur. Neorg. Khim. 11, 1970 (1966).
97. K. K. Kelley, U. S. Bur. Mines, Tech. Papers 676, 26 pp (1945).
98. E. I. Savinkova and T. A. Degtyareva, Izvest. Vysshikh Ucheb. Zavedenii, Khim. i Khim. Technol. 5, 292 (1962).
99. Ya. E. Vel'nyanskii and E. I. Savinkova, Zhur. Priklad. Khim. 26, 808 (1953).
100. N. Beketov, Bull. acad. imp. sci. (St. Petersburg) 34, 291 (1892).
101. A. Finch, P. J. Gardner, and C. J. Steadman, Private Communication, 1967.
102. J. Toguri, H. Flood, and T. Forland, Acta Chem. Scand. 17, 1502 (1963).
103. S. U. Pickering, J. Chem. Soc. 47, 100 (1885).
104. S. U. Pickering, J. Chem. Soc. 51, 290 (1887).

105. K. K. Kelley, Contributions to the data on theoretical metallurgy. VII The thermodynamic properties of sulfur and its inorganic compounds, U. S. Bur. Mines, Bull. 406, 154 pp. (1937).
106. E. W. Dewing and F. D. Richardson, Trans. Faraday Soc. 55, 611 (1959).
107. H. J. Knopf and H. Staude, Z. physik. Chem. 204, 265 (1955).
108. V. S. K. Nair and G. H. Nancollas, J. Chem. Soc. 1958, 3706.
109. E. Lange, Fortschr. Chem., Physik u. physik. Chem. 19, No. 6 (1928).
110. E. Lange and H. Streeck, Z. physik. Chem. A157, 1 (1931).
111. E. Lange and G. Messner, Z. Elektrochem. 33, 431 (1927).
112. E. Lange and G. Messner, Naturwiss. 15, 521 (1927).
113. E. Plake, Z. physik. Chem. A162, 257 (1932).
114. Yu. Ya. Kaganovich and K. P. Mishchenko, Zhur. Obshechi Khim. 21, 28 (1951).
115. J. W. S. Jamieson and G. B. Frost, Can. J. Chem. 34, 583 (1956).
116. K. Kohler and P. Zäske, Z. anorg. u. allgem. Chem. 331, 1 (1964).
117. G. B. Frost, W. G. Breck, R. N. Clayton, A. H. Reddoch, and C. G. Miller, Can. J. Chem. 35, 1446 (1957).
118. C. D. Carpenter and E. R. Jette, J. Am. Chem. Soc. 45, 578 (1923).
119. L. Rolla and L. Accame, Atti accad. nazl. Lincei Rend., Classe sci. fis., mat. e nat. (5) 22II, 109 (1913).
120. J. Bell, J. Chem. Soc. 1940, 72.
121. A. F. Kapustinskii and O. Ya. Samoilov, Zhur. Fiz. Khim. 26, 918 (1952).
122. J. Perreu, Compt. rend. 190, 429 (1930).
123. D. W. Mitchell, Ind. Eng. Chem. 41, 2027 (1949).
124. B. Neumann, C. Kröger, H. Kunz, Z. anorg. u. allgem. Chem. 207, 133 (1932).
125. R. Juza, K. Fasold, C. Haeblerle, Z. anorg. u. allgem. Chem. 234, 75 (1937).
126. B. Neumann, C. Kröger, and H. Haebler, Z. anorg. u. allgem. Chem. 204, 81 (1932).
127. C. Matignon, Compt. rend. 154, 1351 (1912).

128. L. Moser and R. Herzner, *Monatsh.* 44, 115 (1923).
129. L. H. Dreger, Ph.D. thesis, Univ. Wisconsin, microfilm # 62-1960.
130. B. A. Blank, *UCRL* 16018, 45 pp (1965).
131. Dow Chemical Company - JANAF Thermochemical Tables, Dec. 31, 1960.
132. F. E. Young, *J. Am. Chem. Soc.* 66, 773 (1944).
133. H. Hammerschmid and E. Lange, *Z. physik. Chem.* A160, 445 (1932).
134. W. W. Ewing, E. Klinger, and J. D. Brandner, *J. Am. Chem. Soc.* 56, 1053 (1934).
135. S. U. Pickering, *J. Chem. Soc.* 53, 865 (1888).
136. E. Lloyd, C. B. Brown, D. G. R. Bonnell, and W. J. Jones, *J. Chem. Soc.* 1928, 658.
137. F. Irmann, *Helv. Chim. Acta* 31, 1584 (1948).
138. K. K. Kelley, Contributions to the data on theoretical metallurgy. XIII. High temperature heat content, heat-capacity, and entropy data for the elements and inorganic compounds, U. S. Bur. Mines, *Bull.* 584, 232 pp (1960).
139. A. F. Kapustinskiĭ and M. S. Stakhanova, *Izvest. Akad. Nauk S.S.S.R., Otdel. Khim. Nauk* 1954, 587.
140. W. A. Roth, *J. prakt. Chem.* (2) 158, 117 (1941).
141. M. Berthelot, *Ann. chim. et phys.* (5) 4, 160 (1875).
142. B. G. Ellis and M. M. Mortland, *Am. Mineralogist*, 47, 371 (1962).
143. M. Foldvari-Vogl and B. Kliburszky, *Acta Geol. Acad. Sci. Hung.* 5, 187 (1958).
144. R. Marc and A. Simek, *Z. anorg. Chem.* 82, 17 (1913).
145. D. Langmuir, *J. Geol.* 73, 730 (1965).
146. O. Kubaschewski and H. Villa, *Z. Elektrochem.* 53, 32 (1949).
147. V. N. Eremenko and G. M. Lukashenko, *Symp. thermodyn. Nuclear Mtls*, Vienna 1965, Paper SM 66/87, 26 pp.
148. K. Grjotheim, O. Herstad, S. Petrucci, R. Skarbo, and J. Toguri, *Rev. chim. Acad. Rep. Populaire Roumaine* 7, 217 (1962).

149. W. Mamchen and G. Jacobi, Z. Naturforsch. 20b, 178 (1965).
150. G. Furukawa and M. L. Reilly, Natl. Bur. Standards Rept. 7587, pp 94, 146, and 148.
151. D. Henderson and J. Taylor, J. Iron Steel Inst. (London) 204, 39 (1966).
152. E. G. King, R. Barany, W. W. Weller, and L. B. Pankratz, U. S. Bur. Mines Rept. Invest. 6962 19 pp (1967).
153. R. Barany, U. S. Bur. Mines Rept. Invest. 6251, 9 pp (1963).
154. R. A. Robie and J. W. Stout, J. Phys. Chem. 67, 2252 (1963).
155. M. S. Germaidze, P. V. Geld, and S. M. Letun, Zhur. Prikladnoi Khim. 39, 1941 (1966).
156. Dow Chemical Company - JANAF Thermochemical Tables, Mar. 31, 1963.
157. A. Navrotsky and O. J. Kleppa, Inorg. Chem. 5, 192 (1966).
158. R. L. Altman, J. Phys. Chem. 68, 3425 (1964).
159. K. Grjotheim, O. Herstad, and J. M. Toguri, Can. J. Chem. 39, 443 (1961).
160. K. Grjotheim, O. Herstad, and J. M. Toguri, Trans. Can. Inst. Mining Met. 65, 221 (1962).
161. K. Grjotheim, O. Herstad, P. Skarbo^u and J. M. Toguri, Can. J. Chem. 41, 739 (1963).
162. K. Grjotheim, O. Herstad, and K. S. Johannessen, Z. anorg. u. allgem. Chem. 328, 267 (1964).
163. D. Rao and V. V. Dadape, J. Phys. Chem. 71, 537 (1967).
164. Ya. A. Zaionchovskii and E. V. Rubal'skaya, Izvest. Akad. Nauk S.S.S.R. Neorg. Materially 1, 1376 (1965).
165. W. W. Weller and E. G. King, U. S. Bur. Mines Rept. Invest. 6343, 7 pp (1963).
166. L. B. Pankratz and K. K. Kelley, U. S. Bur. Mines Rept. Invest. 6555, 7 pp (1964).

Table III

Selected Values for Some Mg Compounds at 298°K

Compound	State	ΔH_f° kcal/mole	ΔG_f° kcal/mole	S° cal/deg mol
Mg	c	0	0	7.81
Mg	g	35.30	27.04	35.502
Mg ⁺	g	213.100		
Mg ²⁺	g	561.299		
Mg ²⁺	aq			
	std. state, m = 1	-111.58	-108.7	-33.0
MgO	macro crystal (periclase)	-143.81	-136.10	6.44
MgO	micro crystal	-142.92	-135.27	6.67
MgO	g	4.		
MgH ₂	c	-18.0	-8.6	7.43
MgOH ⁺	aq			
	std. state, m = 1		-149.8	
Mg(OH) ₂	c	-220.97	-199.23	15.10
Mg(OH) ₂	ppt	-220.0		
Mg(OH) ₂	aq			
	std. state, m = 1	-221.52	-183.9	-35.6
Mg(OH) ₂	g	-134		
MgF	g	-53.0	-59.2	52.79
MgF ₂	c	-268.5	-255.8	13.68
MgF ₂	g	-173.0	-174.6	61.73
MgCl	g	-10.	-16.	55.8
MgCl ₂	c	-153.28	-141.45	21.42
MgCl ₂	g	-95.7		
MgCl ₂	aq			
	std. state, m = 1	-191.48	-171.4	-6.0
	50 H ₂ O	-190.23		
	100 H ₂ O	-190.59		
	400 H ₂ O	-190.94		
	1,000 H ₂ O	-191.080		
	5,000 H ₂ O	-191.269		
	10,000 H ₂ O	-191.323		
	∞ H ₂ O	-191.48		

Compound	State	ΔH_f° kcal/mole	ΔG_f° kcal/mole	S° cal/deg mol
MgCl ₂ •H ₂ O	c	-231.03	-205.98	32.8
MgCl ₂ •2H ₂ O	c	-305.86	-267.24	43.0
MgCl ₂ •4H ₂ O	c	-453.87	-388.03	63.1
MgCl ₂ •6H ₂ O	c	-597.28	-505.49	87.5
Mg(ClO ₄) ₂	c	-135.97		
Mg(ClO ₄) ₂	aq			
	std. state, m = 1	-173.40	-112.8	54.0
Mg(ClO ₄) ₂ •6H ₂ O	c	-584.5	-445.3	124.5
MgOHC1	c	-191.1	-174.9	20.0
MgBr ₂	c	-125.3	-120.4	28.0
MgBr ₂	g	-74.0		
MgBr ₂	aq			
	std. state, m = 1	-169.68	-158.4	6.4
	100 H ₂ O	-168.98		
	400 H ₂ O	-169.18		
	1,000 H ₂ O	-169.304		
	5,000 H ₂ O	-169.476		
	10,000 H ₂ O	-169.528		
	∞ H ₂ O	-169.68		
MgBr ₂ •6H ₂ O	c	-576.0	-491.4	95
MgI ₂	c	-87.0	-85.6	31.0
MgI ₂	g	-41		
MgI ₂	aq			
	std. state, m = 1	-137.96	-133.4	20.2
	400 H ₂ O	-137.49		
	1,000 H ₂ O	-137.59		
	∞ H ₂ O	-137.96		
MgSO ₄	c	-307.1	-279.8	21.9
MgSO ₄	aq., std. state m = 1, undissoc	-324.1	-289.74	-1.7

Compound	State	ΔH_f° kcal/mole	ΔG_f° kcal/mole	S° cal/deg mol
MgSO ₄	aq			
	std. state, m = 1	-328.90	-286.7	-28.2
	50 H ₂ O	-327.41		
	100 H ₂ O	-327.59		
	400 H ₂ O	-327.88		
	1,000 H ₂ O	-328.08		
	5,000 H ₂ O	-328.358		
	10,000 H ₂ O	-328.467		
	∞ H ₂ O	-328.90		
MgSO ₄ •H ₂ O	c	-382.9	-341.5	30.2
MgSO ₄ •H ₂ O	amorph	-376.4	-335.8	33.0
MgSO ₄ •2H ₂ O	c	-453.2		
MgSO ₄ •4H ₂ O	c	-596.7		
MgSO ₄ •6H ₂ O	c	-737.8	-629.1	83.2
MgSO ₄ •7H ₂ O	c	-809.92	-686.4	89.
Mg ₃ N ₂	c	-110.1		
Mg(NO ₃) ₂	c	-188.97	-140.9	39.2
Mg(NO ₃) ₂	aq			
	std. state, m = 1	-210.70	-161.9	37.0
	50 H ₂ O	-210.14		
	100 H ₂ O	-210.16		
	400 H ₂ O	-210.28		
	1,000 H ₂ O	-210.364		
	5,000 H ₂ O	-210.502		
	10,000 H ₂ O	-210.551		
	∞ H ₂ O	-210.70		
Mg(NO ₃) ₂ •6H ₂ O	c	-624.59	-497.3	108
MgC ₂	c	20		
Mg ₂ C ₃	c	17		
MgCO ₃	c, magnesite	-261.9	-241.9	15.7

Compound	State	ΔH_f° kcal/mole	ΔG_f° kcal/mole	S° cal/deg mol
Mg ₂ Si	c	-18.6	-18.0	18.
MgSiO ₃	c, clinoenstatite	-370.22	-349.46	16.19
Mg ₂ SiO ₄	c, forsterite	-519.6	-491.2	22.74
Mg ₃ Si ₂ O ₅ (OH) ₄	c, chrysotile	-1043.4	-965.1	52.9
Mg ₃ Si ₄ O ₁₀ (OH) ₂	c, talc	-1415.5	-1324.8	62.3
MgB ₁₂	c	-53.	-52.	21.4
MgO·Al ₂ O ₃	c	-552.9	-523.1	19.27
Mg ₂ Al ₄ Si ₅ O ₁₈	c, cordierite	-2177	-2055	97.3

UNCLASSIFIED

Security Classification

DOCUMENT CONTROL DATA - R & D

(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)

1. ORIGINATING ACTIVITY (Corporate author) National Bureau of Standards Washington, D. C. 20234		2a. REPORT SECURITY CLASSIFICATION UNCLASSIFIED	
		2b. GROUP	
3. REPORT TITLE THERMODYNAMIC PROPERTIES OF SELECTED LIGHT-ELEMENT AND SOME RELATED COMPOUNDS			
4. DESCRIPTIVE NOTES (Type of report and inclusive dates) Scientific Interim			
5. AUTHOR(S) (First name, middle initial, last name) Thomas B Douglas Charles W Beckett			
6. REPORT DATE 1 January 1968	7a. TOTAL NO. OF PAGES 123	7b. NO. OF REFS 166	
8a. CONTRACT OR GRANT NO. ISSA-67-6	9a. ORIGINATOR'S REPORT NUMBER(S) 9803		
b. PROJECT NO. 9750-01			
c. 6144501F	9b. OTHER REPORT NO(S) (Any other numbers that may be assigned this report) OSR 68-1625		
d. 681308			
10. DISTRIBUTION STATEMENT This document is subject to special export controls and each transmittal to foreign governments or to foreign nationals may be made only with prior approval of the AFOSR (SRGL).			
11. SUPPLEMENTARY NOTES TECH, OTHER		12. SPONSORING MILITARY ACTIVITY AF Office of Scientific Research (SREP) 1400 Wilson Boulevard Arlington, Virginia 22209	
13. ABSTRACT This report presents the results and interpretation of five recent NBS experimental studies of thermodynamic properties, two reviews which refine data treatment and evaluation, and one new critical assessment of published heats of formation. The heat capacity of beryllium nitride, Be_3N_2 , was precisely measured from 0 to 315 K; after judicious correction for the irreducible impurities, the data led to the common thermodynamic properties from 0 to 315 K, complementing earlier NBS measurements from 273 to 1173 K. Precise high-temperature calorimetry gave the heat capacity of tungsten from 1100 to 2600 K (showing no detectable difference between two samples, one triple-zone-refined and 99.999% pure); finally corrected results are given also for solid and liquid beryllium aluminate, $\text{B}_3\text{Al}_2\text{O}_4$, from 1200 to 2400 K. A mass-spectrometric investigation of Al_2O_3 containing 5.8% BeO identified the high-temperature gas species and gave values for their standard heats of formation. As part of the current NBS microwave and infrared investigation of the alkali-hydroxide molecules, the high-temperature microwave spectra of four isotopic varieties of RbOH were observed and analyzed to give their molecular constants like CsOH (studied earlier), RbOH is linear, with a low-frequency bending vibration of large amplitude. Two reviews deal with reaction calorimetry involving fluorine compounds: One documents the inadequacy of estimation rules for unmeasured inorganic fluorides and recommends a systematic cataloging of results to achieve better consistency; while the other describes a new computer subroutine for the automatic reduction of bomb-calorimetry data on organic fluorine compounds. As the result of an up-to-date critical evaluation of the published data giving $\Delta\text{Hf}_{298}^\circ$, $\Delta\text{Gf}_{298}^\circ$, and S_{298}° of magnesium compounds, values are documented and tabulated for 60 species of interest in "light-element" applications.			

DD FORM 1473
1 NOV 65

UNCLASSIFIED

Security Classification

UNCLASSIFIED

Security Classification

14.	KEY WORDS	LINK A		LINK B		LINK C	
		ROLE	WT	ROLE	WT	ROLE	WT
	Thermochemistry						
	Fluorine Compounds						
	Thermodynamic Properties						
	Heats of Formation						
	Beryllium Nitride						
	Beryllium Aluminate						
	Microwave Spectra						
	RbOH						
	RbOD						
	Magnesium Compounds						
	Tunsten, Enthalpy of Calorimetry						
	Rocket Propulsion						

UNCLASSIFIED

Security Classification

NBS TECHNICAL PUBLICATIONS

PERIODICALS

JOURNAL OF RESEARCH reports National Bureau of Standards research and development in physics, mathematics, chemistry, and engineering. Comprehensive scientific papers give complete details of the work, including laboratory data, experimental procedures, and theoretical and mathematical analyses. Illustrated with photographs, drawings, and charts.

Published in three sections, available separately:

● Physics and Chemistry

Papers of interest primarily to scientists working in these fields. This section covers a broad range of physical and chemical research, with major emphasis on standards of physical measurement, fundamental constants, and properties of matter. Issued six times a year. Annual subscription: Domestic, \$5.00; foreign, \$6.00*.

● Mathematical Sciences

Studies and compilations designed mainly for the mathematician and theoretical physicist. Topics in mathematical statistics, theory of experiment design, numerical analysis, theoretical physics and chemistry, logical design and programming of computers and computer systems. Short numerical tables. Issued quarterly. Annual subscription: Domestic, \$2.25; foreign, \$2.75*.

● Engineering and Instrumentation

Reporting results of interest chiefly to the engineer and the applied scientist. This section includes many of the new developments in instrumentation resulting from the Bureau's work in physical measurement, data processing, and development of test methods. It will also cover some of the work in acoustics, applied mechanics, building research, and cryogenic engineering. Issued quarterly. Annual subscription: Domestic, \$2.75; foreign, \$3.50*.

TECHNICAL NEWS BULLETIN

The best single source of information concerning the Bureau's research, developmental, cooperative and publication activities, this monthly publication is designed for the industry-oriented individual whose daily work involves intimate contact with science and technology—for engineers, chemists, physicists, research managers, product-development managers, and company executives. Annual subscription: Domestic, \$1.50; foreign, \$2.25*.

*Difference in price is due to extra cost of foreign mailing.

NONPERIODICALS

Applied Mathematics Series. Mathematical tables, manuals, and studies.

Building Science Series. Research results, test methods, and performance criteria of building materials, components, systems, and structures.

Handbooks. Recommended codes of engineering and industrial practice (including safety codes) developed in cooperation with interested industries, professional organizations, and regulatory bodies.

Special Publications. Proceedings of NBS conferences, bibliographies, annual reports, wall charts, pamphlets, etc.

Monographs. Major contributions to the technical literature on various subjects related to the Bureau's scientific and technical activities.

National Standard Reference Data Series. NSRDS provides quantitative data on the physical and chemical properties of materials, compiled from the world's literature and critically evaluated.

Product Standards. Provide requirements for sizes, types, quality and methods for testing various industrial products. These standards are developed cooperatively with interested Government and industry groups and provide the basis for common understanding of product characteristics for both buyers and sellers. Their use is voluntary.

Technical Notes. This series consists of communications and reports (covering both other agency and NBS-sponsored work) of limited or transitory interest.

CLEARINGHOUSE

The Clearinghouse for Federal Scientific and Technical Information, operated by NBS, supplies unclassified information related to Government-generated science and technology in defense, space, atomic energy, and other national programs. For further information on Clearinghouse services, write:

Clearinghouse
U.S. Department of Commerce
Springfield, Virginia 22151

Order NBS publications from:
Superintendent of Documents
Government Printing Office
Washington, D.C. 20402

