

FILE COPY

~~Not for publication or
for reference.~~

NATIONAL BUREAU OF STANDARDS REPORT

9912

OUTDOOR PERFORMANCE OF PLASTICS I. INTRODUCTION AND COLOR-CHANGE

Sponsored
by
Manufacturing Chemists' Association



U.S. DEPARTMENT OF COMMERCE
NATIONAL BUREAU OF STANDARDS

NATIONAL BUREAU OF STANDARDS

The National Bureau of Standards¹ was established by an act of Congress March 3, 1901. Today, in addition to serving as the Nation's central measurement laboratory, the Bureau is a principal focal point in the Federal Government for assuring maximum application of the physical and engineering sciences to the advancement of technology in industry and commerce. To this end the Bureau conducts research and provides central national services in four broad program areas. These are: (1) basic measurements and standards, (2) materials measurements and standards, (3) technological measurements and standards, and (4) transfer of technology.

The Bureau comprises the Institute for Basic Standards, the Institute for Materials Research, the Institute for Applied Technology, the Center for Radiation Research, the Center for Computer Sciences and Technology, and the Office for Information Programs.

THE INSTITUTE FOR BASIC STANDARDS provides the central basis within the United States of a complete and consistent system of physical measurement; coordinates that system with measurement systems of other nations; and furnishes essential services leading to accurate and uniform physical measurements throughout the Nation's scientific community, industry, and commerce. The Institute consists of an Office of Measurement Services and the following technical divisions:

Applied Mathematics—Electricity—Metrology—Mechanics—Heat—Atomic and Molecular Physics—Radio Physics²—Radio Engineering²—Time and Frequency²—Astrophysics²—Cryogenics.²

THE INSTITUTE FOR MATERIALS RESEARCH conducts materials research leading to improved methods of measurement standards, and data on the properties of well-characterized materials needed by industry, commerce, educational institutions, and Government; develops, produces, and distributes standard reference materials; relates the physical and chemical properties of materials to their behavior and their interaction with their environments; and provides advisory and research services to other Government agencies. The Institute consists of an Office of Standard Reference Materials and the following divisions:

Analytical Chemistry—Polymers—Metallurgy—Inorganic Materials—Physical Chemistry.

THE INSTITUTE FOR APPLIED TECHNOLOGY provides technical services to promote the use of available technology and to facilitate technological innovation in industry and Government; cooperates with public and private organizations in the development of technological standards, and test methodologies; and provides advisory and research services for Federal, state, and local government agencies. The Institute consists of the following technical divisions and offices:

Engineering Standards—Weights and Measures—Invention and Innovation—Vehicle Systems Research—Product Evaluation—Building Research—Instrument Shops—Measurement Engineering—Electronic Technology—Technical Analysis.

THE CENTER FOR RADIATION RESEARCH engages in research, measurement, and application of radiation to the solution of Bureau mission problems and the problems of other agencies and institutions. The Center consists of the following divisions:

Reactor Radiation—Linac Radiation—Nuclear Radiation—Applied Radiation.

THE CENTER FOR COMPUTER SCIENCES AND TECHNOLOGY conducts research and provides technical services designed to aid Government agencies in the selection, acquisition, and effective use of automatic data processing equipment; and serves as the principal focus for the development of Federal standards for automatic data processing equipment, techniques, and computer languages. The Center consists of the following offices and divisions:

Information Processing Standards—Computer Information—Computer Services—Systems Development—Information Processing Technology.

THE OFFICE FOR INFORMATION PROGRAMS promotes optimum dissemination and accessibility of scientific information generated within NBS and other agencies of the Federal government; promotes the development of the National Standard Reference Data System and a system of information analysis centers dealing with the broader aspects of the National Measurement System, and provides appropriate services to ensure that the NBS staff has optimum accessibility to the scientific information of the world. The Office consists of the following organizational units:

Office of Standard Reference Data—Clearinghouse for Federal Scientific and Technical Information³—Office of Technical Information and Publications—Library—Office of Public Information—Office of International Relations.

¹ Headquarters and Laboratories at Gaithersburg, Maryland, unless otherwise noted; mailing address Washington, D.C. 20234.

² Located at Boulder, Colorado 80302.

³ Located at 5285 Port Royal Road, Springfield, Virginia 22151.

NATIONAL BUREAU OF STANDARDS REPORT

NBS PROJECT

4216201-421.04

12 September 1968

NBS REPORT

9912

*Not for publication or
for reference.*

OUTDOOR PERFORMANCE OF PLASTICS

I. INTRODUCTION AND COLOR-CHANGE

by

Joseph E. Clark*

Nick E. Green*

Paul Giesecke**

Sponsored

by

Manufacturing Chemists' Association

* Research Associate of Manufacturing Chemists' Association

** Group Leader of Appearance Evaluation Group, Central Research Laboratory,
American Cyanamid Company, Stamford, Conn.

IMPORTANT NOTICE

NATIONAL BUREAU OF STANDARDS
for use within the Government.
and review. For this reason, the
whole or in part, is not authorized
Bureau of Standards, Washington
the Report has been specifically

Approved for public release by the
director of the National Institute of
Standards and Technology (NIST)
on October 9, 2015

accounting documents intended
subjected to additional evaluation
listing of this Report, either in
Office of the Director, National
the Government agency for which
lies for its own use.



U.S. DEPARTMENT OF COMMERCE

NATIONAL BUREAU OF STANDARDS



ABSTRACT

This is the first in a series of reports on outdoor performance of 20 plastics. Computerized analysis and graphs of color data are presented. Reports on physical and other properties important to architectural performance are being prepared.

A coding system is given for computerizing more than 10,000 observations on the 8 properties.

Graphs are presented for Adams color-difference (E) versus time of exposure: 24 months in Arizona, Florida and Washington, D. C. Supporting tristimulus color data (L, a, b) are available on request.

Discoloration "failures" ($E > 25$) occurred only in Arizona, and only for 4 clear PVC's. Two other clear PVC films failed by embrittlement in Arizona. All clear PVC's followed similar patterns of sudden catastrophic discoloration. If any of the clear PVC's were slightly superior, it was PVC-B.

All white-pigmented PVC's discolored only slightly, averaging CLASS "B" color-fastness. If any of the white PVC's were slightly more color-fast, it was PVC-A.

PVF and PMMA were quite color-fast (CLASS "A") as expected. PE film (CLASS "A") and sheet (CLASS "B") did not discolor badly, but PE films embrittled in about a year, beginning in Arizona, then Florida, then Washington, D. C.

RP yellowed to color - CLASS "D" (E between 15 to 20 units) within 2 years. PETP discolored to CLASS "B" (E about 5 to 10 units).

Development of this color-fastness classification system is described. It is based on ranking plastics according to the highest color-difference (E) value attained at any time within a given period at any location.

The CLASS system is now being extended to the other properties.

OUTDOOR PERFORMANCE OF PLASTICS

I. INTRODUCTION AND COLOR-CHANGE

1. OBJECTIVE

2. INTRODUCTION

3. EXPERIMENTAL

3.1 Materials

3.2 Exposures

3.3 Properties Measured

4. RESULTS

4.1 Computerization of Data

4.2 Color Code for Computer

4.3 Graphic Results

5. OBSERVATIONS

5.1 Effect of Climate

5.2 Comparison of Plastics

5.2.1 Clear PVC

5.2.2 White-Pigmented PVC

5.2.3 PVF and PMMA

5.2.4 Other Plastics

6. RANKING OF PERFORMANCE

6.1 Failures

6.2 Classification

6.2.1 Classes of Plastics

6.2.2 Changes in Class

7. SUMMARY

8. RECOMMENDATIONS

9. ACKNOWLEDGMENTS

10. REFERENCES

1. OBJECTIVE

This is the first in a planned series of reports on the outdoor performance of plastics. In this series, data will be graphically presented on 20 plastics exposed in Arizona (A), Florida (F), and Washington, D. C. (W).

Eight properties are being measured periodically. These are appearance, physical, and other properties related to architectural performance.

Computerized presentation and analysis of data will be emphasized.

This report considers the color of plastics. The next report, now in preparation, will concentrate on physical properties.

2. INTRODUCTION

Outdoor exposures have been conducted on 20 plastics formulated from 6 base polymers: polyethylene (PE), polymethyl methacrylate (PMMA), polyvinyl fluoride (PVF), polyethylene terephthalate (PETP), glass-reinforced polyester (RP), and polyvinyl chloride (PVC). Clear and white sheet and film have been exposed in Phoenix, Miami and Washington, D. C. for over 2 years.

This is part of an integrated exposure program in which the same plastics are being exposed to accelerated weathering in laboratory environmental chambers.

The goal is to forecast outdoor performance of plastics, by establishing the relation between such accelerated vs. outdoor exposures.

3. EXPERIMENTAL

Details may be found in our earlier NBS Report 9640, "Correlation of Accelerated and Outdoor Weathering Tests of Plastics" [1]^{1/}. The summaries are given below for convenience of the reader.

3.1 Materials

Table 1 summarizes the 20 plastics formulated from 6 base polymers. These materials were selected and approved by the MCA Plastics Technical Subcommittee.

3.2 Exposures

Specimens were placed on supports at a 45° angle to the horizontal and facing the equator, at

South Florida Test Service Inc.
Miami, Florida

(hot, wet)

^{1/} Figures in brackets indicate the literature references at the end of this paper.

Desert Sunshine Exposure Tests Inc.
Phoenix, Arizona

(hot, dry)

Connecticut and Van Ness Streets
(Old NBS Site)
Washington, D. C.

(temperate)

At regular intervals, samples are removed for testing. Samples are not put back on exposure after removal. Where possible, sufficient replicates were exposed initially to allow for 10-years of sampling.

3.3 Properties Measured

Table 2 lists the most common criteria for evaluation of plastics in architectural outdoor applications: appearance, physical and selected additional properties.


Also listed are member companies of MCA who volunteered to perform the indicated tests.

1. Color

Color of all original and outdoor-exposed specimens was measured under the direction of Mr. Paul Giesecke at American Cyanamid Company, Stamford, Connecticut. A GE spectrophotometer yielded the CIE color values of X, Y, Z.

Calculation of total color difference (E) was done by use of Reilly's modification of Glasser's cube-root formula, which is believed to be the best improvement of Adams chromatic-value formula [2]. This required conversion of X, Y, Z values to G, R, B values [2].

Schematically, this calculation of the Adams Color Difference (E) values plotted herein is:



where

(1) is

$$\begin{aligned} G &= -0.10X + 100.05Y + 0.04Z \\ R &= 110.84X + 8.52Y - 14.54Z \\ B &= -0.62X + 3.94Y + 81.92Z \end{aligned}$$

$$(2) \text{ is } \begin{aligned} L &= 25.29 G^{1/3} - 18.38 \\ a &= 106.0 (R'^{1/3} - G^{1/3}) \\ b &= 42.34 (G^{1/3} - B^{1/3}) \\ (R' &= 0.8R + 0.2B) \end{aligned}$$

$$(3) \text{ is } E = [(\Delta L)^2 + (\Delta a)^2 + (\Delta b)^2]^{1/2}$$

An added benefit of this method of calculation is direct comparison of tristimulus spectrophotometer readings with Colormaster tristimulus colorimeter readings. The Colormaster colorimeter is used by us at NBS to read color of specimens exposed to accelerated laboratory weathering.

It should be noted that some color-difference (E) values presented in our earlier NBS Report #9640 were given in the Hunter E system. The Hunter equations convert directly from X, Y, Z to L, a, b and complicate comparison with G, R, B colorimeter values. See Reference [2] for correction of the common reference [3] to the Hunter equation.

Calculations and plots were done on the NBS UNIVAC 1108 computer, using both the OMNITAB english-language program and FORTRAN V.

4. RESULTS

4.1 Computerization of Data

Over 10,000 observations now constitute the bank of data on outdoor performance: 20 plastics X 3 sites X 8 samplings, to-date X 22 property-parameters. To efficiently select, plot, analyze and correlate these data, computer handling was found necessary.

To retrieve any individual observation, or set of observations, from the computer memory all data were coded. The code is given in Table 3. Variables coded are type of exposure, time of exposure, plastic, property measured and value of that property.

For example, Arizona exposure for 3 months of plastic PE-60 mil, and the resulting value of color-difference (E) is coded:

| | | | | |
|---|---|---|-----|------|
| 1 | 3 | 2 | 111 | 4.77 |
|---|---|---|-----|------|

The unexposed control specimen for this appears as:

| | | | | |
|---|---|---|-----|-----|
| 0 | 0 | 2 | 111 | 0.0 |
|---|---|---|-----|-----|

The following conventions were adopted for special cases:

| | | |
|-------------------------------|---------|---------|
| Missing data | 8888.88 | Value |
| Off-scale reading | 9999.99 | Value |
| Repeat exposure of plastic 1 | 101 | Plastic |
| Repeat exposure of plastic 10 | 110 | Plastic |
| Second repeat of plastic 10 | 210 | Plastic |

All available data can be obtained from the authors. At your request, it can be obtained in the following forms:

IBM punched cards
Computer listing of card-contents
Magnetic Tape

4.2 Color Code for Computer

A 3-numeral code is used for the property of color:

| | | |
|----------------|---|-------------------------------|
| First numeral | 1 | Color |
| Second numeral | 1 | E (Adams color-difference) |
| | 2 | L (lightness-darkness) |
| | 3 | a (redness-greenness) |
| | 4 | b (yellowness-blueness) |
| Third numeral | 1 | GE Spectrophotometer |
| | 2 | Meeco Tristimulus Colorimeter |

Only 111 data are presented in this report: Adams color-difference values calculated from measurements on the GE spectrophotometer.

As mentioned previously, the L, a, b values are available on request.

4.3 Graphic Results

In Figures 1 to 20, following, Adams color-difference (E) is plotted versus time of exposure. There is one graph for each of the 20 plastics. Results are given for exposure in Arizona (A), Florida (F) and Washington, D. C. (W).

Note that: a) Not all plastics are exposed in all locations. b) Color data on a plastic may not continue to 2 years because the plastic has completely deteriorated (e.g., Figure 1) or the supply of replicates is exhausted (e.g., Figure 12). c) For color-difference greater than 25 units (our arbitrary pre-set limit), the following note is printed below the graph: "***NOTE: #POINTS FELL OUTSIDE THE SPECIFIED LIMITS AND WERE OMITTED".

5. OBSERVATIONS

5.1 Effect of Climate

Arizona exposure appeared to produce more discoloration for many plastics (e.g., Figures 2, 7, 8, 9, 11, 14, 15, and 18). This is most noticeable for clear PVC (Figures 7 to 13).

In no case did Washington exposure appear most severe.

In one case (Figure 5) Florida may have consistently caused slightly more discoloration.

5.2 Comparison of Plastics

Figures 21 to 30 group the plastics by discoloration at each site. In plots on which various plastics are compared, plastics are designated by the letter corresponding to their coded numbers.

TABLE 4

LETTER DESIGNATIONS FOR PLASTICS

| | | | | | |
|---|----|---------|---|----|---------|
| A | 1 | PE-1 | K | 11 | PVC-C10 |
| B | 2 | PE-60 | L | 12 | PVC-C60 |
| C | 3 | PMMA | M | 13 | PVC-N |
| D | 4 | PVF | N | 14 | PVC-A4 |
| E | 5 | PETP | O | 15 | PVC-A10 |
| F | 6 | RP | P | 16 | PVC-A60 |
| G | 7 | PVC-B4 | Q | 17 | PVC-D4 |
| H | 8 | PVC-B10 | R | 18 | PVC-D10 |
| I | 9 | PVC-B60 | S | 19 | PVC-D60 |
| J | 10 | PVC-C4 | T | 20 | PVC-M |

5.2.1 Clear PVC

Figures 21, 22, 23 group the 7 Clear PVC's by discoloration at each site. Three PVC-B's (G, H, I) are shown by solid lines; three PVC-C's (J, K, L) are shown by dotted lines; PVC-N (M) is shown by a dashed line.

All follow similar patterns of discoloration: initial discoloration, slight bleaching, then rapid discoloration. This harmonic (seasonal) behavior does not seem strongly dependent on formulation or thickness.

If any material showed slight superiority, it was PVC-B.

Note that only Arizona exposure failed some materials (color-change greater than 25 units) within 2 years. This is indicated by the "***NOTE" at the foot of Figure 21.

5.2.2 White-pigmented PVC

Figures 24, 25, 26 group the 7 white PVC's by discoloration at each site. Three PVC-A's (N, O, P) are shown by slashed lines; three PVC-D's (Q, R, S) are shown by dot-dash lines; PVC-M (T) is shown by widely-spaced dots.

These show generally similar patterns of mild discoloration. Slightly periodic (seasonal) behavior can be detected in most of the materials. As for Clear PVC's, harmonic behavior does not appear strongly dependent on formulation or thickness.

If any material showed slight superiority, it was PVC-A.

5.2.3 PVF and PMMA

Figure 27 is a composite comparison of two very good polymeric materials. Based on the polymer structures of polyvinyl fluoride and polymethyl methacrylate, their resistance to weathering should be excellent. These results, and industrial experience with these materials, confirm this prediction.

Both materials performed equally well, and were not affected by location.

5.2.4 Other Plastics

Figures 28, 29, 30 group the various plastics (except PVF and PMMA) by discoloration at each site.

Three white PVC's (N, O, T) were selected for comparison with the clear RP (F), polyethylene (B), and PETP (E). Glass-reinforced polyester (F) consistently discolored most in this group. In comparison, all three white PVC's did not discolor greatly.

Moderate effects of season and location were noted. In PE-60 (B) and RP (F), peaks occur around August in the period of maximum sunlight, and lows occur around January.

6. RANKING OF PERFORMANCE

It is highly desirable to be able to objectively rank the performance of architectural materials. The following section is a first step toward that goal.

6.1 Failures

Plastics with greater than 25 units of color-difference from the original were arbitrarily designated "failures". In fact, visual examination of such specimens confirms that they all discolored greatly.

Table 5 shows that discoloration "failures" to-date have occurred only in Arizona, and only for 4 clear PVC's. After 20-24 months, PVC-B4, B10, C10 and N60 severely discolored.

6.2 Classification

Of course, the acceptable degree of discoloration varies with application. For that reason, a performance ranking rather than a "pass-fail" designation is needed. Unfortunately, it is much more difficult to satisfactorily classify performance.

One system under trial is to arbitrarily create the classification:

| <u>Class</u> | <u>Adams (E) Color-Difference</u> |
|--------------|-----------------------------------|
| A | 0-5 |
| B | 5-10 |
| C | 10-15 |
| D | 15-20 |
| E | 20-25 |
| F | Greater than 25 |

However, the performance rank of a plastic may change significantly with location and time selected for ranking. In fact, not only may a CLASS "A" material fall to lower class, but lower class materials may rise to higher class.

Table 6 presents the results of one solution to this problem. Plastics were ranked according to the highest E-value attained at any time (within 1 year, column 1 or within 2 years, column 2) at any location.

A weakness of this system is that it may lead to over-design (and probably higher cost) of plastics for less-demanding applications. However, small additional cost may be acceptable at this time to improve the "image" to the consumer of plastic construction materials.

Accuracy and precision of color-difference (E) values herein is about ± 1 unit. Therefore, borderline cases were given the better of the two ranks in question, in view of the above-described tendency to "over-design".

6.2.1 Classes of Plastics

A study of Table 6 shows that most of the plastics performed well, in color stability, for 1 year in all locations. Of the 20 plastics, 18 were CLASS "A" or "B" for 1 year. Over half were CLASS "A".

At 2 years, only 4 remained CLASS "A". Of the twenty, 13 were CLASS "A" or "B" for 2 years.

Furthermore, none were "failures" at 1 year, but 4 failed with 2 years.

Thus, 2-year exposure definitely separated the very good materials from the very bad. One-year exposure was much less effective in classifying the plastics.

6.2.2 Changes in Class

No material could better its class, with this system. Thus, the "bleaching" obstacle to ranking was overcome.

Some of the clear PVC's showed a drastic change in classification from 1 to 2 years:

| | |
|---------|--------|
| PVC-B4 | A to F |
| PVC-B10 | A to F |
| PVC-B60 | B to E |
| PVC-C10 | A to F |
| PVC-N60 | B to F |

Of all the plastics exposed, only the clear PVC's have shown this exponential discoloration. Two clear PVC's remain, which are not in the above list: PVC-C4 and PVC-C60. As noted in Table 6, failure of PVC-C60 was likely at 24 months, but the supply of replicates for observation was exhausted. This leaves PVC-C4, which behaved similarly to PE-1: good color retention but total embrittlement of the film in about a year in Arizona and Florida. The Washington specimen of PVC-C4 was intact at 2 years. Thus, almost all clear PVC's failed by either discoloration or embrittlement within about 2 years.

Such examples of catastrophic failure are those which are most difficult to predict. Our other mathematical approaches to this forecasting problem may provide a solution.

7. SUMMARY

This is the first in a series of reports on outdoor performance of 20 plastics. Computerized analysis of color data and graphs are presented. Similar reports are underway for 2 physical properties and 5 other properties related to outdoor architectural performance.

A coding system is given for computerizing more than 10,000 observations on the 8 properties.

Color of all original and outdoor-exposed specimens was measured on a GE spectrophotometer, which yielded CIE color values of X, Y, Z. Total color-difference between original and exposed replicates was calculated in the Adams system from the computed L, a, b values.

Graphs are given of Adams color-difference (E) versus time of exposure: 24 months in Arizona, Florida and Washington, D. C. Supporting tristimulus color data (L, a, b) are available on request on magnetic tape, punched cards or computer listing.

Development of a weatherability classification system is described. This classifies performance as CLASS "A", "B", "C", "D", "E", or "F". It is based on ranking plastics according to the highest property value attained at any time within a given period at any location. Its successful application to the color-difference (E) data is presented. The CLASS system is now being extended to the other properties.

Discoloration "failures" (E>25) occurred only in Arizona, and only for 4 clear PVC's. Two other clear PVC films failed by embrittlement in Arizona.

All clear PVC's followed similar patterns of sudden catastrophic discoloration: initial color change, slight bleaching, then rapid discoloration. All but 1 of 7 clear PVC's failed by discoloration (E>25) or embrittlement (of films) within about 2 years. If any of these clear vinyls were slightly superior over the others, it was PVC-B.

All white-pigmented PVC's showed somewhat periodic slight discoloration. They averaged CLASS "B" color-fastness. If any of the white vinyls were slightly more color-fast, it was PVC-A.

For both clear and white PVC's, periodic discoloration does not appear strongly dependent on formulation or thickness.

PVF and PMMA were quite color-fast, as expected. Both materials performed equally well (CLASS "A"), and were not affected by location.

PE film (CLASS "A") and sheet (CLASS "B") did not discolor badly, but PE films embrittled in about a year, beginning in Arizona, then Florida, then Washington, D. C.

PETP discolored to CLASS "B" and RP yellowed to CLASS "D" within 2 years. In comparison with other intermediate-class plastics, RP consistently discolored most.

Moderate effects of season and location were usually noted, especially for PE-60 and RP.

In overall perspective, most of the plastics were fairly color-fast for 1 year in all locations, but by 2 years varying degrees of significant discoloration were measured. At 2 years, there were:

4 CLASS "A"
9 CLASS "B"
0 CLASS "C"
2 CLASS "D"
1 CLASS "E"
4 CLASS "F"

In CLASS "A", one of the four was PE-1 which retained good color but totally embrittled. Another was white PVC-A60 which was only exposed in Washington, D. C.; Arizona exposure would probably lower its assigned CLASS. Thus, the only 2 truly comparable members of CLASS "A" at 2 years were PVF and PMMA.

8. RECOMMENDATIONS

This series of reports should be completed, to record and summarize the bank of observations.

Graphic and mathematical analysis of the data should be continued and refined. Promising classification systems such as that described herein should be developed further, as an aid in objectively and simply comparing performance of new products.

MCA sponsor-companies should avail themselves of the data bank in the appropriate forms. With the aid of MCA Plastics Technical Subcommittee members, these data can provide a sound base for development of improved plastics.

9. ACKNOWLEDGMENTS

We gratefully acknowledge the help of Dr. J. L. Herndon, for his help in caring for exposed samples and in reducing raw data;

W. C. Cullen, V. E. Gray and the staff of the National Bureau of Standards, Materials Durability and Analysis Section, for always lending helping hands when they were needed;

Dr. W. F. Bartoe, F. H. Carman and the MCA Steering Committee, for guidance toward our goals;

R. Saxon and the American Cyanamid Company, Central Research Laboratory staff, for helping us to obtain the color data on which this report is based.

10. REFERENCES

- [1] "Correlation of Accelerated and Outdoor Weathering Tests of Plastics", J. E. Clark, NBS Report #9640, Second Printing, Dec. 1967.
- [2] "Significance of Recent CIE Recommendations for Color Measurement", F. W. Billmeyer, Color Engineering 6, No. 1, 36, Jan.-Feb. 1968.
- [3] "Color..." 2nd Edition, D. B. Judd and G. Wyszecki, Wiley and Sons, New York, 1963.

TABLE

- 1 Twenty Plastics for Exposure Program
- 2 Evaluation Criteria for Architectural Plastics
- 3 Computer Code for Weathering Data
- 4 Identification Letters for Graphs of Plastics
 (see Text on page 5)
- 5 Discoloration "Failures" by 24-Months
- 6 Color-CLASS of Weathered Plastics

TABLE 1

TWENTY PLASTICS FOR EXPOSURE PROGRAM

| <u>BASE POLYMER</u> | <u>PLASTIC</u> | <u>DESIGNATION</u> |
|-------------------------------|---|--------------------|
| Polyethylene | Translucent - 1 mil | PE-1 |
| | - 60 mil | PE-60 |
| Poly (methyl methacrylate) | Clear - 60 mil | PMMA-60 |
| Poly (vinyl fluoride) | Clear - 1 mil | PVF-1 |
| Poly (ethylene terephthalate) | Clear - 5 mil | PETP-5 |
| Polyester/ x-linked | Clear - 60 mil | RP-60 |
| Poly (vinyl chloride) | Ba-Cd { Clear - 4 mil - 10 mil - 60 mil | PVC-B4 |
| | | -B10 |
| | | -B60 |
| | Sn { Clear - 4 mil - 10 mil - 60 mil | PVC-C4 |
| | | -C10 |
| | | -C60 |
| | Clear - 60 mil | PVC-N60 |
| | Ba-Cd { White - 4 mil - 10 mil - 60 | PVC-A4 |
| | | -A10 |
| | | -A60 |
| | Sn { White - 4 mil -10 mil -60 mil | PVC-D4 |
| | | -D10 |
| | | -D60 |
| | White - 60 mil | PVC-M60 |

TABLE 2

EVALUATION CRITERIA FOR ARCHITECTURAL PLASTICS

| <u>PROPERTY</u> | <u>COMPANY</u> |
|-----------------------|-----------------------------|
| Color | American Cyanamid |
| Haze | Monsanto |
| Gloss | Hercules |
| Surface Roughness | Union Carbide |
| Tensile Properties | W. R. Grace B.F.Goodrich |
| Flexural Properties | W. R. Grace |
| Electrical Properties | Firestone Plastics |
| UV Spectra | E.I.duPont |

TABLE 3

COMPUTER CODE FOR WEATHERING DATA

| <u>EXPOSURE</u> | <u>TIME</u> | <u>PLASTIC</u> | <u>PROPERTY</u> | <u>VALUE</u> |
|-------------------------------|-----------------|-------------------|--------------------------------|--------------|
| <u>0 Control</u> | 0 | 1 <u>PE-1 mil</u> | <u>1 Color</u> | # |
| 1 Arizona | 3 <u>Months</u> | 2 <u>PE-60</u> | 111 E (Adams) | |
| 2 Florida | 6 " | 3 <u>PMMA</u> | 121 L | |
| 3 Wash. D.C. | 9 " | 4 <u>PVF</u> | 131. a | |
| | 12 " | 5 <u>PETP</u> | 141 b | |
| <u>4 Atlas Xe</u> | 16 " | 6 <u>RP</u> | | |
| 41 dry | 20 " | 7 <u>PVC-B4</u> | <u>2 Haze</u> | |
| 42 spray | 24 " | 8 - 10 | 21 T at 420nm | |
| | 30 " | 9 - 60 | 22 T at 550nm | |
| <u>5 Xenotest</u> | 36 " | 10 <u>PVC-C4</u> | | |
| 51 dry, 30% RH, Light | | 11 - 10 | <u>3 Gloss</u> | |
| 52 wet, 30% RH, Light | | 12 - 60 | 31 45° | |
| 53 dry, 30% RH, Lt/Dk | | 13 <u>PVC-N</u> | | |
| 54 wet, 30% RH, Lt/Dk | | 14 <u>PVC-A4</u> | <u>4 Surface Rough.</u> | |
| 55 dry, 90% RH, Lt/Dk | | 15 - 10 | 41 AA | |
| 56 wet, 90% RH, Lt/Dk | 5 <u>Hours</u> | 16 - 60 | 42 Peaks/inch | |
| | 10 " | 17 <u>PVC-D4</u> | | |
| <u>6 Enclosed Carbon</u> | 25 " | 18 - 10 | <u>5 Electrical</u> | |
| 61 dry | 50 " | 19 - 60 | 51 D.C.) | |
| 62 spray | 100 " | 20 <u>PVC-M</u> | 52 D.F.) at 1 KC | |
| | 500 " | | | |
| <u>7 Sunshine Carbon</u> | 1000 " | | <u>6 Tensile</u> | |
| 71 dry | 5000 " | | 61 Modulus x 10 ⁵ | |
| 72 spray | | | 62 Y Stress x 10 ³ | |
| | | | 63 Y Strain % | |
| <u>8 FS/BL</u> | | | 64 Tensile x 10 ³ | |
| | | | 65 Ult. Elong. % | |
| <u>9 Brucksch Device</u> | | | <u>7 Flex</u> | |
| 91 13,000 ppm SO ₂ | | | 71 Modulus x 10 ⁵ | |
| 92 18 ppm SO ₂ | | | 72 Y Stress x 10 ³ | |
| 93 1400 ppm SO ₂ | | | 73 Y Strain x 10 ⁻² | |
| | | | 74 R Stress x 10 ³ | |
| | | | 75 R Strain x 10 ⁻² | |
| | | | 76 5% Stress x 10 ³ | |
| | | | <u>8 UV Spectra</u> | |
| | | | 81 Peak wavelength | |
| | | | 82 Peak height | |

TABLE 5

DISCOLORATION "FAILURES" BY 24 MONTHS*

| <u>PLASTIC</u> | <u>TIME OF OBSERVATION</u> | <u>ADAMS (E) COLOR-DIFFERENCE</u> |
|----------------|--------------------------------|---------------------------------------|
| PVC-B4 | 24 Months | 28.32 |
| -B10 | 24 Months | 42.03 |
| -C10 | 20 Months | 26.59 |
| -C10 | 24 Months | 47.59 |

*ARIZONA only. No E-values greater than 25 were found in this period in Washington, D. C. or Florida

TABLE 6

COLOR-CLASS OF PLASTICS

| <u>CLASS</u> | <u>AT 1 YEAR</u> | <u>AT 2 YEARS</u> |
|--------------|--|---|
| <u>A</u> | PE-1 (1) PMMA-60 PVF-1 PVC-B4 -B10 -C4 -C10 -A4 -A10 -A60 (2) -D60 -M60 | PE-1 (1) PMMA-60 PVF-1 PVC-A60 (2) |
| <u>B</u> | PE-60 PETP-5 PVC-B60 -N60 -D4 -D10 | PE-60 PETP-5 PVC-C4 -A4 -A10 -D4 -D10 -D60 -M60 |
| <u>C</u> | RP-60 PVC-C60 | - |
| <u>D</u> | - | RP-60 PVC-C60 (3) |
| <u>E</u> | - | PVC-B60 |
| <u>F</u> | - | PVC-B4 -B10 -C10 -N60 |

(1) Film embrittled completely at all sites in 1/2 - 1 1/2 years.

(2) Washington, D. C. data only.

(3) Data to 16-months only. Based on comparison with others of its type, the 24-month prediction would be CLASS "E" or "F".

GRAPHS OF COLOR-DIFFERENCE VS. TIME

FIGURE

INDIVIDUAL PLASTICS

| | |
|----|-------------------------------------|
| 1 | Polyethylene (1 mil) |
| 2 | Polyethylene (60 mil) |
| 3 | Polymethyl methacrylate (60 mil) |
| 4 | Polyvinyl fluoride (1 mil) |
| 5 | Polyethylene terephthalate (5 mil) |
| 6 | Glass-reinforced Polyester (60 mil) |
| 7 | Polyvinyl chloride -B (4 mil) |
| 8 | " " -B (10 mil) |
| 9 | " " -B (60 mil) |
| 10 | " " -C (4 mil) |
| 11 | " " -C (10 mil) |
| 12 | " " -C (60 mil) |
| 13 | " " -N (60 mil) |
| 14 | " " -A (4 mil) |
| 15 | " " -A (10 mil) |
| 16 | " " -A (60 mil) |
| 17 | " " -D (4 mil) |
| 18 | " " -D (10 mil) |
| 19 | " " -D (60 mil) |
| 20 | " " -M (60 mil) |

INDIVIDUAL LOCATIONS

| | | | |
|----|-------------------|---|---------------------------|
| 21 | Arizona |) | |
| 22 | Florida |) | 7 Clear PVC's |
| 23 | Washington, D. C. |) | |
| 24 | Arizona |) | |
| 25 | Florida |) | 7 White PVC's |
| 26 | Washington, D. C. |) | |
| 27 | A, F, W | | Exposures of PVF and PMMA |
| 28 | Arizona |) | |
| 29 | Florida |) | PE, PETP, RP, White PVC-A |
| 30 | Washington, D. C. |) | |

POLYETHYLENE (1 MIL)

ADAMS (E) COLOR-DIFFERENCE

25.00+

20.00+

15.00+

10.00+

5.00+

.00+





FIGURE 1

FIGURE 2

POLYETHYLENE (60 MIL)

ADAMS (E) COLOR-DIFFERENCE



POLYMETHYL METHACRYLATE (60 MIL)

ADAMS (E) COLOR-DIFFERENCE

25.00+

20.00+

15.00+

10.00+

5.00+

0.00+

FIGURE 3



FIGURE 4

POLYVINYL FLUORIDE (1 MIL)

ADAMS (E) COLOR-DIFFERENCE

25.00+

20.00+

15.00+

10.00+

5.00+

.00+

APR MAY JUN JUL AUG SEP OCT NOV DEC JAN FEB MAR APR MAY
66 67 68

25.00

20.00

15.00

10.00

5.00

.00

POLYETHYLENE TEREPHTHALATE (5 MIL)

ADAMS (E) COLOR-DIFFERENCE





FIGURE 6



POLYVINYL CHLORIDE-B (4 MIL)

ADAMS (E) COLOR-DIFFERENCE





FIGURE 7

**NOTE: 1 POINTS FELL OUTSIDE THE SPECIFIED LIMITS AND WERE OMITTED.

FIGURE 8

POLYVINYL CHLORIDE - B (10 MIL)

ADAMS (E) COLOR-DIFFERENCE



**NOTE: 1 POINTS FELL OUTSIDE THE SPECIFIED LIMITS AND WERE OMITTED.

FIGURE 9

POLYVINYL CHLORIDE - B (60 MIL)




FIGURE 10

POLYVINYL CHLORIDE - C (4 MIL)

ADAMS (E) COLOR-DIFFERENCE

25.00+

20.00+

15.00+

10.00+

5.00+

.00+

APR MAY JUN JUL AUG SEP OCT NOV DEC JAN FEB MAR APR MAY JUN JUL AUG SEP OCT NOV DEC JAN FEB MAR APR MAY
66 67 68



POLYVINYL CHLORIDE - C (10 MIL)

ADAMS (E) COLOR-DIFFERENCE




FIGURE 11

**NOTE: 2 POINTS FELL OUTSIDE THE SPECIFIED LIMITS AND WERE OMITTED.

FIGURE 12

PLASTIC 12

ENRS: A=ARIZONA F=FLORIDA

WASH, D.C.

POLYVINYL CHLORIDE - C (60 MIL)

ADAMS (E) COLOR-DIFFERENCE

25.00+

20.00+

15.00+

10.00+

5.00+

.00+

5.00

10.00

15.00

20.00


25.00

APR MAY JUN JUL AUG SEP OCT NOV DEC JAN FEB MAR APR MAY

66


67

68



POLYVINYL CHLORIDE - N (60 MIL)

ADAMS (E) COLOR-DIFFERENCE



**NOTE: 1 POINTS FELL OUTSIDE THE SPECIFIED LIMITS AND WERE OMITTED.

FIGURE 14

POLYVINYL CHLORIDE - A (4 MIL)

ADAMS (E) COLOR-DIFFERENCE

25.00+

20.00+

15.00+

10.00+

5.00+

.00+

.00

5.00

10.00

15.00

20.00

25.00


APR MAY JUN JUL AUG SEP OCT NOV DEC

66 67 68

APR MAY JUN JUL AUG SEP OCT NOV DEC JAN FEB MAR APR MAY
66 67 68



FIGURE 15



POLYVINYL CHLORIDE - A (60 MIL)



1
 2
 3
 4
 5
 6
 7
 8
 9
 10
 11
 12
 13
 14
 15
 16
 17
 18
 19
 20
 21
 22
 23
 24
 25
 26
 27
 28
 29
 30
 31
 32
 33
 34
 35
 36
 37
 38
 39
 40
 41
 42
 43
 44
 45
 46
 47
 48
 49
 50
 51
 52
 53
 54
 55
 56
 57
 58
 59
 60
 61
 62
 63
 64
 65
 66
 67
 68
 69
 70
 71
 72
 73
 74
 75
 76
 77
 78
 79
 80
 81
 82
 83
 84
 85
 86
 87
 88
 89
 90
 91
 92
 93
 94
 95
 96
 97
 98
 99
 100
 101
 102
 103
 104
 105
 106
 107
 108
 109
 110
 111
 112
 113
 114
 115
 116
 117
 118
 119
 120
 121
 122
 123
 124
 125
 126
 127
 128
 129
 130
 131
 132
 133
 134
 135
 136
 137
 138
 139
 140
 141
 142
 143
 144
 145
 146
 147
 148
 149
 150
 151
 152
 153
 154
 155
 156
 157
 158
 159
 160
 161
 162
 163
 164
 165
 166
 167
 168
 169
 170
 171
 172
 173
 174
 175
 176
 177
 178
 179
 180
 181
 182
 183
 184
 185
 186
 187
 188
 189
 190
 191
 192
 193
 194
 195
 196
 197
 198
 199
 200
 201
 202
 203
 204
 205
 206
 207
 208
 209
 210
 211
 212
 213
 214
 215
 216
 217
 218
 219
 220
 221
 222
 223
 224
 225
 226
 227
 228
 229
 230
 231
 232
 233
 234
 235
 236
 237
 238
 239
 240
 241
 242
 243
 244
 245
 246
 247
 248
 249
 250
 251
 252
 253
 254
 255
 256
 257
 258
 259
 260
 261
 262
 263
 264
 265
 266
 267
 268
 269
 270
 271
 272
 273
 274
 275
 276
 277
 278
 279
 280
 281
 282
 283
 284
 285
 286
 287
 288
 289
 290
 291
 292
 293
 294
 295
 296
 297
 298
 299
 300
 301
 302
 303
 304
 305
 306
 307
 308
 309
 310
 311
 312
 313
 314
 315
 316
 317
 318
 319
 320
 321
 322
 323
 324
 325
 326
 327
 328
 329
 330
 331
 332
 333
 334
 335
 336
 337
 338
 339
 340
 341
 342
 343
 344
 345
 346
 347
 348
 349
 350
 351
 352
 353
 354
 355
 356
 357
 358
 359
 360
 361
 362
 363
 364
 365
 366
 367
 368
 369
 370
 371
 372
 373
 374
 375
 376
 377
 378
 379
 380
 381
 382
 383
 384
 385
 386
 387
 388
 389
 390
 391
 392
 393
 394
 395
 396
 397
 398
 399
 400
 401
 402
 403
 404
 405
 406
 407
 408
 409
 410
 411
 412
 413
 414
 415
 416
 417
 418
 419
 420
 421
 422
 423
 424
 425
 426
 427
 428
 429
 430
 431
 432
 433
 434
 435
 436
 437
 438
 439
 440
 441
 442
 443
 444
 445
 446
 447
 448
 449
 450
 451
 452
 453
 454
 455
 456
 457
 458
 459
 460
 461
 462
 463
 464
 465
 466
 467
 468
 469
 470
 471
 472
 473
 474
 475
 476
 477
 478
 479
 480
 481
 482
 483
 484
 485
 486
 487
 488
 489
 490
 491
 492
 493
 494
 495
 496
 497
 498
 499
 500
 501
 502
 503
 504
 505
 506
 507
 508
 509
 510
 511
 512
 513
 514
 515
 516
 517
 518
 519
 520
 521
 522
 523
 524
 525

• • •

MAY

66

66

POLYVINYL CHLORIDE - D (4 MIL)

ADAMS (E) COLOR-DIFFERENCE

FIGURE 17




FIGURE 18

POLYVINYL CHLORIDE - D (10 MIL)

ADAMS (E) COLOR-DIFFERENCE

25.00+


20.00+

15.00+

10.00+

5.00+

0.00+



POLYVINYL CHLORIDE - D (60 MIL)

ADAMS (E) COLOR-DIFFERENCE

25.00+

20.00+

15.00+

10.00+

5.00+

.00+




FIGURE 19


25.00
20.00
15.00
10.00
5.00
.00
APR MAY JUN JUL AUG SEP OCT NOV DEC JAN FEB MAR APR MAY
66 67 68

FIGURE 20

POLYVINYL CHLORIDE - M (60 MIL)


ADAMS (E) COLOR-DIFFERENCE

25.00+
20.00+
15.00+
10.00+
5.00+
.00+



APR 66 MAY 66 JUN 66 JUL 66 AUG 66 SEP 66 OCT 66 NOV 66 DEC 66 JAN 67 FEB 67 MAR 67 APR 67 MAY 67 JUN 67 JUL 67 AUG 67 SEP 67 OCT 67 NOV 67 DEC 67 JAN 68 FEB 68 MAR 68 APR 68 MAY 68

ARIZONA



••NOTE. 5 POINTS FELL OUTSIDE THE SPECIFIED LIMITS AND WERE OMITTED.


FIGURE 22

EXPOSURE: 2 TIME: ALL PLASTIC: ALL CLEAR PVC PROPERTY: 111

PVC-B 4 G I H T X L M
 10
 60
 PVC-C 4 G I H T X L M
 10
 60
 PVC-N 60 G I H T X L M

FLORIDA

ADAMS (E) COLOR-DIFFERENCE



EXPOSURE: 3

TIME: ALL

PLASTIC: ALL CLEAR PVC

PROPERTY: 111

WASH., D.C.

PVC-B 4 | G
60 | H
PVC-C 4 | J
60 | K
PVC-N 60 | L
60 | M

ADAMS (E) COLOR-DIFFERENCE

25.00+

20.00+

15.00+

10.00+

5.00+

.00+

APR MAY JUN JUL AUG SEP OCT NOV DEC JAN FEB MAR APR MAY JUN JUL AUG SEP OCT NOV DEC JAN FEB MAR APR MAY
66 67 68

FIGURE 23





FIGURE 24

EXPOSURE: 1 TIME: ALL PLASTIC: ALL WHITE PVC PROPERTY: IIII

ARIZONA

PVC-A 4 | NOGRST
PVC-D 10 4 |
PVC-M 60 60 |

ADAMS (E) COLOR-DIFFERENCE



EXPOSURE: 2 TIME: ALL PLASTIC: ALL WHITE PVC PROPERTY: III

FLORIDA

| | | | | | | |
|-------|---|----|---|----|----|----|
| PVC-A | 4 | 10 | 4 | 10 | 60 | 60 |
| PVC-D | | | | | | |
| PVC-M | | | | | | |

ADAMS (E) COLOR-DIFFERENCE





FIGURE 26

EXPOSURE: 3 TIME: ALL PLASTIC: ALL WHITE PVC PROPERTY: III

WASH., D.C.

PVC-A 4 N
60 P
PVC-D 4 Q
60 S
PVC-M 60 T



ADAMS (E) COLOR-DIFFERENCE

FIGURE 27







FIGURE 27

| | PE-60 | PETP-5 | RP-60 | PVC-A-4 | PVC-A-10 | PVC-M-60 |
|-------|-------|--------|-------|---------|----------|----------|
| BFNOT | | | | | | |

ARIZONA



EXPOSURE: 2 TIME: ALL PLASTIC: 2,5,6,14,15,20 PROPERTY: III

PE-60
PETP-5
RP-60
PVC-A-4
PVC-A-10
PVC-M-60

FLORIDA




FIGURE 29

FIGURE 30

PE-60
PETP-5
RP-60
PVC-A-4
PVC-A-10
PVC-M-60

WASH., D.C.

ADAMS (E) COLOR-DIFFERENCE

