

NATL INST OF STAND & TECH



A11106 064468

NIST
PUBLICATIONS



National Bureau of Standards
Library, E-01 Admin. Bldg.

OCT 1 1981

191006

QC

100
.457

NAT'L INST. OF STAND & TECH



A11106 360212

A UNITED STATES
DEPARTMENT
OF COMMERCE
PUBLICATION



NBS SPECIAL PUBLICATION 260-37

Standard Reference Materials:

METHODS OF ANALYSIS OF NBS CLAY STANDARDS

U.S.
DEPARTMENT
OF
COMMERCE

QC
100
.457
260-37
1972
C.2

NATIONAL BUREAU OF STANDARDS

The National Bureau of Standards¹ was established by an act of Congress March 3, 1901. The Bureau's overall goal is to strengthen and advance the Nation's science and technology and facilitate their effective application for public benefit. To this end, the Bureau conducts research and provides: (1) a basis for the Nation's physical measurement system, (2) scientific and technological services for industry and government, (3) a technical basis for equity in trade, and (4) technical services to promote public safety. The Bureau consists of the Institute for Basic Standards, the Institute for Materials Research, the Institute for Applied Technology, the Center for Computer Sciences and Technology, and the Office for Information Programs.

THE INSTITUTE FOR BASIC STANDARDS provides the central basis within the United States of a complete and consistent system of physical measurement; coordinates that system with measurement systems of other nations; and furnishes essential services leading to accurate and uniform physical measurements throughout the Nation's scientific community, industry, and commerce. The Institute consists of a Center for Radiation Research, an Office of Measurement Services and the following divisions:

Applied Mathematics—Electricity—Heat—Mechanics—Optical Physics—Linac Radiation²—Nuclear Radiation²—Applied Radiation²—Quantum Electronics³—Electromagnetics³—Time and Frequency³—Laboratory Astrophysics³—Cryogenics³.

THE INSTITUTE FOR MATERIALS RESEARCH conducts materials research leading to improved methods of measurement, standards, and data on the properties of well-characterized materials needed by industry, commerce, educational institutions, and Government; provides advisory and research services to other Government agencies; and develops, produces, and distributes standard reference materials. The Institute consists of the Office of Standard Reference Materials and the following divisions:

Analytical Chemistry—Polymers—Metallurgy—Inorganic Materials—Reactor Radiation—Physical Chemistry.

THE INSTITUTE FOR APPLIED TECHNOLOGY provides technical services to promote the use of available technology and to facilitate technological innovation in industry and Government; cooperates with public and private organizations leading to the development of technological standards (including mandatory safety standards), codes and methods of test; and provides technical advice and services to Government agencies upon request. The Institute also monitors NBS engineering standards activities and provides liaison between NBS and national and international engineering standards bodies. The Institute consists of the following divisions and offices:

Engineering Standards Services—Weights and Measures—Invention and Innovation—Product Evaluation Technology—Building Research—Electronic Technology—Technical Analysis—Measurement Engineering—Office of Fire Programs.

THE CENTER FOR COMPUTER SCIENCES AND TECHNOLOGY conducts research and provides technical services designed to aid Government agencies in improving cost effectiveness in the conduct of their programs through the selection, acquisition, and effective utilization of automatic data processing equipment; and serves as the principal focus within the executive branch for the development of Federal standards for automatic data processing equipment, techniques, and computer languages. The Center consists of the following offices and divisions:

Information Processing Standards—Computer Information—Computer Services—Systems Development—Information Processing Technology.

THE OFFICE FOR INFORMATION PROGRAMS promotes optimum dissemination and accessibility of scientific information generated within NBS and other agencies of the Federal Government; promotes the development of the National Standard Reference Data System and a system of information analysis centers dealing with the broader aspects of the National Measurement System; provides appropriate services to ensure that the NBS staff has optimum accessibility to the scientific information of the world, and directs the public information activities of the Bureau. The Office consists of the following organizational units:

Office of Standard Reference Data—Office of Technical Information and Publications—Library—Office of International Relations.

¹ Headquarters and Laboratories at Gaithersburg, Maryland, unless otherwise noted; mailing address Washington, D.C. 20234.

² Part of the Center for Radiation Research.

³ Located at Boulder, Colorado 80302.

JUL 24 1972

[†]Standard Reference Materials: 37

Methods of Analysis of NBS Clay Standards

J. I. Shultz, R. K. Bell, T. C. Rains, and
O. Menis

Analytical Chemistry Division
Institute for Materials Research
National Bureau of Standards
Washington, D.C. 20234



U.S. DEPARTMENT OF COMMERCE, Peter G. Peterson, *Secretary*
NATIONAL BUREAU OF STANDARDS, Lawrence M. Kushner, *Acting Director*,
Issued June 1972

Library of Congress Catalog Card Number: 72-600062

National Bureau of Standards Special Publication 260-37

Nat. Bur. Stand. (U.S.), Spec. Publ. 260-37, 86 pages (June 1972)

CODEN: XNBSAV

PREFACE

Standard Reference Materials (SRM's) as defined by the National Bureau of Standards are "well-characterized materials, produced in quantity, that calibrate a measurement system to assure comparability of measurement in the nation." SRM's are widely used as primary standards in many diverse fields in science, industry, and technology, both within the United States and throughout the world. In many industries traceability of their quality control process to the national measurement system is carried out through the mechanism and use of SRM's. For many of the nation's scientists and technologists it is therefore of more than passing interest to know the details of the measurements made at NBS in arriving at the certified values of the SRM's produced. An NBS series of papers, of which this publication is a member, called the NBS Special Publication - 260 Series is reserved for this purpose.

This 260 Series is dedicated to the dissemination of information on all phases of the preparation, measurement, and certification of NBS-SRM's. In general, much more detail will be found in these papers than is generally allowed, or desirable, in scientific journal articles. This enables the user to assess the validity and accuracy of the measurement processes employed, to judge the statistical analysis, and to learn details of techniques and methods utilized for work entailing the greatest care and accuracy. It is also hoped that these papers will provide sufficient additional information not found on the certificate so that new applications in diverse fields not foreseen at the time the SRM was originally issued will be sought and found.

Inquiries concerning the technical content of this paper should be directed to the author(s). Other questions concerned with the availability, delivery, price, and so forth will receive prompt attention from:

Office of Standard Reference Materials
National Bureau of Standards
Washington, D.C. 20234

J. Paul Cali, Chief
Office of Standard Reference Materials

OTHER NBS PUBLICATIONS IN THIS SERIES

- NBS Spec. Publ. 260, Catalog of Standard Reference Materials, July 1970. 75 cents.* (Supersedes NBS Misc. Publ. 260, January 1968 and NBS Misc. Publ. 241, March 1962.)
- NBS Misc. Publ. 260-1, Standard Reference Materials: Preparation of NBS White Cast Iron Spectrochemical Standards, June 1964. 30 cents.*
- NBS Misc. Publ. 260-2, Standard Reference Materials: Preparation of NBS Copper-Base Spectrochemical Standards, October 1964. 35 cents.*
- NBS Misc. Publ. 260-3, Standard Reference Materials: Metallographic Characterization of an NBS Spectrometric Low-Alloy Steel Standard, October 1964. 20 cents.* (Out of print).
- NBS Misc. Publ. 260-4, Standard Reference Materials: Sources of Information on Standard Reference Materials, February 1965. 20 cents.* (Out of print).
- NBS Spec. Publ. 260-5, Standard Reference Materials: Accuracy of Solution X-Ray Spectrometric Analysis of Copper-Base Alloys, March 1965. 25 cents.* (Out of print).
- NBS Misc. Publ. 260-6, Standard Reference Materials: Methods for the Chemical Analysis of White Cast Iron Standards, July 1965. 45 cents.*
- NBS Misc. Publ. 260-7, Standard Reference Materials: Methods for the Chemical Analysis of NBS Copper-Base Spectrochemical Standards, October 1965. 60 cents.*
- NBS Misc. Publ. 260-8, Standard Reference Materials: Analysis of Uranium Concentrates at the National Bureau of Standards, December 1965. 60 cents.* (Out of print).
- NBS Misc. Publ. 260-9, Standard Reference Materials: Half Lives of Materials Used in the Preparation of Standard Reference Materials of Nineteen Radioactive Nuclides Issued by the National Bureau of Standards, November 1965. 15 cents.*
- NBS Misc. Publ. 260-10, Standard Reference Materials: Homogeneity Characterization on NBS Spectrometric Standards II: Cartridge Brass and Low-Alloy Steel, December 1965. 30 cents.*
- NBS Misc. Publ. 260-11, Standard Reference Materials: Viscosity of a Standard Lead-Silica Glass, November 1966. 25 cents.*
- NBS Misc. Publ. 260-12, Standard Reference Materials: Homogeneity Characterization of NBS Spectrometric Standards III: White Cast Iron and Stainless Steel Powder Compact, September 1966. 20 cents.*
- NBS Misc. Publ. 260-13, Standard Reference Materials: Mossbauer Spectroscopy Standard for the Chemical Shift of Iron Compounds, July 1967. 40 cents.*
- NBS Misc. Publ. 260-14, Standard Reference Materials: Determination of Oxygen in Ferrous Materials — SRM 1090, 1091, and 1092, September 1966. 30 cents.*
- NBS Misc. Publ. 260-15, Standard Reference Materials: Recommended Method of Use of Standard Light-Sensitive Paper for Calibrating Carbon Arcs Used in Testing Textiles for Colorfastness to Light, June 1967. 20 cents.*
- NBS Spec. Publ. 260-16, Standard Reference Materials: Homogeneity Characterization of NBS Spectrometric Standards IV: Preparation and Microprobe Characterization of W-20% Mo Alloy Fabricated by Powder Metallurgical Methods, January 1969. 35 cents.*
- NBS Spec. Publ. 260-17, Standard Reference Materials: Boric Acid; Isotopic and Assay Standard Reference Materials, February 1970. 65 cents.*
- NBS Spec. Publ. 260-18, Standard Reference Materials: Calibration of NBS Secondary Standard Magnetic Tape (Computer Amplitude Reference) Using the Reference Tape Amplitude Measurement "Process A", November 1969. 50 cents.*
- NBS Spec. Publ. 260-19, Standard Reference Materials: Analysis of Interlaboratory Measurements on the Vapor Pressure of Gold (Certification of Standard Reference Material 745), January 1970. 30 cents.*
- NBS Spec. Publ. 260-20, Standard Reference Materials: Preparation and Analysis of Trace Element Glass Standards. (In preparation)

- NBS Spec. Publ. 260-21, Standard Reference Materials: Analysis of Interlaboratory Measurements on the Vapor Pressures of Cadmium and Silver, January 1971. 35 cents.*
- NBS Spec. Publ. 260-22, Standard Reference Materials: Homogeneity Characterization of Fe-3Si Alloy, February 1971. 35 cents.*
- NBS Spec. Publ. 260-23, Standard Reference Materials: Viscosity of a Standard Borosilicate Glass, December 1970. 25 cents.*
- NBS Spec. Publ. 260-24, Standard Reference Materials: Comparison of Redox Standards, January 1972. \$1.*
- NBS Spec. Publ. 260-25, Standard Reference Materials: A Standard Reference Material Containing Nominally Four Percent Austenite, February 1971. 30 cents.*
- NBS Spec. Publ. 260-26, Standard Reference Materials: National Bureau of Standards—U.S. Steel Corporation Joint Program for Determining Oxygen and Nitrogen in Steel, February 1971. 50 cents.*
- NBS Spec. Publ. 260-27, Standard Reference Materials: Uranium Isotopic Standard Reference Materials, April 1971. \$1.25.*
- NBS Spec. Publ. 260-28, Standard Reference Materials: Preparation and Evaluation of SRM's 481 and 482 Gold-Silver and Gold-Copper Alloys for Microanalysis, August 1971. \$1.*
- NBS Spec. Publ. 260-29, Standard Reference Materials: Calibration of NBS Secondary Standard Magnetic Tape (Computer Amplitude Reference) Using the Reference Tape Amplitude Measurement "Process A-Model 2", June 1971. 60 cents.*
- NBS Spec. Publ. 260-30, Standard Reference Materials: Standard Samples Issued in the USSR (A Translation from the Russian), June 1971. \$1.*
- NBS Spec. Publ. 260-31, Standard Reference Materials: Thermal Conductivity of Electrolytic Iron SRM 734 from 4 to 300 K, November 1971. 35 cents.*
- NBS Spec. Publ. 260-32, Standard Reference Materials: The Cooperative Study of Temperature Scale Standards for DTA by ICTA and NBS. (In preparation)
- NBS Spec. Publ. 260-33, Standard Reference Materials: Comparison of Original and Supplemental SRM 705, Narrow Molecular Weight Distribution Polystyrene, H. L. Wagner. (In preparation)
- NBS Spec. Publ. 260-34, Standard Reference Materials: Thermoelectric Voltage. (In preparation)
- NBS Spec. Publ. 260-35, Standard Reference Materials: Thermal Conductivity of Austenitic Stainless Steel, SRM 735 from 5 to 280 K, April 1972. 35 cents.*
- NBS Spec. Publ. 260-36, Standard Reference Materials: A Referee Method for the Determination of Calcium in Serum. SRM 736. (In preparation)
- NBS Spec. Publ. 260-37, Standard Reference Materials: Methods of Analysis of NBS Clay Standards. (In preparation)
- NBS Spec. Publ. 260-38, Standard Reference Materials: Preparation and Calibration of Standards of Spectral Specular Reflectance. (In preparation)
- NBS Spec. Publ. 260-39, Standard Reference Materials: The Eddy Current Decay Method for Resistivity Characterization of High-Purity Metals. (In preparation)

*Send order with remittance to: Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402. Remittance from foreign countries should include an additional one-fourth of the purchase price for postage.

CONTENTS

	PAGE
INTRODUCTION	1
PART I	3
SILICA	3
SILICA BY THE HYDROCHLORIC ACID DEHYDRATION (GRAVIMETRIC) METHOD	3
SOLUBLE SILICON FOLLOWING SILICA DEHYDRATION . . .	7
SILICON BY THE MOLYBDENUM BLUE- (PHOTOMETRIC) METHOD	7
ALUMINA	12
ALUMINA BY THE SODIUM HYDROXIDE-CITRATE-CYANIDE- 8-QUINOLINOL (GRAVIMETRIC) METHOD	12
ALUMINA BY THE AMMONIUM HYDROXIDE-CUPFERRON- (GRAVIMETRIC) METHOD	17
PRECIPITATION WITH AMMONIUM HYDROXIDE	20
PRECIPITATION WITH CUPFERRON	21
PHOSPHORUS	23
PHOSPHORUS BY THE MOLYBDENUM-BLUE (PHOTOMETRIC) METHOD	23
PHOSPHORUS BY THE ION-EXCHANGE (PHOTOMETRIC) METHOD	27
TITANIA BY CUPFERRON (GRAVIMETRIC) METHOD	30
TITANIA BY THE HYDROGEN PEROXIDE (PHOTOMETRIC) METHOD	34
IRON BY THE 1,10-PHENANTHROLINE (PHOTOMETRIC) METHOD.	37
IRON BY $\text{SnCl}_2\text{-K}_2\text{Cr}_2\text{O}_7$ (VOLUMETRIC) METHOD	40
ZIRCONIA BY THE PYROCATECHOL VIOLET (PHOTOMETRIC) METHOD	43
CHROMIUM OXIDE BY THE DIPHENYLCARBAZIDE (PHOTOMETRIC) METHOD	46

CONTENTS-CONTINUED

	PAGE
PART II.	49
ATOMIC ABSORPTION AND FLAME EMISSION SPECTROMETRY. .	49
INSTRUMENTATION.	50
PROCEDURE FOR DISSOLUTION OF CLAY MATERIALS FOR FLAME EMISSION AND ATOMIC ABSORPTION ANALYSES. . .	51
LITHIUM BY FLAME EMISSION SPECTROMETRY	52
SODIUM BY FLAME EMISSION SPECTROMETRY.	55
POTASSIUM BY FLAME EMISSION SPECTROMETRY	58
MAGNESIUM BY ATOMIC ABSORPTION SPECTROMETRY.	61
CALCIUM BY ATOMIC ABSORPTION SPECTROMETRY.	66
STRONTIUM BY ATOMIC ABSORPTION SPECTROMETRY.	69
BARIUM BY FLAME EMISSION SPECTROMETRY.	72
REFERENCES	75
APPENDIX 1	
CERTIFICATE OF ANALYSIS, STANDARD REFERENCE MATERIAL 97a, FLINT CLAY	76
APPENDIX 2	
CERTIFICATE OF ANALYSIS, STANDARD REFERENCE MATERIAL 98a, PLASTIC CLAY	77

FOREWORD

This publication describes an effective combination of classical and instrumental analytical chemistry in characterizing a complex natural product. The attainment of accuracy in such an analysis requires the careful evaluation of systematic errors and the application of appropriate corrections. Specifically, in the gravimetric procedures, corrections for solubility and/or co-precipitation of impurities were determined by spectrophotometric procedures. Similarly, the selection of calibration procedures and standard addition methods in flame spectroscopy reduced the uncertainty in establishing values for minor and trace elements. These data have led to the certification of SRM's that were much needed for the rapid analysis by newer methods such as X-ray fluorescence. The latter methods, while precise, suffer from matrix effects which require appropriate standards to calibrate these instruments.

METHODS OF ANALYSIS OF NBS CLAY STANDARDS

J. I. Shultz, R. K. Bell, T. C. Rains and O. Menis

Institute for Materials Research
National Bureau of Standards
Washington, D.C. 20234

This publication brings together a compilation of methods used at NBS for the analysis of two complex standard reference clay materials. The methods were selected to give the best obtainable results for those elements normally found in clays. In some instances, more than one procedure was employed for an element as a cross-check on the precision and accuracy of the results. The procedures are presented in two parts. Part I is concerned with the determination of the major constituents by the classical analytical procedures. Part II covers the minor elements which are determined instrumentally by flame emission and atomic absorption spectrometry. These clay materials serve as analytical composition standards to provide quality control of the basic raw materials which are used in the ceramics and refractories industries.

Key words: Atomic absorption; ceramics; classical procedures; clay materials; flame emission; refractories; Standard Reference Materials.

INTRODUCTION

The published methods of analysis for clays and similar silicate materials, though fairly extensive, are widely scattered. This publication endeavors to bring together a compilation of methods used at NBS for the analysis of two complex standard reference clay materials, plastic and flint. The methods were selected and designed to give the best obtainable results for those elements normally found in clays. In some instances, more than one procedure was employed for an element as a cross-check on both the precision and accuracy of the results. The procedures are presented in two parts. Part I is concerned with the determination of the major constituents by the classical analytical procedures. Part II covers the minor elements which can most conveniently be determined instrumentally by flame emission and atomic absorption spectro-

etry. These latter procedures are attractive because of their speed, high sensitivity and improved precision and accuracy over the older and more time-consuming methods.

With issuance of these two Standard Reference Materials, NBS is providing renewals of materials that were first issued in 1931. These materials serve as analytical composition standards to provide quality control of the basic raw materials that are used in the ceramics and refractories industries. They will also serve as controls for the calibration of many instrumental methods. Marked advances, in recent years, in both instrumental and analytical techniques that are applicable to these materials, emphasize the need for well characterized standards.

These natural occurring materials have complex compositions and the classical analytical procedures are both time-consuming and difficult. To emphasize their difficulty, Lundell and Hoffman [1], as early as 1928 provided data to show the lack of agreement between analysts who assisted in the cooperative analysis of similar materials. More recently, in 1969, Flanagan [2] of the U.S. Geological Survey reiterated that the problem still exists.

The preparation of the materials, prior to sampling for analysis, consisted of sifting through a 50-mesh sieve and then mixing in a mechanical double-cone porcelain-lined mixer for a total of 2 hours. Homogeneity for each of the clays was established by an extensive sampling procedure conducted by S. D. Rasberry of the Spectrochemical Analysis Section of the Analytical Chemistry Division. Four main samples and 4 sub-samples were tested by x-ray fluorescence for the major elements. Sixteen replicate analyses were performed for silicon, aluminum, iron, titanium, calcium and potassium. The major elements and minor constituents were then determined by gravimetric, titrimetric, spectrophotometric, flame-emission and atomic absorption methods. The loss on ignition was based on heating the dried samples for 2 hours at 1100 °C.

PART I

SILICA

Silica is an important constituent of clays, generally amounting to one-fifth to two-thirds of their composition. Most of the methods for the determination of silicon are gravimetric procedures in which the silicon is converted to a soluble form by fusing with Na_2CO_3 , Na_2O_2 , $\text{K}_2\text{S}_2\text{O}_7$, or $\text{Na}_2\text{S}_2\text{O}_7$. Satisfactory fusions are obtained by using equal parts of Na_2CO_3 and fused $\text{Na}_2\text{B}_4\text{O}_7$, but the $\text{Na}_2\text{B}_4\text{O}_7$ must be removed before making determinations of silica or alumina. A satisfactory fusion is also obtained with anhydrous lithium metaborate.

In clays, virtually all of the silica exists in the combined form as aluminum silicate, iron silicate, and potassium aluminum silicate.

SILICA BY THE HYDROCHLORIC ACID DEHYDRATION- (GRAVIMETRIC) METHOD

I. Scope

This method covers the determination of silica in concentrations from 20 to 70 percent. The relative standard deviation is 0.2 percent.

II. Principle of Method [3]

After fusion of the sample, silicon is converted to silicic acid with hydrochloric acid and made insoluble by double dehydration. The solution is filtered, and the silica is ignited, weighed, and then volatilized with hydrofluoric acid. The residue is ignited and weighed. The loss in weight represents silica (SiO_2). Soluble silica in the filtrate is determined by spectrophotometry and combined with that found by gravimetry.

III. Interferences

Silica is contaminated with alumina, titania, zirconia or their phosphates, but the contaminants do not interfere

since they are weighed after the treatment of the impure silica with sulfuric and hydrofluoric acids.

IV. Procedure

(a) Transfer approximately 1g of sample to a weighing bottle and dry for 2 hrs at 140 °C. Stopper the bottle and cool for 1 hr in a desiccator. Lift the stopper for an instant, replace, and weigh the bottle and sample. Transfer the sample, without brushing, to a 25 ml platinum crucible containing about 1.25g of anhydrous Na_2CO_3 . Reweigh the bottle. The difference is the weight of the sample.

(b) Thoroughly mix the dried sample and Na_2CO_3 by stirring with a platinum rod. Add another 1.25g portion of Na_2CO_3 and mix. Repeat with a third portion of Na_2CO_3 and mix. Use 1.25g of the Na_2CO_3 to clean the stirring rod and then cover the mixture. Heat the covered crucible over a low flame for several min and gradually increase the heat until the mass is molten. Using tongs, slightly tilt and rotate the crucible to fuse any particles which may cling to the side of the crucible above the liquid. Heat over an open flame for 20 min. Tilt and rotate the crucible to spread the melt around the inside of the crucible and cool. Gently heat the crucible over an open flame for 30 secs, and cool.

(c) Cover the fused sample with water, transfer the contents to a platinum dish or Teflon beaker and wash the inside of the crucible and the lid. Cover the fusion with water and allow to stand overnight. Reserve the crucible.

(d) Pulverize the cake and stir the solution. Place the tip of a funnel under the cover of the dish or beaker. Add 5 ml of HCl to the reserved crucible. Slowly and cautiously, pour 40 ml of HCl (1+1) through the funnel. Transfer the contents of the reserved crucible through the funnel. Rinse the crucible and cover with

water and HCl repetitively. Wash the funnel and funnel tip, and remove.

(e) Allow the solution to stand until reaction ceases. Rinse the cover, replace it on the dish or beaker and heat on a steam bath until carbon dioxide is expelled. If any insoluble residue is present, filter, wash the residue with water, transfer the paper to the crucible used for the fusion, and ignite at low heat until carbon is removed. Fuse the residue with 2g of Na_2CO_3 and add the cooled melt to the original solution. Wash the cover and replace it on the dish or beaker containing glass hooks or a triangle and evaporate the solution to dryness with occasional stirring.

(f) Add 50 ml of HCl (1+4) to the dish or beaker, cover, and heat for 10 min. Add 150 ml of hot HCl (1+19), stir to dissolve salts, and filter immediately by decantation through a 11-cm medium filter paper into a 600 ml beaker. Wash the residue once with 15 ml of hot HCl (1+19). Transfer the bulk of the silica to the funnel. Scrub the dish or beaker thoroughly with a rubber-tipped rod. Wash the paper and precipitate 15 times with hot HCl (1+19) and 3 times with hot water. Transfer the paper and contents to a platinum crucible and reserve.

(g) Transfer the filtrate and washings to the original platinum dish or beaker. Evaporate to dryness on a steam bath. Add 50 ml of HCl (1+4), digest and filter through a 9-cm fine filter paper. Scrub and wash the container 10 times with hot HCl (1+19) and 3 times with hot water. Reserve the filtrate (A) and washings after evaporating to about 200 ml for spectrophotometric determination of soluble silica.

(h) Transfer the paper to the reserved platinum crucible, dry and heat slowly to 600 °C until the

carbon is removed. Finally ignite for 1 hr at 1200 °C to constant weight. Cool in a desiccator, and weigh after 30 mins.

(i) Add about 1 ml of water and 6 drops of H_2SO_4 (1+1) to the SiO_2 precipitate. Add 15 ml of HF and evaporate to dryness and then heat at a gradually increasing rate until H_2SO_4 is removed. Ignite for 10 min at 1100 to 1150 °C, cool in desiccator, and weigh. The difference is the weight of silica.

V. Calculation

Calculate the percentage of silica as follows:

$$\text{Silica, percent} = \frac{A-B}{C} \times 100$$

where:

A = initial weight, in grams, of crucible and impure SiO_2 .

B = final weight, in grams, of crucible and residue.

C = grams of sample used.

SOLUBLE SILICON FOLLOWING SILICA DEHYDRATION

Separation of silicon by dehydration with acid is never complete because of the solubility of silicic acid. Soluble silica in the filtrate from the dehydration may be determined spectrophotometrically.

The molybdenum blue method is a useful method for the photometric determination of silicon up to 200 parts per million. Molybdisilicic acid formed in a solution containing hydrofluoric, boric, and molybdic acids at pH 1.7 to 1.8 is extracted with butyl alcohol after addition of tartaric acid. The heteropoly acid is reduced with stannous chloride to the blue complex before measuring the intensity of the color. The addition of tartaric acid prohibits further reactions of the molybdisilicic acid with the silica from reagents or glassware.

SILICON BY THE MOLYBDENUM BLUE-(PHOTOMETRIC) METHOD

I. Scope

This method covers the determination of silicon in concentrations from 5 to 200 ppm in filtrates from silica separations in clays. The standard deviation at this range is 0.0001 percent.

II. Principle of Method [4]

The filtrate from the dehydrated silica is treated with hydrofluoric, boric, and molybdic acids and adjusted to a pH of 1.7 to 1.8. Molybdisilicic acid is extracted with normal butyl alcohol and reduced to a heteropoly blue complex. The spectrophotometric measurement is made at 635 nm.

III. Interferences

The elements normally present in clays do not interfere. Solutions should be kept in plastic containers.

IV. Concentration Range

The recommended concentration range is from 5 to 20 μg of silicon per 50 ml of butyl alcohol, using a 2-cm cell.

V. Stability of Color

The color is stable for at least 1 hr.

VI. Reagents

(a) Ammonium Hydroxide Solution. Bubble ammonia gas using plastic tubing, into cooled distilled water in a polyethylene bottle until the solution is saturated.

(b) Boric Acid Solution (50g/l). Dissolve 50g of H_3BO_3 in 900 ml of warm water, cool, and dilute to 1 liter with water.

(c) Potassium Permanganate Solution (0.6g/l). Dissolve 0.15g of KMnO_4 in 200 ml of water and dilute to 250 ml with water.

(d) Molybdic Acid Solution. Dissolve 25g of ammonium molybdate tetrahydrate in 200 ml of H_2SO_4 (1+9) in a 400-ml plastic beaker, dilute to 250 ml with water, and filter through a close-textured paper in a plastic funnel into a polyethylene bottle.

(e) Tartaric Acid Solution (200g/l). Dissolve 50g of tartaric acid in 200 ml of water and dilute to 250 ml with water.

(f) Stannous Chloride Reducing Solution (20g/l). Dissolve 2g of $\text{SnCl}_2 \cdot 2\text{H}_2\text{O}$ and 1 mg of $\text{CuCl}_2 \cdot 2\text{H}_2\text{O}$ in 100 ml of HCl (sp. gr. 1.18) and store in a glass-stoppered bottle. This solution should be prepared fresh every 3 days.

(g) Silicon, Standard Solution (A) (1 ml \approx 200 μg of Si). Fuse 213.9 mg of SiO_2 with 2g of Na_2CO_3 in a platinum crucible, cool, and dissolve the melt in 200 ml of water in a plastic beaker. Transfer the solution to a 500-ml

volumetric flask, dilute to the mark with water, mix well, and store the solution in a plastic bottle.

(h) Silicon, Standard Solution (B) ($1\text{ ml} \approx 2\text{ }\mu\text{g}$ of Si). Transfer exactly 10 ml of standard silicon solution (A) to a 1-liter volumetric flask, dilute to the mark with water, mix well, and store in a plastic bottle.

(i) Dilute Hydrochloric Acid (20% HCl). Add 100 ml of HCl (low in Si), in a plastic graduate, to 300 ml of water in a plastic bottle, mix, and cool. Dilute to 500 ml with water, and mix.

VII. Preparation of Calibration Curve

(a) Calibration solutions.

(1) Transfer 0.0, 2.5, 5.0, 7.5, and 10.0 ml of standard silicon solution (B) to five covered 250-ml plastic beakers. Add 10 ml of the 20% HCl solution.

(2) Add 0.5 ml of HF, mix, and allow to stand several minutes. Add 40 ml of the boric acid solution and 4 ml of the molybdic acid solution, mixing after each addition. Add 3 or 4 drops of the potassium permanganate solution, mixing after each drop. Add 1 or 2 ml of the ammonium hydroxide solution from a plastic dropper to neutralize some of the acid before using the glass electrode. Adjust the pH of the solution to 1.7 to 1.8 with the ammonium hydroxide solution. Cover the beaker and heat for 10 minutes on a steam bath. Cool in water at $20\text{ }^{\circ}\text{C}$ for 10 minutes. Add 4 ml of the tartaric acid solution and mix thoroughly. Glassware can be used from this point. Transfer the solution to a 250-ml separatory funnel. Wash the beaker twice with water and add the water to the funnel. Dilute the solution to a volume of approximately 90 ml, add 14 ml of H_2SO_4 (1+1), and mix. Cool to room temperature, add 50 ml of butyl alcohol, and shake vigorously for 1 minute. Allow the layers to separate, drain, and

discard the acid layer. Wash the butyl alcohol layer by adding 20 ml of H_2SO_4 (1+99) to the separatory funnel, shaking for 30 seconds, allowing the layers to separate. Drain and discard the acid layer. Repeat the washing 2 more times. Transfer the butyl alcohol to a 50-ml volumetric flask. Wash the funnel twice with small portions (1 or 2 ml) of butyl alcohol and add the washings to the volumetric flask. Add 0.5 ml of the stannous chloride reducing solution to the flask, dilute to the mark with butyl alcohol, and mix.

(b) Spectrophotometry. Fill the reference cell with normal butyl alcohol and adjust the photometer to the initial setting, using a light band centered at approximately 635 nm. While maintaining this photometric adjustment, take the photometric readings of the solutions. One or two drops of the stannous chloride reducing solution may be added to the sample, mixed, and another photometric reading taken to check for the complete reduction of the molybdisilicic acid.

(c) Calibration curve. Plot the photometric readings of the calibration solutions against the micrograms of silicon per 50 ml of solution (Note 1).

VIII. Procedure

(a) Transfer the reserved filtrate of Section IV (g) of Dehydration-Gravimetric Method for Silica, see page 3, to a 250 ml volumetric flask, dilute to volume with water and mix. Using a plastic pipet, transfer a 4.0 ml aliquot to a plastic covered 250-ml plastic beaker and add 10 ml of 20 percent HCl. Proceed as directed in Section VII (a) (2) and (b).

(b) Carry a reagent blank following the same procedure and using the same quantities of all reagents.

(c) By means of the calibration curve, convert the spectrophotometric reading of the sample solution to micrograms of silicon.

IX. Calculation

Calculate the percentage of silica as follows:

$$\text{SiO}_2, \text{ percent} = \frac{(A-B) \times 2.14}{C \times 10}$$

where:

A = micrograms of Si in 50 ml of butyl alcohol extract of the aliquot portion of the sample.

B = micrograms of Si in 50 ml of butyl alcohol extract of the blank.

C = gram of sample in 50 ml of butyl alcohol extract of the sample.

Add the silica percent obtained by spectrophotometry to that obtained by gravimetry for the total percent silica in the sample.

Note 1 - Plot absorbance A, against the respective concentrations on ordinary graph paper; or concentration C, against percentage transmission on semi-logarithmic paper using the semi-log scale for the percentage T values.

ALUMINA

Alumina is an important constituent in clays; with silica it constitutes more than 82 percent of the clay standards. An accurate determination of aluminum in rocks, minerals and ceramic or metallurgical products is difficult for the analyst. Care must be taken to avoid contamination of aluminum with iron, titanium, zirconium, vanadium, phosphorus, and silicon. Improper ignition of the aluminum hydroxide precipitate and erroneous corrections for the impurities in the ignited product are sources of error. The caustic-citrate-cyanide-8-quinolinol-gravimetric method eliminates contamination of the aluminum precipitate, which is dried in an oven, and thus avoids the necessity of an ignition at high temperature.

In another method for alumina in clays, the sample solution is divided into three aliquots. In the first aliquot, Al_2O_3 , Fe_2O_3 , TiO_2 , ZrO_2 , P_2O_5 , Cr_2O_3 and V_2O_5 are precipitated with NH_4OH . In the second aliquot of the same volume, Fe_2O_3 , TiO_2 , ZrO_2 and V_2O_5 are precipitated with cupferron. In the third aliquot, P_2O_5 is determined. Al_2O_3 is then determined by difference.

ALUMINA BY THE SODIUM HYDROXIDE-CITRATE-CYANIDE-8-QUINOLINOL-(GRAVIMETRIC) METHOD

I. Scope

This method covers the determination of alumina in concentrations from 20 to 70 percent. The relative standard deviation is 0.2 percent.

II. Principle of Method [5]

Silicon is separated with hydrofluoric acid. Titanium, iron and zirconium are separated with sodium hydroxide. The alkali salts and magnesium are removed with ammonium hydroxide and aluminum is then precipitated with 8-quinolinol in an ammoniacal solution containing ammonium citrate, hydrogen peroxide and sodium cyanide and weighed.

III. Interferences

Aluminum is separated from phosphorus, arsenic, fluorine and boron by precipitation with 8-quinolinol in an ammoniacal solution. Titanium, vanadium, chromium, molybdenum, tantalum, and niobium do not interfere if precipitation is made in ammoniacal solutions containing hydrogen peroxide. Iron, copper, cobalt, nickel and zinc form complex ions with cyanide in ammoniacal solutions containing alkali cyanide and do not interfere.

IV. Reagents

(a) Citric Acid Solution (500g/l). Dissolve 50g of citric acid monohydrate in 50 ml of warm H_2SO_4 (1+49), dilute to 100 ml with water, and filter.

(b) 8-quinolinol Solution (80g/l). Dissolve 8g of 8-quinolinol in 12 ml of acetic acid, dilute to 100 ml with water at 60 °C, cool and filter.

(c) Cyanide Solution (400g/l). Dissolve 40g of NaCN in 50 ml of warm water, dilute to 100 ml with water, and filter.

(d) Ammonium Hydroxide Solution. Bubble ammonia gas, using plastic tubing, into chilled distilled water in a polyethylene bottle until the solution is saturated.

(e) Hydrogen Peroxide-(3 percent).

(f) Wash Solution-(2 percent). Dissolve 20g each of ammonium tartrate, sodium cyanide, and ammonium chloride in 1-liter of water.

V. Procedure

(a) Transfer approximately 0.5g of sample (use a sample weight containing not more than 0.1g of aluminum) to a weighing bottle and dry for 2 hrs at 140 °C. Stopper the bottle and cool 1 hr in a desiccator. Lift the stopper momentarily, replace, and weigh the bottle and sample. Transfer the sample, without brushing to a 1-liter platinum dish. Reweigh the bottle.

(b) Add 15 ml of water, 10 ml of H_2SO_4 , 15 ml of HNO_3 , and 12 ml of HF to the covered dish and mix. Digest on a steam bath for 30 min with occasional stirring. Remove and wash the cover. Rinse the wall of the dish thoroughly and evaporate the solution to fumes of H_2SO_4 . Cool, rinse the wall of the dish, mix and again evaporate to fumes of H_2SO_4 . Cool, wash, mix and evaporate again. Complete removal of fluorine is essential. Cool, cautiously add 100 ml of warm water, and heat until the salts are in solution. Add paper pulp and filter through a 9-cm fine filter paper into a 600-ml beaker. Wash the paper thoroughly with hot water, and reserve the filtrate (A).

(c) Transfer the paper and residue to a platinum crucible and ignite at 600°C . Cool, add 2 ml of water, 5 ml of H_2SO_4 (1+1) and 5 ml of HF. Evaporate to fumes of H_2SO_4 on a sand bath. Cool, wash the wall of the crucible with water, mix and evaporate to fumes of H_2SO_4 . Cool, add 15 ml of water, mix, heat, and filter through a 7-cm fine filter paper containing paper pulp. Wash thoroughly with hot water. Combine the filtrate with the reserved filtrate (A).

(d) Transfer the paper and residue to a platinum crucible and ignite at 600°C . Cool, add 0.6g of Na_2CO_3 , cover and fuse over an open flame for 20 min. Cool, add 15 ml of water, and digest on a steam bath. Transfer the contents to a 250-ml Teflon beaker or a platinum dish, cover, and add 10 ml of H_2SO_4 (1+1). Heat on a steam bath to expel CO_2 . Remove and rinse the cover. Rinse the wall of the beaker or dish, add 5 ml of HF, mix and evaporate to fumes of H_2SO_4 . Cool, rinse the wall of the beaker with water, mix, and again evaporate to fumes. Cool, add 25 ml of water, heat, and combine the solution with reserved filtrate (A).

(e) Slowly add NaOH solution (40%) to the combined filtrates (A), while stirring, until the solution is nearly neutralized. Heat on a steam bath and pour contents slowly into a 600-ml Teflon beaker containing 100 ml of hot NaOH solution (10%). Heat the solution to boiling and boil for 2 min. Allow the precipitate to settle. Place a 9-cm medium filter paper in a plastic funnel and wash the paper with 50 ml of hot NaOH solution (5%). Discard the wash solution. Filter, collecting the hot NaOH solution in a platinum dish and wash well with hot NaOH solution (5%). Reserve the filtrate and washings (B).

(f) Dissolve the precipitate on the paper with 50 ml of hot H_2SO_4 (1+5), collecting the solution in the original beaker. Wash thoroughly with hot H_2SO_4 (1+99). Nearly neutralize the solution with NaOH. Heat gently and pour into 50 ml of hot NaOH (10%) solution. Heat to boiling and boil for 2 min, allow precipitate to settle. Filter the solution through a plastic funnel containing a 9-cm filter paper. Wash well with hot NaOH solution. Combine the filtrate and washings with the reserved filtrate (B) and evaporate to a volume of about 300 ml.

(g) Neutralize the solution with HCl and add a few drops excess. Transfer to a 600-ml beaker and digest on the steam bath. Adjust the solution to pH 7 with the specially prepared NH_4OH . Digest on a steam bath for 30 min. Check the pH of the solution with a pH meter and adjust to pH 7, if necessary. Filter the precipitate through a 11-cm medium filter paper and wash 5 times with hot, neutral NH_4Cl solution (2%). Discard the filtrate and washings.

(h) Transfer the paper and contents to a 300-ml Kjeldahl flask. Slowly add 10 ml of H_2SO_4 . Digest for about 15 min. Add 25 ml of HNO_3 and digest on a steam bath for 15 min. Heat over an open flame until most of the HNO_3 is expelled. Cautiously add 5 ml HNO_3 and heat to fumes

of H_2SO_4 . Continue the addition of HNO_3 and the heating until organic matter is destroyed. Cool, add 10 ml of water and evaporate until fumes of H_2SO_4 appear. Cool, add 90 ml of water, and digest on a steam bath. Filter the solution through a 9-cm fine filter paper catching the filtrate in a 600-ml beaker. Wash thoroughly with hot water. Discard the filter paper.

(i) Add 5 ml of the citric acid solution, and dilute to about 325 ml. Add 10 ml of H_2O_2 (3%), neutralize with the specially prepared NH_4OH and add 10 ml in excess. Add 5 ml of the NaCN solution and heat to 60°C . Remove from the heat, slowly add 25 ml of 8-quinolinol solution and stir vigorously for 15 min. (Use 0.22 ml of the acetic acid solution of 8-quinolinol per mg of aluminum, plus 2 ml excess). Avoid a large excess of the 8-quinolinol solution to prevent contamination of the aluminum precipitate with reagent. Digest on top of a steam bath for 15 min. Cool the solution to room temperature and filter, using moderate suction, through a weighed 35-ml fritted glass crucible of fine porosity. Wash 8 to 10 times with the cool wash solution and 5 to 10 times with hot water. Finally wash with cold water until the washings are colorless.

(j) Dry the crucible and contents at 140°C for 1.5 hr. Cool for 1 hr in a desiccator and weigh. Repeat, if necessary, to constant weight.

VI. Calculation

Calculate the percentage alumina as follows:

$$\text{Al}_2\text{O}_3, \text{ percent} = \frac{A \times 0.1109}{B} \times 100$$

where:

A = grams of aluminum oxyquinolinol, and

B = grams of sample used.

ALUMINA BY THE AMMONIUM HYDROXIDE-CUPFERRON-
(GRAVIMETRIC) METHOD

I. Scope

This method covers the determination of alumina in concentrations from 20 to 70 percent. The relative standard deviation is 0.36 percent.

II. Principle of Method [1]

Silicon is removed with hydrofluoric acid. An aliquot portion is treated with ammonium hydroxide and the impure Al_2O_3 is ignited and weighed. Another aliquot portion of the same volume is treated with cupferron and the precipitate is ignited and weighed. Phosphorus is determined in a third aliquot spectrophotometrically by the molybdenum blue method. The percent P_2O_5 in the sample is calculated. The weights of the oxides in the cupferron precipitate and the SiO_2 in the NH_4OH precipitate are deducted from the weight of the impure Al_2O_3 . The percentages of $\text{Al}_2\text{O}_3 + \text{P}_2\text{O}_5 + \text{Cr}_2\text{O}_3$ are determined and the alumina is obtained by deducting the percents of P_2O_5 and Cr_2O_3 .

III. Interferences

The amount of chromium in the NH_4OH precipitate is uncertain due to possible oxidation during solution of the sample. Any Cr_2O_3 in the precipitate may be partially oxidized during ignition. The separation of chromium may be assured by its oxidation to the sexivalent state after dissolution of the sample or it may be determined on another sample.

IV. Reagents

(a) Ammonium Hydroxide Solution. Proceed as directed in Section IV of 8-quinolinol method. See page 13.

(b) Cupferron Solution (60g/l). Dissolve 6g of cupferron in 80 ml of cold water, dilute to 100 ml, and filter. Prepare fresh as needed.

V. Procedure

(a) Transfer 2g of sample to a weighing bottle and dry for 2 hr at 140 °C. Stopper the bottle and cool 1 hr in a desiccator. Lift the stopper momentarily, replace, and weigh the bottle and sample. Transfer the sample, without brushing, to a 1-liter platinum dish. Reweigh the bottle.

(b) Add 25 ml of water, 15 ml of H_2SO_4 , 25 ml of HNO_3 , and 20 ml of HF to the covered dish and mix. Digest on a steam bath for 30 min, with occasional stirring. Remove and wash the cover. Rinse the dish thoroughly, evaporate the solution to fumes of H_2SO_4 and cool. Rinse the dish, mix, evaporate to fumes of H_2SO_4 , cool and repeat this operation. Cautiously add 100 ml of warm water, and heat until the salts are in solution. Add paper pulp, and filter through a 9-cm fine filter paper into a 400-ml beaker. Wash the paper thoroughly with hot water and reserve the filtrate (A).

(c) Transfer the paper and residue to a platinum crucible and ignite at 600 °C. Cool, add 1g of Na_2CO_3 , cover, and fuse over an open flame for 15 min. Cool and transfer the crucible and lid to a 250-ml Teflon beaker. Add 50 ml of water and heat on a steam bath to dissolve the fusion. Acidify the solution with H_2SO_4 (1+1) and add 1 ml excess. Remove the crucible and lid and rinse. Filter the solution through a 9-cm fine filter paper containing paper pulp and wash thoroughly with hot water. Combine the filtrate with reserved filtrate (A).

(d) Transfer the paper and residue to a platinum crucible and ignite at 600 °C. Cool, add 2 ml of water, 5 ml of H_2SO_4 (1+1) and 5 ml of HF. Evaporate to fumes of H_2SO_4 on an air bath. Cool, rinse the crucible with water and mix. Evaporate to fumes of H_2SO_4 . Cool, add 15 ml of water, and add the solution to the reserved filtrate (A).

(e) Warm a 500-ml volumetric flask at 110 °C, insert a glass tube, and remove moisture by means of a vacuum. Stopper the flask and cool to room temperature. Weigh the flask to the nearest milligram, using a second flask as a tare. Transfer the reserved filtrate (A) to the weighed flask, dilute to the mark with water, and mix. Reweigh the flask and solution, using the tare.

(f) Using a pipet, transfer 100 ml of the solution to a weighed 600-ml beaker containing a cover. Reweigh the covered beaker and solution immediately to the nearest milligram. Reserve aliquot (A) for precipitation with ammonium hydroxide.

(g) Using a pipet, transfer another 100 ml of the solution to a weighed 400-ml beaker containing a cover. Reweigh the covered beaker and solution immediately to the nearest milligram. Reserve aliquot (B) for precipitation with cupferron.

(h) Using pipets, transfer duplicate 4-ml aliquot portions of standard clay solution SRM 97A, and duplicate 15-ml aliquot portions of standard clay solution SRM 98A, to four 125-ml Erlenmeyer flasks. Reserve these aliquots (C) and (D), respectively for the determination of phosphorus spectrophotometrically.

PRECIPITATION WITH AMMONIUM HYDROXIDE
(Al_2O_3 , Fe_2O_3 , TiO_2 , ZrO_2 , P_2O_5 , V_2O_5 , Cr_2O_3)

(i) Dilute the reserved aliquot (A), above, to 350 ml with water and heat on a steam bath. Adjust the solution to pH 7.0 with the specially prepared NH_4OH . Heat to boiling and boil for 2 min. Allow the precipitate to settle. Check the pH of the solution, and adjust to pH 7.0, if necessary. Filter the precipitate through a 12.5 cm medium filter paper and wash 5 times with hot, neutral NH_4Cl solution (2 percent). Discard the filtrate.

(j) Transfer the paper and contents to the original beaker. Add 50 ml of hot HCl (1+1) and stir to dissolve the precipitate and to macerate the paper. Dilute to 350 ml with hot water. Adjust the solution to pH 7.0 with NH_4OH . Heat to boiling and boil for 2 min. Allow the precipitate to settle. Check the pH of the solution and filter on a medium filter paper. Do not allow the precipitate to run dry. Wash with 150 ml of hot, neutral NH_4Cl solution (2 percent), keeping the filter paper nearly filled. Drain thoroughly and transfer the paper and contents to a weighed platinum crucible.

(k) Dry and heat slowly to 600 °C, until the carbon is destroyed and finally heat at 1200 °C for 1 hr. Cover the crucible, transfer to a desiccator and weigh after 30 min. Reheat the crucible at 1200 °C for 3 min, cool in a desiccator and weigh. Reheat and reweigh, if necessary, to constant weight within 0.2 mg. The weighed precipitate contains Al_2O_3 , Fe_2O_3 , TiO_2 , ZrO_2 , P_2O_5 , V_2O_5 and some Cr_2O_3 .

(l) Add 4g of potassium pyrosulfate to the crucible and fuse over a low flame until a clear solution is obtained. Cool and transfer to a 150-ml beaker. Add 100 ml of H_2SO_4 (1+9) and heat on a steam bath to dissolve the melt. Remove and rinse the crucible. Evaporate the

solution to fumes of H_2SO_4 , cover and fume for 5 min. Cool, dilute to 125 ml with warm water and heat. Filter and wash well with hot water. Transfer the paper to a platinum crucible, dry and heat to 600 °C. Finally, heat the crucible at 1200 °C for 30 min. Cover the crucible, cool in a desiccator and weigh. Moisten the precipitate with 3 drops of water, add 3 drops of H_2SO_4 (1+1) and 5 ml of HF. Heat on an air bath to fumes of H_2SO_4 and continue heating to expel H_2SO_4 . Ignite the crucible over an open flame for 5 min with the cover open. Cool in a desiccator for 30 min and weigh. The difference in weight is the silica in the NH_4OH precipitate.

PRECIPITATION WITH CUPFERRON (Fe_2O_3 , TiO_2 , ZrO_2 , V_2O_5)

(m) Neutralize the reserved aliquot (B) with the specially prepared NH_4OH and then acidify with H_2SO_4 (1+1). Add 40 ml of H_2SO_4 (1+1), dilute to 175 ml with water, and stir. Cool the solution in an ice bath. Add slowly 25 ml of cold cupferron solution (6 percent) and stir. Digest in an ice bath for several min, add paper pulp and stir. Using moderate suction, filter the precipitate through a 11-cm fine filter paper supported by a platinum cone in a funnel. Wash thoroughly with chilled HCl (1+9) containing 25 ml of cupferron solution per liter. Transfer the paper and contents to a platinum crucible. Heat slowly at 600 °C until the carbon is destroyed.

(n) Cool and add 3g of $\text{K}_2\text{S}_2\text{O}_7$ and fuse over a low flame until a clear solution is obtained. Cool, transfer the crucible to 400-ml beaker and add 100 ml of H_2SO_4 (1+9). Heat to dissolve the fusion, remove and rinse the crucible. Dilute to 170 ml with H_2SO_4 (1+9) and add 5 ml of H_2SO_4 (1+1). Cool in an ice bath, add 25 ml of cold cupferron solution and add paper pulp. Filter and wash the precipitate as directed in the preceding paragraph. Transfer the paper and contents to a

weighed platinum crucible. Dry at 50 °C. Heat slowly to 600 °C until carbon is destroyed and finally heat at 1200 °C for 1 hr. Cover the crucible, transfer to a desiccator, and weigh after 30 min. Reheat the crucible at 1200 °C for 30 min, cool in a desiccator and weigh. Reheat and reweigh, if necessary, to constant weight within 0.2 mg. The weighed precipitate contains Fe_2O_3 , TiO_2 , and V_2O_5 . Reserve the oxides for the gravimetric determination of titania.

VI. Calculation

See page 28.

PHOSPHORUS

A useful procedure for the spectrophotometric determination of phosphorus involves the phosphomolybdenum blue complex. The method is based on the measurement of the blue color which develops when a heteropoly acid formed by phosphate and molybdate is reduced with hydrazine sulfate, hydroquinone, ferrous sulfate, or sodium bisulfite. Arsenic and germanium form yellow heteropoly acids which produce a blue color on reduction. Arsenic and germanium can be volatilized by fuming with hydrochloric and hydrobromic acids.

Phosphorus can also be determined by the phosphovanadomolybdate method which is based on the formation of a yellow complex, but the molybdenum blue method is the more sensitive.

A dependable gravimetric method for phosphorus involves its precipitation as ammonium phosphomolybdate and conversion to magnesium pyrophosphate.

PHOSPHORUS BY THE MOLYBDENUM-BLUE (PHOTOMETRIC) METHOD

I. Scope

This method covers the determination of phosphorus pentoxide in concentrations from 0.03 to 1.5 percent. The relative standard deviations at the low and high ranges are 0.002 and 0.1 percent, respectively.

II. Principle of Method [6]

Phosphorus as the ortho acid forms a blue complex with hydrazine sulfate and ammonium molybdate. Photometric measurement is made at 650 nm.

III. Interferences

Arsenic above 0.05 percent interferes and must be separated by volatilization with HBr. Germanium, if present, will be removed by treatment with HBr and HCl.

IV. Concentration Range

The recommended concentration range is from 0.001 to 0.04 mg of phosphorus per 50 ml of solution, using a 2-cm cell.

V. Stability of Color

The color develops within 5 min at 98 °C and is stable for at least 24 hr. Readings are usually made within 30 min.

VI. Reagents

(a) Ammonium Molybdate Solution (2 percent in 11 N H_2SO_4). Add 300 ml of H_2SO_4 (sp gr 1.84) to 500 ml of water and cool. Dissolve 20g of ammonium molybdate in the acid and dilute to 1 liter with water.

(b) Ammonium Molybdate - Hydrazine Sulfate Solution. Dilute 25 ml of the ammonium molybdate solution to 80 ml with water, add 10 ml of the hydrazine sulfate solution, and dilute to 100 ml with water. This solution is not stable and should be prepared as needed.

(c) Hydrazine Sulfate Solution (0.15 percent). Dissolve 1.5g of hydrazine sulfate in 1000 ml of water.

(d) Phosphorus, Standard Solution (A) (1 ml \approx 0.4 mg of P). Dissolve 1.8312g of Na_2HPO_4 in 200 ml of water, add 35 ml of HNO_3 (1+1), dilute to 1 liter in a volumetric flask with water and mix.

(e) Phosphorus, Standard Solution (B) (1 ml \approx 0.01 mg P). Using a pipet, transfer 5.0 ml of standard phosphorus solution (A) to a 200-ml volumetric flask, dilute to the mark with water and mix. Prepare this solution fresh as needed.

(f) Sodium Sulfite Solution (10 percent). Dissolve 100g of anhydrous Na_2SO_3 in 500 ml of water and dilute to 1 liter. Filter through a fine filter paper, but do not wash.

VII. Preparation of Calibration Curve

(a) Transfer 0, 0.5, 1.0, 2.0, 3.0 and 4.0 ml aliquot portions of standard phosphorus solution (B) to six 125-ml Erlenmeyer flasks.

(b) Add 5 ml of HNO_3 (1+1) and 3.0 ml of HClO_4 (60 percent). Evaporate to fumes and fume gently 3 or 4 min to remove HNO_3 .

(c) Cool and add 5 ml of HBr (1+4). Evaporate to fumes and fume gently to remove HBr . Cool, rinse the flask with 5 ml of water and evaporate to fumes. Cool somewhat, and add 10 ml of water and 15 ml of Na_2SO_3 solution. Heat to boiling and boil gently for 30 sec. Add 20 ml of the ammonium molybdate-hydrazine sulfate reagent, heat to 95-98 °C and digest at this temperature for 4 to 5 min. Then heat the solution just to boiling temperature, but do not boil. Cool rapidly to room temperature and transfer the solution to a 50-ml volumetric flask. Rinse the 125-ml flask with 2-ml portions of a dilute solution of the ammonium molybdate-hydrazine sulfate reagent (1+4) and transfer the washings to the 50-ml flask. Dilute to the mark with the diluted solution of the reagent and mix.

(d) Transfer a portion of the solution to a 2-cm absorption cell and measure the transmittance or absorbance at 650 nm, using water as a reference solution for 100 percent transmittance or zero absorbance. Plot the values obtained against milligrams of phosphorus per 50 ml of solution. (Note 1, see page 11.)

VIII. Procedure

(a) Proceed as directed in Section VII, b through d (above), with reserved aliquots C and D prepared in Section V, h of method for determination of Alumina by Ammonium Hydroxide-Cupferron. See page 17.

(b) From the value obtained, determine the milligrams of phosphorus present in 50 ml of the final solution.

(c) Carry a reagent blank through the entire procedure using the same amounts of all reagents but with the sample omitted.

IX. Calculation

Calculate the percentage of phosphorus pentoxide as follows:

$$\text{P}_2\text{O}_5, \text{ percent} = \frac{(A - B) \times 2.2914}{C \times 10}$$

where:

A = milligrams of phosphorus found in 50 ml of final test solution.

B = milligrams of phosphorus found in 50 ml of the reagent blank, and

C = grams of sample in 50 ml of the final test solution.

PHOSPHORUS BY THE ION-EXCHANGE (PHOTOMETRIC) METHOD

I. Scope

This method covers the determination of phosphorus pentoxide in concentrations from 0.03 to 1.5 percent.

II. Principle of Method [6, 7, 8]

After fusion of the sample with lithium metaborate, the fusion is stirred in water containing cation exchange resin. SiO_2 , B_2O_3 and P_2O_5 are eluted with water. Silica is separated with HF and phosphorus is determined spectrophotometrically.

III. Interferences

Arsenic and germanium interfere and must be separated by volatilization with HBr and HCl.

IV. Reagents

(a) Lithium Metaborate, Anhydrous, LiBO_2 .

(b) Resin, Cation Exchange, Dowex 50W-X4 (100-200 mesh).

V. Procedure

(a) Transfer 0.5g of clay SRM 97A or 0.3g of clay SRM 98A sample to a weighing bottle and dry for 2 hr at 140 °C. Cool for 1 hr in a desiccator, and weigh the bottle and sample after opening the bottle momentarily. Transfer the sample to glazed paper and reweigh the bottle. The difference is the weight of the sample. Add 2.5g of LiBO_2 to the glazed paper and mix thoroughly. Transfer to a graphite crucible and fuse in a muffle furnace at 950 °C for 20 min. Remove the crucible, and transfer the fusion to a 400-ml Teflon beaker containing 100 ml of water, and stir.

(b) Decant the aqueous solution into a Teflon beaker and reserve (A). Transfer the fusion to an agate mortar, grind to a powder, and transfer to the beaker containing the water (A). Add double the milliequivalent weight of dry cation resin Dowex 50W-X4 required for the aluminum and lithium. Stir for one hr and allow to settle. Decant the solution and reserve (B). Transfer the resin to a column containing a plug of

polyethylene wool and transfer the reserved solution (B) to the column. Adjust the flow rate to 35 to 45 drops per min. Elute with 400 ml of water and reserve the eluted solutions (C), which contain SiO_2 , B_2O_3 , and P_2O_5 . Elute with 25 ml of water and test for the presence of silicon spectrophotometrically.

(c) Add 10 ml of HClO_4 to the reserved solution (C) and evaporate the solution of standard 97A to a volume of about 225 ml or the solution of standard 98A to a volume of about 90 ml. Transfer the former to a 250-ml volumetric flask or the latter to a 100-ml volumetric flask. Dilute to mark with water, and mix.

(d) Using pipets, transfer a 10-ml aliquot portion of standard 97A or a 20-ml aliquot of 98A to a platinum crucible. Add 2.6 ml or 1.0 ml of HClO_4 to the crucibles containing 97A and 98A, respectively. Add 10 ml of HF and evaporate to fumes in an air bath. Cool, rinse the crucible, and mix. Again evaporate to fumes of HClO_4 . Proceed as directed in Section VII (c), (d), of the method for the determination of Phosphorus by the Molybdenum-Blue (Photometric). See page 23.

The value obtained for phosphorus is calculated as P_2O_5 and deducted from the impure Al_2O_3 precipitate obtained in the determination of alumina by the Ammonium Hydroxide-Cupferron-Gravimetric Method. See page 17.

Chromium is determined as Cr_2O_3 in a subsequent section and is also deducted from the impure Al_2O_3 . See page 46.

VI. Calculation

Calculate the percentage alumina as follows:

$$E = \frac{A - (B + C)}{D} \times 100$$

$$\text{Al}_2\text{O}_3, (\text{percent}) = E - (F + G)$$

where:

- A = grams of oxides in the NH_4OH precipitate in 100 ml aliquot portion,
B = grams of oxides in the cupferron precipitate in 100 ml aliquot,
C = grams of silica in the NH_4OH precipitate,
D = grams of sample in 100 ml aliquot,
E = percent $\text{Al}_2\text{O}_3 + \text{P}_2\text{O}_5 + \text{Cr}_2\text{O}_3$,
F = percent P_2O_5 , and
G = percent Cr_2O_3 .

TITANIA BY CUPFERRON (GRAVIMETRIC) METHOD

I. Principle of Method [1]

After separation of silica with HF, iron, titanium, zirconium, and vanadium are precipitated with cupferron. The ignited oxides are fused with $K_2S_2O_7$ and dissolved in H_2SO_4 . Iron, titanium, and zirconium are separated from vanadium by precipitation with NaOH solution. The precipitate is dissolved in HCl. Tartaric acid is added, and the solution is treated with H_2S . Iron, in the filtrate, is removed as FeS by ammoniacal precipitation with H_2S . Titanium and zirconium are precipitated with cupferron and the ignited oxides are weighed. After fusion with $K_2S_2O_7$, silica is dehydrated, determined, and the weight of the oxides corrected for silica. Hydrogen peroxide is added, zirconium is precipitated with $(NH_4)_2HPO_4$ and ignited to ZrP_2O_7 and weighed. The gravimetric value for TiO_2 is obtained by deducting the weight of the zirconium as ZrO_2 from the combined weight of $ZrO_2 + TiO_2$.

II. Reagents

(a) Cupferron (60g/l). Dissolve 6g of cupferron in 80 ml of cold water, dilute to 100 ml, and filter. Prepare fresh as needed.

(b) Diammonium Hydrogen Phosphate. $[(NH_4)_2HPO_4]$.

(c) Hydrogen Peroxide Solution. (H_2O_2) 30 volume percent.

(d) Hydrogen Sulfide. (H_2S) .

(e) Tartaric Acid. Reagent grade.

(f) Wash Solution. Dissolve 5g of NH_4Cl in 1 liter of water, add 15 ml of NH_4OH , and saturate with H_2S .

III. Procedure

(a) Fuse the reserved oxides of iron, titanium, zirconium, and vanadium, Section V, (n) of the Alumina-Cupferron-Gravimetric Method, with 3g of $K_2S_2O_7$. See page 22.

Cool and transfer the crucible to a 250-ml beaker. Add 100 ml of H_2SO_4 (1+9) and heat to dissolve the fusion. Wash and remove the crucible and lid.

(b) Nearly neutralize the solution with NaOH solution (20 percent). Pour slowly, with constant stirring, into 100 ml of NaOH solution (10 percent) contained in a platinum or Teflon container. Digest for 1 hr on a steam bath. Filter on a filter paper previously washed several times with NaOH solution (10 percent) and wash the precipitate with hot water. Discard the filtrate.

(c) Dissolve the precipitate by pouring 25 ml of hot HCl (1+2) onto the paper and wash with hot HCl (2+98). Add 5g of tartaric acid to the solution and dilute to 200 ml with water. Neutralize with NH_4OH and then add 2 ml of HCl per 100 ml of solution. Heat to boiling and saturate the solution with H_2S to precipitate any platinum. Allow to cool and filter through a fine filter paper. Wash with H_2SO_4 (1+9) saturated with H_2S . Discard the precipitate.

(d) Add NH_4OH to the filtrate until a black precipitate of iron sulfide forms and then add 5 ml in excess. Treat the solution with a rapid stream of H_2S for 5 min. Digest at about 40°C for 30 min and then filter through a fine filter paper. Wash with H_2S wash solution. Discard the filter and precipitate.

(e) Evaporate the filtrate to a volume of about 155 ml and acidify with H_2SO_4 . Add 45 ml of H_2SO_4 (1+1) and chill the solution in ice water. While stirring, add 25 ml of the cooled cupferron solution (60g/l). Add paper pulp and allow to settle for several mins. Insert a platinum cone in a funnel and filter the solution on a fine filter paper using gentle suction. Wash thoroughly with cool HCl (1+9) containing 25 ml of the cupferron solution.

(f) Transfer the paper to a weighed platinum crucible, cautiously char and heat at 1200°C for 15 min. Cool and

weigh as $\text{ZrO}_2 + \text{TiO}_2$. Repeat the heating and weighing to constant weight.

(g) To correct for small amounts of silica in the weighed oxides, fuse the oxides with 1g of $\text{K}_2\text{S}_2\text{O}_7$. Dissolve the fusion in 50 ml of H_2SO_4 (1+9) and evaporate the solution to fumes of H_2SO_4 . Cool, add 45 ml of water, and heat until salts have dissolved. Filter immediately through a 9-cm fine filter paper and wash with hot H_2SO_4 (1+9). Reserve the filtrate (A) and washings for the precipitation of zirconium. Transfer the paper and contents to a platinum crucible, char the paper, and ignite the crucible at 1200°C for 10 min. Cool and weigh. Add several drops of H_2SO_4 (1+1), 5 ml of HF (48 percent) and evaporate to dryness on an air bath. Ignite at 1000°C for 5 min, cool and weigh. The difference in weight is the weight of the silica in the oxides.

(h) Add 2 ml of H_2O_2 (30 percent) to the reserved filtrate (A) to oxidize titanium. Add 0.5g of $(\text{NH}_4)_2\text{HPO}_4$ to precipitate zirconium. Stir and digest overnight at about 40°C . Filter on a 9-cm fine filter paper containing paper pulp and wash with cold NH_4NO_3 solution (5 percent). Transfer the paper to a platinum crucible, and ignite at 1050°C . Cool, and fuse with 1g of $\text{K}_2\text{S}_2\text{O}_7$. Transfer the crucible and fusion to a 250 ml beaker. Dissolve the fusion in 50 ml of H_2SO_4 (1+9). Remove and rinse the crucible with H_2SO_4 (1+9). Add 2 ml of H_2O_2 (30 percent) and precipitate the zirconium as before. Transfer the paper to a weighed platinum crucible and ignite at 1050°C for 15 min. Cool and weigh the zirconium as ZrP_2O_7 .

IV. Calculation

Calculate the percentage titania as follows:

$$\text{TiO}_2, \text{ percent} = \frac{A - (B + C)}{D} \times 100$$

where:

A = grams of mixed oxides, $\text{TiO}_2 + \text{ZrO}_2 + \text{SiO}_2$,

B = grams of silica in the oxides,

C = grams of ZrO_2 , or g of ZrP_2O_7 found X 0.4647, and

D = grams of sample used.

TITANIA BY THE HYDROGEN PEROXIDE (PHOTOMETRIC) METHOD

I. Scope

This method covers the determination of titania in concentrations from 0.02 to 0.8 percent.

II. Principle of Method [9]

After separation of silica, hydrogen peroxide is added to form a yellow complex with titanium in a sulfuric acid solution. Spectrophotometric measurement is made at 410 nm.

III. Concentration Range

The recommended concentration range is from 0.15 to 3.0 mg of titanium per 100 ml of solution, using a 2-cm cell.

IV. Stability of Color

The color is stable for at least 1 hr.

V. Interferences

Interference from vanadium is negligible because of the low concentration present in clays. Fluoride is reduced to a noninterfering level by fuming with sulfuric acid.

VI. Reagents

(a) Hydrogen Peroxide Solution (H_2O_2)-30 volume percent.

(b) Titanium, Standard Solution (A) (1 ml \approx 1.0 mg Ti).

Dry 1g of NBS SRM 154a, Titanium Oxide, at 105 °C for 2 hr and cool. Transfer 0.8374g of the dried sample to a 250 ml Erlenmeyer flask. Add 10g of $(\text{NH}_4)_2\text{SO}_4$ and 25 ml of H_2SO_4 . Insert a short-stemmed glass funnel in the neck of the flask and heat cautiously to boiling while rotating the flask over an open flame. Continue the heating until solution is complete. Cool and rapidly pour the solution into 400 ml of cool water, while stirring. Rinse the flask 5 times with 10 ml portions of H_2SO_4 (1+1), and transfer to a 500-ml volumetric flask. Dilute to volume with H_2SO_4 (1+9), and mix.

(c) Titanium, Standard Solution (B) (1 ml \approx 0.1 mg Ti).

Using a pipet, transfer 20 ml of Solution (A) (1 ml \approx 1.0 mg

Ti) to a 200-ml volumetric flask, dilute to volume with H_2SO_4 (1+9), and mix.

VII. Preparation of Calibration Curve

(a) Calibration Solutions. Using pipets, transfer 5, 10, 20, 25 and 30 ml of Solution (B) (1 ml \approx 0.1 mg Ti) to 100-ml volumetric flasks. Add 90 ml of H_2SO_4 (1+9) and 4 drops of H_2O_2 (30 percent). Dilute to volume with H_2SO_4 (1+9), and mix.

(b) Reference Solution

Transfer 90 ml of H_2SO_4 (1+9) to a 100-ml volumetric flask, add 5 drops of H_2O_2 (30 percent), dilute to volume with H_2SO_4 (1+9), and mix. Using this solution, adjust the spectrophotometer to the initial setting, using a light band centered at 410 nm. While maintaining this photometric adjustment, take the photometric readings of the calibration solutions using a 2-cm cell. Plot the photometric readings of the calibration solutions against milligrams of titanium per 100 ml of solution.

VIII. Procedure

(a) Transfer 2g of sample to a weighing bottle and dry for 2 hrs at 140 °C. Transfer the sample to a platinum dish containing a cover. Add 25 ml of water, 15 ml of H_2SO_4 , 25 ml of HNO_3 and 25 ml of HF and heat gently to dissolve the sample. After dissolution, heat to fumes of H_2SO_4 . Cool, and cautiously add 100 ml of water. Transfer to a 500 ml volumetric flask, dilute to volume with water, and mix.

(b) Using a pipet, transfer a 50-ml aliquot to a 100 ml volumetric flask. Add 15 ml of H_2SO_4 (1+1), dilute to volume with water, and mix.

(c) Transfer a portion of the solution to a 2-cm cell and adjust the spectrophotometer to the initial setting using a light band centered at 410 nm.

(d) Add 4 drops of H_2O_2 (30 percent) to the solution remaining in the flask, mix thoroughly, and measure the absorbance or transmittance at 410 nm.

(e) From the calibration curve determine the number of milligrams of titanium per 100 ml of solution.

IX. Calculation

Calculate the percentage of titania as follows:

$$\text{TiO}_2, \text{ percent} = \frac{A \times 1.668}{B \times 10}$$

where:

A = milligrams of titanium in 100 ml of the final solution, and

B = grams of sample in 100 ml of the final solution.

IRON BY THE 1, 10-PHENANTHROLINE (PHOTOMETRIC) METHOD

I. Scope

This method covers the determination of iron oxide in concentrations from 0.03 to 4 percent.

II. Principle of Method [10]

The sample is dissolved in mixed acids and fumed to remove silica and HF. The pH is adjusted to 5.5-6.0, and 1,10-phenanthroline is added to form an orange-red complex with ferrous iron. Spectrophotometric measurement is made at 510 nm.

III. Interferences

Copper, nickel and zinc form complexes and consume 1,10-phenanthroline; however, sufficient reagent is added to complex the maximum amounts of these elements, in addition to the iron.

IV. Concentration Range

The recommended concentration range is 10 to 150 μg of iron per 100 ml of solution, using a 2-cm cell.

V. Stability of Color

The color is stable for at least 2 hr.

VI. Reagents

(a) Citric Acid Solution (500g/l). Dissolve 250g of citric acid in 300 ml of water and dilute to 500 ml with water.

(b) Hydroxylamine Hydrochloride Solution (100g/l). Dissolve 10g of hydroxylamine hydrochloride ($\text{NH}_2\text{OH} \cdot \text{HCl}$) in 80 ml of water and dilute to 100 ml. Prepare fresh as needed.

(c) Iron, Standard Solution (A) (1 ml = 0.30 mg Fe). Dissolve 150.4 mg of iron (NBS Standard 55E) in 50 ml of HCl (1+1). Heat gently to dissolve the iron. Cool, transfer to a 500-ml volumetric flask, dilute to volume with water, and mix.

(d) Iron, Standard Solution (B) (1 ml = 0.015 mg Fe). Using a pipet, transfer a 25 ml aliquot of iron solution (A) to a 500-ml volumetric flask, dilute to volume with water, and mix.

(e) 1, 10-Phenanthroline Solution (5g/l). Dissolve 0.5g of 1,10-phenanthroline in 80 ml of hot water and dilute to 100 ml with water. Prepare fresh as needed.

(f) Sodium Acetate Solution (400g/l). Dissolve 400g of sodium acetate ($\text{NaC}_2\text{H}_3\text{O}_2 \cdot 3\text{H}_2\text{O}$) in 600 ml of water. Dilute to 1 liter.

VII. Preparation of Calibration Curve

(a) Calibration Solutions.

(1) Transfer 0.0, 1, 3, 5 and 10 ml of iron solution (B) (1 ml \approx 0.015 mg Fe) to six 150-ml beakers. Add 5 ml of citric acid solution and dilute to 50 ml with water.

(2) Add successively 2 ml of the 1,10-phenanthroline solution, 2 ml of the hydroxylamine hydrochloride solution, and 10 ml of the sodium acetate solution, mixing after each addition. Adjust the pH to 5.5-6.0 with NH_4OH (1+3). Transfer the solution to a 100-ml volumetric flask, dilute to approximately 95 ml with water and mix. Place the flask in a water bath at about 70 °C for 30 min. Remove from the bath, cool to room temperature, dilute to volume with water, and mix.

(b) Spectrophotometry. Fill the reference cell with water and adjust the spectrophotometer to the initial setting using a light band centered at approximately 515 nm. While maintaining this adjustment, take the photometric readings of the calibration solutions using a 2-cm cell.

(c) Calibration Curve. Plot the net photometric readings of the calibration solutions against milligrams of iron per 100 ml of solution.

VIII. Procedure

(a) Using pipets, transfer a 10 ml aliquot from 500 ml solution of SRM 97A, or a 4 ml aliquot from 500 ml solution of SRM 98A prepared in Section VIII (a), of Titania by the Hydrogen Peroxide (Photometric) Method to a 150-ml beaker. See page 35. Add 5 ml of citric acid

solution and dilute to about 50 ml. Proceed as directed in Section VII (a) 2 and (b).

(b) From the value obtained, read from the calibration curve the number of milligrams of iron present in 100 ml of solution.

(c) Determine the blank correction by following the same procedure and using the same amounts of all reagents, with the sample omitted.

IX. Calculation

Calculate the percentage of iron oxide as follows:

$$\text{Fe}_2\text{O}_3, \text{ percent} = \frac{(A - B) \times 1.4298}{C \times 10}$$

where:

A = milligrams of iron in 100 ml of the final solution,

B = milligrams of iron in 100 ml of the blank, and

C = grams of sample in 100 ml of the final solution.

IRON BY $\text{SnCl}_2 - \text{K}_2\text{Cr}_2\text{O}_7$ (VOLUMETRIC) METHOD

I. Scope

This method covers the determination of iron oxide in concentrations from 0.03 to 4 percent.

II. Principle of Method [11]

The sample is fused with lithium metaborate and leached in hydrochloric acid. Iron is reduced with SnCl_2 and titrated with a standard solution of $\text{K}_2\text{Cr}_2\text{O}_7$.

III. Interferences

None of the elements present interfere.

IV. Apparatus

Graphite crucible (1 in. X 2.5 in.)

V. Reagents

(a) Mercuric Chloride Solution (saturated). Dissolve 80g of HgCl_2 in 1 liter of hot water, stir and cool to room temperature.

(b) Potassium Dichromate, Standard Solution (0.01N or 1 ml \approx 0.5585 mg Fe). Dissolve 0.4904g of $\text{K}_2\text{Cr}_2\text{O}_7$ (SRM 136c), in about 800 ml of water in a 1-liter volumetric flask. Dilute to volume and mix. This is a primary standard and the theoretical titer of the solution can be used or it may be standardized against high purity iron.

(c) Potassium Permanganate Solution (approximately 0.1N). Dissolve 0.32g of potassium permanganate (KMnO_4) in 100 ml of water.

(d) Sodium Diphenylamine Sulfonate Indicator Solution (2g/l). Dissolve 0.20g of sodium diphenylamine sulfonate in 100 of water.

(e) Stannous Chloride Solution (50g/l). Dissolve 5g of $\text{SnCl}_2 \cdot 2\text{H}_2\text{O}$ in 10 ml of HCl and dilute to 100 ml with water.

(f) Sulfuric-Phosphoric Acid Mixture. Slowly add 150 ml of H_2SO_4 to 500 ml of water, while stirring,

and cool to room temperature. Add 150 ml of H_3PO_4 to the cool solution, dilute to 1 liter with water, and mix.

VI. Procedure

(a) Transfer approximately 0.25g of sample to a weighing bottle and dry for 2 hr at 140 °C. Stopper the bottle and cool 1 hr in a desiccator. Lift the stopper momentarily, replace, and weigh the bottle and sample. Transfer the sample, without brushing, to a larger weighing bottle containing 1.25g of lithium metaborate and weigh the empty bottle.

(b) Mix the sample and lithium metaborate for 10 min. Transfer to a graphite crucible. Dry wash the bottle with a small portion of lithium metaborate and transfer to the crucible. Heat the crucible and contents in an electric muffle furnace at 950 °C for 15 min. While stirring, pour the hot fusion into 30 ml of HCl (1+3) in a 250-ml beaker. Cover the beaker and heat until the fusion is dissolved.

(c) Cool and add 0.1N KMnO_4 solution dropwise until a distinct pink color appears. Heat to boiling, boil for 1 min to expel chlorine, add SnCl_2 solution, drop by drop and with stirring, until the yellow color of ferric chloride disappears. Add one drop in excess, but no more. Wash the wall of the beaker and quickly cool the solution in an ice bath. Add at one stroke 10 ml of the saturated solution of mercuric chloride, stir, and wash the wall of the beaker with cool water. Allow to stand 2 to 5 min, with occasional stirring. Add 100 ml of cool water, 20 ml of H_2SO_4 - H_3PO_4 mixture, and 5 drops of sodium diphenylamine sulfonate indicator. While stirring, titrate the iron with standard $\text{K}_2\text{Cr}_2\text{O}_7$ solution to a permanent reddish-violet color that persists for 1 min.

(d) Make a blank determination, following the same procedure and using the same amounts of all reagents.

VII. Calculation

Calculate the percentage of iron oxide as follows:

$$\text{Fe}_2\text{O}_3, \text{ percent} = \frac{(A - B) C \times 0.05585 \times 1.4298}{D} \times 100$$

where:

A = milliliters of $\text{K}_2\text{Cr}_2\text{O}_7$ solution required to titrate the sample,

B = milliliters of $\text{K}_2\text{Cr}_2\text{O}_7$ solution required to titrate the blank,

C = normality of the $\text{K}_2\text{Cr}_2\text{O}_7$ solution, and

D = grams of sample used.

ZIRCONIA BY THE PYROCATECHOL VIOLET (PHOTOMETRIC) METHOD

I. Scope

This method covers the determination of zirconium in concentrations from 0.005 to 0.5 percent.

II. Principle of Method [12, 13, 14]

Zirconium is extracted with trioctylphosphine oxide (TOPO), dissolved in cyclohexane, and forms a green complex with pyrocatechol violet which is dissolved in absolute alcohol. The photometric measurement is made at 655 nm.

III. Concentration Range

The recommended concentration range is from 4 to 40 μg of zirconium per 25 ml of solution, using a 2 cm cell.

IV. Stability of Color

The color tends to fade on standing. Photometric measurements should be made within 30 min after the addition of the pyrocatechol violet solution.

V. Interferences

Iron and titanium interfere but are removed by backwashing the TOPO extract with HNO_3 .

VI. Reagents

(a) Pyrocatechol Violet Solution. Dissolve 10 mg of pyrocatechol violet in 20 ml of absolute ethyl alcohol.

(b) Trioctylphosphine Oxide (TOPO) (0.1 Molar). Dissolve 3.86g of TOPO in 100 ml of cyclohexane.

(c) Zirconium Perchlorate, Standard Solution (A) (1 ml \approx 1.0 mg Zr). Transfer 1.767g of $\text{ZrOCl}_2 \cdot 8\text{H}_2\text{O}$ to a 300-ml Kjeldahl flask and dissolve in 25 ml of water. Add 40 ml of HClO_4 and evaporate to heavy fumes. Cool, add 100 ml of water, and mix. Transfer to a 500 ml volumetric flask, dilute to volume with water, and mix.

(d) Zirconium Perchlorate, Standard Solution (B) (1 ml \approx 4 μg Zr). Transfer a 2.0 ml aliquot of zirconium solution (A) to a 500-ml volumetric flask, and add 40 ml of

HClO₄. Dilute to volume with water and mix. Prepare fresh as needed.

VII. Preparation of Calibration Curve

(a) Transfer 0.0, 1, 2, 5, and 10-ml of zirconium solution (B) (1 ml \approx 4 μ g Zr) to five 60 ml separatory funnels.

(b) Dilute to 25 ml with HNO₃ (1+1). Add 5 ml of 0.1M TOPO solution, stopper the funnel, and shake for 15 min on a mechanical shaker. Allow the layers to separate and discard the lower acid layer. Add 25 ml of HNO₃ (1+1) and shake for 15 min. Allow the layers to separate and discard the acid layer.

(c) Using a pipet, transfer 2 ml of the TOPO extract to a dry 25-ml volumetric flask. Add 10 ml of absolute alcohol, and 1.5 ml of the pyrocatechol violet solution. Add 5 ml of pyridine to neutralize any acid in the TOPO extract. Dilute to volume with absolute alcohol, and mix.

(d) Fill the reference cell with water and adjust the spectrophotometer to the initial setting using a light band centered at 655 nm. While maintaining this adjustment, take the photometric readings of the calibration solutions in a 2-cm cell within 30 min after addition of the pyrocatechol violet solution.

(e) Plot the photometric readings of the calibration solutions against micrograms of zirconium per 25 ml of solution.

VIII. Procedure

(a) Transfer 0.1g of sample to a weighing bottle and dry for 2 hrs at 140 °C. Cool, and weigh. Mix with 0.5g of anhydrous lithium metaborate and transfer the mixture to a graphite crucible. Heat the crucible and contents in an electric muffle furnace at 950 °C for 15 min. Swirl the melt and transfer to a 400-ml beaker containing 50 ml of

HNO_3 (1+19), while stirring. Transfer the solution to a 100 ml volumetric flask and wash with 47.5 ml of HNO_3 (sp gr 1.42). Dilute to volume with water, and mix.

(b) Using a pipet, transfer a 20-ml aliquot of the solution to a 60 ml separatory funnel and proceed as directed in Section VII, (b) through (d).

(c) From the value obtained, determine the micrograms of zirconium present in 25 ml of solution.

IX. Calculation

Calculate the percentage of zirconia as follows:

$$\text{ZrO}_2, \text{ percent} = \frac{A \times 1.35}{B \times 10^4}$$

where:

A = micrograms of zirconium in 25 ml of the final test solution,

B = grams of sample in 25 ml of the final test solution.

CHROMIUM OXIDE BY THE DIPHENYLCARBAZIDE (PHOTOMETRIC)
METHOD

I. Scope

This method covers the determination of chromium oxide in the range of 0.02 to 0.5 percent. The relative standard deviation is 2 percent.

II. Principle of Method [15]

Chromium is oxidized to the sexivalent state with ammonium peroxydisulfate and silver nitrate. A red-violet complex is then formed with diphenylcarbazide. The photometric measurement is made at 540 nm.

III. Interferences

Iron interferes, but is removed with NaOH. Vanadium in amounts present in clays does not interfere if the solution is allowed to stand for 10 to 15 min after addition of diphenylcarbazide.

IV. Stability of Color

The chromium diphenylcarbazide complex develops almost immediately, but may fade after a short time. Spectrophotometric measurement should be made within 15 to 30 min after addition of diphenylcarbazide.

V. Concentration Range

The recommended concentration range is 0.004 to 0.06 mg of chromium in 100 ml of solution, using a 2-cm cell.

VI. Reagents

(a) Ammonium Peroxydisulfate Solution (100g/l).

Dissolve 10g of ammonium peroxydisulfate $[(\text{NH}_4)_2\text{S}_2\text{O}_8]$ in 90 ml of water. Prepare fresh as needed.

(b) Diphenylcarbazide Solution (0.32 percent). Dissolve 0.320g in 50 ml of ethyl acetate. Transfer the solution to a 100-ml volumetric flask, dilute to volume with ethyl acetate, and mix. Prepare fresh as needed.

(c) Potassium Dichromate, Standard Solution (A)
(1 ml \approx 1 mg Cr). Dissolve 2.829g of $\text{K}_2\text{Cr}_2\text{O}_7$ (NBS

Standard 136c) in 500 ml of water contained in a 1-liter volumetric flask. Dilute to volume with water, and mix.

(d) Potassium Dichromate, Standard Solution (B) (1 ml \approx 0.005 mg Cr). Using a pipet, transfer a 10-ml aliquot of chromium solution (A) to a 2-liter volumetric flask, dilute to volume with water, and mix.

(e) Silver Nitrate Solution (2.5g/l). Dissolve 1.25g of AgNO_3 in 500 ml of water.

(f) Sodium Hydroxide Solution (100g/l). Dissolve 50g of NaOH in 250 ml of water, cool, and dilute to 500 ml.

VII. Preparation of Calibration Curve

(a) Transfer 0.0, 1, 3, 5, 7, and 10 ml of chromium solution (B) (1 ml \approx 0.005 mg Cr) to six 250-ml beakers and add 4 ml of H_2SO_4 (1+1).

(b) Dilute to about 50 ml with water. Add 10 ml of AgNO_3 solution and heat to boiling. Add 5 ml of ammonium peroxydisulfate solution and boil for 25 min. Cool rapidly and transfer to a 100-ml volumetric flask. Dilute to about 90 ml with water and add 2 ml of diphenylcarbazide solution. Dilute to volume with water, and mix.

(c) Fill the reference cell with water and adjust the spectrophotometer to the initial setting using a light band centered at 540 nm. While maintaining this adjustment, take the photometric readings of the calibration solutions in a 2-cm cell within 15 to 30 min after addition of the diphenylcarbazide solution.

(d) Plot the photometric readings of the calibration solutions against milligrams of chromium per 100 ml of solution.

VIII. Procedure

(a) Transfer slowly and with stirring, a 50-ml aliquot from the 500 ml master solution prepared in Section VIII (a) of the Titania by the Hydrogen-Peroxide (Photometric) Method, see page 35, to 150 ml of NaOH

solution (10 percent) contained in a Teflon beaker or platinum dish. Digest on a steam bath for 1 hr and heat to boiling. Allow the precipitate to settle, and filter through a 11-cm medium filter paper previously washed with NaOH (10 percent). Wash the paper and precipitate 5 times with hot water. Using litmus paper as the indicator, acidify the filtrate with H_2SO_4 (1+1) and add 20 ml in excess. Evaporate the solution to about 80 ml, cool and transfer to a 100-ml volumetric flask. Dilute to volume with water, and mix.

(b) Using a pipet, transfer a 20-ml aliquot of the solution to a 250-ml beaker and proceed as directed in Section VII (b) and (c).

(c) From the value obtained, determine the milligrams of chromium present in 100 ml of solution.

(d) Determine the blank correction by following the same procedure and using the same amounts of all reagents, but with the sample omitted.

IX. Calculation

Calculate the percentage of chromium oxide as follows:

$$\text{Cr}_2\text{O}_3, \text{ percent} = \frac{(A - B) \times 1.4616}{C \times 10}$$

where:

A = milligrams of chromium in 100 ml of the final test solution,

B = milligrams of chromium in 100 ml of the blank, and

C = grams of sample in 100 ml of the final test solution.

PART II

ATOMIC ABSORPTION AND FLAME EMISSION SPECTROMETRY

The use of atomic absorption and flame emission spectrometry as analytical techniques are firmly established. Their applications to the determination of the alkali metals such as lithium, sodium and potassium and to the determination of the alkaline-earth metals such as magnesium, calcium, strontium and barium, all important constituents of clay materials, are simple, rapid and reliable.

This section presents practical and well-established spectrometric methods for the analyst and includes a procedure for dissolution of the sample, interferences, reagents, preparation of calibration curves, and clear stepwise directions for performing the analyses.

The instrumental system used in this work is outlined and described in detail.

INSTRUMENTATION

The instrumental system used in this work consists of the following eight basic units, (1) a 0.5m monochromator with exchangeable gratings having 1180 grooves per mm blazed for 3000 and 7500 Å and a dispersion of 1.6 Å per mm of slit width, (2) adjustable flame housing with a total consumption nebulizer burner with O₂ - H₂ gases or premixed air-acetylene and nitrous oxide-acetylene burner, (3) gas flow meters and pressure regulators, (4) multiplier phototube (EMI 9558 AQ7), (5) 0 to 2100 V multiplier phototube power supply, (6) selective amplifier and synchronous detector, (7) recorder, and (8) digital readout.

The atomic absorption instrument is similar to the flame emission equipment except that the mechanical chopper is placed between the hollow-cathode lamp and the nebulizer burner.

PROCEDURE FOR DISSOLUTION OF CLAY MATERIALS FOR FLAME
EMISSION AND ATOMIC ABSORPTION ANALYSES

1. Transfer 0.2g of sample, dried for 2 hr at 140 °C, to a Teflon-lined pressure container [16].
2. Add 1 drop each of HCl and HNO₃ and 4 ml of HF.
3. Seal the container and place in an oven at 125 °C for 2 hrs.
4. Remove from the oven, cool, open the container and transfer the solution, to a platinum dish.
5. Add 5 ml of HF and 5 ml of HClO₄.
6. Heat on a hot plate to dense fumes of HClO₄.
7. Cool, add 1 ml of HCl and 10 ml of H₂O.
8. Warm the sample to dissolve the salts.
9. Cool and transfer the solution to a 25-ml volumetric flask, dilute to volume and mix.
10. Transfer the solution to a plastic bottle for subsequent use.

I. Scope

This flame emission method is applicable to the determination of 0.2 to 1 μg of lithium per milliliter of solution in clay materials. In this range, the relative standard deviation of the method is 1 percent.

II. Principle of Method

Lithium is excited to emission in an oxygen-hydrogen flame and is then determined by measuring the radiation intensity of the light emitted at a wavelength of 6708 Å.

III. Interferences

The resonance line of lithium at 6708 Å is relatively free of spectral line interferences. However, elements such as sodium, calcium and strontium produce a continuum or unresolved band structure in this region of the spectrum. The CaO-CaOH and SrOH bands may cause an increase in flame background. The magnitude of this interference will depend upon the resolution of the monochromator. To make the appropriate background correction it is necessary to scan the wavelength region of the lithium line.

IV. Reagents

(a) Lithium, Standard Solution A (1 ml \approx 1.000 mg Li). Dry approximately 1 gram of reagent grade Li_2CO_3 at 110 °C for 2 hours. Cool in a desiccator. Transfer 0.5324 + 0.0002g of the dry Li_2CO_3 to a 100-ml volumetric flask. Add 60 ml of water and 3 ml of HCl to dissolve the Li_2CO_3 . Swirl the solution to expel CO_2 , dilute to volume with water, and mix.

(b) Lithium, Standard Solution B (1 ml \approx 20 μg Li). Using a pipet, transfer 2 ml of Solution A (1 ml \approx 1.000 mg Li) to a 100-ml volumetric flask, dilute to volume with water, and mix.

V. Preparation of Calibration Curve

1. Using pipets, transfer 1, 2, 3, 4 and 5 ml of Solution B (1 ml \approx 20 μ g Li) to 100 ml volumetric flasks, dilute to volume with water, and mix.
2. Turn on the operating switches of the flame emission spectrometer.
3. Set the voltage to the multiplier phototube at 1000 v.
4. Install the total consumption burner in the flame housing.
5. Open the valves to the oxidant (oxygen) and fuel (hydrogen) cylinders and set the tank regulators at 30 and 20 psi, respectively.
6. Ignite the burner and adjust the pressure and/or flow rates recommended by the manufacturer.
7. Set the wavelength dial of the monochromator to 6807 Å and the slit width at 50 μ .
8. Aspirate the lithium solution with the highest concentration (1 ml \approx 1 μ g Li) from the series prepared in Step 1.
9. Adjust the gain of the operational amplifier to give 85 percent of full scale, as indicated on the recorder.
10. While aspirating, set the wavelength dial of the monochromator at 6804 Å and scan the lithium line at 6807 Å at a rate of 10 Å/min.
11. Repeat step 10 with each calibration solution, in turn, and record its radiation intensity. Aspirate water between each standard solution and record the radiation intensity.
12. Plot the radiation intensity values, corrected for background, against micrograms of lithium per milliliter on rectangular coordinate paper.

VI. Procedure

1. Transfer to two 25-ml volumetric flasks, A and B, two equal test portions containing 10 to 15 μg of lithium.
2. Dilute test portion A to volume with water and mix.
3. To test portion B, add 5 μg of lithium, dilute to volume with water, and mix.
4. Aspirate test portions A and B, and measure the radiation intensity of each. Aspirate water after each test portion.
5. From the calibration curve, determine the lithium concentration as $\mu\text{g}/\text{ml}$.
6. Subtract the concentration, $\mu\text{g}/\text{ml}$, that was added to test portion B. If the concentrations of the two test portions agree, proceed to step 7. If the recoveries do not agree, correct by the standard addition method (Note 1) and proceed to step 7.
7. Calculate the percent lithium as follows:

$$\text{Li}_2\text{O, weight percent} = \frac{C \times Z \times 2.1528}{W \times 10^4}$$

where:

C = lithium concentration, $\mu\text{g}/\text{ml}$

Z = dilution factor

W = test portion of solid sample, grams.

Note 1 - See, Menis, O. and Rains, T. C. Sensitivity, Detection Limits, Precision and Accuracy in Flame Emission and Atomic Absorption Spectrometry. Chapter II pp 47-77 in Analytical Flame Spectroscopy-Selected Topics. Radu Mavrodineanu, Editor. MacMillan and Co. Ltd. (1970), New York.

I. Scope

This flame emission method is applicable to the determination of 1 to 5 μg of sodium per milliliter of solution in clay materials. In this range, the relative standard deviation of the method is 1 percent.

II. Principle of Method

Sodium is excited to emission in an oxygen-hydrogen flame and is then determined by measuring the radiation intensity of the light emitted at a wavelength of 5890 Å.

III. Interferences

The resonance line of sodium at 5890 Å shows very little spectral interference from other elements. Because of the high sensitivity of sodium emission, the flame background, due to a continuum or unresolved band structure, is very small when the resolution of the monochromator is better than 1 Å. The major sources of errors are from the contamination of sodium during the preparation of the sample, and from air-borne dust particles during the flame emission measurements. Extreme care must be taken in handling the sample and disposable or clean gloves must be worn at all times.

IV. Reagents

(a) Sodium, Standard Solution A (1 ml \approx 10.0 mg Na). Dry approximately 5 grams of reagent grade NaCl at 110 °C for 2 hrs. Cool in a desiccator. Transfer 2.542 \pm 0.001g of the dry NaCl to a 100-ml volumetric flask, dissolve in 50 ml of water and then add 10 ml of ultra pure 1N HCl. Dilute to volume with water, and mix.

(b) Sodium, Standard Solution B (1 ml \approx 100 μg Na). Using a pipet, transfer 1 ml of Solution A (1 ml \approx 10.0 mg Na) to a 100-ml volumetric flask, dilute to volume with water, and mix.

V. Preparation of Calibration Curve

1. Using pipets, transfer 1, 2, 3, 4 and 5 ml of Solution B (1 ml \approx 100 μ g Na) to 100-ml volumetric flasks, dilute to volume with water, and mix.

2-6. Proceed as directed in steps 2 to 6 of Section V of the procedure for lithium. See page 53.

7. Set the wavelength dial of the monochromator to 5890 Å and slit width at 50 μ

8. Aspirate the sodium solution with the highest concentration (1 ml \approx 5 μ g Na) from the series prepared in Step 1.

9. Adjust the gain of the operational amplifier to give 85 percent of full scale, as indicated on the recorder.

10. While aspirating, set the wavelength dial of the monochromator at 5885 Å and scan the sodium line at 5890 Å at a rate of 10 Å/min.

11. Repeat step 10 with each calibration solution, in turn, and record the radiation intensity. Aspirate water between each standard solution and record the radiation intensity.

12. Plot data as directed in step 12 of the procedure for lithium. See page 53.

VI. Procedure

1. Transfer to two 25-ml volumetric flasks, A and B, two equal test portions containing 25 to 50 μ g of sodium.

2. Dilute test portion A to volume with water and mix.

3. To test portion B, add 25 μ g of sodium, dilute to volume with water and mix.

4-6. Proceed as directed in steps 4 to 6 of Section VI of the procedure for lithium. See page 54.

7. Calculate the percent sodium as follows:

$$\text{Na}_2\text{O, weight percent} = \frac{C \times Z \times 1.348}{W \times 10^4}$$

where:

C = sodium concentration, $\mu\text{g/ml}$

Z = dilution factor

W = test portion of solid sample, grams.

POTASSIUM BY FLAME EMISSION SPECTROMETRY

I. Scope

This flame emission method is applicable to the determination of 2 to 10 μg of potassium per milliliter of solution in clay materials. In this range, the relative standard deviation of the method is 1 percent.

II. Principle of Method

Potassium is excited to emission in an oxygen-hydrogen flame and is then determined by measuring the radiation intensity of the light emitted at a wavelength of 7665 Å.

III. Interferences

The potassium doublet at 7665 and 7699 Å suffers seriously from the spectral interference of rubidium which emits strongly at 7800 Å. To overcome this interference, it is necessary to have an instrument with good dispersion and resolution. Another source of interference results from the enhancement of the emission of potassium when rubidium or cesium are present. This is due to the repression of the ionization of potassium by electrons produced by these elements in the flame. This enhancement can be corrected by means of the standard addition method.

IV. Reagents

(a) Potassium Standard Solution A (1 ml \approx 10.0 mg K). Dry approximately 2 grams of reagent grade KCl at 110 °C for 2 hrs. Cool in a desiccator. Transfer 1.907 \pm 0.001g of the dry KCl to a 100-ml volumetric flask, dissolve in 50 ml of water and then add 10 ml of ultra pure 1N HCl. Dilute to volume with water, and mix.

(b) Potassium, Standard Solution B (1 ml \approx 100 μg K). Using a pipet, transfer 1 ml of Solution A (1 ml \approx 10.0 mg K) to a 100-ml volumetric flask, dilute to volume with water, and mix.

V. Preparation of Calibration Curve

1. Using pipets, transfer 2, 4, 6, 8 and 10 ml of Solution B (1 ml \approx 100 μ g K) to 100 ml volumetric flasks, dilute to volume with water and mix.

2-6. Proceed as directed in steps 2 to 6 of Section V of the procedure for lithium. See page 53.

7. Set the wavelength dial of the monochromator to 7665 Å and the slit width at 50 μ .

8. Aspirate the potassium solution with the highest concentration (1 ml \approx 10 μ g K) from the series prepared in Step 1.

9. Adjust the gain of the operational amplifier to give 85 percent of full scale, as indicated on the recorder.

10. While aspirating, set the wavelength dial of the monochromator at 7660 Å and scan the potassium line at 7665 Å at a rate of 10 Å/min.

11. Repeat step 10 with each calibration solution, in turn, and record its radiation intensity. Aspirate water between each standard solution and record the radiation intensity.

12. Plot data as directed in step 12 of the procedure for lithium. See page 53.

VI. Procedure

1. Transfer to two 25-ml volumetric flasks, A and B, two equal test portions containing 50 to 100 μ g of potassium.

2. Dilute test portion A to volume with water and mix.

3. To test portion B, add 50 μ g of potassium, dilute to volume with water and mix.

4-6. Proceed as directed in steps 4 to 6 of Section VI of the procedure for lithium. See page 54.

7. Calculate the percent potassium as follows:

$$K_2O, \text{ weight percent} = \frac{C \times Z \times 1.205}{W \times 10^4}$$

where:

C = potassium concentration, $\mu\text{g/ml}$

Z = dilution factor

W = test portion of solid sample, gram.

I. Scope

This atomic absorption method is applicable to the determination of 0.4 to 2.4 μg of magnesium per milliliter of solution in clay materials. In this range, the relative standard deviation of the method is 2 percent.

II. Principle of Method

In atomic absorption spectrometry, the analyte of the test portion is converted to an atomic vapor, and the absorption of light by the ground state atoms in the vapor phase is measured at the specific wavelength which is characteristic of the element. The light source is generally a hollow-cathode lamp adjusted to give an intense and sharp resonance line. Many parameters affect the production of atoms in flame gases. For many elements, the number of ground state resonance atoms will depend not only on the temperature of the flame, but on whether the fuel mixture results in a reducing or oxidizing flame. The concentration of free atoms often varies with the height of observation above the burner tip.

III. Interferences

The interferences in atomic absorption spectrometry are spectral, physical and chemical in nature. Usually spectral interferences are associated with the source of radiation—the hollow-cathode lamp. The filler gas in a hollow-cathode lamp, as well as impurities in the cathode material, will emit its characteristic radiation which may interfere with the analytical line. Spectral interferences from the source can be controlled by determining the constituents within the lamp and by selecting the proper optical condition to minimize or eliminate this interference.

Physical interferences may alter processes within the flame gases. These include aspiration, nebulization, solvent evaporation and vaporization. By selecting the

proper oxidant-fuel gas and burner system, these types of interferences can be minimized.

The greatest number of interferences in atomic absorption are of a chemical nature. Chemical interferences affect the analyte and may occur in the vapor, solid or liquid phase within the flame. Reactions occurring in the vapor phase may suppress or enhance the dissociation of the molecular species into atomic vapor. This is referred to as the condensed-phase interference. To control this type of interference, the oxidant-fuel and nebulizer-burner system must be carefully regulated. To overcome condensed phase types of interference, protective chelating agents can be used. Another approach for minimizing these interferences is by using high temperature flames such as the nitrous oxide-acetylene mixture; however, high temperature flames produce excessive ionization, which is undesirable. Chemical interferences can be overcome most satisfactorily by premixing the oxidant, air-nitrous oxide, in the proper ratio to provide the proper flame temperature.

IV. Reagents

(a) Magnesium, Standard Solution A (1 ml \approx 10.0 mg Mg). Transfer 1.0000 \pm 0.0005g of high purity magnesium metal to a 150-ml beaker. Add 50 ml of water. Slowly add 6 ml of HCl. After dissolution of the sample, transfer to a 100-ml volumetric flask, dilute to volume with water and mix.

(b) Magnesium, Standard Solution B (1 ml \approx 40 μ g Mg). Using a pipet, transfer 1 ml of Solution A (1 ml \approx 10.0 mg Mg) to a 250-ml volumetric flask, dilute to volume with 0.1M HCl, and mix.

(c) Lanthanum, Standard Solution (1 ml \approx 10.0 mg La). Transfer 11.73g of La₂O₃ to a 100-ml beaker. While stirring, add 20 ml of HCl and heat to dissolve. Cool, add

90 ml of HClO_4 and heat to fumes. Cool, transfer to a 1-liter volumetric flask, dilute to volume with water, and mix.

(d) Glycerol Solution (50 v/v percent, alkaline-earth free). Transfer 500 ml of analytical-reagent grade glycerol to a 1-liter volumetric flask and dilute to volume with water. Prepare an ion-exchange resin column by mixing an equal weight of Dowex 50-X8 (50 to 100 mesh) and Dowex 1-X10 (50 to 100 mesh) in a beaker. Wash with 6M HCl and then with water. Transfer the resin to a 1 x 15-cm glass column to provide a bed 10 cm in depth. Pass the glycerol solution through the column and collect for subsequent use.

V. Preparation of Calibration Curve

1. Using pipets, transfer 0, 1, 2, 3, 4 and 5 ml of Solution B (1 ml \approx 40 μg Mg) to 100-ml volumetric flasks and dilute to about 50 ml with water.

2. To each solution, add 10 ml of the standard solution of lanthanum and 20 ml of the purified glycerol solution.

3. Dilute the flasks to volume with water, and mix. The solutions will contain 1000 μg of lanthanum/ml in 0.1N HClO_4 and 10 percent glycerol.

4. Install the magnesium hollow-cathode lamp in the atomic absorption instrument.

5. Set the current at two-thirds of the maximum operating current.

6. Turn on the operating switches of the atomic absorption instrument and allow the hollow-cathode lamp to warm up for 15 min.

7. Set the slit width at 50 μ and the voltage to the multiplier phototube (R-106) at 500 V.

8. Install the premixed-laminar flow burner equipped with a 10-cm head within the flame housing.

9. Open the valves to the oxidant (air) and fuel (acetylene) cylinders and set the tank regulators at 40 and 15 psi, respectively.

10. Align the burner within the optical path of the light source.

11. Ignite the burner and adjust the pressure and/or flow rates to produce a reducing flame. Note. Observe the manufacturer's safety precautions in lighting the premixed burner.

12. Adjust the wavelength dial of the monochromator to Aspirate water between each standard and record the absorbance.

13. Adjust the gain of the operational amplifier to 100 percent transmission and the dark current to zero.

14. Aspirate the magnesium solution with the highest concentration ($1\text{ ml} \approx 2\text{ }\mu\text{g Mg}$) from the series prepared in Step 1 and adjust the height and alignment to give the maximum absorbance.

15. Aspirate each calibration solution, in turn, including the reagent blank, and record the absorbance. Aspirate water between each standard and record the absorbance.

16. Plot the absorbance values, corrected for reagent blanks, etc. against micrograms of magnesium per milliliter, on rectangular coordinate paper. (The calibration curve should pass through the origin, but may deviate at higher concentrations of the analyte.)

VI. Procedure

1. Transfer to two 10-ml volumetric flasks, A and B, two equal test portions containing 4 to 12 μg of magnesium.

2. To test portion A, add 1 ml of the standard solution of lanthanum ($1\text{ ml} \approx 10\text{ mg La}$), 2 ml of glycerol, dilute to volume with water, and mix.

3. To test portion B, add 4 μg of magnesium, 1 ml of the standard solution of lanthanum (1 ml \approx 10 mg La), 2 ml of glycerol, dilute to volume with water, and mix.

4. Aspirate test portions, A and B, and measure the absorbance of each.

5. From the calibration curve, determine the magnesium concentrations, $\mu\text{g}/\text{ml}$.

6. Recheck the calibration curve with standard solutions of magnesium.

7. Subtract the concentration, $\mu\text{g}/\text{ml}$, that was added to test portion B. If the concentrations of the two test portions agree, proceed to step 8. If the recoveries do not agree, correct by the standard addition method, and proceed to step 8.

8. Calculate the percent magnesium as follows:

$$\text{MgO, weight percent} = \frac{C \times Z \times 1.658}{W \times 10^4}$$

where:

C = magnesium concentration, $\mu\text{g}/\text{ml}$

Z = dilution factor

W = test portion of solid sample, grams.

CALCIUM BY ATOMIC ABSORPTION SPECTROMETRY

I Scope

This atomic absorption method is applicable to the determination of 0.2 to 1.0 μg of calcium per milliliter of solution in clay materials. In this range, the relative standard deviation of the method is 2 percent.

II. Principle of Method

See Section II of Magnesium Method.

III. Interferences

See Section III of Magnesium Method.

IV. Reagents

(a) Calcium, Standard Solution A (1 ml \approx 10.0 mg Ca). Dry approximately 3 grams of CaCO_3 (NBS-915) at 110 $^{\circ}\text{C}$ for 2 hrs. Cool in a desiccator. Transfer $2.497 \pm 0.001\text{g}$ of the dry CaCO_3 to a 100-ml volumetric flask. Slowly add 55 ml of ultra pure 1M HCl and warm to dissolve. Swirl the solution to expel CO_2 , dilute to volume with 0.1M HCl, and mix.

(b) Calcium, Standard Solution B (1 ml \approx 20 μg Ca). Using a pipet, transfer 1 ml of Solution A (1 ml \approx 10.0 mg Ca) to a 500-ml volumetric flask, dilute to volume with 0.1M HCl, and mix.

(c) Aluminum, Standard Solution (1 ml \approx 10.0 mg Al). Transfer 5.0 grams of aluminum metal (NBS 44e) to a 400-ml beaker. Add 50 ml of water and 40 ml of HCl. Warm to dissolve, cool, transfer to a 500-ml volumetric flask. Dilute to volume with water, and mix.

(d) Potassium, Standard Solution (1 ml \approx 10.0 mg K). Transfer 9.5 grams of KCl to a 500-ml volumetric flask. Add 200 ml of water and 10 ml of 1M HCl. Dilute to volume with water, and mix.

V. Preparation of Calibration Curve

1. Using pipets, transfer 0, 1, 2, 3, 4 and 5 ml of Solution B (1 ml \approx 20 μg Ca) to 100-ml volumetric flasks, and dilute to about 50 ml with water.

2. To each flask, add 5 ml of the standard solution of potassium and 5 ml of the standard solution of aluminum.

3. Dilute to volume with water, and mix. The solutions will contain 500 μg of potassium and aluminum/ml.

4. Install the calcium hollow-cathode lamp in the atomic absorption instrument.

5-7. Proceed as directed in steps 5 to 7 of Section V of the Magnesium Method. See page 63.

8. Install the premixed-laminar flow burner equipped with a 5-cm head (N_2O) in the flame housing.

9-10. Proceed as directed in steps 9 and 10 of Section V of the Magnesium Method.

11. Ignite the air-acetylene burner and adjust the flame to fuel rich conditions by gradually introducing C_2H_2 . Then introduce N_2O and C_2H_2 until the N_2O ratio to air is 80-20. Note. Observe the manufacturer's safety precautions in the use of the nitrous oxide-acetylene flame.

12. Adjust the wavelength dial of the monochromator to the resonance line of calcium at 4227 Å to yield a maximum reading.

13. Proceed as directed in steps 13 to 16 of Section V of the Magnesium Method. See page 64.

VI. Procedure

1. Transfer to two 25-ml volumetric flasks, A and B, two equal test portions containing 5 to 15 μg of calcium.

2. Dilute test portion A to volume with water and mix.

3. To test portion B, add 8 μg of calcium, dilute to volume with water, and mix.

4. Aspirate test portions, A and B, and measure the absorbance of each.

5. From the calibration curve, determine the calcium concentration, $\mu\text{g}/\text{ml}$.

6. Recheck the calibration curve with standard solutions of calcium.

7. Subtract the concentration, $\mu\text{g/ml}$, that was added to test portion B. If the concentrations of the two test portions A and B agree, proceed to step 8. If the recoveries do not agree, correct by the standard addition method, and proceed to step 8.

8. Calculate the percent calcium as follows:

$$\text{CaO, weight percent} = \frac{C \times Z \times 1.399}{W \times 10^4}$$

where:

C = calcium concentration, $\mu\text{g/ml}$

Z = dilution factor

W = test portion of solid sample, grams.

STRONTIUM BY ATOMIC ABSORPTION SPECTROMETRY

I. Scope

This atomic absorption method is applicable to the determination of 1 to 5 μg of strontium per milliliter of solution in clay materials. In this range, the relative standard deviation of the method is 2 percent.

II. Principle of Method

See Section II of Magnesium Method.

III. Interferences

See Section III of Magnesium Method.

IV. Reagents

(a) Strontium, Standard Solution A (1 ml \approx 10.0 mg Sr).

Dry approximately 2 grams of reagent grade SrCO_3 at 110 °C for 2 hrs. Cool in a desiccator. Transfer 1.685 \pm 0.001g of the dry SrCO_3 to a 100 ml volumetric flask. Slowly add 50 ml of ultra pure 1M HCl and warm to dissolve. Swirl the solution to expel CO_2 , dilute to volume with 0.1M HCl, and mix.

(b) Strontium, Standard Solution B (1 ml \approx 100 μg Sr).

Using a pipet, transfer 1 ml of Solution A (1 ml \approx 10.0 mg Sr) to a 100-ml volumetric flask, dilute to volume with 0.1M HCl, and mix.

(c) Aluminum, Standard Solution (1 ml \approx 10.0 mg Al).

Proceed as directed in Section IV of Calcium Method. See page 66.

(d) Potassium, Standard Solution (1 ml \approx 10.0 mg K).

Proceed as directed in Section IV of Calcium Method. See page 66.

V. Preparation of Calibration Curve

1. Using pipets, transfer 0, 1, 2, 3, 4 and 5 ml of Solution B (1 ml \approx 100 μg Sr) to 100-ml volumetric flasks, and dilute to about 50 ml with water.

2. To each flask, add 5 ml of the standard solution of potassium and 5 ml of the standard solution of aluminum.

3. Dilute to volume with water, and mix. The solutions will contain 500 μg of potassium and aluminum/ml.

4. Install the strontium hollow-cathode lamp in the atomic absorption instrument.

5-7. Proceed as directed in steps 5 to 7 of Section V of the Magnesium Method. See page 63.

8. Install the premixed-laminar flow burner equipped with a 5-cm head (N_2O) in the flame housing.

9-10. Proceed as directed in Steps 9 to 10 of Section V of the Magnesium Method. See page 64.

11. Ignite the air-acetylene burner and adjust the flame to fuel rich conditions by gradually introducing C_2H_2 . Then introduce N_2O and C_2H_2 until the N_2O ratio to air is 80-20.

Note. Observe the manufacturers safety precautions in the use of the nitrous oxide-acetylene flame.

12. Adjust the wavelength dial of the monochromator to the resonance line of strontium at 4607 Å to yield a maximum reading.

13. Proceed as directed in Steps 13 to 16 of Section V of the Magnesium Method. See page 64.

VI. Procedure

1. Transfer to two 25-ml volumetric flasks, A and B, two equal test portions containing 25 to 50 µg of strontium.

2. Dilute test portion A to volume with water and mix.

3. To test portion B, add 25 µg of strontium, dilute to volume with water, and mix.

4. Aspirate test portions, A and B, and measure the absorbance of each.

5. From the calibration curve, determine the strontium concentrations, µg/ml.

6. Recheck the calibration curve with standard solutions of strontium.

7. Subtract the concentration, µg/ml, that was added to test portion B. If the concentrations of the two test portions agree, proceed to step 8. If the recoveries do not agree, correct by the standard addition method, and proceed to step 8.

8. Calculate the percent strontium as follows:

$$\text{SrO, weight percent} = \frac{C \times Z \times 1.183}{W \times 10^4}$$

where:

C = strontium concentration, $\mu\text{g/ml}$

Z = dilution factor

W = test portion of solid sample, grams.

I. Scope

This flame emission method is applicable to the determination of 0.5 to 2.5 μg of barium per milliliter of solution in clay materials. In this range, the relative standard deviation of the method is 2 percent.

II. Principle of Method

Barium is excited to emission in a nitrous oxide, air (80-20)-acetylene flame and is then determined by measuring the radiation intensity of the light emitted at a wavelength of 5536 \AA .

III. Interferences

The resonance line of barium at 5536 \AA suffers from serious spectral interference of the CaO-CaOH band system when a low temperature flame is used. Using a high temperature flame such as nitrous oxide-acetylene, the interference is minimized. The magnitude of the interference will depend upon the resolution of the monochromator.

IV. Reagents

(a) Barium, Standard Solution A (1 ml \approx 10.0 mg Ba). Dry 2 grams of reagent grade BaCO_3 at 110 $^\circ\text{C}$ for 2 hrs. Cool in a desiccator. Transfer 1.437g \pm 0.001g of the dry BaCO_3 to 100-ml volumetric flask. Add 40 ml of 1M HCl and warm to dissolve. Swirl the solution to expel CO_2 , dilute to volume with 0.1M HCl, and mix.

(b) Barium, Standard Solution B (1 ml \approx 50 μg Ba). Using a pipet, transfer 1 ml of Solution A (1 ml \approx 10.0 mg Ba) to a 200-ml volumetric flask, dilute to volume with 0.1M HCl, and mix.

(c) Aluminum, Standard Solution (1 ml \approx 10.0 mg Al). Prepare as directed in Section IV of the Calcium Method. See page 66.

(d) Potassium, Standard Solution (1 ml \approx 10.0 mg K). Prepare as directed in Section IV of the Calcium Method. See page 66.

V. Preparation of Calibration Curve

1. Using pipets, transfer 0, 1, 2, 3, 4 and 5 ml of Barium Solution B (1 ml \approx 50 μ g Ba) to 100 ml volumetric flasks, and dilute to about 50 ml with water.
2. To each flask, add 5 ml of the standard solution of potassium and 5 ml of the standard solution of aluminum.
3. Dilute to volume with water, and mix.
4. Turn on the operating switches of the flame emission spectrometer.
5. Set the voltage to the multiplier phototube at 1400 V.
6. Install the premixed laminar flow burner equipped with a 5-cm head (N_2O) in the flame housing.
7. Ignite the air-acetylene burner and adjust the flame to fuel rich conditions by gradually introducing C_2H_2 . Then introduce N_2O and C_2H_2 until the N_2O ratio to air is 80-20.
Note. Observe the manufacturer's safety precautions in the use of the nitrous oxide-acetylene flame.
8. Set the wavelength of the monochromator to 5536 \AA and the slit width at 50 μ .
9. Aspirate the barium solution with the highest concentration (1 ml \approx 2.5 μ g Ba) from the series prepared in step 1.
10. Adjust the gain of the operational amplifier to give 85 percent of full scale, as indicated on the recorder.
11. While aspirating set the wavelength of the monochromator at 5530 \AA and scan the barium line at 5536 \AA at a rate of 10 $\text{\AA}/\text{min}$.
12. Repeat step 10 with each calibration solution, in turn, and record its radiation intensity. Aspirate water between each standard solution and record the radiation intensity.
13. Plot the radiation intensity values, corrected for background, against micrograms of barium per milliliter, on rectangular coordinate paper.

VI. Procedure

1. Transfer to two 25-ml volumetric flasks, A and B, two equal test portions containing 15 to 30 μg of barium.
2. Dilute test portion A to about 15 ml with water, add 1 ml of standard solution of potassium, dilute to volume with water and mix.
3. To test portion B, add 15 μg of barium, 1 ml of standard solution of potassium, dilute to volume with water and mix.
4. Aspirate test portions, A and B, and measure the radiation intensity of each.
5. From the calibration curve, determine the barium concentrations, $\mu\text{g}/\text{ml}$.
6. Recheck the calibration curve with standard solutions of barium.
7. Subtract the concentration, $\mu\text{g}/\text{ml}$, that was added to test portion B. If the concentrations of the two test portions agree, proceed to step 8. If the recoveries do not agree correct by the standard addition method, and proceed to step 8.
8. Calculate the percent barium as follows:

$$\text{BaO, weight percent} = \frac{C \times Z \times 1.117}{W \times 10^4}$$

where:

C = barium concentration, $\mu\text{g}/\text{ml}$

Z = dilution factor

W = test portion of solid sample, grams.

The authors are particularly appreciative of the valuable assistance of Mrs. Mary Pantazis in typing and assembling this report and of Mrs. Rosemary Maddock who provided overall coordination and editorial assistance.

REFERENCES

- [1] Lundell, G. E. F. and Hoffman, J. I., NBS J. Res. 1, 90 (1928) RP 5.
- [2] Flanagan, F. J., U. S. Geol. Survey, *Giochim et Cosmochim Acta* 33, 81-120 (1969).
- [3] Peck, L. C., U. S. Geol. Survey Bulletin 1170, 21 (1964).
- [4] Bell, R. K., NBS Misc. Publ. 260-7, 82 (1965).
- [5] Hillebrand, W. F., Lundell, G. E. F., Bright, H. A. and Hoffman, J. I., *Applied Inorganic Analysis*, 2nd ed. 507 (1953), John Wiley & Sons, New York.
- [6] Hague, J. L. and Bright, H. A., *Colorimetric Determination of Phosphorus in Steel and Iron*, J. Res. Nat. Bur. Std. 26, A05 (1941) RP 1386.
- [7] Suher, N. H. and Ingamells, C. O., *Solution Technique for Analysis of Silicates*, *Anal. Chem.* 38, 6, 730 (1966).
- [8] Govindaraju, K., *Ion Exchange Dissolution Method for Silicate Analysis*, *Anal. Chem.* 40, 24 (1968).
- [9] ASTM Chemical Analysis of Metals; Sampling and Analysis of Metal Bearing Ores, Part 32, p. 158 (1971).
- [10] *ibid* p. 144.
- [11] Lundell, G. E. F., Hoffman, J. I. and Bright, H. A., *Chemical Analysis of Iron and Steel*, p. 532 (1931), John Wiley & Sons, New York.
- [12] Young, J. P., French, J. R. and White, J. C., *Anal. Chem.* 30, 422 (1958).
- [13] Young, J. P. and White, J. C., *Talanta* 1, 263 (1958).
- [14] Wood, D. F. and Jones, J. T., *The Analyst* 90, 1068 (1965).
- [15] ASTM Chemical Analysis of Metals; Sampling and Analysis of Metal Bearing Ores, Part 32, p. 137 (1971).
- [16] Bernas, B., *Anal. Chem.* 40, 1682 (1968).

APPENDIX 1

Certificate of Analysis

STANDARD REFERENCE MATERIAL 97a

Flint Clay

(Results based on sample dried for two hours at 140 °C)

Analyst	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	TiO ₂	P ₂ O ₅	K ₂ O	Na ₂ O	Li ₂ O	ZrO ₂	BaO	MgO	CaO	SrO	Cr ₂ O ₃	Loss on Ignition
1 ^[1] -----	43.74	38.65	{0.45 ^a .46 ^b }	{1.88 ^c 1.89 ^d }	0.34	0.53 ^e	0.033 ^e	0.12 ^e	0.063 ^f	0.078 ^e	0.16 ^e	0.11 ^e	0.17 ^e	0.028 ^g	13.32
2 ^[2] -----	43.68	38.95	.45	1.95	.35	.51 ^e	.041 ^e	.10 ^e	-----	.07	.14 ^e	.11 ^e	.18 ^e	.03	13.31
3-----	43.60	38.79	.43 ^a	1.87 ^d	.38 ⁱ	.46 ^e	-----	-----	-----	-----	-----	-----	-----	-----	-----
Average--	43.67	38.79	0.45	1.90	0.36	0.50	0.037	0.11	-----	0.07 ₅	0.15	0.11	0.18	0.03	13.32

References: [1] G.E.F. Lundell and J.I. Hoffman, NBS J. Res. 1, 91 (1928) RP5.
[2] L. C. Peck, Geological Survey Bulletin 1170, (1964).

^ao-phenanthroline photometric method.
^bIron reduced with SnCl₂ and titrated with standard potassium dichromate solution.
^cCupferron gravimetric method.
^dH₂O₂ photometric method.

^eFlame emission spectrometric method.
^fPyrocatechol violet photometric method.
^gAtomic absorption method.
^hDiphenylcarbazide photometric method.
ⁱMolybdenum-blue photometric method.

List of Analysts

1. R. K. Bell, B. B. Bendigo, T. C. Rains, T. A. Rush, E. R. Deardorff, J. R. Baldwin, R. A. Paulson, W. P. Schmidt, and S. D. Rasberry, Analytical Chemistry Division, Institute for Materials Research, National Bureau of Standards.
2. L. C. Peck, United States Geological Survey, Denver, Colorado.
3. L. M. Melnick, J. D. Selvaggio, and D. G. Cunningham, Applied Research Laboratory, United States Steel Corporation, Pittsburgh, Pennsylvania.

The material for the preparation of this standard was provided by the A. P. Green Fire Brick Company, Mexico, Missouri.

The overall direction and coordination of the technical measurements leading to certification were performed under the chairmanships of O. Menis and J. I. Shultz.

The technical and support aspects involved in the preparation, certification and issuance of this Standard Reference Material were coordinated through the Office of Standard Reference Materials by J. L. Hague.

Washington, D. C. 20234
October 8, 1969

J. Paul Cali, Acting Chief
Office of Standard Reference Materials

APPENDIX 2

Certificate of Analysis

STANDARD REFERENCE MATERIAL 98a

Plastic Clay

(Results based on sample dried for two hours at 140 °C)

Analyst	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	TiO ₂	P ₂ O ₅	K ₂ O	Na ₂ O	Li ₂ O	ZrO ₂	BaO	MgO	CaO	SrO	Cr ₂ O ₃	Loss on Ignition
1 ^[1]	48.98	33.13	{1.34* 1.37*}	{1.56* 1.63*}	0.11	1.07*	0.080*	0.075*	0.042*	0.031*	0.42*	0.31*	0.041*	0.030*	12.40
2 ^[2]	48.91	33.31	1.35	1.64	.10	1.08*	.083*	.064*	-----	.03	.43*	.31*	.037*	.04	12.49
3.....	-----	33.12	1.28*	1.61 ⁴	.11 ¹	0.98*	-----	-----	-----	-----	-----	-----	-----	-----	-----
Average..	48.94	33.19	1.34	1.61	0.11	1.04	0.082	0.070	-----	0.03	0.42	0.31	0.039	0.03	12.44

References: [1] G.E.F. Lundell and J.I. Hoffman, NBS J. Res. 1, 91 (1928) RP5.

[2] L.C. Peck, Geological Survey Bulletin 1170, (1964).

*o-phenanthroline photometric method.

¹Iron reduced with SnCl₂ and titrated with standard potassium dichromate solution.

²Cupferron gravimetric method.

⁴H₂O₂ photometric method.

*Flame emission spectrometric method.

³Pyrocatechol violet photometric method.

*Atomic absorption method.

⁵Diphenylcarbazide photometric method.

⁶Molybdenum-blue photometric method.

List of Analysts

1. R. K. Bell, B. B. Bendigo, T. C. Rains, T. A. Rush, E. R. Deardorff, J. R. Baldwin, R. A. Paulson, W. P. Schmidt, and S. D. Rasberry, Analytical Chemistry Division, Institute for Materials Research, National Bureau of Standards.

2. L. C. Peck, United States Geological Survey, Denver, Colorado.

3. L. M. Melnick, J. D. Selvaggio, and D. G. Cunningham, Applied Research Laboratory, United States Steel Corporation, Pittsburgh, Pennsylvania.

The material for the preparation of this standard was provided by the A. P. Green Fire Brick Company, Mexico, Missouri.

The overall direction and coordination of the technical measurements leading to certification were performed under the chairmanship of O. Menis and J. I. Shultz.

The technical and support aspects involved in the preparation, certification and issuance of this Standard Reference Material were coordinated through the Office of Standard Reference Materials by J. L. Hague.

U.S. DEPT. OF COMM. BIBLIOGRAPHIC DATA SHEET		1. PUBLICATION OR REPORT NO. NBS SP 260-37	2. Gov't Accession No.	3. Recipient's Accession No.
4. TITLE AND SUBTITLE Standard Reference Materials: Methods of Analysis of NBS Clay Standards			5. Publication Date June 1972	
			6. Performing Organization Code	
7. AUTHOR(S) J. I. Shultz, R. K. Bell, T. C. Rains and O. Menis			8. Performing Organization	
9. PERFORMING ORGANIZATION NAME AND ADDRESS NATIONAL BUREAU OF STANDARDS DEPARTMENT OF COMMERCE WASHINGTON, D.C. 20234			10. Project/Task/Work Unit No.	
			11. Contract/Grant No.	
12. Sponsoring Organization Name and Address Same as 9.			13. Type of Report & Period Covered final	
			14. Sponsoring Agency Code	
15. SUPPLEMENTARY NOTES				
16. ABSTRACT (A 200-word or less factual summary of most significant information. If document includes a significant bibliography or literature survey, mention it here.) This publication brings together a compilation of methods used at NBS for the analysis of two complex standard reference clay materials. The methods were selected to give the best obtainable results for those elements normally found in clays. In some instances, more than one procedure was employed for an element as a cross-check on the precision and accuracy of the results. The procedures are presented in two parts. Part I is concerned with the determination of the major constituents by the classical analytical procedures. Part II covers the minor elements which are determined instrumentally by flame emission and atomic absorption spectrometry. These clay materials serve as analytical composition standards to provide quality control of the basic raw materials which are used in the ceramics and refractories industries.				
17. KEY WORDS (Alphabetical order, separated by semicolons) Atomic absorption; ceramics; classical procedures; clay materials; flame emission; refractories; Standard Reference Materials.				
18. AVAILABILITY STATEMENT <input checked="" type="checkbox"/> UNLIMITED. <input type="checkbox"/> FOR OFFICIAL DISTRIBUTION. DO NOT RELEASE TO NTIS.			19. SECURITY CLASS (THIS REPORT) UNCLASSIFIED	21. NO. OF PAGES 86
			20. SECURITY CLASS (THIS PAGE) UNCLASSIFIED	22. Price \$.75

JOURNAL OF RESEARCH reports National Bureau of Standards research and development in physics, mathematics, and chemistry. Comprehensive scientific papers give complete details of the work, including laboratory data, experimental procedures, and theoretical and mathematical analyses. Illustrated with photographs, drawings, and charts. Includes listings of other NBS papers as issued.

Published in two sections, available separately:

• Physics and Chemistry

Papers of interest primarily to scientists working in these fields. This section covers a broad range of physical and chemical research, with major emphasis on standards of physical measurement, fundamental constants, and properties of matter. Issued six times a year. Annual subscription: Domestic, \$9.50; \$2.25 additional for foreign mailing.

• Mathematical Sciences

Studies and compilations designed mainly for the mathematician and theoretical physicist. Topics in mathematical statistics, theory of experiment design, numerical analysis, theoretical physics and chemistry, logical design and programming of computers and computer systems. Short numerical tables. Issued quarterly. Annual subscription: Domestic, \$5.00; \$1.25 additional for foreign mailing.

TECHNICAL NEWS BULLETIN

The best single source of information concerning the Bureau's measurement, research, developmental, cooperative, and publication activities, this monthly publication is designed for the industry-oriented individual whose daily work involves intimate contact with science and technology—for engineers, chemists, physicists, research managers, product-development managers, and company executives. Includes listing of all NBS papers as issued. Annual subscription: Domestic, \$3.00; \$1.00 additional for foreign mailing.

Bibliographic Subscription Services

The following current-awareness and literature-survey bibliographies are issued periodically by the Bureau: Cryogenic Data Center Current Awareness Service (weekly), Liquefied Natural Gas (quarterly), Superconducting Devices and Materials (quarterly), and Electromagnetic Metrology Current Awareness Service (monthly). Available only from NBS Boulder Laboratories. Ordering and cost information may be obtained from the Program Information Office, National Bureau of Standards, Boulder, Colorado 80302.

Applied Mathematics Series. Mathematical tables, manuals, and studies.

Building Science Series. Research results, test methods, and performance criteria of building materials, components, systems, and structures.

Handbooks. Recommended codes of engineering and industrial practice (including safety codes) developed in cooperation with interested industries, professional organizations, and regulatory bodies.

Special Publications. Proceedings of NBS conferences, bibliographies, annual reports, wall charts, pamphlets, etc.

Monographs. Major contributions to the technical literature on various subjects related to the Bureau's scientific and technical activities.

National Standard Reference Data Series. NSRDS provides quantitative data on the physical and chemical properties of materials, compiled from the world's literature and critically evaluated.

Product Standards. Provide requirements for sizes, types, quality, and methods for testing various industrial products. These standards are developed cooperatively with interested Government and industry groups and provide the basis for common understanding of product characteristics for both buyers and sellers. Their use is voluntary.

Technical Notes. This series consists of communications and reports (covering both other-agency and NBS-sponsored work) of limited or transitory interest.

Federal Information Processing Standards Publications. This series is the official publication within the Federal Government for information on standards adopted and promulgated under the Public Law 89-306, and Bureau of the Budget Circular A-86 entitled, Standardization of Data Elements and Codes in Data Systems.

Consumer Information Series. Practical information, based on NBS research and experience, covering areas of interest to the consumer. Easily understandable language and illustrations provide useful background knowledge for shopping in today's technological marketplace.

CATALOGS OF NBS PUBLICATIONS

NBS Special Publication 305, Publications of the NBS, 1966-1967. When ordering, include Catalog No. C13.10:305. Price \$2.00; 50 cents additional for foreign mailing.

NBS Special Publication 305, Supplement 1, Publications of the NBS, 1968-1969. When ordering, include Catalog No. C13.10:305/Suppl. 1. Price \$4.50; \$1.25 additional for foreign mailing.

NBS Special Publication 305, Supplement 2, Publications of the NBS, 1970. When ordering, include Catalog No. C13.10:305/Suppl. 2. Price \$3.25; 85 cents additional for foreign mailing.

U.S. DEPARTMENT OF COMMERCE
National Bureau of Standards
Washington, D.C. 20234

OFFICIAL BUSINESS

Penalty for Private Use, \$300

POSTAGE AND FEES PAID
U.S. DEPARTMENT OF COMMERCE
215

