


Reference book not to be
taken from the library.

National Bureau of
Library, E-01

NAT'L INST OF STAND & TECH

 A11106 173869
 NATIONAL BUREAU OF STANDARDS

NBS SPECIAL PUBLICATION 260

SUPPLEMENT

1974 PRICE LIST

NBS
Publi-
cations


REFERENCE

U.S. DEPARTMENT OF COMMERCE / National Bureau of Standards



QC
100
457
no.260
1974

STANDARD REFERENCE MATERIALS



Standard Reference Materials are well-characterized materials disseminated by the National Bureau of Standards to be used to calibrate and evaluate measuring instruments, methods, and systems or to produce scientific data that can be referred readily to a common base. The materials are certified for chemical composition or for a particular physical or chemical property. They are used on-site in science and industry to calibrate instruments and methods used in production and quality control of raw materials, chemicals, metals, ceramics, fuels, and radioactive nuclides in manufacturing processes and in research.

ORDERING

GENERAL

Orders should be addressed to the Office of Standard Reference Materials, National Bureau of Standards, Washington, D.C. 20234. Telephonic or telegraphic communications should be addressed to the attention of the Office of Standard Reference Materials (Telephone 301-921-2045). Orders should give the amount (number of units), catalog number and name of the standard requested. For example: 150g (1 unit) of No. 11h, Basic-Open-Hearth Steel, 0.2 percent C. These materials are distributed only in the units listed.

Acceptance of an order does not imply acceptance of any provision set forth in the order contrary to the policy, practice, or regulations of the National Bureau of Standards or the U.S. Government. Prices listed herein are subject to change without notice. Price changes when made are first announced in various NBS publications and in announcements mailed to users of these materials.

Prices in effect at time of shipment will be billed to the purchaser. No discounts are given on NBS Standard Reference Materials.

To provide better service to users of SRM's our name-label files are periodically updated and/or corrected. If your name and address are not correct, please return the name-label portion of the envelope and indicate the corrections. Send it and all other inquiries to:

Office of Standard Reference Materials
Room B311, Chemistry Building
National Bureau of Standards
Washington, D.C. 20234

FOREIGN ORDERS

A. Both prepaid and non-prepaid orders will be processed, subject to export-import regulations of the United States and the country from which the order originates. (See mode of shipment—Foreign Shipments.) Payment may be made by any of the following:

1. UNESCO coupons;
2. Bankers' draft against U.S. bank;
3. Bank to bank transfer on U.S. bank;
4. Letter of credit on a U.S. bank;
5. International Money Order.

All checks, coupons, etc., should be made payable to the National Bureau of Standards and must be in U.S. dollars.

B. Pro-forma service, subject to export-import regulations, may require 60 days or more for processing. Customers are urged to order directly whenever possible for fast service and to supply all necessary import documents and information with their order. Payment may be made by any of the means shown under A above.

DOMESTIC SHIPMENTS

Shipments of material (except for certain restricted categories, e.g., hydrocarbons, organic sulfur compounds, special nuclear materials, compressed gases and radioactive standards) intended for the United States, Mexico, and Canada are normally shipped prepaid air parcel post (providing that the parcel does not exceed the weight limits as prescribed by Postal Laws and Regulations) unless the purchaser requests a different mode of shipment, in which case the shipment will be sent collect. It is impractical for the Bureau to prepay shipping charges and add this cost to the billing invoice. Hydrocarbons, organic sulfur compounds, compressed gases, rubber compounding materials, radioactive standards and similar materials are shipped express collect.

FOREIGN SHIPMENTS

Both prepaid and non-prepaid orders will be shipped by prepaid International Air Parcel Post, subject to size, weight, and category of material limitations. Any other mode of shipment requested by customer must be paid for by the customer. Shipments excluded from International Air Parcel Post for any reason, must be handled through an agent (shipping or brokerage firm) located in the U.S. as designated by the Purchaser. These parcels will be packed for overseas shipment and forwarded via express collect to the U.S. firm designated as agent. NOTE: Nuclear SRM's will not be shipped through an agent, they will be shipped direct.

TECHNICAL INQUIRIES

All technical inquiries regarding SRM's, RM's, and GM's should be directed to the Office of Standard Reference Materials, National Bureau of Standards, Washington, D.C. 20234. Telephone (301) 921-2045.

**AVAILABILITY AND PRICE LIST
A. STANDARD REFERENCE MATERIALS**

SRM	Type	Unit	Price	SRM	Type	Unit	Price
1b	Limestone, argillaceous	50 g	\$ 38	83c	Arsenic trioxide, oxidimetric	75 g	38
3b	Iron, white	110 g	39	84h	Potassium phthalate, acid, acidimetric	60 g	32
5L	Iron, cast	150 g	47	85b	Aluminum alloy, wrought	75 g	39
6g	Iron, cast	150 g	42				
7g	Iron, cast (high phosphorus)	150 g	39	87a	Aluminum-silicon alloy	75 g	39
8j	Steel, bessemer (simulated), 0.1C	150 g	39	88a	Limestone, dolomitic	50 g	38
10g	Steel, bessemer, 0.2C	150 g	39	89	Glass, lead-barium	45 g	33
11h	Steel, B.O.H. 0.2C	150 g	39	90	Ferrophosphorus	75 g	35
12h	Steel, B.O.H. 0.4C	150 g	39	91	Glass, opal	45 g	33
				92	Glass, low boron	45 g	33
13g	Steel, B.O.H. 0.6C	150 g	39	93a	Glass, high boron	ea	56
14e	Steel, B.O.H. 0.8C	150 g	39	94c	Zinc-base die-casting alloy	150 g	41
15g	Steel, B.O.H. 0.1C	150 g	39	97a	Clay, flint	60 g	88
16e	Steel, B.O.H. 1.1C	150 g	39	98a	Clay, plastic	60 g	88
17a	Sucrose (cane sugar)	60 g	32	99a	Feldspar, soda	40 g	38
				100b	Steel, manganese (SAE T1340)	150 g	39
19g	Steel, A.O.H. 0.2C	150 g	39	101f	Steel, stainless, Cr 18-Ni9(SAE 304)	100 g	39
20g	Steel, AISI 1045	150 g	39	103a	Chrome refractory	60 g	33
25c	Ore, manganese	100 g	33				
27e	Ore, iron, Sibley	100 g	34	105	Steel, high-sulfur 0.2C carbon only	150 g	31
30f	Steel, Cr-V (SAE 6150)	150 g	39	106b	Steel, Cr-Mo-Al (Nitalloy G)	150 g	39
				107b	Iron, cast, Ni-Cr-Mo	150 g	39
32e	Steel, Ni-Cr (SAE 3140)	150 g	39	113a	Zinc Concentrate	100 g	34
33d	Steel, Ni-Mo (SAE 4820)	150 g	39				
36b	Steel, Cr2-Mo1	150 g	39	114m	Cement, turbidimetric and fineness std.	set (20)	52
37e	Brass, sheet	150 g	39	115a	Iron, cast, Cu-Ni-Cr	150 g	39
39i	Benzoic acid, calorimetric	30 g	38	120b	Phosphate Rock (Florida)	90 g	51
				121d	Steel, Cr 17-Ni11-Ti0.3, AISI 321	150 g	39
40h	Sodium oxalate, oxidimetric	60 g	38	122c	Iron, cast (car-wheel)	150 g	39
41a	Dextrose (glucose)	70 g	32	123c	Steel, Cr17-Ni11-Nb0.7, AISI 348	150 g	39
42g	Tin, freezing-point std.	350 g	62	124d	Bronze (Cu85-Pb5-Sn5-Zn5) ounce metal	150 g	39
43h	Zinc, freezing-point	350 g	52	125b	Steel, high silicon	150 g	39
44f	Aluminum, freezing-point std.	200 g	77	126c	Steel, high-nickel (36% Ni)	150 g	39
				127b	Solder (Sn40-Pb60)	150 g	39
45d	Copper, freezing-point std.	450 g	52	129c	Steel, high-sulfur	150 g	39
49e	Lead, freezing-point std.	600 g	52	131b	Steel, low-carbon silicon	100 g	33
50c	Steel, W18-Cr4-V1	150 g	39	132b	Steel, tool	150 g	39
51b	Steel, electric furnace 1.2C	150 g	39	133a	Steel, stainless (Cr13-Mo0.3-S0.3)	150 g	39
53e	Bearing metal, lead-base	150 g	39	134a	Steel, Mo8-W2-Cr4-V1	150 g	39
54d	Bearing metal, tin-base	170 g	39	136c	Potassium dichromate, oxidimetric	60 g	38
57	Silicon, refined	60 g	35	139a	Steel, Cr-Ni-Mo (AISI 8640)	150 g	39
58a	Ferrosilicon (Si 75%)	75 g	52	140b	Benzoic acid	2 g	34
59a	Ferrosilicon (Si 50%)	50 g	46	141b	Acetanilide	2 g	34
				142	Anisic acid	2 g	32
64b	Ferrochromium (high carbon)	100 g	37				
65d	Steel, basic electric, 0.3C	150 g	39				
70a	Feldspar, potash	40 g	38				
71	Calcium molybdate	60 g	35				
72f	Steel, Cr-Mo (SAE X4130)	150 g	39				
73c	Steel, stainless Cr13 (SAE 420)	150 g	39				
79a	Fluorspar	120 g	46				
82b	Iron, nickel-chromium cast	150 g	39				

SRM	Type	Unit	Price	SRM	Type	Unit	Price
143c	Cystine . . . Temporarily out of stock	2 g		333	Molybdenum, concentrate . . .	35 g	52
147	Triphenyl phosphate	2 g	34	335	Steel, B.O.H. 0.1C (carbon only)	300 g	33
148	Nicotinic acid	2 g	30	336	Steel, Cr-V (carbon only), 1-g pins	75 g	37
152a	Steel, B.O.H. 0.5C, 0.03 Sn	150 g	39	337	Steel, B.O.H. 1.1C (carbon only)	300 g	33
153a	Steel, Co8-Mo9-W2-Cr4-V2 . .	150 g	39	339	Steel, stainless, Cr17-Ni9-0.2Se (SAE 303Se)	150 g	46
154b	Titanium Dioxide	90 g	56	340	Ferroniobium	100 g	51
155	Steel, Cr0.5-W0.5	150 g	39	341	Iron, ductile	150 g	39
157a	Nickel silver (Cu58-Ni12-Zn29)	135 g	39	342	Iron, nodular	150 g	39
158a	Bronze, silicon	150 g	39	342a	Iron, nodular	150 g	41
160b	Steel, stainless, Cr19-Ni14-Mo3 (SAE 316)	150 g	39	343	Steel, stainless, Cr16-Ni2 (SAE 431)	150 g	39
162a	Monel-type (Ni64-Cu31)	150 g	39	344	Steel, stainless, Cr15-Ni7-Mo2-Al1	150 g	39
163	Steel, 0.9C, 0.9Mn, 1.0Cr . .	100 g	46	345	Steel, stainless, Cr16-Ni4-Cu3	150 g	39
166c	Steel, stainless, low-carbon . .	100 g	31	346	Steel, valve (Cr22-Ni4-Mn9)	150 g	46
168	Cobalt-base alloy, Co41-Mo4-Nb3-Ta1-W4	150 g	39	348	Steel, Ni26-Cr15 (A286)	150 g	39
171	Magnesium-base alloy	100 g	39	349	Nickel-base alloy (Ni57-Co14-Cr20)	150 g	39
173a	Titanium alloy 6Al-4V	100 g	39	350	Benzoic acid, acidimetric . . .	30 g	38
174	Titanium alloy 4Al-4Mn	100 g	39	352	Titanium, unalloyed, for hydrogen	20 g	41
176	Titanium alloy 5Al-2.5Sn	100 g	39	353	Titanium, unalloyed, for hydrogen	20 g	41
178	Steel, basic oxygen 0.4C	150 g	39	354	Titanium, unalloyed, for hydrogen	20 g	41
180	Fluorspar, high-grade	120 g	46	355	Titanium, unalloyed, for oxygen	20 g	46
181	Ore, lithium (Spodumene) . . .	45 g	33	356	Titanium alloy, 6Al-4V	20 g	46
182	Ore, lithium (Petalite)	45 g	33	360a	Zircaloy-2	100 g	61
183	Ore, lithium (Lepidolite)	45 g	33	361	Steel, AISI 4340, chip	150 g	39
184	Bronze, leaded-tin	150 g	39	362	Steel, AISI 94B17 (modified), chip	150 g	39
185e	Potassium hydrogen phthalate, pH	60 g	41	363	Steel, Cr-V (modified), chip	150 g	39
186lc	Potassium dihydrogen phosphate, pH	30 g	41	364	Steel, high carbon (modified), chip	150 g	39
186llc	Disodium hydrogen phosphate, pH	30 g	36	365	Iron, electrolytic, chip	150 g	39
187h	Borax, pH	30 g	36	366	Set, 1 ea of 361, 362, 363, 364 and 365	set	106
188	Potassium hydrogen tartrate, pH	60 g	36	370d	Zinc oxide (Set of 4)	8 kg	40
189	Potassium tetroxalate, pH . . .	65 g	36	371g	Sulfur (Set of 4)	6 kg	44
191	Sodium bicarbonate, pH	30 g	39	372h	Stearic acid (Set of 4)	3.2 kg	44
192	Sodium carbonate, pH	30 g	39	373f	Benzothiazyl disulfide (Set of 4)	2 kg	46
193	Potassium Nitrate, Fertilizer	90 g	51	374c	Tetramethylthiuram disulfide	2 kg	46
194	Ammonium dihydrogen phosphate, Fertilizer	90 g	51	375f	Channel black (Set of 4)	28 kg	73
195	Ferrosilicon (75% Si, High Purity)	75 g	52	376a	Light magnesia	450 g	31
196	Ferrochromium (low carbon)	100 g	51	377	Phenyl-beta-naphthylamine . .	600 g	33
198	Silica refractory (0.2% Al ₂ O ₃)	45 g	33	378a	Oil furnace black (Set of 4) . .	28 kg	42
199	Silica refractory (0.5% Al ₂ O ₃)	45 g	33	379	Conducting black	5.5 kg	32
217b-5	2,2,4-Trimethylpentane	5 ml	64	380	Calcium carbonate	6 kg	31
217b-8S	2,2,4-Trimethylpentane	8 ml	71	381	Calcium silicate	4 kg	31
217b-25	2,2,4-Trimethylpentane	25 ml	186	382a	Gas furnace black (Set of 4)	32 kg	58
276	Tungsten Carbide	75 g	33	383	Mercaptobenzothiazole (Set of 4)	3.2 kg	39
307	Metallic brown	60 g	32				
329	Zinc Concentrate	100 g	34				
330	Copper, millheads	100 g	52				
331	Copper, milltails	100 g	52				
332	Copper, concentrate	50 g	52				

SRM	Type	Unit	Price	SRM	Type	Unit	Price
384b	N-tertiary-Butyl-2-benzo- thiazolesulfenamide (set of 4)	3.2 kg	65	478	Microprobe, cartridge brass	set (2)	50
385b	Natural rubber	31.4 kg	111	479	Microprobe, Fe-Cr-Ni Alloy	ea	56
386g	Styrene-butadiene type 1500	34 kg	73	480	Microprobe, Tungsten—20% Molybdenum alloy	ea	131
389	Styrene-butadiene, type 1503	34 kg	60	481	Microprobe, Gold-silver wires	set	136
391	Acrylonitrile-butadiene rubber	25 kg	111	482	Microprobe, Gold-copper wires	set	136
404a	Steel, basic electric	ea	36	483	Microprobe, Iron-3% silicon	ea	56
405a	Steel, medium manganese	ea	36	485	Austenite in ferrite	ea	91
407a	Steel, chromium-vanadium	ea	36	493	Iron carbide in ferrite	ea	91
408a	Steel, chromium-nickel	ea	36	593	Hydrocarbon blends—Blend No. 2	set	38
409b	Steel, nickel	ea	36	594	Hydrocarbon blends—Blend No. 3	set	38
413	Steel, A.O.H. 0.4C	ea	36	595	Hydrocarbon blends—Blend No. 4	set	38
414	Steel, Cr-Mo (SAE 4140)	ea	36	596	Hydrocarbon blends—Blend No. 5	set	38
417a	Steel, B.O.H. 0.4C	ea	36	597	Hydrocarbon blends—Blend No. 6	set	38
418	Steel, Cr-Mo (SAE X4130)	ea	36	599	Hydrocarbon blends—Blend No. 8	set	38
418a	Steel, Cr-Mo (SAE X4130)	ea	36	607	Potassium Feldspar, Trace Rubidium and Strontium	5 g	42
420a	Iron, ingot	ea	36	608	Glass, trace elements, set 1 each 614 and 616	set	202
427	Steel, Cr-Mo (boron only) (SAE 4150)	ea	36	609	Glass, trace elements, set 1 each 615 and 617	set	202
431	Tin A	ea	41	610	Glass, trace elements 500 ppm, 3 mm	ea	69
432	Tin B	ea	41	611	Glass, trace elements 500 ppm, 1 mm	ea	69
433	Tin C	ea	41	612	Glass, trace elements 50 ppm, 3 mm	ea	69
434	Tin D	ea	41	613	Glass, trace elements 50 ppm, 1 mm	ea	69
435	Tin E	ea	41	614	Glass, trace elements 1 ppm, 3 mm	ea	69
436	Steel, special Cr6-Mo3-W10	ea	41	615	Glass, trace elements 1 ppm, 1 mm	ea	69
437	Steel, special Cr8-Mo2-W3- Co3	ea	41	616	Glass, trace elements .02 ppm, 3 mm	ea	69
438	Steel, Mo high speed (AISI- SAE-M30)	ea	41	617	Glass, trace elements .02 ppm, 1 mm	ea	69
439	Steel, Mo high speed (AISI- SAE-M36)	ea	41	618	Glass, trace elements, 3 mm	set	202
440	Steel, special W high speed Cr2-W13-Co12	ea	41	619	Glass, trace elements, 1 mm	set	202
441	Steel, W high speed (AISI- SAE-T1)	ea	41	620	Glass plate, soda lime	pkg (3)	51
442	Steel, stainless, Cr16-Ni10	ea	41	625	Zinc-base A	ea	56
443	Steel, stainless, Cr18.5-Ni9.5	ea	41	626	Zinc-base B	ea	56
444	Steel, stainless, Cr20.5-Ni10	ea	41	627	Zinc-base C	ea	56
445	Steel, stainless, Cr13-Mo0.9 (Modified AISI 410)	ea	41	628	Zinc-base D	ea	56
446	Steel, stainless, Cr18-Ni9 (Modified AISI 321)	ea	41	629	Zinc-base E	ea	56
447	Steel, stainless, Cr24-Ni13 (Modified AISI 309)	ea	41	630	Zinc-base F	ea	56
448	Steel, stainless, Cr9-Mo0.3 (Modified AISI 403)	ea	41	631	Zinc spelter (Modified)	ea	56
449	Steel, stainless, Cr5.5-Ni6.5	ea	41	633	Cement, Portland B (red)	set (3)	34
450	Steel, stainless, Cr3-Ni25	ea	41	634	Cement, Portland C (gold)	set (3)	34
461	Steel, low-alloy A	ea	41				
462	Steel, low-alloy B	ea	41				
463	Steel, low-alloy C	ea	41				
464	Steel, low-alloy D	ea	41				
465	Iron, ingot E	ea	41				
466	Iron, ingot F	ea	41				
467	Steel, low-alloy G	ea	41				
468	Steel, low-alloy H	ea	41				

SRM	Type	Unit	Price
635	Cement, Portland D (blue) ..	set (3)	34
636	Cement, Portland F (yellow)	set (3)	34
637	Cement, Portland G (pink) ..	set (3)	34
638	Cement, Portland I (green) ..	set (3)	34
639	Cement, Portland J (clear) ..	set (3)	34
641	Titanium alloy 8Mn(A)	ea	56
642	Titanium alloy 8Mn(B)	ea	56
643	Titanium alloy 8Mn(C)	ea	56
644	Titanium alloy 2Cr-2Fe- 2Mo(A)	ea	56
645	Titanium alloy 2Cr-2Fe- 2Mo(B)	ea	56
646	Titanium alloy 2Cr-2Fe- 2Mo(C)	ea	56
654a	Titanium alloy, 6Al-4V	ea	41
661	Steel, AISI 4340, rod	ea	31
662	Steel, AISI 94B17 (modified), rod	ea	31
663	Steel, Cr-V (modified), rod ..	ea	31
664	Steel, high carbon (modified), rod	ea	31
665	Iron, electrolytic, rod	ea	31
666	Set of one each (661 & 665) ..	set	46
667	Set of one each (662 & 663) ..	set	46
668	Set of one each (661, 662, 663, 664 and 665)	set	81
671	Nickel oxide 1	25 g	41
672	Nickel oxide 2	25 g	41
673	Nickel oxide 3	25 g	41
680L-1	Platinum, high-purity	ea	46
680L-2	Platinum, high-purity	ea	196
681L-1	Platinum, doped	ea	46
681L-2	Platinum, doped	ea	196
682	Zinc, high-purity	ea	96
683	Zinc metal	ea	61
685R	Gold, high-purity (rod)	ea	157
685W	Gold, high-purity (wire)	ea	87
700c	Paper, light-sensitive	pkg	46
701c	Paper, standard faded strips	bklt	161
702	Plastic chips, light-sensitive	pkg	46
703	Plastic chips, light-sensitive	pkg	46
704a	Paper, internal tearing resistance	set (4)	62
705	Polystyrene, narrow molecular weight	5 g	89
706	Polystyrene, broad molecular weight	18 g	39
707	Water vapor permeance, 12 sheets	pkg	51
708	Glass, relative stress optical coefficient	set (2)	77
709	Glass, extra dense lead, 4x4x5 cm	500 g	72
710	Glass, soda-lime silica	900 g	58
711	Glass, lead-silica	1.3 kg	81
712	Glass, mixed alkali lead silicate	225 g	44

SRM	Type	Unit	Price
713	Glass, dense barium crown ..	225 g	44
714	Glass, alkaline earth alumina silicate	225 g	44
715	Glass, alkali-free aluminosilicate	200 g	44
716	Glass, neutral (borosilicate) ..	250 g	44
717	Glass, standard, borosilicate	450 g	77
718	Polycrystalline alumina, Elasticity	ea	201
720	Sapphire, synthetic (Al ₂ O ₃) ..	15 g	62
723	Tris(hydroxymethyl)amino- methane, basimetric	50 g	57
724a	Tris(hydroxymethyl)amino- methane, calorimetric	50 g	51
725	Mossbauer Differential Chemical Shift	ea	161
726	Selenium	450 g	51
728	Zinc	450 g	49
731L1	Borosilicate glass, thermal expansion, 2 in.	ea	77
731L2	Borosilicate glass, thermal expansion, 4 in.	ea	125
731L3	Borosilicate glass, thermal expansion, 6 in.	ea	173
733	Thermocouple wire, Silver— 28% Gold, 32 AWG (0.2019 mm dia.) and 3 meters long ..	ea	91
734S	Iron, electrolytic, thermal conductivity, rod 6.4 mm dia., 305 mm long	ea	81
734L1	Iron, electrolytic, thermal conductivity, rod, 31.8 mm dia., 152 mm long	ea	91
734L2	Iron, electrolytic, thermal conductivity, rod 31.8 mm dia., 305 mm long	ea	156
735M1	Stainless steel, thermal conductivity, rod 1.25 cm dia., 15 cm long	ea	106
735M2	Stainless steel, thermal conductivity, rod 1.25 cm dia., 30 cm long	ea	156
735L1	Stainless steel, thermal conductivity, rod 3.2 cm dia., 5 cm long	ea	131
735L2	Stainless steel, thermal conductivity, rod 3.2 cm dia., 10 cm long	ea	181
736L1	Copper, thermal expansion, 2 in.	ea	77
736L2	Copper, thermal expansion, 4 in.	ea	125
736L3	Copper, thermal expansion, 6 in.	ea	173
739L1	Fused-silica, thermal expansion, 2 in.	ea	77
739L2	Fused-silica, thermal expansion, 4 in.	ea	125
739L3	Fused-silica, thermal expansion, 6 in.	ea	173

SRM	Type	Unit	Price	SRM	Type	Unit	Price
740	Zinc, primary freezing-point std.	350 g	102	D837	Steel, special (Cr8-Mo2-W3-Co3)	ea	56
741	Tin, primary freezing-point std.	350 g	127	838	Steel, Mo high speed (AISI-SAE-M30)	ea	49
742	Alumina, high temperature melting point	10 g	69	D838	Steel, Mo high speed (AISI-SAE-M30)	ea	56
745	Gold, vapor pressure std. ...	ea	91	D839	Steel, Mo high speed (AISI-SAE-M36)	ea	56
746	Cadmium, vapor pressure std.	ea	71	840	Steel, special W high speed (Cr2-W13-Co12)	ea	49
748	Silver, vapor pressure std. ..	ea	81	D840	Steel, special W high speed (Cr2-W13-Co12)	ea	56
755	Quartz, SiO ₂	2 g	41	841	Steel, W high speed (AISI-SAE-T1)	ea	49
756	Potassium nitrate	5 g	41	D841	Steel, W high speed (AISI-SAE-T1)	ea	56
758	DTA temperature std. (125-435°C)	set (5)	51	845	Steel, Cr13-Mo0.9 (Modified AISI 410)	ea	49
759	DTA temperature std. (295-675°C)	set (5)	51	D845	Steel, Cr13-Mo0.9 (Modified AISI 410)	ea	56
760	DTA temperature std. (570-940 °C)	set (5)	51	D846	Steel, Cr18-Ni9 (Modified AISI 321)	ea	56
763-1	Aluminum, magnetic susceptibility, cylinder	ea	47	D847	Steel, Cr24-Ni13 (Modified AISI 309)	ea	56
763-2	Aluminum, magnetic susceptibility, wire	ea	42	849	Steel, Cr5.5-Ni6.5	ea	49
763-3	Aluminum, magnetic susceptibility, (GOUY), rod ..	ea	102	D849	Steel, Cr5.5-Ni6.5	ea	56
764-1	Platinum, magnetic susceptibility, cylinder	ea	92	850	Steel, Cr3-Ni25	ea	49
764-2	Platinum, magnetic susceptibility, wire	ea	52	D850	Steel, Cr3-Ni25	ea	56
765-1	Palladium, magnetic susceptibility, cylinder	ea	102	911	Cholesterol, clinical	0.5 g	36
765-2	Palladium, magnetic susceptibility, wire	ea	62	912	Urea, clinical	25 g	42
765-3	Palladium, magnetic susceptibility, sponge	ea	77	913	Uric acid, clinical	10 g	36
766-1	Manganese Fluoride, magnetic susceptibility, cube	ea	77	914	Creatinine, clinical	10 g	42
767	Superconducting fixed point	ea	252	915	Calcium carbonate, clinical ..	20 g	36
803a	Steel, A.O.H. 0.6C	ea	36	916	Bilirubin, clinical	100 mg	98
D803a	Steel, A.O.H. 0.6C	ea	41	917	D-Glucose, clinical	25 g	49
804a	Steel, basic electric	ea	36	918	Potassium chloride, clinical ..	30 g	46
805a	Steel, medium manganese ...	ea	36	919	Sodium chloride, clinical	30 g	46
D805a	Steel, medium manganese ...	ea	41	920	D-Mannitol, clinical	50 g	63
807a	Steel, chromium-vanadium ..	ea	36	921	Cortisol	1 g	65
D807a	Steel, chromium-vanadium ..	ea	41	922	Tris(hydroxymethyl)amino-methane, clinical	25 g	46
808a	Steel, chromium-nickel	ea	36	923	Tris(hydroxymethyl)amino-methane hydrochloride, clinical	35 g	46
809b	Steel, nickel	ea	36	924	Lithium carbonate, clinical ..	30 g	56
D809b	Steel, nickel	ea	41	925	VMA(4-Hydroxy-3-Methoxy-mandelic acid) clinical	1 g	59
810a	Steel, Cr2-Mo1	ea	36	930a	Glass filters for spectrophotometry, clinical ..	set (3)	306
817a	Steel, B.O.H. 0.4C	ea	36	931a	Liquid filters for spectrophotometry, clinical, 3 sets of 4 (Temporarily out of stock)	set	
820a	Iron, ingot	ea	36	932	Quartz cuvette for spectrophotometry	ea	211
D820a	Iron, ingot	ea	41	944	Plutonium sulfate tetrahydrate, assay	0.5 g	82
821	Steel, Cr-W, 0.9C	ea	36	945	Plutonium metal, std matrix	5 g	506
827	Steel, Cr-Mo (boron only) (SAE 4150)	ea	36				
837	Steel, special (Cr8-Mo2-W3-Co3)	ea	49				

SRM	Type	Unit	Price	SRM	Type	Unit	Price
946	Plutonium, 12% isotopic	0.25 g	156	1029	Calcium silicate phosphor	14 g	30
947	Plutonium, 18% isotopic	0.25 g	156	1030	Magnesium arsenate phosphor	28 g	30
948	Plutonium, 8% isotopic	0.25 g	73	1031	Calcium halophosphate phosphor	28 g	30
949d	Plutonium metal, assay	0.5 g	156	1032	Barium silicate phosphor	28 g	30
950a	Uranium oxide (U ₃ O ₈)	25 g	34	1033	Calcium phosphate phosphor	28 g	30
951	Boric acid	100 g	61	1051b	Barium cyclohexanebutyrate	5 g	37
952	Boric acid, 95% enriched ¹⁰ B	0.25 g	46	1052b	Bis(1-phenyl-1, 3-butenediono) oxovanadium (IV)	5 g	37
953	Neutron density monitor wire, 1 meter long	ea	45	1053a	Cadmium cyclohexanebutyrate	5 g	37
960	Uranium metal, assay	26 g	56	1055b	Cobalt cyclohexanebutyrate	5 g	37
961	Fission Track Glass U-461	set (6)	52	1057b	Dibutyltin bis(2-ethylhexanoate)	5 g	37
962	Fission Track Glass U-37	set (6)	52	1059b	Lead cyclohexanebutyrate	5 g	37
963	Fission Track Glass U-0.8	set (6)	52	1060a	Lithium cyclohexanebutyrate	5 g	37
964	Fission Track Glass U-0.07	set (6)	52	1061c	Magnesium cyclohexanebutyrate	5 g	37
975	Sodium chloride— isotopic	0.25 g	46	1062a	Manganous cyclohexanebutyrate	5 g	37
976	Copper metal— isotopic	0.25 g	46	1063a	Methyl borate	5 g	37
977	Sodium bromide— isotopic	0.25 g	46	1064	Mercuric cyclohexanebutyrate	5 g	37
978	Silver nitrate— isotopic	0.25 g	46	1065b	Nickel cyclohexanebutyrate	5 g	37
979	Chromium nitrate— isotopic	0.25 g	46	1066a	Octaphenylcyclotetrasiloxane	5 g	37
980	Magnesium metal— isotopic	0.25 g	46	1069b	Sodium cyclohexanebutyrate	5 g	37
981-3	Lead— isotopic	set	111	1070a	Strontium cyclohexanebutyrate	5 g	37
984	Ruthidium chloride, isotopic	1 g	49	1071a	Triphenyl phosphate	5 g	37
987	Strontium carbonate, isotopic	1 g	46	1073b	Zinc cyclohexanebutyrate	5 g	37
988	Strontium-84 spike, isotopic	1 mg	156	1074a	Calcium 2-ethylhexanoate	5 g	37
989	Rhenium, assay and isotopic	pkg (50)	102	1075a	Aluminum 2-ethylhexanoate	5 g	37
999	Potassium chloride, primary	60 g	59	1076	Potassium erucate	5 g	37
1001	X-ray step tablet, 0-4	ea	76	1077a	Silver 2-ethylhexanoate	5 g	37
1002b	Hardboard sheet	set (4)	41	1078b	Tris(1-phenyl-1,3-butenediono) chromium (III)	5 g	39
1003	Glass spheres (5-30 μm)	40 g	39	1079b	Tris(1-phenyl-1,3-butenediono) iron (III)	5 g	37
1004	Glass beads (sieve No. 140-400)	63 g	54	1080	Bis(1-phenyl-1, 3-butenediono) copper (II)	5 g	37
1006a	Smoke density std., non-flaming (Temporarily out of stock)			1089	Gasometric, Set: 1 ea of 1095, 1096, 1097, 1098, and 1099	set (5)	81
1007a	Smoke density std., flaming (Temporarily out of stock)			1090	Gasometric, Iron, ingot	ea	61
1008	Photographic step tablet, 0-4	ea	74	1091	Gasometric, Steel, stainless (AISI 431)	ea	61
1009	Photographic step tablet 0-3	ea	60	1092	Gasometric, Steel, vacuum-melted	ea	61
1010a	Microcopy test chart	set (5)	16	1093	Gasometric, Steel, valve	ea	61
1016	Cement, Portland	set (3)	34	1094	Gasometric, Steel, maraging	ea	61
1017a	Glass beads (sieve nos. 50-140)	84 g	46	1095	Gasometric, Steel, AISI 4340, rod	ea	39
1018a	Glass beads (sieve nos. 25-60)	74 g	46	1096	Gasometric, Steel, AISI 94B17 (modified), rod	ea	39
1019	Glass spheres (sieves No. 8-18)	100 g	37	1097	Gasometric, Steel, Cr-V (modified), rod	ea	39
1020	Zinc sulfide phosphor	14 g	30				
1021	Zinc silicate phosphor	28 g	30				
1022	Zinc sulfide phosphor	14 g	30				
1023	Zinc-cadmium sulfide phosphor (Ag activator)	14 g	32				
1024	Zinc-cadmium sulfide phosphor (Cu activator)	14 g	30				
1025	Zinc phosphate phosphor	28 g	30				
1026	Calcium tungstate phosphor	28 g	30				
1027	Magnesium tungstate phosphor	28 g	30				
1028	Zinc silicate phosphor	28 g	30				

SRM	Type	Unit	Price	SRM	Type	Unit	Price
1098	Gasometric, Steel, high-carbon (modified), rod	ea	39	1139	Steel, cast 2	ea	71
1099	Gasometric, Iron, electrolytic, rod	ea	39	1140a	Iron, ductile 1	ea	71
1101	Brass, cartridge B	ea	71	1141a	Iron, ductile 2	ea	71
C1101	Brass, cartridge B	ea	71	1142	Iron, ductile 3	ea	71
1102	Brass, cartridge C	ea	71	1143	Iron, blast furnace I	ea	71
1103	Brass, free-cutting A	ea	71	1144	Iron, blast furnace 2	ea	71
C1103	Brass, free-cutting A	ea	71	1147a	Iron, white cast	ea	71
1104	Brass, free-cutting B	ea	71	1148	Iron, white	ea	71
C1104	Brass, free-cutting B	ea	71	1149	Iron, white	ea	71
1105	Brass, free-cutting C	ea	71	1152	Steel, stainless B (Cr18-Ni10)	ea	71
C1105	Brass, free-cutting C	ea	71	1154	Steel, stainless D (Cr19-Ni10)	ea	71
1106	Brass, naval A	ea	71	1155	Steel, stainless, Cr18-Ni12-Mo2	ea	71
C1106	Brass, naval A	ea	71	1156	Steel, maraging (disk form)	ea	71
1107	Brass, naval B	ea	71	1157	Steel, tool	ea	56
C1107	Brass, naval B	ea	71	1158	Steel, high nickel (36% Ni)	ea	56
1108	Brass, naval C	ea	71	1159	Nickel-base alloy, 49% Ni, balance Fe	ea	71
C1108	Brass, naval C	ea	71	1160	Nickel-base alloy, 80% Ni, 4% Mo, balance Fe	ea	71
1109	Brass, red A	ea	71	1166	Iron, ingot F	ea	71
C1109	Brass, red A	ea	71	1169	Steel, leaded	ea	71
1110	Brass, red B	ea	71	1170a	Steel, selenium-bearing	ea	40
C1110	Brass, red B	ea	71	1171	Steel, Cr17-Ni11-Ti0.3, AISI 321, disk	ea	56
1111	Brass, red C	ea	71	1172	Steel, Cr17-Ni11-Nb0.7, AISI 348, disk	ea	56
C1111	Brass, red C	ea	71	1185	Steel, stainless, AMS 5360A, AISI 316 alloy	ea	71
1112	Gilding metal A	ea	71	1197	High temperature alloy, M308	ea	55
C1112	Gilding metal A	ea	71	1198	High temperature alloy, Incoloy 901 (Sold only in a set with SRM 1201)	set (2)	80
1113	Gilding metal B	ea	71	1199	High temperature alloy, L605 (Sold only in a set with SRM 1200)	set (2)	80
C1113	Gilding metal B	ea	71	1200	High temperature alloy, S816 (Sold only in a set with SRM 1199, above)	set (2)	80
1114	Gilding metal C	ea	71	1201	High temperature alloy, Hastaloy (Sold only in a set with SRM 1198, above)	set (2)	80
C1114	Gilding metal C	ea	71	1206-2	High temperature alloy, René 41	ea	56
1115	Bronze, commercial A	ea	71	1207-1	High temperature alloy, Waspaloy (No. 1)	ea	56
C1115	Bronze, commercial A	ea	71	1207-2	High temperature alloy, Waspaloy (No. 2)	ea	56
1116	Bronze, commercial B	ea	71	1208-1	High temperature alloy, Inco 718 (No. 1)	ea	56
C1116	Bronze, commercial B	ea	71	1208-2	High temperature alloy, Inco 718 (No. 2)	ea	56
1117	Bronze, commercial C	ea	71	1209	High temperature alloy, Set, 1 ea of 1206-2, 1207-1, 1207-2, 1208-1, and 1208-2	set	205
C1117	Bronze, commercial C	ea	71	1210	Zirconium metal A	ea	96
1118	Brass, aluminum A	ea	71	1212a	Zirconium metal C	ea	60
C1118	Brass, aluminum A	ea	71	1261	Steel, AISI 4340, disk	ea	51
1119	Brass, aluminum B	ea	71				
C1119	Brass, aluminum B	ea	71				
1120	Brass, aluminum C	ea	71				
C1120	Brass, aluminum C	ea	71				
1121	Beryllium copper CA-172	ea	71				
C1121	Beryllium copper CA-172	ea	71				
1122	Beryllium copper CA-170	ea	71				
C1122	Beryllium copper CA-170	ea	71				
1123	Beryllium copper CA-175	ea	71				
C1123	Beryllium copper CA-175	ea	71				
1131	Solder (Sn40-Pb60)	ea	56				
1132	Bearing metal, lead-base	ea	56				
1134	Steel, high silicon	ea	56				
1135	Steel, high-silicon	ea	56				
1136	Steel, high-sulfur	ea	56				
1138	Steel, cast 1	ea	71				

SRM	Type	Unit	Price	SRM	Type	Unit	Price
1262	Steel, AISI 94B17 (modified), disk	ea	51	1337	Metal coating, magnetic, 0.0016 in thick	ea	41
1263	Steel, Cr-V (modified), disk ..	ea	51	1338	Metal coating, magnetic, 0.0020 in thick	ea	41
1264	Steel, high carbon (modified), disk	ea	51	1339	Metal coating, magnetic, 0.0025 in thick	ea	41
1265	Iron, electrolytic, disk	ea	51	1341	Metal coating, magnetic, 0.00012 in thick	ea	41
1266	Set, 1 ea of 1261, 1262, 1263, 1264, and 1265	set	181	1342	Metal coating, magnetic, 0.00035 in thick	ea	41
1301	Metal coating, nonmagnetic, 0.00010 in thick	ea	41	1343	Metal coating, magnetic, 0.00065 in thick	ea	41
1302	Metal coating, nonmagnetic, 0.00025 in thick	ea	41	1344	Metal coating, magnetic, 0.0010 in thick	ea	41
1303	Metal coating, nonmagnetic, 0.00050 in thick	ea	41	1345	Metal coating, magnetic, 0.0015 in thick	ea	41
1304	Metal coating, nonmagnetic, 0.00075 in thick	ea	41	1346	Metal coating, magnetic, 0.0020 in thick	ea	41
1305	Metal coating, nonmagnetic, 0.0010 in thick	ea	41	1351	Set of one each 1307 and 1311	set (2)	53
1306	Metal coating, nonmagnetic, 0.0015 in thick	ea	41	1352	Set of one each 1332 and 1334	set (2)	53
1307	Metal coating, nonmagnetic, 0.0020 in thick	ea	41	1353	Set of one each 1335 and 1339	set (2)	53
1308	Metal coating, nonmagnetic, 0.0025 in thick	ea	41	1361	Set of one each 1302, 1303, 1305, and 1307	set (4)	77
1309	Metal coating, nonmagnetic, 0.0027 in thick	ea	41	1362	Set of one each 1306, 1310, 1311, and 1312	set (4)	77
1310	Metal coating, nonmagnetic, 0.0032 in thick	ea	41	1363	Set of one each 1313, 1314, 1315, and 1316	set (4)	77
1311	Metal coating, nonmagnetic, 0.0055 in thick	ea	41	1364	Set of one each 1317, 1318, 1319, and 1320	set (4)	77
1312	Metal coating, nonmagnetic, 0.0080 in thick	ea	41	1365	Set of one each 1331, 1332, 1333, and 1334	set (4)	77
1313	Metal coating, nonmagnetic, 0.010 in thick	ea	41	1366	Set of one each 1335, 1336, 1337, and 1338	set (4)	77
1314	Metal coating, nonmagnetic, 0.015 in thick	ea	41	1367	Set of one each 1341, 1342, 1343, and 1344	set (4)	77
1315	Metal coating, nonmagnetic, 0.020 in thick	ea	41	1368	Set of one each 1312, 1313, 1314, and 1315	set (4)	77
1316	Metal coating, nonmagnetic, 0.025 in thick	ea	41	1369	Set of one each 1316, 1317, 1318, and 1319	set (4)	77
1317	Metal coating, nonmagnetic, 0.03 in thick	ea	41	1370	Set of one each 1312, 1313, 1314, 1315, 1316, 1317, 1318, and 1319	set (8)	148
1318	Metal coating, nonmagnetic, 0.04 in thick	ea	41	1371	Gold coating (Fe-Ni-Co) 30 microinches	ea	72
1319	Metal coating, nonmagnetic, 0.06 in thick	ea	41	1372	Gold coating (Fe-Ni-Co) 60 microinches	ea	72
1320	Metal coating, nonmagnetic, 0.08 in thick	ea	41	1373	Gold coating (Fe-Ni-Co) 120 microinches	ea	72
1331	Metal coating, magnetic, 0.00012 in thick	ea	41	1374	Gold coating (Fe-Ni-Co) 280 microinches	ea	72
1332	Metal coating, magnetic, 0.00035 in thick	ea	41	1375	Gold coating (Nickel) 30 microinches	ea	72
1333	Metal coating, magnetic, 0.00055 in thick	ea	41	1376	Gold coating (Nickel) 60 microinches	ea	72
1334	Metal coating, magnetic, 0.00075 in thick	ea	41	1377	Gold coating (Nickel) 120 microinches	ea	72
1335	Metal coating, magnetic, 0.0010 in thick	ea	41				
1336	Metal coating, magnetic, 0.0013 in thick	ea	41				

SRM	Type	Unit	Price	SRM	Type	Unit	Price
1378	Gold coating (Nickel) 350 microinchees	ea	72	1571	Botanical, orchard leaves, trace element	75 g	74
1381	Set of one each 1371 and 1372	set (2)	115	1577	Biological, Liver, bovine	50 g	94
1382	Set of one each 1372 and 1373	set (2)	115	1579	Powdered lead-base paint ...	35 g	37
1383	Set of one each 1373 and 1374	set (2)	115	1600	Tape, magnetic, secondary std., cassette	ea	142
1384	Set of one each 1375 and 1376	set (2)	115	1604a	Oxygen in nitrogen, 1.5 ppm	cyl	116
1385	Set of one each 1376 and 1377	set (2)	115	1606	Oxygen in nitrogen, 112 ppm	cyl	116
1386	Set of one each 1377 and 1378	set (2)	115	1607	Oxygen in nitrogen, 211 ppm	cyl	116
1398	Set of one each 1371, 1372, 1373, and 1374	set (4)	188	1608	Oxygen in nitrogen, 978 ppm	cyl	116
1399	Set of one each 1375, 1376, 1377, and 1378	set (4)	188	1609	Oxygen in nitrogen, 20.98 mole percent	cyl	116
1402	Emittance std., 1/2 in. disk ...	ea	186	1621	Sulfur in residual fuel oil, 1.05 wt percent	100 ml	36
1403	Emittance std., 7/8 in. disk ...	ea	196	1622	Sulfur in residual fuel oil, 2.14 wt percent	100 ml	36
1404	Emittance std., 1 in. disk ...	ea	211	1623	Sulfur in residual fuel oil, 0.268 wt percent	100 ml	36
1405	Emittance std., 1 1/8 in. disk	ea	246	1624	Sulfur in distillate fuel oil, 0.211 wt percent	100 ml	36
1406	Emittance std., 1 1/4 in. disk	ea	261	1625	Sulfur dioxide permeation tube 10 cm	ea	67
1407	Emittance std., 2 in. × 2 in.	ea	396	1626	Sulfur dioxide permeation tube 5 cm	ea	67
1408	Emittance std., 1 in. × 10 in.	ea	761	1627	Sulfur dioxide permeation tube 2 cm	ea	67
1409	Emittance std., 3/4 in. × 10 in.	ea	611	1630	Trace mercury in coal	50 g	51
1420	Emittance std., 1/2 in. disk ...	ea	186	1631	Sulfur in coal, three concentrations, 5 sets of 3 ...	set	59
1421	Emittance std., 7/8 in. disk ...	ea	186	1632	Trace Elements in Coal	75 g	73
1422	Emittance std., 1 in. disk ...	ea	186	1633	Trace Elements in Fly Ash ...	75 g	73
1423	Emittance std., 1 1/8 in. disk	ea	186	1634	Trace Elements in Fuel Oil ...	100 ml	73
1424	Emittance std., 1 1/4 in. disk	ea	186	1651	Zirconium-barium chromate heat source powder (ca 350 cal/g)	50 g	61
1425	Emittance std., 2 in × 2 in.	ea	186	1652	Zirconium-barium chromate heat source powder (ca 390 cal/g)	50 g	61
1427	Emittance std., 3/4 in. × 10 in.	ea	186	1653	Zirconium-barium chromate heat source powder (ca 425 cal/g)	50 g	61
1428	Emittance std., 1/4 in. × 8 in.	ea	186	1654	α-Quartz for hydrofluoric acid solution calorimetry	25 g	181
1440	Emittance std., 1/2 in. disk ...	ea	186	1665	Propane in Air 2.8 ppm	cyl	278
1441	Emittance std., 7/8 in. disk ...	ea	186	1666	Propane in Air 9.5 ppm	cyl	278
1442	Emittance std., 1 in. disk ...	ea	186	1667	Propane in Air 48 ppm	cyl	278
1443	Emittance std., 1 1/8 in. disk	ea	186	1668	Propane in Air 95 ppm	cyl	278
1444	Emittance std., 1 1/4 in. disk	ea	186	1669	Propane in Air 475 ppm	cyl	278
1445	Emittance std., 2 in. × 2 in.	ea	186	1673	Carbon Dioxide in N ₂ 0.95% ...	cyl	278
1475	Polyethylene, linear	50 g	106	1674	Carbon Dioxide in N ₂ 7.2% ...	cyl	278
1476	Polyethylene, branched	50 g	81	1675	Carbon Dioxide in N ₂ 14.2% ...	cyl	278
1511	Cyclohexane, dielectric	400 ml	131	1677	Carbon Monoxide in N ₂ 9.74 ppm	cyl	301
1512	1,2 Dichloroethane, dielectric	400 ml	126	1678	Carbon Monoxide in N ₂ 47.1 ppm	cyl	301
1513	Nitrobenzene, dielectric	400 ml	126	1679	Carbon Monoxide in N ₂ 94.7 ppm	cyl	301
1516	Permittivity Std., 38 mm × 2.5 mm	ea	199	1680	Carbon Monoxide in N ₂ 484 ppm	cyl	301
1517	Permittivity Std., 38 mm × 5 mm	ea	199	1681	Carbon Monoxide in N ₂ 957 ppm	cyl	301
1518	Permittivity Std., 51 mm × 2.5 mm	ea	199	1810	Linerboard for tape test	pkg	39
1519	Permittivity Std., 51 mm × 5 mm	ea	199				
1520	Resistivity, Boron-Doped Silicon	set (2)	427				
1541	Mossbauer, iron foil	ea	156				

SRM	Type	Unit	Price	SRM	Type	Unit	Price
2001	Aluminum on glass, specular spectral reflectance	ea	281	2316	Set of one each 2312 and 2313	set (2)	115
2002	Aluminum on glass, specular spectral reflectance	ea	281	2317	Set of one each 2313 and 2314	set (2)	115
2003	Aluminum on glass, specular spectral reflectance	ea	281	2318	Set of one each 2311, 2312, 2313, and 2314	set (4)	188
2005	Gold on glass, specular spectral reflectance	ea	281	2331	Tin coating 60 microinches	ea	72
2006	Gold on glass, specular spectral reflectance	ea	281	2332	Tin coating 110 microinches	ea	72
2007	Gold on glass, specular spectral reflectance	ea	281	2333	Tin coating 160 microinches	ea	72
2008	Gold on glass, specular spectral reflectance	ea	281	2334	Tin coating 275 microinches	ea	72
2101-5	Color std.	set	381	2335	Tin coating 650 microinches	ea	72
2106	ISCC-NBS color charts	set	11	2338	Set of one each 2332 and 2335	set (2)	115
2141	Urea	2 g	39	2339	Set of one each 2331, 2333, 2334, and 2336	set (4)	188
2142	o-Bromobenzoic acid	2 g	39	2340	Set of one each 2331, 2332, 2333, 2334, 2335, and 2336	set (6)	267
2143	p-Fluorobenzoic acid	2 g	48	3200	Tape, magnetic, secondary std. reel	ea	701
2144	m-chlorobenzoic acid	2 g	41	4200-B	Cesium-137, gamma-ray point source	ea	66
2186-1	Potassium dihydrogen phosphate, pD	30 g	47	4201-B	Niobium-94, gamma-ray point source	ea	158
2186-11	Disodium hydrogen phosphate, pD	30 g	47	4202	Cadmium-109, gamma-ray point source	ea	99
2191	Sodium bicarbonate, pD	30 g	47	4203-C	Cobalt-60, gamma-ray point source	ea	114
2192	Sodium carbonate, pD	30 g	47	4205	Thorium-228, gamma-ray point source	ea	104
2201	Sodium chloride ion-selective electrode	125 g	40	4207	Cesium-137, gamma-ray point source	ea	66
2202	Potassium chloride ion-selective electrode	160 g	40	4210	Cobalt-60, gamma-ray point source	ea	92
2203	Potassium fluoride ion-selective electrode	125 g	76	4211	Americium-241, gamma-ray point source	ea	134
2301	Gold coating (epoxy) 30 microinches	ea	72	4212	Krypton-85, gamma-ray point source	ea	166
2302	Gold coating (epoxy) 60 microinches	ea	72	4213	Americium-241, gamma-ray point source	ea	134
2303	Gold coating (epoxy) 120 microinches	ea	72	4214	Cobalt-57, gamma-ray point source	ea	84
2304	Gold coating (epoxy) 280 microinches	ea	72	*4215	*Mixed Radionuclides, gamma-ray point source		
2305	Set of one each 2301 and 2302	set (2)	115	*4216	*Mixed Radionuclides, gamma-ray point source		
2306	Set of one each 2302 and 2303	set (2)	115	4222	Carbon-14(n-hexadecane) soln. std.	3 g	61
2307	Set of one each 2303 and 2304	set (2)	115	4223	Carbon-14(n-hexadecane) soln. std.	3 g	61
2308	Set of one each 2301, 2302, 2303, and 2304	set (4)	188	4224	Carbon-14(n-hexadecane) soln. std.	3 g	61
2311	Gold coating (copper) 30 microinches	ea	72	4226	Nickel-63, soln. std.	4 g	155
2312	Gold coating (copper) 60 microinches	ea	72	4228	Selenium-75, soln. std.	4.6 g	124
2313	Gold coating (copper) 120 microinches	ea	72	4229	Aluminum-26, soln. std.	4.6 g	206
2314	Gold coating (copper) 280 microinches	ea	72	4233	Cesium-137-Barium-137 Burn-up solution standard	5.1 g	101
2315	Set of one each 2311 and 2312	set (2)	115				

* Available periodically.

SRM	Type	Unit	Price	SRM	Type	Unit	Price
4235	Krypton-85, gamma-ray std.	ea	106	4957	Radium solution std., 0.5 μg		
4240	Bismuth-207, gamma-ray point source	ea	145		Ra	5 g	69
4242-C	Mixed radionuclides	450 ml	56	4958	Radium solution std., 1 μg Ra	5 g	69
4243-C	Mixed radionuclides	50 ml	56	4959	Radium solution std., 2 μg Ra	5 g	69
4244-C	Mixed radionuclides	15 ml	56	4960	Radium solution std., 5 μg Ra	5 g	69
*4252	Mixed radionuclides, test std.	450 ml		4961	Radium solution std. 10 μg Ra	5 g	69
*4253	Mixed radionuclides, test std.	50 ml		4962	Radium solution std., 20 μg Ra	5 g	78
*4300	Argon-37, gas std.			4963	Radium solution std., 50 μg Ra	5 g	69
*4301	Argon-37, gas std.			4964-B	Radium solution std., 102 μg Ra	5 g	69
*4304	Xenon-131m, gas std.			4990-B	Carbon-14, contemporary std. for dating	1 lb	33
*4305	Xenon-131m, gas std.			4991-C	Sodium-22, gamma-ray point source	ea	85
*4306	Xenon-131m, gas std.			4996-B	Sodium-22, gamma-ray point source	ea	85
*4307	Xenon-131m, gas std.			U-0002	Uranium oxide—depleted (U-235)	1 g	65
**4900	Polonium-210, alpha-particle source			U-005	Uranium oxide—depleted (U-235)	1 g	55
**4901	Polonium-210, alpha-particle source			U-010	Uranium oxide—depleted (U-235)	1 g	55
**4902	Polonium-210, alpha-particle source			U-015	Uranium oxide—depleted (U-235)	1 g	55
4904-D	Americium-241, alpha-particle source	ea	130	U-020	Uranium oxide—depleted (U-235)	1 g	55
4906	Plutonium-238, alpha-particle source	ea	164	U-030	Uranium oxide—depleted (U-235)	1 g	55
4907	Gadolinium-148, alpha-particle source	ea	98	U-050	Uranium oxide—depleted (U-235)	1 g	55
4919-C	Strontium-90, soln. std.	5 g	92	U-100	Uranium oxide—depleted (U-235)	1 g	56
4921-C	Sodium-22, soln. std.	3 g	48	U-150	Uranium oxide—depleted (U-235)	1 g	57
4922-E	Sodium-22, soln. std.	5 g	67	U-200	Uranium oxide—depleted (U-235)	1 g	58
4925	Carbon-14 (benzoic acid in toluene)	3 g	54	U-350	Uranium oxide—depleted (U-235)	1 g	61
4926	Hydrogen-3 (water)	25 g	54	U-500	Uranium oxide—depleted (U-235)	1 g	62
4927	Hydrogen-3 (water)	3 g	54	U-750	Uranium oxide—depleted (U-235)	1 g	68
4929-C	Iron-55, soln. std.	4 g	121	U-800	Uranium oxide—depleted (U-235)	1 g	68
4935-C	Krypton-85, beta-particle gas std.	10 ml	106	U-850	Uranium oxide—depleted (U-235)	1 g	69
4940-B	Promethium-147, soln. std.	3 g	66	U-900	Uranium oxide—depleted (U-235)	1 g	70
4941-D	Cobalt-57, soln. std.	5 g	102	U-930	Uranium oxide—depleted (U-235)	1 g	72
4943	Chlorine-36, soln. std.	3 g	49	U-970	Uranium oxide—depleted (U-235)	1 g	75
4945-C	Strontium-89, soln. std.	5 g	92				
4947	Hydrogen-3 (tritiated toluene)	4 g	52				
4949	Iodine-129, soln. std.	1 g	88				
4950-B	Radium solution std., 10 ⁻⁹ g (Rd analysis)	20 g	87				
4951	Radium solution std., 10 ⁻¹¹ g (Rd analysis)	100 g	54				
4953	Radium solution std., 10 ⁻⁸ g (Rd analysis)	20 g	87				
4955	Radium solution std., 0.1 μg Ra	5 g	69				
4956	Radium solution std., 0.2 μg Ra	5 g	69				

* Available periodically.

** Available on request.

B. RESEARCH MATERIALS

RM	Type	Unit	Price
RM-1C	Ultra-purity aluminum, single crystal cube	ea	\$ 96
RM-1R	Ultra-purity aluminum, polycrystalline rod	ea	56
RM-100	SEM Resolution Test Specimen (A1-W)	ea	46

C. GENERAL MATERIALS

GM	Type	Unit	Price
GM-1	Hydrogen in steel	set	\$ 92
GM-2	Hydrogen in steel	set	92
GM-5	Nickel and Vanadium in Residual Oil	500 ml	32
GM-2007	Clay, Attapulugus	18 kg	175

